

**BS EN 2590:2017**



**BSI Standards Publication**

# **Aerospace series — Steel — Sheets and plates, hot rolled — Dimensions**

**National foreword**

This British Standard is the UK implementation of EN 2590:2017.

The UK participation in its preparation was entrusted to Technical Committee ACE/61, Metallic materials for aerospace purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017.  
Published by BSI Standards Limited 2017

ISBN 978 0 580 95661 4

ICS 49.025.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2017.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

EUROPEAN STANDARD

**EN 2590**

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2017

ICS 49.025.10

English Version

**Aerospace series - Steel - Sheets and plates, hot rolled -  
Dimensions**Série aérospatiale - Acier - Tôles et plaques laminées à  
chaud - DimensionsLuft- und Raumfahrt - Stahl - Bleche und Platten,  
warmgewalzt - Maße

This European Standard was approved by CEN on 14 November 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

	Page
European foreword .....	3
1 Scope.....	4
2 Normative references.....	4
3 Required characteristics.....	5
3.1 Materials.....	5
3.2 Form.....	5
3.3 Dimensions .....	5
3.3.1 Thicknesses and masses .....	5
3.3.2 Widths .....	6
3.3.3 Lengths .....	6
3.4 Dimensional tolerances.....	7
3.4.1 Thicknesses .....	7
3.4.2 Widths .....	7
3.4.3 Lengths .....	8
3.5 Form tolerances .....	8
3.5.1 Squareness.....	8
3.5.2 Local straightness .....	8
3.5.3 Flatness.....	9
4 Designation.....	9

## European foreword

This document (EN 2590:2017) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard defines the dimensions and tolerances of sheets and plates, hot rolled, in steel, used in aerospace constructions.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2209, *Aerospace series — Steel FE-PL1502 (25CrMo4) — 900 MPa ≤ R<sub>m</sub> ≤ 1100 MPa — Sheets, strips and plates — 0,5 mm ≤ a ≤ 20 mm<sup>1)</sup>*

EN 2212, *Aerospace — steel FE-PL 43 S, 670 MPa ≤ R<sub>m</sub> ≤ 870 MPa, sheets, strips and plates 0,5 mm ≤ a ≤ 20 mm<sup>1)</sup>*

EN 2215, *Aerospace — steel FE-PL 52 S, 980 MPa ≤ R<sub>m</sub> ≤ 1180 MPa, sheets 0,5 mm ≤ a ≤ 6 mm<sup>2)</sup>*

EN 2216, *Aerospace — steel FE-PL 52 S, 1050 MPa ≤ R<sub>m</sub> ≤ 1250 MPa, sheets a ≤ 2 mm<sup>1)</sup>*

EN 2217, *Aerospace — steel FE-PL 52 S, 1080 MPa ≤ R<sub>m</sub> ≤ 1250 MPa, sheets and plates 2 mm ≤ a ≤ 20 mm<sup>1)</sup>*

EN 2228, *Aerospace — steel FE-PA 12, 500 MPa ≤ R<sub>m</sub> ≤ 700 MPa, sheets 0,5 mm ≤ a ≤ 6 mm<sup>1)</sup>*

EN 2246, *Steel FE-PL43S — 1150 MPa ≤ R<sub>m</sub> ≤ 1300 MPa — Sheet strip and plate — 0,5 mm ≤ A ≤ 20 mm<sup>2)</sup>*

EN 2250, *Steel FE-PL52S — R<sub>m</sub> ≥ 700 MPa — Sheets strips and plates — 0,3 mm ≤ A ≤ 12 mm<sup>2)</sup>*

EN 2273, *Aerospace — steel FE-PM 13 S, 1800 MPa ≤ R<sub>m</sub> ≤ 2000 MPa — sheets and plates a ≤ 30 mm<sup>1)</sup>*

EN 2276, *Aerospace — steel FE-PA 95, 1750 MPa ≤ R<sub>m</sub> ≤ 2000 MPa — sheet and plate a ≤ 40 mm<sup>1)</sup>*

EN 2280, *Aerospace — steel FE-PM 37, 900 MPa ≤ R<sub>m</sub> ≤ 1100 MPa — sheet a ≤ 6 mm<sup>1)</sup>*

EN 2467, *Aerospace series — Steel FE-PA3901 (X2CrNi18-9) — Air melted — Softened — Plate, sheet and strip — 0,4 mm ≤ a ≤ 20 mm — 520 MPa ≤ R<sub>m</sub> ≤ 670 MPa<sup>1)</sup>*

EN 2538, *Aerospace series — Steel FE-PM3801 (X5CrNiCu17-4) — Air melted — Solution treated and precipitation treated — Sheet and strip, a ≤ 6 mm, R<sub>m</sub> ≥ 1310 MPa<sup>1)</sup>*

EN 2540, *Aerospace series — Steel FE-PM3902 (X7CrNiAl17-7) air melted, solution treated and precipitation hardened — Sheet and strip, a ≤ 6 mm, 1240 MPa ≤ R<sub>m</sub> ≤ 1450 MPa<sup>1)</sup>*

---

<sup>1)</sup> Published as ASD-STAN pre-standard at the date of publication of this European Standard.

<sup>2)</sup> In preparation at the date of publication of this European Standard.

EN 2543, *Aerospace series — Steel FE-PL1502 (25CrMo4) — Annealed — Sheet and strip —  $0,3 \text{ mm} \leq a \leq 2 \text{ mm}$  — For prevailing torque nuts<sup>1)</sup>*

EN 2600, *Aerospace series — Designation of metallic semi-finished products — Rules<sup>1)</sup>*

EN 2770, *Steel FE-PL53S — hardened and tempered —  $1050 \leq R_m \leq 1220 \text{ MPa}$  — Sheet and plate —  $0,5 \leq a \leq 12 \text{ mm}$ <sup>1)</sup>*

EN 2773, *Aerospace series — Steel FE-PM3801 (X5CrNiCu17-4), consumable electrode remelted, solution treated and precipitation treated — Sheet and strip,  $a \leq 6 \text{ mm}$ ,  $R_m \geq 1310 \text{ MPa}$ ; Inactive for new design<sup>1)</sup>*

EN 2776, *Aerospace series — Steel FE-P11 —  $R_m \leq 340 \text{ MPa}$  — Sheet and strip —  $a \leq 2 \text{ mm}$ <sup>1)</sup>*

### 3 Required characteristics

#### 3.1 Materials

Steels EN 2209, EN 2212, EN 2215, EN 2216, EN 2217, EN 2228, EN 2246, EN 2250, EN 2273, EN 2276, EN 2280, EN 2467, EN 2538, EN 2540, EN 2543, EN 2770, EN 2773, EN 2776.

#### 3.2 Form

In accordance with Figure 1.




Figure 1

#### 3.3 Dimensions

##### 3.3.1 Thicknesses and masses

###### 3.3.1.1 Sheets

In accordance with Table 1.

**Table 1**

Dimensions in millimetres

Thickness <i>a</i>	Mass per unit area <sup>a</sup> kg/m <sup>2</sup>
1,2	9,4
1,4	11
1,6	12,6
1,8	14,1
2	15,7
2,5	19,6
3	23,6
4	31,4
5	39,3
6	47,1

<sup>a</sup> For information, calculated with a density: 7,85 kg/dm<sup>3</sup>.

### 3.3.1.2 Plates

In accordance with Table 2.

**Table 2**

Dimensions in millimetres

Thickness <i>a</i>	Mass per unit area <sup>a</sup> kg/m <sup>2</sup>
8	63
10	78,5
12	94
15	118

<sup>a</sup> For information, calculated with a density: 7,85 kg/dm<sup>3</sup>.

### 3.3.2 Widths

Widths are not defined.

### 3.3.3 Lengths

Lengths are not defined.



### 3.4 Dimensional tolerances

#### 3.4.1 Thicknesses

In accordance with Table 3.

Measurements shall be taken at least 20 mm from the edge.

**Table 3**

Dimensions in millimetres

Thickness	Tolerances ( $\pm$ ) in accordance with $R_{p0,2}$ in MPa for $a$ width:					
	$b \leq 1\,200$			$1\,200 < b \leq 1\,500$		
	$R_{p0,2} \leq 355$	$355 < R_{p0,2} \leq 460$	$R_{p0,2} > 460$	$R_{p0,2} \leq 355$	$355 < R_{p0,2} \leq 460$	$R_{p0,2} > 460$
$a \leq 2,0$	0,17	0,19	0,21	0,19	0,21	0,24
$2,0 < a \leq 2,5$	0,18	0,20	0,23	0,20	0,22	0,25
$2,5 < a \leq 3,0$	0,20	0,22	0,25	0,22	0,24	0,28
$3,0 < a \leq 4,0$	0,22	0,24	0,28	0,24	0,26	0,30
$4,0 < a \leq 5,0$	0,24	0,26	0,30	0,26	0,29	0,33
$5,0 < a \leq 6,0$	0,26	0,29	0,33	0,28	0,31	0,35
$6,0 < a \leq 8,0$	0,29	0,32	0,36	0,30	0,33	0,38
$8,0 < a \leq 10$	0,32	0,35	0,40	0,33	0,36	0,41
$10 < a \leq 12,5$	0,35	0,38	0,44	0,36	0,40	0,45
$12,5 < a \leq 15$	0,38	0,42	0,48	0,40	0,44	0,50

#### 3.4.2 Widths

In accordance with Table 4.

**Table 4**

Dimensions in millimetres

Widths	Tolerances
$b \leq 1\,200$	+4 0
$1\,200 < b \leq 1\,500$	+6 0

### 3.4.3 Lengths

In accordance with Table 5.

**Table 5**

Dimensions in millimetres

Lengths	Tolerances
$l \leq 2\,000$	+10 0
$l > 2\,000$	$+0,005 \times l$ 0

### 3.5 Form tolerances

#### 3.5.1 Squareness

In accordance with Figure 1 and Table 6.

Difference of the diagonals. See Figure 1.


**Table 6**

Dimensions in millimetres

Lengths	Difference of diagonals
$1\,200 < l \leq 2\,500$	+10 0
$l > 2\,500$	$+0,004 \times l$ 0

#### 3.5.2 Local straightness

In accordance with Figure 2.



#### Key

1 References


**Figure 2**

### 3.5.3 Flatness

#### 3.5.3.1 Method of measurement

The sheet or plate shall be placed on a flat surface, under its own mass.

The raised surface is given by the measurement of the max. distance between the sheet or plate and a reference line which coincides in two points with the sheet or plate, see Figure 3.



#### Key

- 1  $l$  or  $b$
- $W$  length of local amplitude
- $X_1$  raised surface for measuring length  $l$  or  $b$
- $X_2$  raised surface for measuring length  $W$

Figure 3

#### 3.5.3.2 Tolerances

In accordance with Table 7.

Table 7

Dimensions in millimetres

Thickness	$X_1$ for:		$X_2$ for:
	$l$ or $b \leq 1\ 200$	$1\ 200 > l$ or $b \leq 1\ 500$	$W \geq 300$
$a \leq 15$	<b>10</b>	<b>15</b>	1 % of $W$ max. $X_1$

## 4 Designation

In accordance with EN 2600.





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

## Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

## Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Useful Contacts

### Customer Services

**Tel:** +44 345 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 345 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

### BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK