

BS EN 4595:2013



BSI Standards Publication

**Aerospace series — Paints and
varnishes — Two component
cold curing polyurethane finish
— Subsonic erosion resistance**

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 4595:2013.

The UK participation in its preparation was entrusted to Technical Committee ACE/65, Non-metallic materials for aerospace purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.
Published by BSI Standards Limited 2013.

ISBN 978 0 580 73665 0

ICS 49.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2013.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN 4595

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2013

ICS 49.040

English Version

Aerospace series - Paints and varnishes - Two component cold curing polyurethane finish - Subsonic erosion resistance

Série aéronautique - Peintures et vernis - Deux composants durcissement à froid, finition polyuréthane - Résistance à l'érosion subsonique

Luft- und Raumfahrt - Beschichtungsmittel - Zweikomponenten Polyurethan-Decklack, raumtemperaturhärtend - Unterschall-Erosionsbeständigkeit

This European Standard was approved by CEN on 19 February 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword.....	3
Introduction	4
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	5
4 Classification.....	5
5 Batch release and qualification testing.....	5
5.1 Batch release testing	5
5.2 Qualification tests	5
6 Designation	9

Foreword

This document (EN 4595:2013) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2013, and conflicting national standards shall be withdrawn at the latest by July 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This standard has been prepared in accordance with AECMA TR 7000-9.

1 Scope

This European Standard specifies the requirements for a two component polyurethane, topcoat, with a medium degree of resistance to erosion by the effects of rain, available in a range of colours and levels of gloss, to be applied over a primer for aerospace applications on areas where rain erosion at subsonic speeds may be a problem e.g. leading edges and air intakes.

The properties specified in this standard are obtained on defined aluminium alloy test pieces prepared in accordance with EN 3837 Procedure A and EN 23270 and painted with primer to EN 2435. The ability of the material to be used for a specific application (e.g. alternative substrate, alternative primer, specific drying conditions etc.) shall be determined by supplementary tests to confirm that the requirements of this standard are met.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2334, *Aerospace series — Chromic-sulphuric acid pickle of aluminium and aluminium alloys*

EN 2379, *Aerospace series — Fluids for assessment of non-metallic materials*¹⁾

EN 2435 (all parts), *Aerospace series — Paints and varnishes — Corrosion resistant chromated two component cold curing primer*

EN 3837, *Aerospace series — Paints and varnishes — Nature and method for surface preparation of test pieces in aluminium alloys*¹⁾

EN 3840, *Aerospace series — Paints and varnishes — Technical specification*

EN 23270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing (ISO 3270)*

EN ISO 1513, *Paints and varnishes — Examination and preparation of test samples for testing (ISO 1513)*

EN ISO 2431, *Paints and varnishes — Determination of flow time by use of flow cups (ISO 2431)*

EN ISO 2811 (all parts), *Paints and varnishes — Determination of density*

EN ISO 2812-1, *Paints and varnishes — Determination of resistance to liquids — Part 1: Immersion in liquids other than water (ISO 2812)*

1) Published as AECMA Prestandard at the date of publication of this standard.

EN ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20°, 60° and 85°(ISO 2813)*

EN ISO 2884-1, *Paints and varnishes - Determination of viscosity using rotary viscometers - Part 1: Cone-and-plate viscometer operated at a high rate of shear (ISO 2884-19)*

EN ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content (ISO 3251)*

EN ISO 3675, *Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method (ISO 3675)*

EN ISO 3679, *Determination of flash point — Rapid equilibrium closed cup method (ISO 3679)*

EN ISO 3680, *Determination of flash/no flash — Rapid equilibrium closed cup method (ISO 3680)*

EN ISO 9117-1, *Paints and varnishes — Drying tests — Part 1: Determination of through-dry state and through-dry time (ISO 9117-1)*

EN ISO 9514, *Paints and varnishes — Determination of the pot life of multicomponent coating systems — Preparation and conditioning of samples and guidelines for testing (ISO 9514)*

EN ISO 11890-1, *Paints and varnishes — Determination of volatile organic compound (VOC) content — Part 1: Difference method (ISO 11890-1)*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 2781, *Rubber, vulcanized or thermoplastics — Determination of density*

ISO 7724 (all parts), *Paints and varnishes — Colorimetry*

3 Terms and definitions

Not applicable

4 Classification

Not applicable

5 Batch release and qualification testing

5.1 Batch release testing

For batch acceptance the tests marked with an * shall be performed.

5.2 Qualification tests

For product qualification, all tests mentioned in this standard, in the tables 1 to 4, shall be performed.

Table 1 — General requirements

Characteristic number	Characteristic	Requirements			
1.001	Material description	Two component cold curing polyurethane coating with high resistance to erosion by rain			
1.002	Formulation	Base — a base containing an hydroxyl functional resin, solvents and pigments to give the required colour and gloss and other ingredients to give rain erosion resistance Activator — a polyisocyanate activator solution Thinner — if required			
1.003	Preparation	These components shall be mixed in simple whole number proportions, by volume or by weight, in accordance with the manufacturer's instructions			
1.004	Technical specification	See EN 3840			
1.007	Visual colour	See EN 3840			
1.008	Freedom from defects	See EN ISO 1513			
1.009	Application and use	Dry film thickness of $(250 \pm 50) \mu\text{m}$			
1.010	Storage stability	See EN 3840			
1.011	Shelf life	See EN 3840			
1.013	Drying conditions	EN 23270 for 7 days before testing unless otherwise specified			
1.093	Quality assurance	See EN 3840			
1.094	Designation	Polyurethane Finish Rain Erosion Resistant Coating EN 4595			
1.095	Packaging	See EN 3840			
1.096	Marking	See EN 3840			
1.097	Flash point	EN 3840			
		Test 7 EN ISO 3679 or EN ISO 3680			
			base	activator ^f	thinner ^f
		°C	≥ reference value ^c	≥ reference value ^c	≥ reference value ^c
1.098	Health and safety	See EN 3840			
1.999	Notes	^f Test only if component is present. ^c The reference value is that established during qualification.			

Table 2 — Physical and chemical characteristics (1 of 2)

Characteristic number	Characteristic	Requirements			
2.008	Condition *	1	EN ISO 1513		
		6	As received in original container		
		7	Shall be free from extraneous matter and show no skinning, gelling, hard settlement or other defect which will prevent satisfactory application to produce a defect free film		
2.009	Application properties and finish *	1	None		
		3	EN 3837 — A ₂	2024-T3 clad	
		4	EN 3837 — Process A	EN 2334 Pickle	
		5	EN 2435 primer + finish to this standard		
		7	Liquid paint shall result in an opaque even finish, free from runs, sags, wrinkling, pinholing or other defect		
2.106	Reactivity Pot life *	–	EN 3840		
		1	Test 20 EN ISO 9514 followed by Test 8 ^a EN ISO 2431 or Test 9 ^a EN ISO 2884		
		6	base + activator + thinner		
		7	s or Pa s	≤ 2 × initial value after 30 min	
2.107	Viscosity	–	EN 3840		
		1	Test 8 EN ISO 2431 ^a or Test 9 EN ISO 2884 ^a		
		6	base + activator + thinner		
		7	s or Pa s	± 10 % ^{b, c}	
2.104	Composition — Non volatile matter	–	EN 3840		
		1	Test 1 EN ISO 3251		
		7		base	activator
		–	%	± 2 ^{b, c}	± 2 ^{b, c}
2.104	Composition — Volatile organic compound (VOC) content	–	EN 3840		
		1	Test 49 EN ISO 11890-1		
		6	base + activator + thinner		
		7	g/l	≤ reference value ^{b, c}	
2.301	Density *	–	EN 3840		
		1	Test 3 EN ISO 2811		
		6	base		
		7	of ref. value	± 2 ^{b, c}	
2.301	Density *	–	EN 3840		
		1	Test 4 EN ISO 3675		
		6	activator + thinner		
		7		activator	thinner
		–	of ref. value	± 2 ^{b, c}	± 2 ^{b, c}

Table 2 (2 of 2)

Characteristic number	Characteristic	Requirements		
2.106	Reactivity — Through-dry time	–	EN 3840	
		1	Test 23 EN ISO 9117 mass = 1 500 g	
		3	EN 3837 — A ₂ 2024-T3 clad	
		4	EN 3837 Process A EN 2334 Pickle	
		5	EN 2435 primer + finish to this standard	
		6	EN 23270	
		7	h	≤ 16
2.999	Notes	<p>^a Test 8 shall be used for non-thixotropic paints and test 9 for thixotropic paints.</p> <p>^b The deviation is that compared to the reference value.</p> <p>^c The reference value is that established during qualification.</p>		

Table 3 — Mechanical characteristics

Characteristic number	Characteristic	Requirements		
3.111	Optical properties colour	–	EN 3840	
		1	Test 30 ISO 7724	
		3	EN 3837 — A ₂ 2024-T3 clad	
		4	EN 3837 Process A EN 2334 Pickle	
		5	EN 2435 primer + finish to this standard	
		6	EN 23270	
		7	ΔE	shall match the colour specified
3.111	Optical properties gloss 60°	–	EN 3840	
		1	Test 27 EN ISO 2813	
		3	EN 3837 — A ₂ 2024-T3 clad	
		4	EN 3837 Process A EN 2334 Pickle	
		5	EN 2435 primer + finish to this standard	
		6	EN 23270	
		7	Gloss units	shall match the gloss specified

Table 4 — Environmental characteristics

Characteristic number	Characteristic	Requirements	
4.306	Ultimate tensile elongation *	1	ISO 37
		3	PTFE sheet or similar material
		4	Finish only applied
		5	Free film of finish, allowed to condition for a further 8 h after removal from substrate
		6	EN 23270
		7	% ≥ 100
		4.110	Density of dried film *
3	PTFE sheet or similar material		
4	Finish only applied		
5	Free film of finish, allowed to condition for a further 8 h after removal from substrate		
6	EN 23270		
7	g/ml ≤ 1,3		
4.501	Resistance to fluids *		
		1	Test 35 EN ISO 2812-1
		3	EN 3837 — A ₂ 2024-T3 clad
		4	EN 3837 Process A EN 2334 Pickle
		5	EN 2435 primer + finish to this standard, panel cut to substrate with a knife immediately before testing
		6	Tri-n-butyl phosphate for 100 h at 70 °C
		7	No blistering, softening, lifting or other film defect
4.320	Rain erosion resistance *	1	Whirling arm test rig ^a
		3	EN 3837 — A ₂ 2024-T3 clad
		4	EN 3837 Process A EN 2334 Pickle
		5	EN 2435 primer + finish to this standard
		6	EN 23270
		7	< 50 g/m ² erosion; no pitting of the film after 1 × 15 min runs
		999	Notes

6 Designation

EXAMPLE

Description block	Identity block
POLYURETHANE FINISH RAIN EROSION RESISTANT COATING	EN 4595

Number of this standard _____

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™