BS EN 4655:2010



BSI Standards Publication

Aerospace series — Steel FE-PM1506 (X1CrNiMoAlTi12-10-2) — Vacuum induction melted and consumable electrode remelted — Solution treated and precipitation treated — Bars — a or D ≤ 200 mm — Rm ≥ 1 400 MPa

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



National foreword

This British Standard is the UK implementation of EN 4655:2010.

The UK participation in its preparation was entrusted to Technical Committee ACE/61/-/15, Steels for Aerospace Purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 62734 7

ICS 49.025.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2010.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 4655

September 2010

ICS 49.025.10

English Version

Aerospace series - Steel FE-PM1506 (X1CrNiMoAlTi12-10-2) - Vacuum induction melted and consumable electrode remelted - Solution treated and precipitation treated - Bars - a or D \leq 200 mm - Rm \geq 1 400 MPa

Série aérospatiale - Acier FE-PM1506 (X1CrNiMoAITi12-10-2) - Élaboré sous vide par induction et refondu à l'électrode consommable - Mis en solution et vieilli - Barres - a ou D ≤ 200 mm - Rm ≥ 1 400 MPa

Luft- und Raumfahrt - Stahl FE-PM1506 (X1CrNiMoAlTi12-10-2) - Vakuuminduktionserschmolzen und mit selbstverzehrender Elektrode umgeschmolzen -Lösungsgeglüht und ausgehärtet - Stangen - a oder D ≤ 200 mm - Rm ≥ 1 400 MPa

This European Standard was approved by CEN on 19 June 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2010 CEN

All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 4655:2010: E

Con	itents	Page
Forew	vord	3
Introd	duction	4
1	Scope	4
2	Normative references	1

Foreword

This document (EN 4655:2010) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2011, and conflicting national standards shall be withdrawn at the latest by March 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

BS EN 4655:2010 EN 4655:2010 (E)

Introduction

This European Standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This European Standard has been prepared in accordance with EN 4500-005.

1 Scope

This European Standard specifies the requirements relating to:

Steel FE-PM1506 (X1CrNiMoAlTi12-10-2) Vacuum induction melted and consumable electrode remelted Solution treated and precipitation treated Bars $a \text{ or } D \leq 200 \text{ mm}$ $R_m \geq 1 \text{ 400 MPa}$

for aerospace applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2043, Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings) 1)

EN 2951, Aerospace series — Metallic materials — Test method — Micrographic determination of content of non-metallic inclusions

EN 4258, Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use

EN 4500-005, Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 5: Specific rules for steels 1)

EN 4700-002, Aerospace series — Steel and heat resisting alloy — Technical specification — Part 002: Bar and section

Copyright British Standards Institution
Provided by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

¹⁾ Published as ASD-STAN Prestandard at the date of publication of this standard.

1	Material designation				F	E-PM15	06 (X1Cı	NiMoAlT	ī12-10-2)				
2	Chemical	Element	С	Si	Mn	Р	S	Cr	Ni	Мо	Al	Ti	N_2	Fe
	composition	min.	_	-	-	-	-	11,5	9,2	1,85	0,80	0,28	-	bass
	%	max.	0,015	0,10	0,10	0,010	0,005	12,5	10,2	2,15	1,10	0,40	0,01	base
3	Method of melting	Vacuum induction melted and consumable electrode remelted												
4.1	Form						В	ar						
4.2	Method of product	ion						-	-					1
4.3	.3 Limit dimension(s) mm a or $D \le 200$													
5	Technical specifical						EN 470	00-002						

6.1 Delivery condition		Solution treated	Solution treated and precipitation treated		
	Heat treatment	820 °C $\leq \theta \leq$ 860 °C / OQ, AQ or WQ + cooling to $\theta \leq$ 20 °C	820 °C \leq θ \leq 860 °C / OQ, AQ or WQ + cooling to θ \leq 20 °C + 530 °C \leq θ \leq 550°C / t \geq 4 h / AC + cooling to θ \leq 20 °C		
6.2	Delivery condition code	W	U		
7	Use condition	Solution treated and precipitation treated	Delivery condition		
	Heat treatment	Delivery condition + 530 °C $\leq \theta \leq$ 550°C / t \geq 4 h / AC	-		

Characteristics

8.1	Те	est sample(s)				See EN 4700-002.			
8.2	Те	est piece(s)			See EN 4700-002.				
8.3	He	eat treatment			Delivery condition Use condition				
9		mensions concerne		mm	a or <i>D</i> ≤ 200	a or <i>D</i> ≤ 200 ^a	75 ≤ a or <i>D</i> ≤ 200 ^a		
10	Th ea	ickness of cladding ch face	on	%	-	-	_		
11	Dii	rection of test piece	;		-	L	Т		
12		Temperature	θ	°C	-	Ambient	Ambient		
13		Proof stress	R _{p0,2}	MPa	-	≥ 1 300	≥ 1 300		
14	Т	Strength	R _m	MPa	-	≥ 1 400	≥ 1 400		
15		Elongation	Α	%	-	≥ 9	≥ 8		
16		Reduction of area	Z	%	-	≥ 50	≥ 45		
17	На	ardness			≤ 363 HB	≥ 400 HB	≥ 400 HB		
18	Sh	near strength	R_{c}	MPa	-	-	_		
19	Ве	ending	k	-	-	-	-		
20	lm	pact strength			-	Notch direction T $KV \ge 50 \text{ J, ambient}$ + $KV \ge 20 \text{ J, at} - 40 ^{\circ}\text{C}$	Notch direction L $KV \ge 40 \text{ J, ambient}$ + $KV \ge 15 \text{ J, at} - 40 ^{\circ}\text{C}$		
21		Temperature	θ	°C		-			
22		Time		h		-			
23		Stress	σ_{a}	MPa		-			
24	С	Elongation	а	%		_			
25		Rupture stress	σ_{R}	MPa		_			
26		Elongation at rupture	Α	%	-				
27	No	otes (see line 98)				а			

		1			
30	Microstructure	1		EN 4700-002	
		2		One per cast	
		3		Corresponding to ingot top	
		7	The	e δ ferrite content shall not exceed 2	%.
34	Grain size	-		See EN 4700-002.	
		7		$G \ge 6$, some 5 accepted	
44	External defects	-		See EN 4700-002.	
		1		Visual	
50	Cleanliness / inclusion content	-		See EN 4700-002.	
	(micro-cleanness)	7		EN 2951 - Category 5	
51	Macrostructure	-		See EN 4700-002.	
		7	Class	Condition	Severity
			1	Freckles	А
			2	White spots	А
			3	Radial segregation	А
			4	Ring pattern	В
61	Internal defects	-		See EN 4700-002.	
		7		EN 4050-4 - Class 5	
95 96 98	Marking inspection Dimensional inspection Notes	_ _ _	a 75 mm ≤ a or D ≤ 2100	See EN 4700-002. See EN 4700-002. mm may be tested in L or T direction	1
99	Typical use	_		-	
<u> </u>		<u> </u>			

100	-	Product qualification	_	See EN 2043.
				Qualification programme to be agreed between manufacturer and purchaser.

This page deliberately left blank

This page deliberately left blank

British Standards Institution (BSI)

BSI is the independent national body responsible for preparing British Standards and other standards-related publications, information and services. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001

BSI offers Members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Tel: +44 (0)20 8996 7669 Fax: +44 (0)20 8996 7001 Email: plus@bsigroup.com

Buying standards

You may buy PDF and hard copy versions of standards directly using a credit card from the BSI Shop on the website **www.bsigroup.com/shop.** In addition all orders for BSI, international and foreign standards publications can be addressed to BSI Customer Services.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Knowledge Centre.

Tel: +44 (0)20 8996 7004 Fax: +44 (0)20 8996 7005 Email: knowledgecentre@bsigroup.com

Various BSI electronic information services are also available which give details on all its products and services.

Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

BSI Subscribing Members are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration

Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at **www.bsigroup.com/BSOL**

Further information about BSI is available on the BSI website at **www.bsi-group.com/standards**

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. This does not preclude the free use, in the course of implementing the standard of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained. Details and advice can be obtained from the Copyright & Licensing Manager.

Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Tel +44 (0)20 8996 9001 Fax +44 (0)20 8996 7001 www.bsigroup.com/standards

