



BSI Standards Publication

**Aerospace series — Steel FE-
PM1507 (X1CrNiMoAlTi12-11-2)
— Vacuum induction melted
and consumable electrode
remelted — Solution treated
and precipitation treated —
Forgings — a or $D \leq 200$ mm
— $R_m \geq 1\,520$ MPa**

National foreword

This British Standard is the UK implementation of EN 4658:2010.

The UK participation in its preparation was entrusted to Technical Committee ACE/61/-/15, Steels for Aerospace Purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 62806 1

ICS 49.025.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2011.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN 4658

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2010

ICS 49.025.10

English Version

**Aerospace series - Steel FE-PM1507 (X1CrNiMoAlTi12-11-2) -
Vacuum induction melted and consumable electrode remelted -
Solution treated and precipitation treated - Forgings - a or $D \leq$
200 mm - $R_m \geq 1\,520$ MPa**

Série aérospatiale - Acier FE-PM1507 (X1CrNiMoAlTi12-11-2) - Élaboré sous vide par induction et refondu à l'électrode consommable - Mis en solution et vieilli - Pièces forgées et pièces matricées - a ou $D \leq 200$ mm - $R_m \geq 1\,520$ MPa

Luft- und Raumfahrt - Stahl FE-PM1507 (X1CrNiMoAlTi12-11-2) - Vakuuminduktionserschmolzen und mit selbstverzehrender Elektrode umgeschmolzen - Lösungsgeglüht und ausgelagert - Schmiedestücke - a oder $D \leq 200$ mm - $R_m \geq 1\,520$ MPa

This European Standard was approved by CEN on 9 July 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5

Foreword

This document (EN 4658:2010) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2011, and conflicting national standards shall be withdrawn at the latest by June 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-5.

1 Scope

This standard specifies the requirements relating to:

Steel FE-PM1507 (X1CrNiMoAlTi12-11-2)
Vacuum induction melted and consumable electrode remelted
Solution treated and precipitation treated
Forgings
 a or $D \leq 200$ mm
 $R_m \geq 1\,520$ MPa

for aerospace applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings)* ¹⁾

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4500-5, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 5: Specific rules for steels* ¹⁾

EN 4670, *Aerospace series — Steel FE-PM1507 (X1CrNiMoAlTi12-11-2) — Vacuum induction melted and consumable electrode remelted — Softened — Forging stock — a or $D \leq 300$ mm*

EN 4700-006, *Aerospace series — Steel and heat resisting alloys — Wrought products — Technical specification — Part 006: Pre-production and production forgings*

¹⁾ Published as ASD-STAN Prestandard at the date of publication of this standard by Aerospace and Defence Industries Association of Europe-Standardization (ASD-STAN) (www.asd-stan.org).

Material designation		FE-PM1507 (X1CrNiMoAlTi12-11-2)												
2	Chemical composition %	Element	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Ti	N ₂	Fe
		min.	–	–	–	–	–	11,0	10,25	1,75	1,35	0,20	–	base
		max.	0,015	0,10	0,10	0,010	0,005	12,5	11,25	2,25	1,75	0,50	0,01	
3	Method of melting	Vacuum induction melted and consumable electrode remelted												
4.1	Form	Forgings												
4.2	Method of production	Forged from forging stock EN 4670												
4.3	Limit dimension(s)	mm	a or D ≤ 200											
5	Technical specification	EN 4700-006												

6.1	Delivery condition	Solution treated		Solution treated and precipitation treated	
	Heat treatment	840 °C ≤ θ ≤ 860 °C / 2 h / WQ + Sub-zero to θ – 75 °C / 8 h		840 °C ≤ θ ≤ 860 °C / 2 h / WQ + Sub-zero to θ – 75 °C / 8 h + 525 °C ≤ θ ≤ 545 °C / t ≥ 8 h / AC	
6.2	Delivery condition code	W		U	
7	Use condition	Solution treated and precipitation treated		Delivery condition	
	Heat treatment	Delivery condition + 525 °C ≤ θ ≤ 545 °C / t ≥ 8 h / AC		–	

Characteristics

8.1	Test sample(s)	See EN 4700-006.			
8.2	Test piece(s)	See EN 4700-006.			
8.3	Heat treatment	Delivery condition		Use condition	
9	Dimensions concerned	mm	a or D ≤ 200	a or D ≤ 200 ^a	75 ≤ a or D ≤ 200 ^a
10	Thickness of cladding on each face	%	–	–	–
11	Direction of test piece		–	L	T
12	Temperature	θ	°C	–	Ambient
13	Proof stress	R _{p0,2}	MPa	–	≥ 1 380
14	T Strength	R _m	MPa	–	≥ 1 520
15	Elongation	A	%	–	≥ 10
16	Reduction of area	Z	%	–	≥ 40
17	Hardness		≤ 363 HB	≥ 426 HB	≥ 426 HB
18	Shear strength	R _c	MPa	–	–
19	Bending	k	–	–	–
20	Impact strength		–	Notch direction T KV ≥ 30 J; ambient	Notch direction L KV ≥ 25 J; ambient
21	Temperature	θ	°C	–	
22	Time		h	–	
23	Stress	σ _a	MPa	–	
24	Elongation	a	%	–	
25	Rupture stress	σ _R	MPa	–	
26	Elongation at rupture	A	%	–	
27	Notes (see line 98)			a	

30	Microstructure	1	See EN 4700-006.		
		2	One per cast.		
		3	Corresponding to ingot top.		
		7	The δ ferrite content shall not exceed 2 %.		
34	Grain size	–	See EN 4700-006.		
		7	$G \geq 6$, some 5 accepted.		
44	External defects	–	See EN 4700-006.		
		1	Visual.		
50	Cleanliness / inclusion content (micro-cleanness)	1	EN 4700-006		
		7	Category 5		
51	Macrostructure	–	See EN 4700-006.		
		7	Class	Condition	Severity
			1	Freckles	A
			2	White spots	A
			3	Radial segregation	A
4	Ring pattern	B			
61	Internal defects	–	See EN 4700-006.		
		6	a or $D \leq 100$ mm may be tested either on the product or at an earlier stage of manufacturing.		
		7	Class 5		
95	Marking inspection	–	See EN 4700-006.		
96	Dimensional inspection	–	See EN 4700-006.		
98	Notes	–	^a $75 \text{ mm} \leq a$ or $D \leq 200$ mm may be tested in L or T direction.		
99	Typical use	–	–		

100	-	Product qualification	-	See EN 2043.
				Qualification programme to be agreed between manufacturer and purchaser.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™