

BS EN 4688:2012



BSI Standards Publication

Aerospace series — Paints and varnishes — Corrosion inhibiting two components cold curing primer for military application

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 4688:2012.

The UK participation in its preparation was entrusted to Technical Committee ACE/65/-/3, Paints, Surface Finish and Protective Treatments for Aerospace Purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 76850 7

ICS 49.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2012.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN 4688

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2012

ICS 49.040

English Version

Aerospace series - Paints and varnishes - Corrosion inhibiting two components cold curing primer for military application

Série aérospatiale - Peinture et vernis - Peinture primaire anti corrosion chromate à deux composants polymérisant à température ambiante pour applications militaires

Luft- und Raumfahrt - Beschichtungsstoffe - Zweikomponenten Grundbeschichtung, korrosionshemmend, raumtemperaturhärtend, für militärische Anwendung

This European Standard was approved by CEN on 21 January 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	6
4 Surface pretreatment.....	7
5 Classification.....	7
6 Batch release and qualification testing	7
7 Designation	18

Foreword

This document (EN 4688:2012) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2012, and conflicting national standards shall be withdrawn at the latest by September 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard defines the requirements for a two components, high corrosion inhibiting epoxy primer.

The coating should be suitable for use on suitably prepared metallic substrates, chromic acid anodized or conversion coated aluminium alloys, fibre reinforced composite materials and other suitably prepared substrates.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2101, *Aerospace series — Chromic acid anodizing of aluminium and wrought aluminium alloys*

EN 2334, *Aerospace series — Chromic-sulphuric acid pickle of aluminium and aluminium alloys*

EN 2437, *Aerospace series — Chromate conversion coatings (yellow) for aluminium and aluminium alloys*

EN 3212, *Aerospace series — Paints and varnishes — Corrosion test by alternate immersion in a buffered sodium chloride solution*

EN 3837, *Aerospace series — Paints and varnishes — Nature and method for surface preparation of test pieces in aluminium alloys*¹⁾

EN 3840, *Aerospace series — Paints and varnishes — Technical specification*

EN 3847, *Aerospace series — Paints and varnishes — Determination of sedimentation rating*¹⁾

EN 4160, *Aerospace series — Non-metallic materials — Paints and varnishes — Test methods — Determination of the effect of thermal exposure*¹⁾

EN 4687, *Aerospace series — Paints and varnishes — Chromate free non corrosion inhibiting two components cold curing primer for military application*

EN 4689, *Aerospace series — Paints and varnishes — Two components cold curing polyurethane finish — High flexibility and chemical agent resistance for military application*

EN ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

EN ISO 1518, *Paints and varnishes — Scratch test*

EN ISO 1519, *Paints and varnishes — Bend test (cylindrical mandrel)*

EN ISO 1520, *Paints and varnishes — Cupping test*

EN ISO 1524, *Paints, varnishes and printing inks — Determination of fineness of grind*

1) Published as ASD-STAN Prestandard at the date of publication of this standard (www.asd-stan.org).

- EN ISO 2409, *Paints and varnishes — Cross-cut test*
- EN ISO 2431, *Paints and varnishes — Determination of flow time by use of flow cups*
- EN ISO 2811-1, *Paints and varnishes — Determination of density — Part 1: Pyknometer method*
- EN ISO 2811-2, *Paints and varnishes — Determination of density — Part 2: Immersed body (plummet) method*
- EN ISO 2811-3, *Paints and varnishes — Determination of density — Part 3: Oscillation method*
- EN ISO 2811-4, *Paints and varnishes — Determination of density — Part 4: Pressure cup method*
- EN ISO 2812-1, *Paints and varnishes — Determination of resistance to liquids — Part 1: Immersion in liquids other than water*
- EN ISO 2812-2, *Paints and varnishes — Determination of resistance to liquids — Part 2: Water immersion method*
- EN ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20°, 60° and 85°*
- EN ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*
- EN ISO 3675, *Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method*
- EN ISO 3678, *Paints and varnishes — Print-free test*
- EN ISO 3679, *Determination of flash point — Rapid equilibrium closed cup method*
- EN ISO 3680, *Determination of flash/no flash — Rapid equilibrium closed cup method*
- EN ISO 4623-2, *Paints and varnishes — Determination of resistance to filiform corrosion — Part 2: Aluminium substrates*
- EN ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*
- EN ISO 4628-8, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 8: Assessment of degree of delamination and corrosion around a scribe*
- EN ISO 4628-10, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 10: Assessment of degree of filiform corrosion*
- EN ISO 6270-1, *Paints and varnishes — Determination of resistance to humidity — Part 1: Continuous condensation*
- EN ISO 9117-1, *Paints and varnishes — Drying tests — Part 1: Determination of through-dry state and through-dry time*
- EN ISO 9117-3, *Paints and varnishes — Drying tests — Part 3: Surface-drying test using ballotini*
- EN ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

EN ISO 9514, *Paints and varnishes — Determination of the pot life of multicomponent coating systems — Preparation and conditioning of samples and guidelines for testing*

EN ISO 11890-1, *Paints and varnishes — Determination of volatile organic compound (VOC) content — Part 1: Difference method*

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 7724-1, *Paints and varnishes — Colorimetry — Part 1: Principles*

ISO 7724-2, *Paints and varnishes — Colorimetry — Part 2: Colour measurement*

ISO 7724-3, *Paints and varnishes — Colorimetry — Part 3: Calculation of colour differences*

MIL-PRF-5606H, *Performance specification: Hydraulic fluid, petroleum base; aircraft, missile, and ordnance. (NATO H-515) ²⁾*

MIL-PRF-6081D, *Performance specification: Lubricating oil, jet engine. (NATO O-133) ²⁾*

MIL-PRF-23699F, *Performance specification: Lubricating oil, aircraft turbine engine, synthetic base, NATO code number O-156 ²⁾*

MIL-DTL-83133G, *Detail specification: Turbine fuel, aviation, kerosene type, JP-8 (NATO F-34), NATO F-35, and JP-8+100 (NATO F-37) ²⁾*

AMS 1526B, *Cleaner for aircraft exterior surfaces water-miscible, pressure- spraying type ³⁾*

AMS 1527B, *Standard Practice for Operating Salt Spray (Fog) Apparatus ³⁾*

AMS 1533A, *Cleaner for exterior aircraft surfaces gel-type, solvent-base ³⁾*

ASTM B 117, *Cleaner for exterior aircraft surfaces gel-type, solvent-base ⁴⁾*

DEF STAN 68-10, *Corrosion Preventive, Water Displacing NATO Code: C-634 Joint Service Designation: PX-24*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 3840 apply.

2) Published by: DoD National (US) MIL. Department of Defense <http://www.defenselink.mil/>

3) Published by: SAE National (US) Society of Automotive Engineers <http://www.sae.org/>

4) Published by: ASTM National (US) American Society for Testing and Materials <http://www.astm.org/>

4 Surface pretreatment

In accordance with EN 3837, the surface pretreatment applicable to aluminium alloy test panels are the following:

EN 3837 — Procedure A : Sulfochromic pickling in accordance with EN 2334;

EN 3837 — Procedure B : Chromic acid anodizing in accordance with EN 2101;

EN 3837 — Procedure C : Chromate conversion coating in accordance with EN 2437.

5 Classification

The primer is classified according to the following types:

TYPE I: Standard solvent content (VOC < 680 g/l);

TYPE II: Low volatile organic (VOC < 420 g/l);

TYPE III: Waterborne (VOC < 350 g/l).

6 Batch release and qualification testing

6.1 General

The general requirements for qualification and batch release testing shall be in accordance with (i.a.w.) EN 3840 and the applicable appendix for the specific material.

6.2 Qualification tests

For product qualification, all tests defined in this standard, in the Tables 2 to 7, shall be performed. A minimum of three batches shall be tested for qualification purposes.

6.3 Batch acceptance testing

The Manufacturer shall give evidence on the Test Report or the Certificate of Conformance that all the tests marked with the symbol * in this specification shall be performed for batch acceptance tests.

6.4 Compatibility of waterborne paints to solventborne paints

The waterborne primer type III shall be compatible to solventborne primers type I and type II according to this standard and to type I and type II primers to EN 4687. All tests to demonstrate the compatibility are defined in Table 7 and shall be performed.

6.5 Purchaser batch release testing

The purchaser may perform any of the test of this specification deemed necessary to ensure continuing uniform quality in material shipments.

Table 1 — General requirements

	Material description	Primer, corrosion inhibiting, for aerospace applications
	Formulation	Base Activator Thinner – if appropriate
	Preparation	These components shall be mixed in simple whole number proportions, by volume or weight, in accordance with the manufacturer's instructions.
	Technical specification	EN 3840
	Marking	See EN 3840.
	Storage stability	See EN 3840.
	Application and use	Dry film thickness of $(25 \pm 5) \mu\text{m}$
	Drying conditions	$(23 \pm 2) ^\circ\text{C}$ / $(50 \pm 5) \% \text{RH}$ for 7 (seven) days before testing, or after air drying for 4 (four) hours to 6 (six) hours before the application of the topcoat EN 4689. ISO 3270 for 7 (seven) days before application of the top EN 4689.
	Quality assurance	See EN 3840.
	Designation	Primer corrosion inhibiting
	Packaging	See EN 3840.
	Health and safety	See EN 3840.

Table 2 — Physical and chemical characteristics – Delivery conditions

Tests according to EN 3840	Test	Test criteria	Test requirements			
— *	Condition	Test method	EN ISO 1513 (as received in the original container)			
		Requirement	Shall be free from contaminants and show no skinning, gelling, hard settlement, or other defect.			
1 *	Non volatile matter	Test method	EN ISO 3251			
		Requirement	% m/m	Base $\pm 2 \% \text{ reference value }^{a b}$	Activator $\pm 2 \% \text{ reference value }^{a b}$	Thinner —
49	Volatile organic content (VOC) (not Type I)	Test method	EN ISO 11890-1			
		Test condition	Base + Activator + Thinner			
		Requirement	g/l	< reference value ^a		

continued

Table 2 — Physical and chemical characteristics – Delivery conditions (continued)

Tests according to EN 3840	Test	Test criteria	Test requirements			
7	Flash point	Test method	EN ISO 3679 or EN ISO 3680			
		Requirement	°C	Base	Activator	Thinner
				≥ reference value ^a	≥ reference value ^a	≥ reference value ^a
8 *	Flow time	Test method	EN ISO 2431			
		Test condition	Base + Activator + Thinner			
		Requirement	s	± 10 % reference value ^{a b}		
5	Sedimentation rating	Test method	EN 3847			
		Coating	Base + Activator + Thinner			
		Requirement	ml/4 h	≤ 30		
3 * 4 *	Density	Test method	EN ISO 2811-1 to EN ISO 2811-4 or EN ISO 3675			
		Test condition	(23 ± 2) °C / (50 ± 5) % RH			
		Requirement	g/cm ³	Base	Activator	Thinner
				a	a	a
10	Fineness of grind	Test method	EN ISO 1524			
		Requirement	µm	Base	Activator	Thinner
				c	c	—
— *	Application, properties and finish	Test method	None			
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)			
		Pretreatment	EN 3837 — Procedure A or B or C			
		Coating	Coating to this standard.			
		Test condition	(23 ± 2) °C / (50 ± 5) % RH			
		Requirements	The paint film applied shall result in an opaque even finish free from runs, sags, wrinkling, pinholing or other defects.			
20 *	Pot life	Test method	EN ISO 9514			
		Coating	Base + Activator + Thinner			
		Requirement	s or Pa.s	a		

continued

Table 2 — Physical and chemical characteristics – Delivery conditions (concluded)

Tests according to EN 3840	Test	Test criteria	Test requirements	
21 *	Drying time at the surface	Test method	EN ISO 9117-3	
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)	
		Pretreatment	EN 3837 — Procedure A or B or C	
		Coating	Coating to this standard.	
		Requirement	h	Type I ≤ 1 Type II ≤ 2,5 Type III ≤ 2 Type IV ^a Type V ^a
22 *	Drying time – Print free test	Test method	EN ISO 3678	
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)	
		Pretreatment	EN 3837 — Procedure A or B or C	
		Coating	Coating to this standard.	
		Requirement	h	Type I ≤ 4 using a mass of 1 000 g Type II ≤ 5 using a mass of 1 000 g Type III ≤ 4 using a mass of 1 000 g Type IV ^a Type V ^a
23 *	Through dry time	Test method	EN ISO 9117-1	
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)	
		Pretreatment	EN 3837 — Procedure A or B or C	
		Coating	Coating to this standard.	
		Requirement	h	≤ 16 using a mass of 1 500 g

* See 6.3.

^a The reference value is that established during qualification.

^b The deviation is that compared to the reference value.

^c To be agreed between manufacturer and customer.

Table 3 — Mechanical and physical characteristics – Dried film

Tests according to EN 3840	Test	Test criteria	Test requirements
24 *	Cross cut adhesion	Test method	EN ISO 2409
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedures B and C (CAA and CCC)
		Coating	Coating to this standard.
		Test condition	(23 ± 2) °C / (50 ± 5) % RH
		Requirement	Classification 0
29 *	Scratch resistance	Test method	EN ISO 1518
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedures B and C (CAA and CCC)
		Coating	Coating to this standard.
		Test condition	(23 ± 2) °C / (50 ± 5) % RH
		Requirement	≥ 1 500 g ^a
46 *	Slow deformation	Test method	EN ISO 1520
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedures B and C (CAA and CCC)
		Coating	Coating to this standard.
		Test condition	(23 ± 2) °C / (50 ± 5) % RH
		Requirement	≥ 3 m ^b
30 *	Colour	Test method	ISO 7724-1 to ISO 7724-3
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure A or B or C
		Coating	Coating to this standard.
		Test condition	(23 ± 2) °C / (50 ± 5) % RH
		Requirement	c

continued

Table 3 — Mechanical and physical characteristics – Dried film (concluded)

Tests according to EN 3840	Test	Test criteria	Test requirements
27 *	Specular gloss	Test method	EN ISO 2813
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure A or B or C
		Coating	Coating to this standard.
		Test condition	(23 ± 2) °C / (50 ± 5) % RH
		Requirement	c
25	Bend test cylindrical mandrel	Test method	EN ISO 1519 (mandrel Ø = 100 mm)
		Panel	EN 3837 — A ₆ 2024-T3 clad
		Pretreatment	EN 3837 — Procedures B and C
		Coating	Coating to this standard.
		Test condition	(– 55 ± 2) °C
		Requirement	Mandrel: Ø 100 mm ^b
<p>* See 6.3.</p> <p>a Substrate not exposed.</p> <p>b No cracking or detachment (×10 magnification).</p> <p>c To be agreed between manufacturer and customer.</p>			

Table 4 — Environmental exposure/testing – Dried film

Tests according to EN 3840	Test	Test criteria	Test requirements
38	Thermal exposure (resistance to high temperature)	Test method	EN 4160
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedures B and C
		Coating	Coating to this standard.
		Exposure	(150 ± 2) °C 24 h
		Requirement ^a	EN 3840 test 24 — Classification 0 EN 3840 test 29 ≥ 1 500 g ^b EN 3840 test 46 ≥ 3 mm ^c
37	Resistance to humidity	Test method	EN ISO 6270-1
		Panel	EN 3837 — A ₁ (2024-T3 unclad)
		Pretreatment	EN 3837 — Procedures B and C
		Coating	Coating to this standard.
		Exposure	(40 ± 2) °C / (95 to 100) % RH 1 000 h
		Requirement ^a	EN 3840 test 24 — Classification 0 EN 3840 test 29 ≥ 1 500 g ^b EN 3840 test 46 ≥ 3,0 mm ^c EN ISO 4628-2, degree of blistering 0
34	Water behaviour	Test method	EN ISO 2812-2
		Panel	EN 3837 — A ₁ (2024-T3 unclad)
		Pretreatment	EN 3837 — Procedures B and C
		Coating	Coating to this standard.
		Exposure	(40 ± 2) °C 168 h
		Requirement ^a	EN 3840 test 24 — Classification ≤ 1 EN 3840 test 29 ≥ 1 500 g ^b EN 3840 test 46 ≥ 3 mm ^c EN ISO 4628-2, degree of blistering 0
^a Tests to be performed at (23 ± 2) °C / (50 ± 5) % RH. ^b Substrate not exposed. ^c No cracking or detachment (×10 magnification).			

Table 5 — Corrosion tests – Dried film

Tests according to EN 3840	Test	Test criteria	Test requirements
42	Resistance to neutral salt spray	Test method	EN ISO 9227 or ASTM B 117
		Panel	EN 3837 — A ₁ 2024-T3 unclad
		Pretreatment	EN 3837 — Procedure (A and C) or (B and C)
		Coating	Coating to this standard.
		Exposure	(35 ± 2) °C 3 000 h — Procedure B (35 ± 2) °C 1 000 h — Procedures A and C
		Requirement	EN 3840 test 24 — Classification ≤ 1 EN 3840 test 29 ≥ 1 500 g ^a EN 3840 test 46 ≥ 3 mm ^b EN ISO 4628-8 No corrosion more than 1,25 mm from the scratch EN ISO 4628-2, degree of blistering 0
41	Resistance to alternate immersion	Test method	EN 3212
		Panel	EN 3837 — A ₁ 2024-T3 unclad
		Pretreatment	EN 3837 — Procedures B and C
		Coating	Coating to this standard.
		Exposure	(35 ± 2) °C 1 500 h
		Requirement	EN 3840 test 24 — Classification ≤ 1 EN 3840 test 29 ≥ 1 500 g ^a EN ISO 4628-8 No corrosion more than 1,25 mm from the scratch EN ISO 4628-2, degree of blistering 0
43	Filiform corrosion resistance	Test method	EN ISO 4623-2
		Panel	EN 3837 — A ₁ 2024-T3 unclad
		Pretreatment	EN 3837 — Procedures B and C
		Coating	Primer according to this standard plus Top Coat according to EN 4689
		Exposure	(40 ± 2) °C (82 ± 3) % RH 1 000 h
		Requirement	EN ISO 4628-10 No corrosion more than 2,0 mm from the scratch EN ISO 4628-2, degree of blistering 0
^a Substrate not exposed. ^b No cracking or detachment (×10 magnification).			

Table 6 — Exposure to system fluids and corrosion generating environment/testing — Dried film

Tests according to EN 3840	Test	Test criteria	Test requirements
35	Resistance to fluids – Hydraulic oil MIL-PRF-5606H (NATO H-515)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(70 ± 2) °C 300 h
		Requirement ^a	EN 3840 test 24 — Classification ≤ 1 ^b EN 3840 test 29 ≥ 1 500 g ^c EN ISO 4628-2, degree of blistering 0
35	Resistance to fluids – Jet fuel MIL-DTL-83133G (NATO F-34)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(40 ± 2) °C 1 000 h
		Requirement ^a	EN 3840 test 24 — Classification ≤ 1 ^b EN 3840 test 29 ≥ 1 500 g ^c EN 3840 test 46 ≥ 3 mm ^d EN ISO 4628-2, degree of blistering 0
35	Resistance to fluids – Aircraft washing agent (AMS 1527B)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(23 ± 2) °C 24 h
		Requirement ^a	EN 3840 test 24 — Classification 0 EN 3840 test 29 ≥ 1 500 g ^c EN 3840 test 46 ≥ 3 mm ^d EN ISO 4628-2, degree of blistering 0

continued

Table 6 — Exposure to system fluids and corrosion generating environment/testing – Dried film (continued)

Tests according to EN 3840	Test	Test criteria	Test requirements
35	Resistance to fluids – Corrosion preventive compound DEF STAN 68-10 (NATO C-634)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(40 ± 2) °C 1 000 h
		Requirement ^a	EN 3840 test 24 — Classification 0 EN 3840 test 29 ≥ 1 500 g ^c EN 3840 test 46 ≥ 3 mm ^d EN ISO 4628-2, degree of blistering 0
35	Resistance to fluids – Aircraft cleaning compound (AMS 1526B/ AMS 1533A)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(23 ± 2) °C 24 h
		Requirement ^a	EN 3840 test 24 — Classification 0 EN 3840 test 29 ≥ 1 500 g ^c EN 3840 test 46 ≥ 3 mm ^d EN ISO 4628-2, degree of blistering 0
35	Resistance to fluids – Engine oil MIL-PRF-23699F (NATO O-156)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(70 ± 2) °C 300 h
		Requirement ^a	EN 3840 test 24 — Classification ≤ 1 ^b EN 3840 test 29 ≥ 1 500 g ^c EN ISO 4628-2, degree of blistering 0

continued

Table 6 — Exposure to system fluids and corrosion generating environment/testing – Dried film (concluded)


Tests according to EN 3840	Test	Test criteria	Test requirements
35	Resistance to fluids – Engine corrosion inhibiting fluid MIL-PRF-6081D (NATO O-133)	Test method	EN ISO 2812-1
		Panel	EN 3837 — A ₁ or EN 3837 — A ₂ (2024-T3 unclad or 2024-T3 clad)
		Pretreatment	EN 3837 — Procedure B or C
		Coating	Coating to this standard.
		Exposure	(60 ± 2) °C 168 h
		Requirement ^a	EN 3840 test 24 — Classification 0 EN 3840 test 29 ≥ 1 500 g ^c EN 3840 test 46 ≥ 3 mm ^d EN ISO 4628-2, degree of blistering 0
^a Tests to be performed at (23 ± 2) °C / (50 ± 5) % RH. ^b Degrease surface before application of tape. ^c Substrate not exposed. ^d No cracking or detachment (×10 magnification).			

Table 7 — Demonstration of compatibility of solvent borne primer to waterborne primer, mechanical and physical characteristics – Primer type I or II and primer type III

Tests according to EN 3840	Test	Test criteria	Test requirements
24 *	Cross cut adhesion	Test method	EN ISO 2409
		Panel	EN 3837 — A ₂ 2024-T3 clad
		Pretreatment	EN 3837 — Procedure (A and C) or (B and C) plus coating (see below)
		Coating	All types according to this standard shall be tested on compatibility among each other
		Exposure	—
		Requirement	Classification 0
46 *	Slow deformation	Test method	EN ISO 1520
		Panel	EN 3837 — A ₂ 2024-T3 clad
		Pretreatment	EN 3837 — Procedure (A and C) or (B and C) plus coating (see below)
		Coating	All types according to this standard shall be tested on compatibility among each other
		Exposure	—
		Requirement	≥ 3 mm ^a
34	Water behaviour	Test method	EN ISO 2812-2
		Panel	EN 3837 — A ₂ 2024-T3 clad
		Pretreatment	EN 3837 — Procedure (A and C) or (B and C) plus coating (see below)
		Coating	All types according to this standard shall be tested on compatibility among each other
		Exposure	(40 ± 2) °C 168 h
		Requirement	EN ISO 2409 — Classification ≤ 1 EN ISO 4628-2, degree of blistering 0
* See 6.3.			
^a No cracking or detachment (×10 magnification).			

7 Designation

EXAMPLE



British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™