BS EN 4800-004:2010



BSI Standards Publication

Aerospace series — Titanium and titanium alloys — Technical specification

Part 004: Wire

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



National foreword

This British Standard is the UK implementation of EN 4800-004:2010.

The UK participation in its preparation was entrusted to Technical Committee ACE/61/-/49, Titanium and its Alloys for Aerospace Purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 53322 8

ICS 49.025.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2010.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 4800-004

November 2010

ICS 49.025.30

English Version

Aerospace series - Titanium and titanium alloys - Technical specification - Part 004: Wire

Série aérospatiale - Titane et alliages de titane -Spécification technique - Partie 004: Fils Luft- und Raumfahrt - Titan und Titanlegierungen Kneterzeugnisse - Technische Lieferbedingungen - Teil 004: Drähte

This European Standard was approved by CEN on 20 February 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2010 CEN

All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 4800-004:2010: E

Cont	tents	Page
Forew	ord	3
Introd	uction	4
1	Scope	5
2	Normative references	5
3	Terms and definitions	6
4	Wording of order	6
	Health and safety	
6	Technical requirements	7

Foreword

This document (EN 4800-004:2010) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2011, and conflicting national standards shall be withdrawn at the latest by May 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

1 Scope

This standard defines the requirements for the ordering, manufacture, testing, inspection and delivery of titanium and titanium alloy wire. It shall be applied when referred to and in conjunction with the EN material standard unless otherwise specified on the drawing, order or inspection schedule.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2002-001, Aerospace series — Metallic materials — Test methods — Part 001: Tensile testing at ambient temperature

EN 2002-002, Aerospace series — Metallic materials — Test methods — Part 002: Tensile testing at elevated temperature

EN 2002-005, Aerospace series — Test methods for metallic materials — Part 005: Uninterrupted creep and stress-rupture testing

EN 2002-16, Aerospace series — Metallic materials — Test methods — Part 16: Non-destructive testing — Penetrant testing ¹⁾

EN 2003-009, Aerospace series — Test methods — Titanium and titanium alloys — Part 009: Determination of surface contamination

EN 2032-1, Aerospace series — Metallic materials — Part 1: Conventional designation

EN 2032-2, Aerospace series — Metallic materials — Part 2: Coding of metallurgical condition in delivery condition

EN 2078, Aerospace series — Metallic materials — Manufacturing schedule, inspection schedule, inspection and test report — Definition, general principles, preparation and approval

EN 2955, Aerospace series — Recycling of titanium and titanium alloy scrap

EN 3238, Aerospace series — Metallic materials — Test method — Shear test for wires and rivets

EN 3114-001, Aerospace series — Test method — Microstructure of $(\alpha + \beta)$ titanium alloy wrought products — Part 001: General requirements

EN 3114-002, Aerospace series — Test method — Microstructure of $(\alpha + \beta)$ titanium alloy wrought products — Part 002: Microstructure of bars, sections, forging stock and forgings

EN 3683, Aerospace series — Test methods — Titanium alloy wrought products — Determination of primary α content — Point count method and line intercept method

EN 3684, Aerospace series — Test methods — Titanium alloy wrought products — Determination of β transus temperature — Metallographic method

_

¹⁾ Published as ASD-STAN Prestandard at the date of publication of this standard.

EN 3976, Aerospace series — Titanium and titanium alloys — Test method — Chemical analysis for the determination of hydrogen content

EN 4258, Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use

EN 4259, Aerospace series — Metallic materials — Definition of general terms ²⁾

EN 9100, Quality Management Systems — Requirements for Aviation, Space and Defense Organizations

EN 9133, Aerospace series — Quality management systems — Qualification procedure for aerospace standard parts

EN ISO 643, Steels — Micrographic determination of the apparent grain size (ISO 643:2003)

EN ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2009)

prEN ISO 6892-2, Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature (ISO/DIS 6892-2:2009)

ISO 7800, Metallic materials — Wire — Simple torsion test

ISO 7801, Metallic materials — Wire — Reverse bend test

ISO 7802, Metallic materials — Wire — Wrapping test

ISO 9649, Metallic materials — Wire — Reverse torsion test

TR 2410, Aerospace series — Metallic materials — Relationship between dimensional standards and material standards 3)

AMS 2750, Pyrometry 4)

Terms and definitions

For the purposes of this document, the terms and definitions given in EN 4259 apply.

Wording of order

The order shall clearly indicate:

- quantities to be supplied;
- dates of delivery;
- material standard number;

²⁾ Published as ASD-STAN Prestandard at the date of publication of this standard

³⁾ Published as ASD-STAN Technical Report at the date of publication of this standard.

⁴⁾ Published by: American Society for Testing and Materials (ASTM), 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA, 19428-2959 USA.

- delivery condition and metallurgical code of products;
- dimensions and tolerances or reference to an appropriate dimensional standard;
- product designation, when required;
- forwarding address;
- nature and type of packing, if required;
- definition and frequency of any special tests and their retest procedures, if required.

5 Health and safety

Products in the delivery condition shall fulfil the health and safety laws of the area of the country when and where it is to be delivered.

A product safety data sheet shall be available.

6 Technical requirements

6.1 General

The product shall be manufactured in accordance with the requirements of the relevant material standard and the applicable requirements of this specification. A manufacturing schedule shall be established and applied in accordance with EN 2078.

The product shall satisfy the requirements of the material standard and/or order and shall be free from irregularities prejudicial to the subsequent manufacture or use of this product.

Notwithstanding previous acceptance complying with this material standard, any product that is found, at a later stage, to contain such defects shall be rejected

Unless otherwise specified, the requirements in Tables 1 and 2 shall apply in conjunction with those of the relevant material standard. Table 1 relates to lines 1 to 29 (inclusive) of the material standard and Table 2 relates to lines 30 onwards in which the sub-line format is also used. Lines 2 to 98 may also be opened in line 100 if the material standard details specific qualification requirements. If a specific line number is not shown in Tables 1 and 2, the requirement is stated in the material standard and/or order.

The requirements of the order and/or material standard shall over-ride the requirements of the technical specification

6.2 Qualification requirements

Qualification requirements when invoked by the material standard and/or order are detailed in Tables 1 and 2. Unless otherwise agreed between the manufacturer and purchaser the qualification phase shall be run on the first three batches, coming from three different ingots.

6.3 Release requirements

6.3.1 Release tests

Release testing shall be the responsibility of the manufacturer.

The purchaser reserves the right to perform any of the inspections and/or tests required by the material standard and/or order.

The test samples shall be representative of the product.

When required the manufacturer shall inform the purchaser of the planned dates for extraction of samples and release testing in order that these operations may be witnessed.

Tables 1 and 2 detail the requirements for each line of the material standard. Unless otherwise specifically requested by the purchaser, a particular inspection and/or test for release shall be carried out if corresponding acceptance criteria and/or values are stated in the applicable material standard, but see also 6.3.5.

6.3.2 Retests

If the test procedure or test piece preparation is faulty, testing shall be re-applied at the original frequency after rectification of the original cause of failure.

When failure cannot be attributed to faulty testing, or test piece preparation, further test samples shall be selected at twice the original frequency from the product, one of which shall be that on which the original results were obtained unless already withdrawn by the manufacturer after suitable identification of the cause of failure. If all retest results are satisfactory, the batch shall be accepted. If one or more tests are unsatisfactory, the batch shall be:

- rejected; or
- 100 % retested and the conforming products accepted; or
- partially or fully re-heat treated if heat treatment can rectify the cause of the failure and tested as a completely new batch except for chemical composition, for which redetermination of hydrogen content is required. No product or test sample shall be re-heat treated more than twice.

6.3.3 Rejection

Any failure to meet the requirements of the material standard shall be cause for rejection.

6.3.4 Special tests

Special tests may be required by the purchaser. In such cases, the nature of the test, method, frequency and technical requirements shall be specified on the order or inspection schedule and shall be mutually agreed by the manufacturer and purchaser.

6.3.5 Capability clause

Where capability clause is invoked and where sufficient statistical evidence exists, the test shall not be carried out (unless specifically requested by the purchaser). However, this in no way reduces the obligations of the manufacturer to fulfil the requirements. If subsequent testing indicates that the product does not comply with the requirements, the batch shall be rejected.

If sufficient statistical evidence does not exist, the test shall be carried out at a frequency agreed between the manufacturer and the purchaser.

6.3.6 Statistical process control

Reduction in the extent of release testing, other than that defined in 6.3.5 above, may be negotiated with the purchaser on the basis of appropriate statistical process control and/or statistical data.

6.3.7 Inspection and test report

The manufacturer shall furnish, with each delivery, a report conforming to the requirements of EN 2078 stating the following:

- manufacturer's name and address and, if appropriate, identification of the plant;
- order number:
- material standard number;
- delivery condition and metallurgical code of the product;
- quantity and dimensions;
- manufacturing and inspection schedule reference;
- cast and batch number;
- batch and/or test samples heat treatment condition;
- results of the tests and retests if any.

6.4 Traceability

Each product shall be traceable to the cast, production batch and/or heat treatment batch at all stages of manufacture, testing and delivery.

Table 1 — Technical requirements for lines 1 to 29, where appropriate

	Material standard line		Frequency	of testing
N	reference	Requirements		Release
1	Material designation	See EN 2032-1.	_	-
2	Chemical composition	The test samples used for chemical analysis shall be representative of the product and shall be taken from location corresponding to top and bottom of each ingot produced after the final melting stage. The method of chemical analysis shall be at the discretion of the manufacturer unless otherwise stated in the material standard or order. In cases of dispute, the method of chemical analysis shall be agreed between the manufacturer and purchaser preferably using existing chemical analysis standards. The measured chemical composition shall be stated on the certificate of conformance.		2 per cast
		Specific requirements for hydrogen content: The hydrogen content shall be determined on each batch in the delivery condition in accordance with EN 3976.	1 per batch	1 per batch
3	Method of melting	Method of melting consists of multiple melt using combination of non-consumable electrode, consumable electrode and cold hearth (electron beam or plasma arc) melting practices. Some of the following requirements are dependent on the actual melting route. NOTE Non-consumable electrode melting should be used for consolidation purpose only. 1 Raw material:	-	
		Raw materials shall be purchased only from suppliers approved by the manufacturer and registered in his list of approved suppliers. Approval of suppliers shall be made in accordance with written procedures contained within the quality assurance system of the manufacturer. Titanium sponge and alloying elements: The requirements shall be specified by the manufacturer who shall also establish the following procedures for the evaluation and acceptance testing of each batch: — titanium sponge: manufacturing method, level of impurities, particle size, freedom from surface contamination; — alloying elements: chemical composition including level of impurities, particle size, freedom from foreign particles.		

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

Material standard line reference					Frequency	of testing
No.	1	Requirements			Qualification	Release
3 Method of melting (continued)		Recycling of scrap: See EN 2955. The categories and sub-categorifollowing table.	es of scrap which may be used by	y the manufacturer are given in the	_	-
		Scrap categories and sub- categories (see EN 2955)	Melting method which includes cold hearth	VAR-only melt method		
		1	allowed	allowed		
		2	allowed	allowed		
		3	allowed	allowed		
		4.1	allowed ^a	allowed ^a		
		4.2.1	allowed ^{a b}	allowed ^a		
		4.2.2	allowed ^{a b}	not allowed a		
		4.3.1	allowed ^{a b}	allowed ^a		
		4.3.2	allowed ^{a b}	not allowed a		
		5.1	allowed	allowed		
		5.2	not allowed	not allowed		
		6	not allowed	not allowed		
		a Only turnings produced by the mb X-ray inspection not required.	nelter shall be used, unless otherwise a	greed by the purchaser.		
		Foundry scrap, castings, bolts or	used components shall not be use	ed.		
		The manufacturer shall maintair categories of scrap for which the		cessors. The list shall indicate the		
			o EN 2955, specify the category an the limits for O_2 , C and H_2 shall als	nd, if necessary, the sub-category of so be specified.		

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

Material standard line reference			Frequency	of testing
No.	1	Requirements		Release
3	Method of melting	2 Charge preparation:	_	_
	(continued)	The melter shall establish procedures for the charge make up which shall include, if appropriate:		
		scrap categories and sub-categories to be used;		
		— amount of recycled scrap;		
		— charge composition;		
		 requirements for recording the constitution of each charge; 		
		— compaction.		
		The scrap shall be of the same alloy, or compatible with the final alloy composition.		
		3 Electrode constitution (if appropriate):		
		Build up of electrodes and attachment of their stubs shall be carried out under a vacuum or inert gas atmosphere in accordance with the procedure defined by the manufacturer.		
		4 Welding:		
		The welding method to be used for fabricating electrodes, joining electrodes and joining stubs to the electrode shall be Metal Inert Gas (MIG) or Plasma in an inert gas atmosphere or Electron Beam (EB) under vacuum. In addition stubs may be attached to electrodes by electric arc in a VAR furnace.		
		5 Melting:		
		Melting process consist of:		
		 a first melting using a consumable electrode or a cold hearth process, (non consumable electrode is no longer in use as a first melt); 		
		 at least one consumable electrode remelting, except where a cold heart melting route is used for commercially pure titanium. 		
		Scrap may only be used during the first melt, except for striking the arc.		
		The stub weld interface shall not be melted during the second or subsequent melts. The stub weld interface may be melted during the first melting operation if the stub is of the same alloy and the weld has been made without filler metal, in a vacuum or inert gas atmosphere.		
		Arc breaks during the final melting operation shall not exceed 60 s.		
		An appropriate system shall be provided for the control, checking and verification of the voltage, pressure, and either current or melt rate.		

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

	Material standard line		Frequency	of testing
No	reference . Title	Requirements	Qualification	Release
3	Method of melting (concluded)	The manufacturer shall establish written procedures which define (if appropriate): — the cleaning of furnace and ingot-moulds; — the purity of inert gas used; — the current, the voltage and the maximum allowed pressure during melting; — the maximum allowed leak rate in the furnace; — the hot topping cycle at the end of the final melt; — the inspection of the stub weld interface after melting.	-	-
4.1	Form	Wire	_	_
4.2	Method of production	 Mechanical hot working: The manufacturer shall establish a procedure for the mechanical cold working. This procedure shall define: the homogenisation thermal cycle; the thermo-mechanical working processes; the manufacturing schedule for each process: the temperatures and durations of pre-heating; the maximum time of each working process; the dimensions of the products at each step and conditions for heat treatment between operations. Mechanical cold working: The manufacturer shall establish a procedure for the mechanical cold working. This procedure shall define: the mechanical working processes; the manufacturing schedule for each process; the dimensions of the products at each step and heat treatment conditions between operations. Final conversion shall be done by hot or cold rolling according to material standard. Straightening: Straightening and stress relieving operations shall be indicated in the manufacturing schedule and shall not cause any defects prejudicial to the intended use. 		

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

	Material standard line		Frequency	of testing
No.	reference Title	Requirements	Qualification	Release
	Method of production (concluded)	Surface finishing: Products shall be supplied in the descaled condition. For products in the machined condition, all additional requirements shall be defined on the order. The surface finish shall allow the satisfactory performance of the inspection operation specified. The method used for removal of defects such as cracks, burrs, etc. from the edges and ends of products shall be agreed between manufacturer and purchaser.	_	-
4.3	Limit dimension(s)	Minimum and/or maximum size of the product expressed as the nominal thickness a , or nominal thicknesses for multi-legged/flanged sections, or as a nominal diameter, D , of round bar or as equivalent diameter $D_{\rm e}$ of non-circular or non-rectangular section products.	-	-
5	Technical specification	Reference to this technical specification EN 4800-004. In cases of conflict, the requirements of the material standard shall take precedence over those of this technical specification.	-	-
6.1	Delivery condition	Product shall be supplied in the delivery condition specified in this line in the material standard and/or as stated on the order. Marking: The method of marking used shall not cause corrosion, crack initiation, contamination or unacceptable deformation. The marking shall remain permanently visible after handling and contact with protective products. Unless otherwise specified, the nature and colour of marking ink and type of marking characters shall be left to the discretion of the manufacturer. The marking inks shall be removable with cleaning products which do not leave a residue which could affect further processing. The cleaning products shall not give rise to corrosion.	-	_

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

	Material standard line			Frequency	of testing
No	reference	Qualification	Release		
6.1	Delivery condition (continued)	All lengths shall be marked legibly as indicated in the following manufacturer and purchaser:	tables unless otherwise agreed between the	_	-
		Products of diameter or major sectional d	limension, a or $D \ge 12,5$ mm		
		Continuous marking ^a	End marking ^b		
		 Material standard Nominal dimensions in millimetres or part/drawing no. Delivery condition code Manufacturer/plant identification 	-		
		 a Ink or similar product shall be used. All information shall b Hard stamping on one end of the length. 	be repeated at least every 500 mm.		
		Products of diameter or major sectional d	limension, a or D < 12,5 mm		
		The information stated in the above table shall the attached to each bundle or products.			
		Packing:			
		All necessary precautions shall be taken to prevent damage to surface finish shall be maintained.	o the product, especially where the delivered	ered	
		The packing shall be suitable for the type of transportation use	ed.		
		The exterior of the packing shall bear the following information — name and address of recipient; — mass; — order number and sufficient information to enable documentation.		nt	
		Shipment:			
		The responsibility for shipping shall be detailed in a transport	contract.		

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

	Material standard line					Frequency	of testing
No.	reference Title		Requirements				Release
6.1	Heat treatment (Delivery condition)	standard and are listed i treated more than once	in the same order as they ar	e to be applied. No pro e purchaser. Abbreviat	ct as specified in the material oduct shall be re-solution heat ions and symbols used in the n full.	-	-
		Term	Abbreviation/Symbol	Term	Abbreviation/Symbol		
		temperature	θ	water quench	WQ		
		time	t	oil quench	OQ		
		hour	h	forced air quench	AQ		
		minuto	min	air cool	AC		
		minute	min	furnace cool	FC		
		AMS 2750 to be used un	less otherwise agreed between	en customer and supplie	er.		
		shall be mandatory. If a tolerances of the furnac	a temperature range is state e, shall be selected. The to	ed, a temperature withi tal volume of the char	lard or order, that temperature n that range, reduced by the ge shall be maintained at the le, for the period stated in the		
		Selected	l temperatures	Tole	erances		
			°C		°C		
			on treatment nnealing		± 15		
			ss relieving		10		
			Ageing		± 10		
l		When the duration of the	heat treatment is stated as a	fixed value, the tolerand	ce shall be: $({}^{+} {}^{20}_{0}) \%$.		
		When the duration of the heat treatment stage is stated as a range, a time within that range shall be selected. When the duration is not specified, it shall be at the discretion of the manufacturer.					
6.2	Delivery condition code		See EN	2032-2.		_	_

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

Material standard line reference						Frequency	of testing
No.	Requirements						Release
7	Use condition	The use condition treatme	ent of the product is stated in	the material standard.		-	_
	Heat treatment	If the delivery condition is	the use condition, no further	heat treatment shall be	applied to the product.	_	_
		same order as those spe		ard. Abbreviations and	ect to heat treatment(s) in the symbols used in the material		
		Term	Abbreviation/Symbol	Term	Abbreviation/Symbol		
		temperature	θ	water quench	WQ		
		time	t	oil quench	OQ		
		hour	h	forced air quench	AQ		
		minute	min	air cool	AC		
		minute	111111	furnace cool	FC		
		AMS 2750 to be used unle	ess otherwise agreed between	en customer and supplie	er.		
		shall be mandatory. If a tolerances of the furnace	temperature range is state, shall be selected. The to	ed, a temperature withi tal volume of the char	lard or order, that temperature n that range, reduced by the ge shall be maintained at the le, for the period stated in the		
		Selected	temperatures °C	Tole	erances °C		
		Solution	n treatment				
		Ar	nealing	:	± 15		
		Stres	s relieving				
		ļ.	ageing		± 10		
		When the duration of the	neat treatment is stated as a	fixed value, the tolerand	ce shall be: (+ 20) %.		
			e heat treatment stage is son is not specified, it shall be		me within that range shall be manufacturer.		

Table 1 — Technical requirements for lines 1 to 29, where appropriate (continued)

Material standard line reference		ne		Frequency	of testing	
No.	reference Requirements Title					Release
8.1	Test sample(s)		This line relates to test samples for the tests defined in lines 12 to 26.	-	-
				Test samples shall not be worked after removal from the product they represent.		
				Test samples and associated test pieces shall be marked in such a manner that their identity, location and orientation with respect to the product and batch are maintained.		
8.2	Test piece(s)			This line relates to test pieces for the test defined in lines 12 to 26.	-	_
				Test pieces shall be machined from the test samples taken in accordance with the requirements of line 8.1 of this technical specification.		
				Test piece type and dimensions shall be as specified for the appropriate test/line number in the material standard and/or this technical specification and/or test method.		
8.3	Heat treatme	nt		The heat treatment shall be as specified in the material standard. If the delivery condition is the use condition, further heat treatment shall not be applied.	-	-
9	Dimensions of	concerr	ned	Nominal thickness, <i>a</i> , or nominal diameter <i>D</i> , of the product to which the properties, in lines 11 to 26 of the material standard, relate.	-	-
10	Thickness of each face	claddi	ng on	Not used for steel and titanium alloys.		
11	Direction of to	est pie	се	As specified in the material standard and relates to the direction of the test piece used for tensile and creep testing.	-	_
	Tensile t	test		Lines 12 to 16	-	_
12	Temperature	θ	°C	As specified in the material standard and relates to the temperature at which the tensile tests is carried out.	_	_
13	Proof stress	R _{p0,2}	MPa	Tensile testing shall be carried out in accordance with EN 2002-001 for testing at ambient temperature	1 specimen per	1 specimen per
14				and EN 2002-002 for testing at elevated temperature. EN ISO 6892-1 and prEN ISO 6892-2 are also applicable subject to agreement between customer and supplier on the test method (A or B method)	batch	batch
15	Elongation A % The test specimen orientation shall be longitudinal.					
16	Reduction of aera	Z	%			

Table 1 — Technical requirements for lines 1 to 29, where appropriate (concluded)

	Material standard line reference		ne		Frequency	of testing
No.	reference Titl			Requirements	Qualification	Release
17	Hardness			Not normally used for titanium alloys.	_	_
18	Shear strengt	h		Test in accordance with EN 3238.	1 specimen per batch	1 specimen per batch
19	Bending			Not used for this type of product.	-	-
20	Impact streng	th		Not normally used for titanium alloys.	ı	_
	Creep parameters		1	Lines 21-26	-	_
21	Temperature	θ	°C	As specified in the material standard and relates to the temperature at which the creep and/or stress rupture tests are carried out.	-	-
22	Time		h	tests are carried out.		
23	Stress	σ_{a}	MPa	Test in accordance with EN 2002-005.	1 specimen per	1 specimen per
24	Elongation	а	%	The test piece definition and position within the product shall be agreed between the manufacturer and purchaser.	batch	batch
25	Rupture stress	σ _R	MPa	The test specimen orientation shall be longitudinal.		
26	Elongation at rupture	Α	%			
27	Notes			List of indices appearing on page 4 of the material standard which relate to normative and/or interpretative notes which are subsequently explained in line 98 of the material standard.	-	-
29	Reference hea	at trea	tment	When required, reference heat treatment is applied to the test samples, see line 8.3.	-	

Table 2 — Technical requirements for lines 30 onwards, where appropriate

30		Microstructure					
Test method		1	For alpha/beta alloys: — EN 3114-002 Other alloys: — To be agreed between the manufacturer and purchaser.				
Freque	ency of testing	2	Qualification	Release testing			
			25 % of product per batch	10 % of product per batch			
Sai	mple type	3	See EN 3	114-001.			
Test pi	ece definition	4	One end. Longitudinal and transverse	sections examined. Cut in the centre.			
	ment condition of est piece	5	Use condition or see material standard.				
Testir	ng condition	6	See EN 3114-001.				
Accep	tance criteria	7	See materia	al standard.			

30		Microstructure (Primary α content)		
Tes	st method	1	EN 3	683
Frequency of testing		2	Qualification	Release testing
			1 per batch	1 per batch
Sar	mple type	3	Centre of product.	
Test pie	ece definition	4	See EN 3683.	
	ment condition of est piece	5	Use condition or see material standard.	
Testir	ng condition	6	See EN 3683.	
Accept	tance criteria	7	See material standard.	

Table 2 — Technical requirements for lines 30 onwards, where appropriate (continued)

34		Grain size		
Tes	st method	1	EN ISO	O 643
Freque	ency of testing	2	Qualification	Release testing
			As release testing	1 end of each coil
Saı	mple type	3	Longitudinal sample	
Test pi	iece definition	4	See EN ISO 643.	
	ment condition of est piece	5	Use condition or see material standard.	
Testir	ng condition	6	See EN ISO 643.	
Accep	tance criteria	7	See material standard.	

36		Reverse torsion test		
Test method 1 ISO 9649		9649		
Freque	ency of testing	2	Qualification	Release testing
			Both ends of each coil	1 end of each coil
Sa	ample type	3	-	
Test p	iece definition	4	ISO 9	9649
	tment condition of est piece	5	_	
Testi	ing condition	6	See material standard.	
Accep	otance criteria	7	See ISO 9649.	

Table 2 — Technical requirements for lines 30 onwards, where appropriate (continued)

37		Bending		
Te	est method	1	ISO 7	7801
Frequency of testing		2	Qualification	Release testing
			Both ends of each coil	1 end of each coil
Sa	ample type	3	_	
Test p	piece definition	4	See ISO	O 7801
	tment condition of est piece	5	Delivery condition	
Test	ing condition	6	See material standard.	
Acce	otance criteria	7	See materia	al standard.

	1			
42		Simple torsion test		
Te	est method	1	ISO 7	7800
Frequ	ency of testing	2	Qualification	Release testing
			Both ends of each coil	1 end of each coil
Sa	ample type	3	_	
Test p	piece definition	4	See ISC	7800.
	tment condition of est piece	5	Delivery condition	
Test	ing condition	6	See material standard.	
Acce	otance criteria	7	See material standard.	
	·			

Table 2 — Technical requirements for lines 30 onwards, where appropriate (continued)

43		Wrapping test			
Те	st method	1	ISO 7	7802	
Freque	Frequency of testing		Qualification Release testing		
			Both ends of each coil	1 end of each coil	
Sa	mple type	3	_		
Test p	iece definition	4	See ISC	7802.	
	ment condition of est piece	5	Delivery condition		
Testi	ng condition	6	See material standard.		
Accep	tance criteria	7	See materia	al standard.	

ethod	1		External defects		
	'	Visual inspection			
of testing	2	Qualification	Release testing		
		Each product 100 %	10 % of wire length		
e type	3	_			
definition	4	Delivery condition after etching			
t condition of liece	5	Delivery condition			
ondition	6	-			
ce criteria	7	Product shall be clean and free from harmful defects (such as cracks, pits, score marks, indentations, inclusions, alpha case, etc.).			
it	definition condition of ece	definition 4 condition of 5 ece 5 ondition 6	type 3 — definition 4 Delivery condition condition of ecce Dendition 6 —		

Table 2 — Technical requirements for lines 30 onwards, where appropriate (continued)

44		External defects (penetrant)			
Те	Test method 1		EN 2002-16		
Frequency of testing		2	Qualification	Release testing	
			Each product 100 %	Each product 100 %	
Sa	imple type	3	_		
Test p	iece definition	4	Delivery condition aft	er etching.	
	ment condition of est piece	5	Delivery condition		
Testi	ng condition	6	-		
Accep	otance criteria	7	Product shall be clean and free from harmful defects (such as cracks, pits, sco	re marks, indentations, inclusions, alpha case, etc.).	

74		Surface contamination		
Те	est method	1	EN 2003-009 (mid	croexmination)
Frequency of testing		2	Qualification Release testing	
			1 per batch	1 per batch
Sa	ample type	3	Cur section perpendicular to the surface.	
Test p	iece definition	4	See EN 2003-009.	
	tment condition of est piece	5	Delivery condition	
Testi	ing condition	6	-	
Accep	otance criteria	7	Sample shall be free from any α-stabilized layer	
1	•			

Table 2 — Technical requirements for lines 30 onwards, where appropriate (continued)

82		Batch uniformity			
Test method 1 The method used shall be at the discretion of the manufacture.		scretion of the manufacturer.			
Freque	Frequency of testing		Qualification Release testing		
			Each product 100 %	Each product 100 %	
Sa	ample type	3	See sublin	See subline 1.	
Test p	piece definition	4	1		
	tment condition of est piece	5	Delivery con	Delivery condition	
Test	ing condition	6	The product shall be tested at final inspection.		
Accep	otance criteria	7	The manufacturer has to guarantee that all the	he products belong to the same batch.	

86		β-transus temperature			
Те	Test method		EN 3684		
Frequency of testing		2	Qualification Release testing		
			3 samples per ingot representing top, middle and bottom of the ingot	2 representing top and bottom of the ingot	
Sa	ample type	3	See EN 3684.		
Test p	iece definition	4	See EN 3684.		
	tment condition of est piece	5	Delivery condition		
Testi	ing condition	6	See EN 3684.		
Accep	otance criteria	7	See material standard.		

Table 2 — Technical requirements for lines 30 onwards, where appropriate (continued)

95		Marking inspection			
Te	est method	1	Visual inspection		
Freque	ency of testing	2	Qualification	Release testing	
			Each product	The frequency adopted by the manufacturer shall be sufficient to permit him to certify compliance with the requirements.	
Sa	ample type	3			
Test p	piece definition	4	_	-	
	tment condition of est piece	5	_		
Test	ing condition	6	_	-	
Accep	otance criteria	7	The requirements of line 6.1 of this	technical specification shall be met.	

96	Dimensional inspection				
Test method		1	Measuring equipment and procedures suitable for the tolerances shall be used.		
Frequency of testing		2	Qualification	Release testing	
			Each product	The frequency adopted by the manufacturer shall be sufficient to permit him to certify compliance with the requirements.	
Sample type		3		_	
Test piece definition		4		-	
Heat treatment condition of test piece		5	-		
Testing condition		6		7	
Accer	Acceptance criteria		Dimensions and tolerances shall conform to the requirements of the dimensional standard stated on the order or the relevant standard given in TR 2410.		

Table 2 — Technical requirements for lines 30 onwards, where appropriate (concluded)

98	Notes –	Normative and/or interpretive notes appearing on pages 4 and 5 of the material standard.	
99	Typical use	This line is not normally completed for steel and heat resisting alloys.	
100	Qualification	For approval of the manufacturaria quality austoma, and FN 0100	
100	Qualification –	For approval of the manufacturer's quality systems, see EN 9100. For product qualification, see EN 9133.	

British Standards Institution (BSI)

BSI is the independent national body responsible for preparing British Standards and other standards-related publications, information and services. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001

BSI offers Members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Tel: +44 (0)20 8996 7669 Fax: +44 (0)20 8996 7001 Email: plus@bsigroup.com

Buying standards

You may buy PDF and hard copy versions of standards directly using a credit card from the BSI Shop on the website **www.bsigroup.com/shop.** In addition all orders for BSI, international and foreign standards publications can be addressed to BSI Customer Services.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Knowledge Centre.

Tel: +44 (0)20 8996 7004 Fax: +44 (0)20 8996 7005 Email: knowledgecentre@bsigroup.com

Various BSI electronic information services are also available which give details on all its products and services.

Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

BSI Subscribing Members are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration

Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at **www.bsigroup.com/BSOL**

Further information about BSI is available on the BSI website at **www.bsi-group.com/standards**

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. This does not preclude the free use, in the course of implementing the standard of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained. Details and advice can be obtained from the Copyright & Licensing Manager.

Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Tel +44 (0)20 8996 9001 Fax +44 (0)20 8996 7001 www.bsigroup.com/standards

