

# Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections —

## Part 3: Sections

The European Standard EN 10163-3:2004 has the status of a  
British Standard

ICS 77.140.60; 77.140.70



## National foreword

This British Standard is the official English language version of EN 10163-3:2004. It supersedes BS EN 10163-3:1991 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/12, Structural steels, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 16 December 2004

### Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 8, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

### Amendments issued since publication

Amd. No.	Date	Comments

© BSI 16 December 2004

ISBN 0 580 45119 4

**This document is now  
PUBLIC**

English version

## Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections - Part 3: Sections

Conditions de livraison relatives à l'état de surface des tôles, larges plats et profilés en acier laminés à chaud -  
Partie 3: Profilés

Lieferbedingungen für die Oberflächenbeschaffenheit von warmgewalzten Stahlerzeugnissen (Blech, Breitflachstahl und Profile) - Teil 3: Profile

This European Standard was approved by CEN on 4 November 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Contents

	Page
Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	4
4 General.....	4
5 Classification.....	4
6 Requirements .....	5
6.1 Depth and affected area of discontinuities .....	5
6.2 Repair requirements .....	5
6.2.1 Class C .....	5
6.2.2 Class D .....	6
6.3 Repair procedures .....	6
6.3.1 Grinding .....	6
6.3.2 Welding .....	7
Bibliography .....	8

Licensed Copy: London South Bank University, London South Bank University, Fri Mar 24 04:48:01 GMT 2006, Uncontrolled Copy, (c) BSI



## Foreword

This document (EN 10163-3:2004) has been prepared by Technical Committee ECISS/TC 10 “Structural steels – Grades and qualities”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

This document supersedes EN 10163-3:1991, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 3: Sections*.

This series of standards consists of the following parts, under the general title *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections*:

- *Part 1: General requirements*
- *Part 2: Plate and wide flats*

During the 5 year review of EN 10163-3:1991 the members of ECISS/TC 10 agreed to revise EN 10163-3:1991. It was asked to actualise the normative references and to bring the text in line with ECISS DOCS N 809 “Iron and steel standardization – Model for a product standard”.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

This document is now  
**POOBLIC**

## 1 Scope

In addition to EN 10163-1 this document specifies the delivery requirements for surface condition of sections to which the European Standards mentioned in Clause 2 apply and applies to all surfaces excluding edges.

NOTE In this document section toes (see EN 10055) are considered as part of the surfaces of a section.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 1: General requirements.*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **imperfections for long products**

surface discontinuities with a depth and/or area equal to or less than a specified limiting value

### 3.2

#### **defects for long products**

surface discontinuities with a depth and/or area greater than a specified limiting value

## 4 General

The conditions stated in EN 10163-1 apply.

## 5 Classification

The surface requirements and repair conditions are subdivided into 2 classes and each class is further subdivided into 3 subclasses:

Class C General applications.

The surface condition shall comply with the requirements of 6.2.1 and 6.3.

Class D Special applications.

The surface condition shall comply with the requirements of 6.2.2 and 6.3.

Subclass 1 Repair by chipping and/or grinding followed by welding is permitted in compliance with 6.3.2.2 and 6.3.2.3.

Subclass 2 Repair by welding is only permitted if agreed at the time of the order and under agreed conditions (see 6.3.2.4).

Subclass 3 Repair by welding is not allowed.

The required class and subclass is specified in the appropriate material or product standard. If this is not the case the class and subclass shall be class C and subclass 1 unless otherwise specified at the time of the order.

## 6 Requirements

### 6.1 Depth and affected area of discontinuities

The requirements of EN 10163-1 apply.

### 6.2 Repair requirements

#### 6.2.1 Class C

##### 6.2.1.1 Imperfections

Discontinuities not exceeding the limits of Table 1 are regarded as being inherent of the manufacturing process and are permissible irrespective of their number.

A surface area with discontinuities within the limits of Table 1 but with a remaining thickness under the discontinuities less than the minimum thickness as specified in the applicable European Standards (see Clause 2) is permissible with a maximum of 15 % of the inspected surface.

##### 6.2.1.2 Defects

**6.2.1.2.1** Discontinuities with a depth exceeding the limits of Table 1 shall be repaired irrespective of their number.

**6.2.1.2.2** Discontinuities with a surface area with a remaining thickness under the discontinuities less than the minimum thickness as specified in the applicable European Standards (see Clause 2) of more than 15 % of the inspected surface shall be repaired.

**Table 1 — Maximum permissible depth of discontinuities for class C**

Dimensions in millimetres

Nominal thickness of the product $t$	Maximum permissible depth of discontinuities
$3 \leq t < 6$	20 % of $t$
$6 \leq t < 20$	1,2
$20 \leq t < 40$	1,7
$40 \leq t < 80$	2,5
$80 \leq t < 160$	3,0

This document is now  
**POOBLIC**

**6.2.2 Class D**

**6.2.2.1 Imperfections**

Discontinuities not exceeding the limits of Table 2 are regarded as being inherent of the manufacturing process and are permissible irrespective of their number.

A surface area with discontinuities within the limits of Table 2 but with a remaining thickness under the discontinuities less than the minimum thickness as specified in the applicable European Standards (see Clause 2) is permissible with a maximum of 2 % of the inspected surface.

**Table 2 — Maximum permissible depth of discontinuities for class D**

Dimensions in millimetres

Nominal thickness of the product <i>t</i>	Maximum permissible depth of discontinuities
$3 \leq t < 20$	0,5
$20 \leq t < 40$	0,7
$40 \leq t < 80$	1,0
$80 \leq t < 160$	1,5

**6.2.2.2 Defects**

**6.2.2.2.1** Discontinuities with a depth exceeding the limits of Table 2 shall be repaired irrespective of their number.

**6.2.2.2.2** Discontinuities with a surface area with a remaining thickness under the discontinuities less than the minimum thickness as specified in the applicable European Standards (see Clause 2) of more than 2 % of the inspected surface shall be repaired.

**6.3 Repair procedures**

**6.3.1 Grinding**

The maximum permitted grinding allowance below the minimum thickness as specified in the European Standards specifying tolerances is given in Table 3.

Furthermore the following conditions apply.

For ground areas with a thickness under the minimum permissible thickness, as specified in the European Standards specifying tolerances, the sum of all ground areas shall not exceed 15 % of the surface for class C and 2 % for class D.

Licensed Copy: London South Bank University, London South Bank University, Fri Mar 24 04:48:01 GMT 2006, Uncontrolled Copy, (c) BSI





**Table 3 — Grinding allowance below the minimum thickness**

Dimensions in millimetres

Nominal thickness of the product $t$	Maximum permitted grinding allowance below the minimum specified thickness
$3 \leq t < 20$	0,4
$20 \leq t < 40$	0,6
$40 \leq t < 80$	1,2
$80 \leq t < 160$	2,0

**6.3.2 Welding****6.3.2.1 General**

The following conditions apply for the repair by welding of defects which cannot be repaired by grinding as stated under 6.3.1.

**6.3.2.2 Class C Subclass 1**

The sum of the welded areas shall not exceed 15 % of the surface area under inspection.

**6.3.2.3 Class D Subclass 1**

The sum of the welded areas shall not exceed 2 % of the surface area under inspection.

**6.3.2.4 Subclass 2**

Repair by welding is only allowed if agreed at the time of the order. In this case requirements different from 6.3.2.2 and 6.3.2.3 can be specified.

**6.3.2.5 Subclass 3**

Repair by welding is not allowed.

This document is now  
**POOBLIC**

## Bibliography

- [1] EN 10024, *Hot rolled taper flange I sections - Tolerances on shape and dimensions.*
- [2] EN 10034, *Structural steel I and H sections - Tolerances on shape and dimensions.*
- [3] EN 10055, *Hot-rolled steel equal flange tees with radiused root and toes - Dimensions and tolerances on shape and dimensions.*
- [4] EN 10056-1, *Structural steel equal and unequal leg angles - Part 1: Dimensions.*
- [5] EN 10056-2, *Structural steel equal and unequal leg angles - Part 2: Tolerances on shape and dimensions.*
- [6] EN 10279, *Hot rolled steel channels - Tolerances on shape and dimensions and mass.*

*blank*



## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).