

# Natural stone test methods — Petrographic examination

The European Standard EN 12407:2007 has the status of a  
British Standard

ICS 73.020; 91.100.15

## National foreword

This British Standard was published by BSI. It is the UK implementation of EN 12407:2007. It supersedes BS EN 12407:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/545, Natural stone.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2007

© BSI 2007

ISBN 978 0 580 50839 4

### Amendments issued since publication

Amd. No.	Date	Comments

English Version

## Natural stone test methods - Petrographic examination

Méthodes d'essai de pierres naturelles - Examen  
pétrographique

Prüfverfahren für Naturstein - Petrographische Prüfung

This European Standard was approved by CEN on 21 January 2007.

CEN members are bound to comply with the CEN/GENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

# Contents

Page

Foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Normative references .....	5
3 Principle.....	5
4 Apparatus .....	5
5 Preparation of thin and polished sections.....	6
5.1 General.....	6
5.2 Preparation of thick samples.....	6
5.3 Preparation of thin samples .....	6
5.4 Staining.....	7
5.4.1 Feldspar staining .....	7
5.4.2 Carbonate staining .....	7
6 Macroscopic description .....	7
6.1 General.....	7
7 Microscopic description .....	8
8 Petrographic definition .....	9
9 Test report .....	10
Annex A (informative) Template for the petrographic description of rocks .....	11
Bibliography.....	18

## Foreword

This document (EN 12407:2007) has been prepared by Technical Committee CEN/TC 246 "Natural stones", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2007, and conflicting national standards shall be withdrawn at the latest by September 2007.

This document supersedes EN 12407:2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## Introduction

A petrographic description of natural stone is important not only for the purposes of petrographic classification but also in order to highlight features influencing its chemical, physical and mechanical behaviour. In the same way the determination of the stone's origin could be necessary (e.g. in the case of restoration of historical monuments). It is therefore essential to characterize the natural stones not only from the point of view of their mineral components and of their fabric and structure but also in terms of any features as: colour, presence of veins, of fossils, of discontinuities, etc.

To ensure that the petrographic classification is objective, it is essential that the characterization of the material be, as far as possible, quantitative.

## 1 Scope

This European Standard specifies methods for making technical petrographic descriptions of natural stone, except for roofing slates. For this product, the method for the petrographic examination is defined in EN 12326 –2. Although chemical and physical methods of analysis are required for petrographic classification of some stone types, these methods will not be described in this standard.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12670, *Natural stone – Terminology*

EN 12440, *Natural stone – Denomination criteria*

## 3 Principle

First a macroscopic description of the sample is undertaken. The macroscopic description may involve a visual inspection aided by a hand lens or a stereoscopic microscope. Then one or more thin sections prepared from the sample are examined using a petrographic microscope in order to give a microscopic description of the sample; where appropriate an additional polished section shall be prepared.

## 4 Apparatus

- 4.1 Hand lens or stereoscopic microscope (if required)
- 4.2 Rock cutter with sliding guide, water cooled and with a vertical diamond disk 3 mm thick
- 4.3 Electrical heating plate
- 4.4 Glass plate 300 mm x 400 mm x 10 mm
- 4.5 Bristle brush
- 4.6 Multiple rectifier for thin slides for 16 slides, water cooled and semiautomatic stop. Thin sections can also be prepared by hand by a thin slides preparation expert
- 4.7 Electric solder
- 4.8 Multi Form mold 40 mm and plastic cup
- 4.9 Grinding and polishing machine
- 4.10 Petrographic microscope
- 4.11 Point counter or image analysis (if required)

4.12 A Rock Colour Chart or another colour reference chart (if required)

4.13 Reactives and products: Canada Balsam, Thermoplastic cement, Epoxi resin, Epoxi hardener, Carborundum (F220, F400, F600, F800), Supporting glass (28 mm x48 mm x1,8 mm), cover glass (24 mm x32 mm), diamond disks, xileno & ethanol, sodium cobalt nitrite, hydrofluoric acid, hydrochloric acid, sulphosodic alizarine solution.

## 5 Preparation of thin and polished sections

### 5.1 General

The sampling is not responsibility of the test laboratory except where specially requested.

The dimensions of the sample shall be large enough to be representative of the petrographic characteristics of the stone being examined.

One or more thin sections are then prepared.

A thin section is a portion of material mounted on a slide and mechanically reduced to a thin sheet measuring  $(0,030 \pm 0,005)$  mm in thickness, and normally protected by a slide cover. For special purposes (observations with reflected light microscope for the determination of opaque minerals or microprobe analysis) polished sections or polished thin sections shall be prepared. Polished sections and polished thin sections have one side polished with alumina polishing paste (5  $\mu$ m to 12  $\mu$ m grade) and diamond paste (6  $\mu$ m, 3  $\mu$ m and 1  $\mu$ m). The polished side remains uncovered.

The section normally measures about 44 mm x 28 mm, but in the case of larger grain size stones, larger dimensions may be used (e.g. 75 mm x 50 mm) or several sections of normal dimensions can be prepared. If the rock is anisotropic it is necessary to prepare at least two sections with different orientation with respect to the anisotropy (e.g. parallel and perpendicular to bedding planes, cleavage planes).

#### Preparation of thick samples

The sample shall be sufficiently coherent so as not to disintegrate when cut. If the stone is brittle or fragile, it will be necessary to strengthen it by means of impregnation, preferably in a vacuum, with resins with an index of refraction approximately 1,54 (e.g. epoxy resins).

Using the rock cutter several small blocks are cut of 44 mm x 32 mm and 3 to 4 mm thick. In case of porous samples pores are filled with Canada balsam, heated on the plate to approximately 100 °C and then cooled.

Blocks are then successfully ground using diamond discs between 1 and 2 min depending on the type and hardness of the stone.

#### Preparation of thin samples

Blocks are cleaned placed on the plate and then treated with Canada balsam until caramel colour. After cooling and scratching the balsam off the surface, they are grinded dry in the glass plate with carborundum avoiding the appearance of pores. The blocks are then cleaned with the bristle brush to eliminate all carborundum particles. They are later heated in the plate with the adhesive mounting them on the supporting glass with thermoplastic adhesive. The samples are then mounted in the rectifying machine until sample thickness is 1 mm. Then they are subjected to another wet grinding process on the glass plates with the different carborundum sizes, checking the thickness every now and then controlling polarizing colours of one reference mineral existing in the sample, ending the process once the stipulated colours have been achieved (first order white and grey for quartz and feldspar for example). Thin slides are then washed with water and dried with a cloth. Samples are then cut by the edges with a cutter up until the measures of the cover glass (generally 24 mm x 32 mm). Then a volume of balsam of approximately 0,5 ml is poured over the samples and heated on the plate to 60 °C, exerting pressure on the cover plate to favour a thorough cover of the balsam over the sample avoiding the formation of bubbles.



Balsam residues remaining between cover and supporting glass can be eliminated burning them with the solder. Finally the thin slides are washed with xilene, water and soap, are left to dry in open air and are labelled with a permanent marker on the cover glass.

To facilitate the identification of some minerals with similar colours or optical properties it might be necessary in many cases to use selective staining methods of its mineral components. Out of the many existing techniques two are so common that are always carried out in all samples unless otherwise stated; these are feldspar staining methods and carbonate staining methods which are described below. Any other staining method different from those mentioned shall be clearly stated in the working order.

## 5.2 Staining

### 5.2.1 Feldspar staining

In order to carry out the feldspar staining, the thin section shall be subjected to HF acid vapour under the extracting hood and during one minute, using a plastic recipient of the same size of the cover glass. Then three drops of a solution of sodium cobaltonitrite are dropped over the section and left to act during 4 to 5 min. Then the section is washed with water: the K-feldspar is stained with yellow tones whereas the other feldspars and quartz show no change.

### 5.2.2 Carbonate staining

If samples are suspected of containing carbonates, their selective staining can be carried out. Samples are attacked with a HCl solution 1:20 and then immersed in a alizarine solution during 3 min. Then samples are washed with water and are left to dry in open air. Calcite will then stain with a dark red colour, dolomite will maintain its original colour and other carbonates will be stained between rose and violet colour depending on the case. It is possible to discriminate other carbonates than calcite using other chemical attacks, but this is not frequent.

## 6 Macroscopic description

### 6.1 General

Macroscopic description shall be carried out both on fresh cut samples and on polished samples.

The following items shall be included in the macroscopic description.

**6.2** The general colour or range of colours of the hand specimen. The colour can be estimated by visual impression or defined using a colour reference chart (Rock Colour Chart is recommended).

**6.3** Fabric

**6.4** Grain size (e.g. coarse, medium or fine)

**6.5** Open and refilled macroscopic cracks, pores and cavities (when relevant)

**6.6** Evidence of weathering and alteration: staining by sulphide alteration, diffusion of iron hydroxides, alteration of feldspars etc. (when relevant)

**6.7** Presence of macrofossils (when relevant)

**6.8** Presence of xenolithic and mafic intrusions (when relevant)

## 7 Microscopic description

The following items shall be included in the microscopic description:

### 7.1 Fabric

### 7.2 Constituents

#### 7.2.1 Minerals/Grains

NOTE For the determination of the opaque minerals polished sections should be used.

For each mineral or grain identified, the characteristics listed below shall be specified (when relevant).

**7.2.1.1** Percentage by volume, specifying the method used (e.g. estimate, point counter).

**7.2.1.2** Dimensions: mean value and range of variation (if necessary for the groundmass and also for the larger crystals or grains). The range of sizes to be used will be: Very coarse (> 10 mm), Coarse (4 mm -10 mm), Medium (1 mm - 4 mm), Fine (< 1 mm). Degree of sorting (in clastic rocks): very well sorted, well sorted, moderately sorted, poorly sorted, very poorly sorted.

**7.2.1.3** Habit (e.g. idiomorphic, anhedral).

**7.2.1.4** Shape (e.g. isometric, anisometric, flattened, elongated). Detrital grains in sedimentary rocks shall be described in terms of sphericity and roundness.

**7.2.1.5** Boundaries (e.g. straight, lobate, dentate).

**7.2.1.6** Distribution (e.g. homogeneous, heterogeneous, in layers, in patches).

**7.2.1.7** Orientation (e.g. isotropic, shape preferred orientation, dimensional preferred orientation, isorientation of lamellar or tabular grains, isorientation of elongated, prismatic grains).

**7.2.1.8** Evidence of weathering and alteration: staining by sulphide alteration, diffusion of iron hydroxides, chloritization of biotite; sericization of feldspars, radioactive decay of minerals such as zircon or allanite etc.

#### 7.2.2 Groundmass:

**7.2.2.1** In volcanic rocks mesostasis which can be glassy, ipocrystalline, microcrystalline, devitrified

**7.2.2.2** In sedimentary rocks have to be distinguished matrix (microcrystalline pelitic, carbonatic or silicic mud which includes grains when present, or fills the interstices) and cement (amorphous to crystalline materials partially or completely filling cavities)

**7.2.3** Organogenic remains: e.g. organic or replaced (pyrite, apatite etc.) organogenic remains

### 7.3 Discontinuities

**7.3.1** Pores, microcavities (size, shape, relative abundance and filling material if present)

**7.3.2** Cracks and open fractures

**7.3.2.1** Width (most frequent value, minimum and maximum)

**7.3.2.2** Length (most frequent value, minimum and maximum)

**7.3.2.3** Type (intergranular, intragranular, transgranular)

- 7.3.2.4 Orientation
- 7.3.2.5 Distribution
- 7.3.3 Filled fractures and veins
  - 7.3.3.1 Width (most frequent value, minimum and maximum)
  - 7.3.3.2 Length (most frequent value, minimum and maximum)
  - 7.3.3.3 Type (intergranular, intragranular, transgranular)
  - 7.3.3.4 Orientation
  - 7.3.3.5 Distribution
  - 7.3.3.6 Filling (extent, nature, structure)
  - 7.3.3.7 Nature (e.g. stylolites, late veins)
- 7.4 Alterations.
  - 7.4.1 Description of the minerals with alterations
  - 7.4.2 Alteration grade of the rock

Templates for the petrographic description of the various types of rocks are given in Annex A (informative).

## 8 Petrographic definition

On the basis of the data generated from the macroscopic and microscopic examination relating to grain size, fabric and mineralogical composition a petrographic definition shall be assigned to the stone sample, using EN 12670 and fixing at least the rock family.

If the petrographic description provides insufficient data to assign a petrographic definition, further testing may be necessary, namely chemical or X-ray diffraction determinations.

## 9 Test report

The test report shall contain the following information:

- a) unique identification number for the report;
- b) number, title and date of issue of this European Standard;
- c) name and address of the test laboratory and the address of where the examination was carried out if different from the test laboratory;
- d) name and address of the client;
- e) it is the responsibility of the client to supply the following information:
  - 1) commercial name of the stone, in accordance with EN 12440;
  - 2) country and region of extraction;
  - 3) name of the supplier;
  - 4) direction of any existing plane of anisotropy (if relevant to the test) to be clearly indicated on the sample by means of two parallel lines;
  - 5) name of the person or organization which carried out the sampling;
- f) date of delivery of the sample;
- g) date of preparation of the thin sections and the date of the examination;
- h) number and dimensions of the thin sections;
- i) macroscopic and microscopic description of the stone;
- j) photography of the thin section under the following light conditions: crossed polarizers and plain light;
- k) petrographic definition of the stone, in accordance with EN 12670;
- l) any deviation from this standard and the reasons for any such deviation;
- m) remarks.

The test report shall contain the signature(s) and role(s) of the competent(s) geologist(s) responsible(s) for the testing and the date of issue of the report. It shall also state that the report shall not be partially reproduced without the written consent of the laboratory.

## Annex A (informative)

### Template for the petrographic description of rocks

The user of this form is allowed to copy this present form.

#### **TEMPLATE FOR PIROCLASTIC ROCKS**

	SAMPLE N°	LOCATION	SOURCE	COMMERCIAL NAME	
IDENTIFICATION					

HAND SAMPLE DESCRIPTION

POLISHED PLATE DESCRIPTION

MICROSCOPIC DESCRIPTION

Texture:

Composition      Main components and vitroclasts

Accessory components: Lithoclasts of piroclastic and related volcanic rocks

Accidental components: Cristaloblasts and lithoclasts

Porosity:              Degree:

Alterations:

Remarks:

CLASSIFICATION:

COMPLEMENTARY DATA

Type ( )	Plutonic.....P	QAPF	Chemical analysis	Main components...M
	Hipoabisal.....H	Modal analysis	CIPW norm	Minor/traces.....T
	Volcanic.....V			Other.....O

**TEMPLATE FOR CLASTIC ROCKS**

	SAMPLE N°	LOCATION	SOURCE	COMMERCIAL NAME	
IDENTIFICATION					

HAND SAMPLE DESCRIPTION

POLISHED PLATE DESCRIPTION

MICROSCOPIC DESCRIPTION

	%		
Quartz		Matrix	
FK			
F Ca Na			
Volcanic rock fragments		Cements	
Metamorphic rock fragments			
Limestone fragments			
Sandstone fragments		Accessories	
Slate fragments			
Chert fragments			

Porosity	Primary:	Secondary:	Degree:
----------	----------	------------	---------

Granulometry	Maximum	Minimum	Predominant	Selection

Alterations:

Remarks:

CLASSIFICATION:

Textural:

Descriptive:

**TEMPLATE FOR SEDIMENTARY ROCKS**

	SAMPLE N°	LOCATION	SOURCE	COMMERCIAL NAME	
IDENTIFICATION					

HAND SAMPLE DESCRIPTION

POLISHED PLATE DESCRIPTION

MICROSCOPIC DESCRIPTION

	%	Textural components	
Clays		Intraclasts	
Quartz		Oolites	
Feldspar		Fossils	
Rock fragments		Pellets	

	%	Accessories	%
Allochemical			
Orthochemical			

Porosity	Primary:	Secondary:	Degree:
----------	----------	------------	---------

Granulometry		Maximum	Predominant	Selection
	Terrigenous			
	Alochemical			

Diagenesis		Intensity	Mineralogy
	Recrystallization		
	Dolomitization		
	Silicification		

Alterations:



Remarks:

CLASSIFICATION:

Textural:

**TEMPLATE FOR IGNEOUS ROCKS**

	SAMPLE N°	LOCATION	SOURCE	COMMERCIAL NAME	
IDENTIFICATION					

HAND SAMPLE DESCRIPTION

POLISHED PLATE DESCRIPTION

MICROSCOPIC DESCRIPTION

Texture:

Composition:      Main components/Fenocrystals

Accidental components / matrix:

Porosity:            Degree:

Alterations:

Remarks:

CLASSIFICATION:

COMPLEMENTARY DATA

Type ( )	Plutonic.....P	QAPF	Chemical analysis	Main components...M
	Hipoabisal.....H	Modal analysis	CIPW norm	Minor/traces.....T
	Volcanic.....V			Other.....O

**TEMPLATE FOR METAMORPHIC ROCKS**

	SAMPLE N°	LOCATION	SOURCE	COMMERCIAL NAME	
IDENTIFICATION					

HAND SAMPLE DESCRIPTION

POLISHED PLATE DESCRIPTION

MICROSCOPIC DESCRIPTION

Texture:

Composition: Main components

Metamorphism:

Type: Degree:

Facies:

Porosity: Degree:

Alterations:

Remarks:

CLASSIFICATION:

COMPLEMENTARY DATA

Chemical analysis	Main components...M
	Minor/traces.....T
	Other.....O

## Bibliography

- [1] EN 1925, Natural stone test methods - Determination of water absorption coefficient by capillarity
- [2] EN 1926, Natural stone test methods - Determination of uniaxial compressive strength
- [3] EN 1936, Natural stone test methods - Determination of real density and apparent density, and of total and open porosity
- [4] EN 12370, Natural stone test methods - Determination of resistance to salt crystallisation
- [5] EN 12371, Natural stone test methods - Determination of frost resistance
- [6] EN 12372, Natural stone test methods - Determination of flexural strength under concentrated load
- [7] EN 13161, Natural stone test methods - Determination of flexural strength under constant moment
- [8] EN 13364, Natural stone test methods - Determination of the breaking load at dowel hole
- [9] EN 13373, Natural stone test methods - Determination of geometric characteristics on units
- [10] EN 13755, Natural stone test methods - Determination of water absorption at atmospheric pressure
- [11] EN 13919, Natural stone test methods - Determination of resistance to ageing by SO<sub>2</sub> action in the presence of humidity
- [12] EN 14066, Natural stone test methods - Determination of resistance to ageing by thermal shock
- [13] EN 14146, Natural stone test methods - Determination of the dynamic modulus of elasticity (by measuring the fundamental resonance frequency)
- [14] EN 14147, Natural stone test methods - Determination of resistance to ageing by salt mist
- [15] EN 14157, Natural stone test methods - Determination of the abrasion resistance
- [16] EN 14158, Natural stone test methods - Determination of rupture energy
- [17] EN 14205, Natural stone test methods - Determination of Knoop hardness
- [18] EN 14231, Natural stone test methods - Determination of the slip resistance by means of the pendulum tester
- [19] EN 14579, Natural stone test methods - Determination of sound speed propagation
- [20] EN 14580, Natural stone test methods - Determination of static elastic modulus
- [21] EN 14581, Natural stone test methods - Determination of linear thermal expansion coefficient



---

---

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.  
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.  
Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.  
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.  
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.  
Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.  
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.  
Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).