

Furniture — Assessment of surface resistance to wet heat

ICS 97.140

National foreword

This British Standard is the UK implementation of EN 12721:2009+A1:2013. It supersedes BS EN 12721:2009 which is withdrawn.

The start and finish of text introduced or altered by amendment is indicated in the text by tags. Tags indicating changes to CEN text carry the number of the CEN amendment. For example, text altered by CEN amendment A1 is indicated by **A1** **A1**.

The UK participation in its preparation was entrusted by Technical Committee FW/0, Furniture to Subcommittee FW/0/1, Common Test Methods for Furniture.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2009

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 82224 7

Amendments/corrigenda issued since publication

Date	Comments
31 December 2013	Implementation of CEN amendment A1:2013

ICS 97.140

English Version

Furniture - Assessment of surface resistance to wet heatAmeublement - Évaluation de la résistance de la surface à
la chaleur humideMöbel - Bewertung der Beständigkeit von Oberflächen
gegen feuchte Hitze

This European Standard was approved by CEN on 3 January 2009 and includes Amendment 1 approved by CEN on 3 September 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN 12721:2009+A1:2013) has been prepared by Technical Committee CEN/TC 207 “Furniture”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 2013-09-03.

This document supersedes A1 EN 12721:2009 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

Informative A1 Annex A A1 provides details of significant technical changes between this European Standard and the previous edition.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Contents

Page

1	Scope.....	4
2	Normative references.....	4
3	Terms and definitions	4
4	Principle.....	5
5	Apparatus and materials.....	5
5.1	Thermometer.....	5
5.2	Heat source	5
5.3	Oven.....	6
5.4	Cleaning cloth	6
5.5	White polyamide fibre cloth.....	6
5.6	Deionized or distilled water	6
5.7	Heat-insulating foam.....	6
5.8	Diffuse light source.....	6
6	Preparation and conditioning.....	7
6.1	Conditioning.....	7
6.2	Test surface.....	7
7	Test procedure	7
7.1	Testing.....	7
7.2	Test temperatures	8
8	Examination of the test panel.....	8
9	Assessment of results	8
10	Test report.....	9
Annex A (informative) Significant technical changes in revised edition of this standard		11
Bibliography.....		12

Tables

Table 1 — Descriptive numerical rating code.....	8
--	---

Figures

Figure 1 — Aluminium block used as heat source	6
--	---

1 Scope

This European standard specifies a method for the assessment of the resistance to wet heat of all rigid furniture surfaces regardless of materials.

It does not apply to leather and textile surfaces.

The test is intended to be carried out on a part of the finished furniture, but can be carried out on test panels of the same material, finished in an identical manner to the finished product, and of a size sufficient to meet the requirements of the test.

The test should be carried out on unused surfaces.

A1 *deleted text* **A1**

2 Normative references

A1 The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies. **A1**

EN ISO 4287:1998, *Geometrical Product Specifications (GPS) – Surface texture: Profile method – Terms, definitions and surface texture parameters (ISO 4287:1997)*

EN ISO 4288:1997, *Geometrical Product Specifications (GPS) – Surface texture: Profile method – Rules and procedures for the assessment of surface texture (ISO 4288:1996)*

ISO 209:2007, *Aluminium and aluminium alloys – Chemical composition*

ISO 1770:1981, *Solid-stem general purpose thermometers*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

test panel

panel including the test surface

NOTE It may be cut from a finished item of furniture or it may be a separate panel produced in the same manner as the finished item of furniture.

3.2

test surface

part of the test panel

3.3

test area

part of the test surface under the heat source (5.2)

3.4

roughness

R_a

arithmetic mean of the absolute values of the profile deviations from the mean line

4 Principle

A standard aluminium alloy block at a specified test temperature is placed on a damp cloth in contact with the test surface. After a specified test period, the block and damp cloth are removed and the test surface is left for 16 h to 24 h. Thereafter, the test surface is cleaned and examined for damages such as discolouration, change in gloss, change in colour, blistering and swelling. The test result is stated in a numerical rating code.

5 Apparatus and materials

5.1 Thermometer

As specified in ISO 1770:1981, capable of insertion to the bottom of the centre bore of the heat source (5.2) or other means of measuring the temperature of the heat source to an accuracy of ± 1 °C.

5.2 Heat source

A block as shown in Figure 1 manufactured from aluminium alloy according to ISO 209:2007, Al Mg Si (alloy shall contain more than 94% aluminium). The roughness of bottom surface shall be (2 ± 1) μm , expressed as *Ra*, according to EN ISO 4287:1998 and EN ISO 4288:1997.

NOTE Alloy 6060 and 64430 are suitable

The following tolerances are applicable:

Lengths: $\pm 0,2$ mm of the nominal length

Angles: $\pm 2^\circ$ of the nominal angle




Figure 1 — Aluminium block used as heat source

5.3 Oven

An oven which can heat the heat source to a temperature higher than the test temperature.

5.4 Cleaning cloth

White soft absorbent cloth.

5.5 White polyamide fibre cloth

A plain weave having approximately 40 threads/cm in both warp and weft direction, weighing approximately 50 g/m², and cut (120 ± 3) mm square.

5.6 Deionized or distilled water

5.7 Heat-insulating foam

A melamine foam, with the following characteristics: density between 8,5 kg/m³ and 11,5 kg/m³; heat conductivity, less than 0,035 W/mK. The foam shall withstand at a temperature higher than 200 °C.

5.8 Diffuse light source

Light source providing evenly diffused light, giving an illumination on the test surface of (1200 ± 400) lx. This may either be diffused daylight or be diffused artificial daylight.

NOTE The daylight should be unaffected by surrounding trees, etc. When artificial daylight is used it is recommended that it should have a correlated colour temperature of (6500 ± 50) K and an R_a greater than 92, by using a colour matching booth in accordance with EN ISO 3668:2001. [1]

6 Preparation and conditioning

6.1 Conditioning

Conditioning of test surface shall begin at least one week before testing and shall be carried out in air at a temperature of (23 ± 2) °C and relative humidity of $(50 \pm 5)\%$.

The conditioning time shall be stated in the test report.

6.2 Test surface

The test surface shall be substantially flat and with a size sufficient to meet the requirements of Clause 7.

7 Test procedure

7.1 Testing

Immediately after conditioning, the test shall be carried out in a test atmosphere of (23 ± 2) °C.

The test surface shall be placed horizontally. It shall accommodate the required number of tests, with at least 15 mm spacing between the perimeter of adjacent test surfaces, and between the perimeters of the test surfaces and the edges of the panel. Where tests are carried out simultaneously, the perimeters of the test surfaces shall be separated by a minimum of 50 mm. If there is any reason to suppose that the properties of the test surface may vary, two identical tests shall be carried out simultaneously.

The test surface shall be lightly wiped with a cleaning cloth (5.4) before the testing.

Using the oven (5.3), raise the temperature of the heat source to a temperature higher than the specified test temperature, and transfer it to the heat insulating foam (5.7).

Place the thermometer (5.1) or other means of measuring temperature in the centre bore of the heat source (5.2). If the temperature is not higher than the specified test temperature, the heat source shall be placed again in the oven until achieving this higher temperature.

Place the white polyamide fibre cloth (5.5) centrally on the test surface. Spread $(2 \pm 0,2)$ cm³ of distilled or deionized water (5.6) uniformly over the whole area of the white polyamide fibre cloth.

NOTE A graduated eye dropper is suitable for dispensing the distilled or deionised water.

When the heat source reaches the specified test temperature with an accuracy of ± 1 °C, immediately place it on the centre of the white polyamide fibre cloth.

After 20 min in this position, remove the block.

Wipe the test surface dry with the cleaning cloth (5.4) when it has cooled.

Record the position of each test surface and its temperature.

Allow the test surface to stand undisturbed from 16 h to 24 h.

Wipe each test surface with the cleaning cloth (5.4) and examine the test panel.

7.2 Test temperatures

The test temperatures shall be stated in requirement specifications, selected from the following:

55 °C 70 °C 85 °C 100 °C

8 Examination of the test panel

Carefully examine the test surface using the light source (5.8), for damage, e. g. discoloration, change in gloss and colour, blistering, swelling and other defects. For this purpose illuminate the surface separately and examine from different angles, directions and planes, including angle combinations such that the light is reflected from the test surface and towards the observer's eye. Viewing distance shall be 0,25 m to 1,0 m.

Changes caused by the test shall also be determined by touching the surface.

9 Assessment of results

Rate the test surfaces by comparing the test area with the area surrounding it according to Table 1:

Table 1 — Descriptive numerical rating code

Numerical rating	Description
5	No change test area indistinguishable from adjacent surrounding area
4	Minor change test area distinguishable from adjacent surrounding area, only when the light source is mirrored on the test surface and is reflected towards the observer's eye, e. g. discoloration, change in gloss and colour no change in the surface structure, e.g. deformation, swelling, fibre raising, cracking, blistering
3	Moderate change test area distinguishable from adjacent surrounding area, visible in several viewing directions, e. g. discoloration, change in gloss and colour no change in the surface structure, e.g. swelling, fibre raising, cracking, blistering
2	Significant change test area clearly distinguishable from adjacent surrounding area, visible in all viewing directions, e. g. discoloration, change in gloss and colour, and / or structure of the surface slightly changed, e.g. swelling, fibre raising, cracking, blistering
1	Strong change the structure of the surface being distinctly changed and / or discoloration, change in gloss and colour, and / or the surface material being totally or partially removed, and / or the polyamide fibre cloth adhering to the surface

Each test surface shall be rated by an experienced observer.

In cases of doubt, three observers shall be required. All observers shall have good colour vision. In case of three observers, the reported rating for the test surface shall be the average to the nearest nominal value.

Duplicate tests shall be assessed and reported separately.

10 Test report

The test report shall include at least the following information:

- a) reference to this European Standard;
- b) description of the test panel (relevant data);
- c) the test temperature or temperatures;
- d) conditioning time;
- e) the assessment of each test surface in accordance with Clause 9;
[A1] *deleted text* **[A1]**;
- f) if applicable, additional information regarding type of damage;
- g) any deviations from this European standard;
- h) name and address of the test facility;
- i) date of the test.

☐_{A1} *deleted text* ☐_{A1}

Annex A (informative)

Significant technical changes in revised edition of this standard

Significant technical differences between this document and EN 12721:1997 are as follows:

a) change in the illumination of the diffuse light source; it is now (1200 ± 400) lx;

A1 *deleted text* A1

b) changes in the descriptive numerical rating code: new descriptions apply.

Bibliography

- [1] EN ISO 3668:2001, *Paints and varnishes - Visual comparison of the colour of paints (ISO 3668:1998)*

This page deliberately set blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™