

Bitumen and bituminous binders — Framework for specification of oxidised bitumen

ICS 75.140; 91.100.50

National foreword

This British Standard is the UK implementation of EN 13304:2009. It supersedes BS EN 13304:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/510/19, Bitumen and related products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2009

© BSI 2009

ISBN 978 0 580 63911 1

Amendments/corrigenda issued since publication

Date	Comments

EUROPEAN STANDARD

EN 13304

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2009

ICS 75.140; 91.100.50

Supersedes EN 13304:2003

English Version

Bitumen and bituminous binders - Framework for specification of oxidised bitumens

Bitumes et liants bitumineux - Cadre de spécifications des bitumes oxydés

Bitumen und bitumenhaltige Bindemittel - Spezifikationsrahmen für oxidiertes Bitumen

This European Standard was approved by CEN on 10 February 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG**Management Centre: Avenue Marnix 17, B-1000 Brussels**

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Properties and test methods	4
4	Typical grades.....	5

Foreword

This document (EN 13304:2009) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2009, and conflicting national standards shall be withdrawn at the latest by September 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13304:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard provides a framework for the specification of oxidised bitumens used mainly in roofing, waterproofing, adhesives and thermal and phonic insulations.

Within Europe several types of oxidised bitumens are used and, dependent on climatic conditions, type of building construction and traditional practices, different grades may be used for the same purpose. The framework given in this European standard provides a basis for quality agreements to be established between supplier and client.

The oxidised bitumen products are graded by a combination of the values of ring and ball softening point, and penetration at 25 °C, expressed as multiples of 5.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1426, *Bitumen and bituminous binders – Determination of needle penetration*

EN 1427, *Bitumen and bituminous binders – Determination of the softening point – Ring and Ball method*

EN 12592, *Bitumen and bituminous binders – Determination of solubility*

EN 12593, *Bitumen and bituminous binders – Determination of the Fraass breaking point*

EN 13301, *Bitumen and bituminous binders – Determination of staining tendency of bitumen*

EN 13302, *Bitumen and bituminous binders – Determination of viscosity of bitumen using a rotating spindle apparatus*

EN 13303, *Bitumen and bituminous binders – Determination of the loss in mass after heating of industrial bitumen*

EN 15326, *Bitumen and bituminous binders – Measurement of density and specific gravity – Capillary-stoppered pycnometer method*

EN ISO 2592, *Determination of flash and fire points - Cleveland open cup method (ISO 2592:2000)*

3 Properties and test methods

The specification of oxidised bitumens shall be made according to the rules given in Table 1:

Table 1 — Properties and test methods

Property	Test methods	Unit	Limits and tolerance
Ring and ball softening point ^a	EN 1427	°C	± 5 of mid-point value ^e
Penetration at 25 °C	EN 1426	0,1 mm	± 5 of mid-point value ^e
Solubility in toluene ^b	EN 12592	%	≥ 99,0
Loss in mass after heating	EN 13303	%	≤ 0,5
Flash point	EN ISO 2592	°C	> 250
Fraass breaking point	EN 12593	°C	NR ^c
Staining properties	EN 13301	mm	NR ^c
Dynamic viscosity ^d	EN 13302	Pa·s	NR ^c
Density	EN 15326	kg/m ³	NR ^c

^a Ring and ball softening point testing for oxidised bitumens are carried out in glycerol, as the values typically are above 80 °C.

^b If other solvents are used, it shall be stated in the test report.

^c NR: No requirements. Values can be agreed between the client and the supplier

^d The type of instrument used to determine viscosity should be agreed between supplier and client.

^e Mid-point value: value which defines the ring and ball softening point class or the penetration class.

4 Typical grades

Typical grades for oxidised bitumens are:

85/25; 85/40; 95/25; 95/35; 100/40; 105/35; 110/30; 115/15.

EXAMPLE 85/25 means that the ring and ball softening point of the product is between 80 °C and 90 °C and penetration between 20 x 0,1 mm and 30 x 0,1 mm.

NOTE This list does not imply that all grades are available in all countries, neither is it intended to be comprehensive or limiting. Other grades may be supplied in accordance with the local practices and by agreement between client and supplier.

BS EN
13304:2009

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com

BSI Group
Headquarters 389
Chiswick High Road,
London, W4 4AL, UK
Tel +44 (0)20 8996 9001
Fax +44 (0)20 8996 7001
[www.bsigroup.com/
standards](http://www.bsigroup.com/standards)