

BS EN 13523-14:2014



BSI Standards Publication

Coil coated metals — Test methods

Part 14: Chalking (Helmen method)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 13523-14:2014. It supersedes BS EN 13523-14:2001 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/21, Surface preparation of steel.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.
Published by BSI Standards Limited 2014

ISBN 978 0 580 80215 7
ICS 17.040.20; 25.220.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2014.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

Coil coated metals - Test methods - Part 14: Chalking (Helmen method)Tôles prélaquées - Méthodes d'essai - Partie 14: Farinage
(méthode Helmen)Bandbeschichtete Metalle - Prüfverfahren - Teil 14: Kreiden
(Verfahren nach Helmen)

This European Standard was approved by CEN on 7 May 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

Contents		Page
Foreword		3
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Principle	6
5	Apparatus and materials	6
6	Sampling	6
7	Test specimens	6
8	Procedure	6
8.1	General	6
8.2	Checking the adhesive tape	6
8.3	Calibration	7
8.4	Measurement	7
9	Expression of results	7
10	Precision	7
11	Test report	7
Bibliography		8

Foreword

This document (EN 13523-14:2014) has been prepared by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014, and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13523-14:2001.

The main changes are:

- a) the text was editorially revised and the normative references were updated;
- b) in 8.4.2 rubbing with a finger as an alternative to rubbing with the plastic spatula for an optimum adhesion between the tape and the coating was added.

EN 13523, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*
- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*
- *Part 13: Resistance to accelerated ageing by the use of heat*
- *Part 14: Chalking (Helmen method)*
- *Part 15: Metamerism*

- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*
- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Colour stability in humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasma test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This Part of EN 13523 describes the procedure for determining objectively the chalking resulting from natural or artificial weathering of an organic coating on a metallic substrate.

The advantage of this procedure for measuring chalking of an organic coating is that the result can be read off immediately on an instrument. Subjective judgement by visual comparison of test specimens with reference specimens is not necessary.

Reproducible results can only be obtained by careful execution of the test. Special attention is paid to the adhesive tape and its application to the test surface.

The test method is not applicable to embossed coatings. In the case of textured coatings, the degree of texture will influence readings. Also dirt collection can influence readings on outdoor weathered specimens.

NOTE Different methods for assessing chalking are in use. The results of these different methods are not comparable.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0:2014, *Coil coated metals — Test methods — Part 0: General introduction*

EN 13523-10, *Coil coated metals — Test methods — Part 10: Resistance to fluorescent UV radiation and water condensation*

EN 13523-19, *Coil coated metals — Test methods — Part 19: Panel design and method of atmospheric exposure testing*

EN 23270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing (ISO 3270)*

EN 60454-2, *Pressure-sensitive adhesive tapes for electrical purposes — Part 2: Methods of test (IEC 60454-2)*

EN ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20°, 60° and 85° (ISO 2813)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0:2014 and the following apply.

3.1 chalking

appearance of a loosely adherent powder on the surface of a film or coat arising from the degradation of one or more of its constituents

[SOURCE: FprEN ISO 4618:2014, 2.41]

4 Principle

Following the Helmen method, a piece of transparent adhesive tape is placed on the test surface and rubbed with a plastic spatula or a finger until there is optimum adhesion. Then the rubbed adhesive tape is removed and its transparency measured. Two types of apparatus can be used, one giving a direct reading for chalking, the other one measures transmission which is converted to chalking as follows: x % transmission is equivalent to $(100 - x)$ % chalking.

5 Apparatus and materials

5.1 Portable chalking apparatus, giving a direct reading for chalking, commercially available such as the Helmen chalking tester, or **60° glossmeter** or **multi-angle glossmeter** with 60° adjustment, in accordance with EN ISO 2813, both with chalking adaptor.

The type of light detector can influence the readings. A silicon photocell is therefore recommended.

NOTE Differences in the light path between the light source and the photocell can influence readings.

5.2 Transparent pressure-sensitive adhesive tape, 25 mm wide, with an adhesion strength of (10 ± 1) N per 25 mm width when tested in accordance with EN 60454-2, and checked as described in 8.2.

5.3 Plastic spatula, typically of 25 mm width, with a smooth surface.

6 Sampling

See EN 13523-0.

7 Test specimens

See EN 13523-0, EN 13523-10, and EN 13523-19.

8 Procedure

8.1 General

Measure the chalking of the organic coating at ambient temperature. For more accurate tests, as required for instance in case of dispute, the ambient temperature shall be (23 ± 2) °C and the relative humidity (50 ± 5) %, in accordance with EN 23270.

As dirt collection can influence readings, outdoor weathered test specimens shall be measured after gentle cleaning of the area to be measured. The cleaning procedure shall be agreed between the interested parties but shall not remove any degradation products.

8.2 Checking the adhesive tape

Measure the transmission of the adhesive tape (5.2) on an appropriate support. If the transmission is less than 90 %, that roll of adhesive tape shall not be used.

8.3 Calibration

Calibrate the apparatus by applying a new piece of adhesive tape (5.2) onto the appropriate support and adjust the reading to be equivalent to 100 % transmission. Then remove the adhesive tape.

8.4 Measurement

8.4.1 Do not wipe or touch the test surface unless otherwise specified or agreed for the cleaning, as in the case of outdoor weathered specimens.

8.4.2 Apply a new piece of adhesive tape (5.2) of length about 30 mm to the flat test surface and rub with the plastic spatula (5.3) or a finger until there is optimum adhesion between the tape and the coating (as seen by the glossy, transparent appearance of the applied tape).

8.4.3 Remove the piece of tape carefully and uniformly from the test surface in a single movement and apply it to the support of the measuring instrument (5.1). Then take the reading.

9 Expression of results

Express the result as a percentage of chalking.

Values below 10 % chalking shall be expressed as “no chalking”.

10 Precision

No precision data are currently available.

11 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of EN 13523 (EN 13523-14);
- c) the history of the test specimen (e.g. whether natural or artificial weathering);
- d) in the case of outdoor exposed test specimens: the cleaning procedure and whether dirt is present;
- e) the description of the measuring instrument used;
- f) the results of the test, as indicated in Clause 9;
- g) any deviation from the test method specified;
- h) any unusual features (anomalies) observed during the test;
- i) the date of the test.

Bibliography

- [1] EN 1396, *Aluminium and aluminium alloys - Coil coated sheet and strip for general applications — Specifications*
- [2] EN 10169, *Continuously organic coated (coil coated) steel flat products — Technical delivery conditions*
- [3] EN ISO 4628-6, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 6: Assessment of degree of chalking by tape method (ISO 4628-6)*
- [4] FprEN ISO 4618:2014, *Paints and varnishes — Terms and definitions (ISO/FDIS 4618:2014)*
- [5] T. Helmen: *Kreidungsmessung und Kreidungsbeurteilung (Measurement and judgement of chalking), farbe + lack 84 (1978), 5, p. 315–322 (This article also reports results of comparative testing by means of DIN 53159 and ASTM D 659.)*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™