BS EN 13523-23:2015



BSI Standards Publication

Coil coated metals — Test methods

Part 23: Resistance to humid atmospheres containing sulfur dioxide



National foreword

This British Standard is the UK implementation of EN 13523-23:2015. It supersedes BS EN 13523-23:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/21, Paint systems and surface preparation for metallic substrates.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 84651 9

ICS 17.180.20; 25.220.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2015.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 13523-23

July 2015

ICS 17.180.20; 25.220.60

Supersedes EN 13523-23:2002

English Version

Coil coated metals - Test methods - Part 23: Resistance to humid atmospheres containing sulfur dioxide

Tôles prélaquées - Méthodes d'essai - Partie 23 : Résistance à des atmosphères humides contenant du dioxyde de soufre Bandbeschichtete Metalle - Prüfverfahren - Teil 23: Beständigkeit gegen feuchte, Schwefeldioxid enthaltende Atmosphären

This European Standard was approved by CEN on 27 May 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents European foreword Introduction		Page
1	Scope	6
2	Normative references	6
3	Terms and definitions	6
4	Principle	6
5	Apparatus	6
6	Sampling	7
7	Test specimens	7
8	Procedure	
9	Expression of results	8
10	Precision	8
11	Test report	8
Bibli	liography	

European foreword

This document (EN 13523-23:2015) has been prepared by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This document supersedes EN 13523-23:2002.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2016, and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

The main technical changes are:

- a) the title and scope was changed from colour stability to resistance;
- b) the assessment of changes was added in Clause 8.

EN 13523, *Coil coated metals* — *Test methods*, consists of the following parts:

- Part 0: General introduction
- Part 1: Film thickness
- Part 2: Gloss
- Part 3: Colour difference Instrumental comparison
- Part 4: Pencil hardness
- Part 5: Resistance to rapid deformation (impact test)
- Part 6: Adhesion after indentation (cupping test)
- Part 7: Resistance to cracking on bending (T-bend test)
- Part 8: Resistance to salt spray (fog)
- Part 9: Resistance to water immersion
- Part 10: Resistance to fluorescent UV radiation and water condensation
- Part 11: Resistance to solvents (rubbing test)
- Part 12: Resistance to scratching
- Part 13: Resistance to accelerated ageing by the use of heat
- Part 14: Chalking (Helmen method)
- Part 15: Metamerism
- Part 16: Resistance to abrasion

BS EN 13523-23:2015 **EN 13523-23:2015 (E)**

- Part 17: Adhesion of strippable films
- Part 18: Resistance to staining
- Part 19: Panel design and method of atmospheric exposure testing
- Part 20: Foam adhesion
- Part 21: Evaluation of outdoor exposed panels
- Part 22: Colour difference Visual comparison
- Part 23: Resistance to humid atmospheres containing sulfur dioxide
- Part 24: Resistance to blocking and pressure marking
- Part 25: Resistance to humidity
- Part 26: Resistance to condensation of water
- Part 27: Resistance to humid poultice (Cataplasm test)
- Part 29: Resistance to environmental soiling (Dirt pick-up and striping)

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Previous work by the European Coil Coating Association (ECCA) has established that this test method is not a reliable or reproducible test for assessing the degree of corrosion on coil coated products, but that the test method may be used to evaluate the colour fastness of coil coated products.

The procedure has been aligned with EN ISO 3231, except for the amount of sulfur dioxide.

1 Scope

This part of EN 13523 defines terms of the procedure for determining the resistance of an organic coating on a metallic substrate to humid atmospheres containing sulfur dioxide.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0, Coil coated metals - Test methods - Part 0: General introduction

EN 13523-3, Coil coated metals - Test methods - Part 3: Colour difference - Instrumental comparison

EN 13523-22, Coil coated metals - Test methods - Part 22: Colour difference - Visual comparison

EN 23270, Paints and varnishes and their raw materials - Temperatures and humidities for conditioning and testing (ISO 3270)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0 apply.

4 Principle

Test specimens are exposed to an atmosphere containing sulfur dioxide. The degree of colour change is measured or visually assessed. The degree of other types of degradation, e.g. spotting, streaking, loss of gloss, of the test specimen may also be assessed.

5 Apparatus

An apparatus consisting of an airtight cabinet of capacity (300 ± 10) I, in the base of which is a water-tight trough fitted with a means of heating the water so that it can raise the air temperature in the cabinet to (40 ± 3) °C in about 1½ h and maintain this temperature for a total period of 8 h from the commencement of the test cycle.

The dimensions and design of the cabinet are not critical provided the stand for supporting the test panels is made of, or coated with an inert material and is of sufficient size to accommodate test specimens with a total surface area of (0.5 ± 0.1) m².

The cabinet shall also be constructed of an inert material and have a roof which prevents condensed moisture dripping onto the test specimens.

The cabinet shall be provided with a means of relieving excess pressure and a gas inlet pipe which shall be situated immediately above the water trough.

A gas cylinder or gas generating apparatus fitted with appropriate regulating and measuring apparatus to ensure the supply of the correct volume of sulfur dioxide.

The cabinet shall also be provided with a means of controlling the temperature which shall be measured in the space above the test specimens.

NOTE Some typical designs of apparatus are shown in EN ISO 3231:1997, Figures 1 and 2.

6 Sampling

See EN 13523-0.

7 Test specimens

See EN 13523-0.

The test specimens shall be nominally 150 mm × 100 mm, unless otherwise specified or agreed.

The reverse face and edges of the panel shall be coated with a suitable protective material such as a lacquer or adhesive tape to prevent attack by the sulfur dioxide.

8 Procedure

Condition the test specimens for at least 24 h under ambient conditions of temperature and humidity. If required, for instance in case of dispute, conditioning shall be carried out at (23 ± 2) °C and a relative humidity of (50 ± 5) %, in accordance with EN 23270.

During this conditioning, the test specimens shall not be exposed to direct sunlight.

After conditioning, carry out the test procedure as soon as possible.

Set-up the testing apparatus (Clause 5) in an environment protected from draughts and direct sunlight.

Arrange the test specimens vertically in the test apparatus so that they are at least 100 mm from any wall or cover, at least 20 mm from each other and so that the lower edges of the specimens are at least 200 mm above the water. Where possible, arrange the test specimens at the same level for comparative tests. Care shall be taken to ensure that water condensed on upper specimens does not drip onto the lower specimens.

As the same volume of sulfur dioxide is introduced at each test cycle, the total surface area of the test specimens in the cabinet is important. For comparative tests, the total test specimen area in the cabinet should be the same.

Fill the trough with $(2,0 \pm 0,2)$ I of distilled or deionised water. Prior to each test cycle, drain and renew this distilled or deionised water.

After closing the apparatus, introduce $(2,0\pm0,2)$ I of sulfur dioxide into the test cabinet, switch on the heating appliance and raise the air temperature to (40 ± 3) °C in about $1\frac{1}{2}$ h. Maintain this temperature for a total period of 8 h from the commencement of the test cycle. At the end of this period, switch off the heating appliance and ensure the chamber is fully purged. Open the door completely or raise the hood of the apparatus to at least the height of the upper edges of the test specimens.

Leave the test specimens in the cabinet for a further 16 h. This constitutes one test cycle. Start a new cycle by changing the water and introducing fresh sulfur dioxide. Repeat for a total of 5 test cycles. Cycles shall be continuous and without interruption.

At the end of 5 test cycles, remove the test specimens from the cabinet, wash with clean water, blot with absorbent paper and immediately examine the whole test surface of each specimen for colour change using EN 13523-3 or EN 13523-22.

Measure or assess visually the degree of colour change. The degree of other types of degradation, e.g. spotting, streaking, loss of gloss, of the test specimen may also be assessed.

9 Expression of results

Express the result as the mean of the measurements taken or the visual difference in colour.

If specified, report observations on spotting, streaking, loss of gloss and any other degradation effects.

10 Precision

No precision data are currently available.

11 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of EN 13523;
- c) the results of the test, as indicated in Clause 9;
- d) any deviation from the test method specified;
- e) the date of the test.

Bibliography

- [1] EN 1396, Aluminium and aluminium alloys Coil coated sheet and strip for general applications Specifications
- [2] EN 10169, Continuously organic coated (coil coated) steel flat products Technical delivery conditions
- [3] EN ISO 3231:1997, Paints and varnishes Determination of resistance to humid atmospheres containing sulfur dioxide (ISO 3231:1993)





British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

