

Products and systems for the protection and repair of concrete structures — Test methods — Water absorption and resistance to alkali for hydrophobic impregnations

The European Standard EN 13580:2002 has the status of a
British Standard

ICS 91.080.40

National foreword

This British Standard is the official English language version of EN 13580:2002.

The UK participation in its preparation was entrusted by Technical Committee B/517, Concrete, to Subcommittee B/517/8, Protection and repair of concrete structures, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Building and Civil Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 18 September 2002

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 10, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 18 September 2002

ISBN 0 580 40400 5

ICS 91.080.40

English version

Products and systems for the protection and repair of concrete structures - Test Methods - Water absorption and resistance to alkali for hydrophobic impregnations

Produits et systèmes pour la protection et la réparation des structures en béton - Méthodes d'essai - Absorption d'eau et résistance aux alcalis pour imprégnations hydrofuges

Produkte und Systeme für den Schutz und die Instandsetzung von Betontragwerken - Prüfverfahren - Wasseraufnahme und Alkalibeständigkeit für hydrophobierende Imprägnierungen

This European Standard was approved by CEN on 23 December 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Symbols	4
4 Principle.....	5
5 Apparatus	5
6 Preparation of test specimens	5
7 Treatment.....	6
8 Test procedure	7
9 Test report	8
Annex A (informative)	9
Annex B (informative)	10

Foreword

This document (EN 13580:2002) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

It has been elaborated by Subcommittee SC 8 "Products and systems for the protection and repair of concrete structures", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2003, and conflicting national standards shall be withdrawn at the latest by February 2003.

The Annexes A and B are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a test method to evaluate the effect of a hydrophobic impregnation. It deals with the rate at which treated concrete absorbs water and with the alkali resistance of that surface treatment. The method primarily relates to the protection of concrete structures.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1766, *Products and systems for the protection and repair of concrete structures – Test methods – Reference concretes for testing.*

EN 13579, *Products and systems for the protection and repair of concrete structures – Test methods – Drying test for hydrophobic impregnation.*

3 Symbols

Symbol	Explanation	Unit
AR	Absorption ratio	%
$AR_{(alk)}$	Absorption ratio after exposure to alkali	%
C_m	Mean consumption of impregnant during treatment	g/m ²
C_n	Consumption of impregnant for each face of test cube during treatment	g/m ²
i_1	Weight of a test cube at start of immersion test	g
i_2	Weight of a test cube at end of immersion test	g
I_t	Rate of increase in weight of a treated test cube	g/(m ² · h ^{0,5})
$I_{t(alk)}$	Rate of increase in weight of a treated test cube after exposure to alkali	g/(m ² · h ^{0,5})
I_{tm}	Mean rate of increase in weight of three treated test cubes	g/(m ² · h ^{0,5})
$I_{tm(alk)}$	Mean rate of increase in weight of three treated test cubes after exposure to alkali	g/(m ² · h ^{0,5})
I_u	Rate of increase in weight of an untreated test cube	g/(m ² · h ^{0,5})
I_{um}	Mean rate of increase in weight of three untreated test cubes	g/(m ² · h ^{0,5})
M'_t	Estimated moisture content of each test cube after conditioning	%
M_m	Mean saturated surface dry moisture content of 3 oven dry test cubes	%
M_{ssd}	Saturated surface dry moisture content of a test cube	%
W'_{od}	Estimated weight of a test cube in oven dry condition	g
W_{od}	Weight of a test cube in oven dry condition	g
W_{ssd}	Weight of a test cube in saturated surface dry condition	g
W_t	Actual weight of test cube after conditioning	g
W_{t1}	Weight of test cube immediately prior to treatment	g
W_{t2}	Weight of test cube immediately after treatment	g

4 Principle

Impregnants applied to the surface of the concrete reduce the ingress of water and salt solutions into concrete. The principle of the test method described in this standard is to compare rate of uptake of water of treated and untreated test cubes from the same batch of concrete. The ratio of the rates is defined as the absorption ratio. The long term durability is assessed by measuring the water absorption after a defined exposure to alkali.

5 Apparatus

- 5.1 Nine moulds for concrete cubes (100 mm x 100 mm x 100 mm).
- 5.2 Soft brush
- 5.3 Absorbent paper towel
- 5.4 Balance with an accuracy of 0,01 g.
- 5.5 Support for test cubes on bench in laboratory or in fume cupboard to allow air to circulate around all 6 faces.
- 5.6 Laboratory or chamber maintained at constant temperature $(21 \pm 2) ^\circ\text{C}$ and relative humidity of $(60 \pm 10) \%$
- 5.7 Forced air circulation oven to run at $(105 \pm 5) ^\circ\text{C}$.
- 5.8 Desiccator cabinet containing silica gel.
- 5.9 Fume cupboard.
- 5.10 Two suitable air tight boxes containing saturated potassium sulphate solution for storing specimens. Note that treated and untreated test cubes must be stored in separate boxes.
- 5.11 One 150 mm diameter petri dish with 2 spacers glued to bottom of dish to support the test cubes during treatment
- 5.12 Demineralised water (conductivity $< 50 \mu\text{S}$).
- 5.13 Six 5 l beakers with suitable spacers to support test cubes.
- 5.14 Potassium-hydroxide solution (5,6 g/l).
- 5.15 Cling film.

6 Preparation of test specimens

Nine 100 mm concrete test cubes shall be cast from a single batch of Type C (0.45) concrete and cured for 28 days according to EN 1766. No oil or release agent will be permitted on the surface of the moulds (5.1). After removal from the curing tank, the test cubes shall be cleaned with tap water using a soft brush (5.2) to remove any loose material. The surface of the test cubes shall not be grit blasted. The test cubes shall be surface dried with an absorbent paper towel (5.3) and then weighed (W_{ssd}) using the balance (5.4).

Six test cubes (No. 1 - 6), suitably supported to allow air to circulate around each of the 6 faces (5.5), shall be conditioned on a bench in the laboratory (temperature $(21 \pm 2) ^\circ\text{C}$ and relative humidity $(60 \pm 10) \%$) (5.6) for 7 days and reweighed (W_r). The remaining three test cubes (No. 7 - 9) shall be oven dried at $(105 \pm 5) ^\circ\text{C}$ (5.7) for 7 days, cooled in a desiccator cabinet containing silica gel (5.8) and reweighed (W_{od}).

The saturated surface dry moisture content (M_{ssd}) of the 3 oven dry test cubes (No. 7 - 9), shall be calculated using the following formula :

$$M_{ssd} = \frac{W_{ssd} - W_{od}}{W_{od}} \cdot 100 \text{ in percentage by weight} \quad (1)$$

The estimated oven dry weight (W'_{od}) of each of the remaining 6 test cubes (No. 1 - 6) shall be calculated using the formula :

$$W'_{od} = \frac{W_{ssd}}{1 + \left(\frac{M_m}{100}\right)} \text{ in grams} \quad (2)$$

where

M_m is the mean saturated surface dry moisture content of the 3 oven dry test cubes (No. 7 - 9), in percentage by weight.

The estimated moisture content (M'_t) of each of the test cubes after conditioning shall be calculated from the weight, W_t

$$M'_t = \frac{W_t - W'_{od}}{W'_{od}} \cdot 100 \text{ in percentage by weight} \quad (3)$$

The test cubes (No. 1 - 6) shall be weighed daily during conditioning from the fourth day until the weight W_t obtained is equivalent to a moisture content of $(5,0 \pm 0,5) \%$.

7 Treatment

Three test cubes from the batch shall be treated in a fume cupboard (5.9) with the fan on immediately after the conditioning. The 3 untreated test cubes shall be placed in an airtight box (5.10) over a saturated solution of potassium sulphate until required for the absorption test.

Each cube shall be treated by dipping each face in the impregnant. Immediately prior to treatment of each face, the cube shall be weighed (W_{t1}). 60 ml of the material shall be measured into a petri dish 150 mm in diameter (5.11).

One side of the cube, supported on the 2 mm plastic spacers, shall be dipped in the material for (120 ± 5) s, and then removed. Excess liquid on the cube shall be allowed to drain back into the dish and the cube immediately reweighed (W_{t2}). The excess material in the dish is then to be discarded. This procedure shall be repeated for first side of the other two cubes.

The consumption (C_n) of the material for each face of the cube shall be calculated as follows :

$$C_n = \frac{W_{t2} - W_{t1}}{0,01} \text{ in grams by square meters} \quad (4)$$

The above procedure shall be repeated on the remaining faces of each of the cubes and the average consumption for each cube shall be calculated.

The mean consumption (C_m) for the three test cubes shall be calculated.

If the consumption is below the manufacturer's recommended value the time of dipping can be extended.

If it is not practical to treat test cubes by this method, the treatment should be carried out in accordance with the manufacturer's instructions.

The cubes shall be stored, suitably supported to allow air to circulate around all 6 faces, in the fume cupboard (5.3) for (48 ± 1) h after the start of treatment with the fan off. The treated cubes shall then be stored over a saturated potassium sulphate solution in an airtight box.

Note that it is essential that the treated and untreated cubes are stored in separate boxes.

8 Test procedure

The tests shall either be carried out on 3 treated and 3 untreated test cubes prepared as described in sections 6 and 7 above or on test cubes that have been used previously for the drying test as described in prEN 13579. In both cases, the absorption test shall commence 14 days after treatment.

Sufficient demineralised water (Conductivity $< 50 \mu\text{S}$) (5.12) shall be placed into each of the 6 beakers (5.13) so that each test cube supported on a spacer will be fully covered with a head of (25 ± 5) mm. The three treated and the three untreated test cubes shall each be weighed (i_1) and immersed in demineralised water. The treated and untreated test cubes shall be removed from the water after $(24,0 \pm 0,1)$ hours and $(1,00 \pm 0,02)$ hour respectively, surface dried with an absorbent cloth and reweighed (i_2).

The rate of increase in weight for each treated test cube (I_t) shall be calculated from the equation :

$$I_t = \frac{i_2 - i_1}{\sqrt{24} \cdot 0,06} \text{ in } \frac{\text{g}}{\text{m}^2 \cdot \text{h}^{0,5}} \quad (5)$$

and for each untreated test cube from the equation :

$$I_u = \frac{i_2 - i_1}{\sqrt{1} \cdot 0,06} \text{ in } \frac{\text{g}}{\text{m}^2 \cdot \text{h}^{0,5}} \quad (6)$$

The absorption ratio (AR) shall be calculated :

$$AR = \frac{I_{tm}}{I_{um}} \cdot 100 \text{ in percentage} \quad (7)$$

where

I_{tm} is the mean rate of weight gain of the three treated test cubes ; and

I_{um} is the mean rate of weight gain of the untreated test cubes.

Immediately after the immersion test, the three treated test cubes shall be placed in individual beakers containing sufficient potassium hydroxide solution (5,6 g/l) (5.14) to fully cover a test cube supported on a spacer with a head of (25 ± 5) mm. The beakers are securely covered with cling film (5.15) and left for $(21 \pm 0,1)$ days. The test cubes shall be removed from the beakers and dried, suitably supported on a bench to allow air to circulate around each of the 6 faces in the laboratory, until their weight is within ± 2 g of their weight prior to the start of the immersion test (i_1). A second immersion test shall be carried out and rate of increase in weight of each treated test cube after the alkali test $I_{(alk)}$ calculated. The absorption ratio (AR_{alk}) shall be calculated by :

$$AR_{alk} = \frac{I_{tm(alk)}}{I_{um}} \cdot 100 \text{ in percentage} \quad (8)$$

where

$I_{tm(alk)}$ is the mean rate of weight gain of the three test cubes after immersion in alkali, in grams.

9 Test report

The test report shall contain at least the following information :

- a) a reference to this European standard ;
- b) name and address of the test laboratory ;
- c) identification number and date of the test report ;
- d) name and address of the manufacturer or supplier of the product(s) ;
- e) name and identification marks or batch number of the product(s) ;
- f) date of supply of the product ;
- g) date of preparation of the test specimens and any deviation from the prescribed method of preparation ;
- h) numbering of cubes ;
- i) details of the concrete mix design ;
- j) conditions of storage of prepared specimens prior to test ;
- k) the mean saturated surface dry moisture content of the test cubes ;
- l) the mean moisture content of the test cubes after conditioning ;
- m) the mean consumption of the impregnant ;
- n) the absorption ratio before and after exposure to alkali ;
- o) date of test and details of the test equipment used ;
- p) any deviation from the test method specified ;
- q) date of the report and signature ;
- r) any other observations.

Annex A (informative)




Figure A.1 : Flow chart of test procedure for absorption and resistance to alkali test

Annex B (informative)

If all parties agree, the tests can be carried out on Type C (0,70) concrete as specified in EN 1766.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.