Methods of test for screed materials —

Part 6: Determination of surface hardness

The European Standard EN 13892-6:2002 has the status of a British Standard

 $ICS\ 91.100.10$



National foreword

This British Standard is the official English language version of EN 13892-6:2002.

The UK participation in its preparation was entrusted by Technical Committee B/544, Plastering, rendering, dry lining, screeds and in situ floorings, to Subcommittee B/544/6, Screeds and in situ floorings, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled "International Standards Correspondence Index", or by using the "Search" facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Building and Civil Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 28 November 2002

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 7 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No. Date Comments

© BSI 28 November 2002

ISBN 0 580 40878 7

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 13892-6

November 2002

ICS 91.100.10

English version

Methods of test for screed materials - Part 6: Determination of surface hardness

Méthodes d'essai des matériaux pour chapes - Partie 6: Détermination de la dureté superficielle Prüfverfahren für Estrichmörtel und Estrichmassen - Teil 6: Bestimmung der Oberflächenhärte

This European Standard was approved by CEN on 9 October 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

		page
Foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Symbols and abbreviations	4
5	Apparatus	4
6	Procedure	5
7	Test report	5
Bibliography		7
	~ · ·	

Foreword

This document (EN 13892-6:2002) has been prepared by Technical Committee CEN/TC 303, "Floor screeds and in-situ floorings in buildings", the secretariat of which is held by DIN.

It was prepared by Working Group 2 "Screed materials and floor screeds -Test-methods" taking into account the proposals submitted by Working Group 1 "Screed materials and floor screeds - Definitions, properties and requirements".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2003, and conflicting national standards shall be withdrawn at the latest by May 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European standard specifies a method for determining the surface hardness of moulded mortar specimens made from magnesite screed material or from cementitious screed-, calcium sulphate screed-, magnesia screed- and synthetic resin screed material. This method is only suitable for screed materials having aggregates of size less than 4 mm.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 13813, Screed material and floor screeds - Screed material - Properties and requirements

EN 13892-1, Test methods for screed materials – Part 1: Sampling, making and curing specimens for test.

3 Principle

The surface hardness is determined by measuring the permanent depth of indentation produced by a steel ball placed on the surface under a standard load. The surface hardness is calculated as the load on the ball devided by the surface area of indentation.

NOTE: On completion of the measurement of surface hardness, the flexural and compressive strength may be measured on the same specimens.

4 Symbols and abbreviations

d is the diameter of the steel ball

t is the indentation depth

 F_V is the initial load of (10 0,1) N

F is the main load of (500 5) N

SH is the surface hardness in N/mm², as determined from the test parameters

5 Apparatus

Hardness tester capable of applying vertically an initial and a main load on to a (10 0,01) mm steel ball with precise measurement of the vertical movement using a dial gauge with 0,001 mm scale intervals.

NOTE The steel ball may be embedded in the end of a steel bar, through which the loads are applied.

6 Procedure

The surface hardness shall be measured on 3 specimens made in accordance with EN 13892-1. Each specimen shall be weighed, the width and depth of the specimen shall be measured mid way along its length, and the density shall be calculated.

A polished steel ball of 10 mm diameter, d, shall be placed on the upper surface of the specimen, as prepared.

The initial load, F_V , of (10 0,1) N (preload) shall be applied to the steel ball, carefully and without impact. The initial value shall be measured with a dial gauge or the dial gauge shall be put to zero.

Then the main load, F, of (500 5) N shall be applied to the steel ball carefully and without impact, and it shall be maintained for a period of 1 min.

After this period, the steel ball shall be unloaded to the preload level of (10 0.1) N. After a period of 1 min the indentation depth, t, in excess of the initial value shall be measured with a dial gauge to the nearest of 0.01 mm.

The surface hardness. SH. shall be calculated, in N/mm², using the following equation:

$$S = \frac{F}{d \times x}$$

The surface hardness shall be recorded to the nearest 0,1 N/mm² as the arithmetic mean of 3 measurements on each specimen, and also as the arithmetic mean for the 3 specimens.

7 Test report

The test report shall include the following information:

- a) number, title and date of issue of this European Standard;
- b) name and address of the laboratory carrying out the tests and name and address of the laboratory preparing the samples (if different);
- c) identification number of the test report;
- d) name and address of the manufacturer or supplier of the product;
- e) name and identification marks or batch number of the product;
- f) date of supply of the product;
- g) method of sampling (by reference to EN 13892-1 and by which organisation);
- h) place, date and time of sampling;
- i) identification of the screed samples, including type, origin and designation of the screed material by reference to the relevant product standard EN 13813;
- j) preparation (mixing, casting) and storage (curing) conditions by reference to EN 13892-1;
- k) date and time of preparing samples for test (i. e. date and time of any mixing, casting, moulding or demoulding procedure, if appropriate);
- age of screed material when tested;

EN 13892-6:2002 (E)

- m) density of each individual test sample;
- n) test method used (reference manual or alternative method, if appropriate), and details of test specimens including number, dimensions, mass, etc. if appropriate;
- o) date of test and the identification number of the apparatus or details of the test equipment used, including the make, type and capacity and the calibrations details;
- p) test results (individual values to the nearest 0,05 N/mm², and corresponding mean value stated to the nearest 0,1 N/mm²);
- q) remarks;
- r) date of test report and signature.

Bibliography

EN 13318, Screed materials and floor screeds – Definitions.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at http://www.bsi-global.com.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.

Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.

Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at http://www.bsi-global.com/bsonline.

Further information about BSI is available on the BSI website at http://www.bsi-global.com.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means — electronic, photocopying, recording or otherwise — without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

BSI 389 Chiswick High Road London W4 4AL