

Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics —

Part 2: Determination of colouristic properties and ease of dispersion in plasticized polyvinyl chloride by two-roll milling

The European Standard EN 13900-2:2003 has the status of a
British Standard

ICS 83.040.30

Confirmed September 2008

National foreword

This British Standard is the official English language version of EN 13900-2:2003.

The UK participation in its preparation was entrusted to Technical Committee STI/1, Pigments, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 21 February 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 9 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 21 February 2003

ISBN 0 580 41285 7

ICS 83.040.30

English version

Pigments and extenders - Methods of dispersion and
assessment of dispersibility in plastics - Part 2: Determination of
colouristic properties and ease of dispersion in plasticized
polyvinyl chloride by two-roll milling

Pigments et matières de charge - Méthodes de dispersion
et évaluation des caractéristiques de dispersibilité dans les
plastiques - Partie 2: Détermination des propriétés
colorimétriques et de la facilité de dispersion dans le
chlorure de polyvinyle plastifié par calandrage sur bicylindre

Pigmente und Füllstoffe - Dispergiervverfahren und
Beurteilung der Dispergiierbarkeit in Kunststoffen - Teil 2:
Bestimmung der koloristischen Eigenschaften und der
Dispergiierhärte in weichmacherhaltigen Polyvinylchlorid
(PVC-P)- Formmassen im Walztest

This European Standard was approved by CEN on 12 December 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN 13900-2:2003) has been prepared by Technical Committee CEN/TC 298, "Pigments and extenders", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2003, and conflicting national standards shall be withdrawn at the latest by August 2003.

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This part of this European Standard specifies a method of determining the colouristic properties of a test pigment relative to a standard, and the ease of dispersion DH_{PVC-P} of pigments from the differences in colour strength on dispersing colouring materials under various conditions in plasticized polyvinyl chloride (PVC-P) compounds.

The method is appropriate for use with organic and inorganic black and colour pigments and for pigment preparations.

The ease of dispersion determined in this way is valid only for the dispersion equipment, dispersion conditions and dispersion medium being used. The use of test conditions differing from those specified may give different results; this applies both to the absolute magnitude and to the relation between values of the ease of dispersion of various pigments. The subscript DH_{PVC-P} is therefore used to designate the value obtained as specified in this part of this European Standard.

The principle of this standard may also be used for routine quality control purposes by reference to the photometric data generated from the sheets milled at 130 °C. For quality control purposes, the ratio of pigment to TiO_2 may be agreed between the interested parties. Ratios of 1:10 for organic pigments and 0,2 to 0,5:1 for inorganic pigments are suggested as convenient and widely used standard ratios.

Annex A is informative and gives a description of a suitable basic compound.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12877-1, *Colouring materials in plastics - Determination of colour stability to heat during processing of colouring materials in plastics - Part 1: General introduction*.

EN ISO 787-24:1995, *General method of tests for pigments and extenders - Part 24: Determination of relative tinting strength of coloured pigments and relative scattering power of white pigments - Photometric methods (ISO 787-24:1985)*.

EN ISO 15528, *Paints, varnishes and raw materials for paints and varnishes - Sampling (ISO 15528:2000)*.

ISO 7724-2:1984, *Paints and varnishes – Colorimetry - Part 2: Colour measurement*.

3 Term and definition

For the purposes of this European Standard the following term and definition applies.

3.1

ease of dispersion [DH_{PVC-P}]

measure of the rate at which or the degree to which a pigment or extender achieves a given level of dispersion when dispersed in a plastics material. The DH_{PVC-P} is derived from the increase in colour strength achieved by two-roll milling as specified in 8.2, relative to the colour strength achieved as specified in 8.1

4 Principle

Using a two-roll mill, the pigment under test is dispersed at $160\text{ °C} \pm 5\text{ °C}$ in the basic compound. The milled sheet obtained in this way is then subjected to the higher shearing forces resulting from two-roll milling at $130\text{ °C} \pm 5\text{ °C}$. The resulting increase in colour strength is a measure of the ease of dispersion DH_{PVC-P} .

5 Material

A suitable and recommended basic compound is described in annex A. An alternative compound may be agreed between the interested parties and is to be mentioned in the test report.

The quantity of the pigment used shall be such that a depth of shade (see EN 12877-1) of approximately 1/25 SD is achieved.

6 Apparatus

6.1 Two-roll mill

Equipped with heating facilities and having rollers adjustable for spacing. The roll diameter shall be between 80 mm and 200 mm, and the ratio of the speeds of rotation of the two rollers shall be between 1:1,1 and 1:1,2.

NOTE It has been found that comparable results on different two-roll mills will be obtained under the following conditions

— ratio of roller diameters of the two machines: between 1:1 and 1:1,5,

— ratio of peripheral speeds: between 1:1 and 1:1,1,

— H_k (bank) to H_s (gap width) should be $H_k/H_s \geq 20$.

If smaller roller sets are used (roller diameter e.g. 80 mm), the settings of the thickness of the milled sheet from 0,4 mm to 0,5 mm with the recommended conditions of similarity can lead to difficulties with regard to the requirement for a rolling bank.

6.2 Plate press

Provided with heating facilities and, advantageously, with cooling facilities as well.

6.3 Photometer

7 Sampling

Representative samples of the colouring materials to be tested shall be taken as described in EN ISO 15528.

8 Procedure

8.1 Milling at $160\text{ °C} \pm 5\text{ °C}$

The mixture consisting of the pigment under test and the basic compound shall be processed to produce a milled sheet. A test specimen having dimensions of 1 mm by at least 50 mm × 50 mm shall be produced from a portion of the milled sheet.

NOTE In this method increased shear is obtained by milling the reference sheet at a lower temperature of 130 °C, as a result of which the wetting-out properties of the PVC-P compound are also changed. The routine use of this method thus requires either that the temperature of a single mill is increased and decreased, which is time consuming, or that two mills operating simultaneously at different temperatures are employed. An alternative principle by which the milling temperature is maintained, and increased shear is generated by reducing the gap as in EN 12877-4, is being investigated for comparability and as a potentially more efficient method.

8.1.1 Premixing of the test materials

The prescribed quantities of colouring material and basic PVC-P compound required for the test specimens are mixed together in a suitable container, for example using a mixing shaker, for 5 min.

NOTE In the case of colouring materials in paste form, it is recommended to mix the components in a polyethylene or polypropylene beaker by hand using a mixing rod (not of glass) until the mixture appears to be homogeneous.

8.1.2 Two-roll milling

The pre-mixed material is added to the rotating mill rolls which have been brought to a temperature of $160\text{ °C} \pm 5\text{ °C}$. Any material falling through the nip shall be returned quickly and carefully from the tray to the moving mill rolls.

The quantity of mixture to be used shall be such that a continuously rotation bead is formed in the nip, once the sheet has been formed. Set the gap so that the sheet has a uniform thickness of 0,4 mm to 0,5 mm thickness across its width.

Mill the material, limiting the width of the sheet by frequent cutting to one half and by reversal and lateral rolling, to prevent the material from running up onto the roll guides and to achieve adequate dispersion of the colouring material. Alternatively it may be removed repeatedly and returned without delay to the rolls to ensure thorough mixing. In this case the number of such repetitions shall be defined as part of the method and recorded in the test report.

Mixing is carried out for a total of 200 rotations of the rolls. According to the diameter of the rolls of the machine being used (see 6.1) the duration of milling shall not be less than 5 min but shall not exceed 10 min.

The sheet is then removed from the rolls. To facilitate this step the roll gap and, if necessary, roll speed and friction may be adjusted.

After each milling operation the rolls shall be cleaned.

8.1.3 Pressing

For photometric measurement it is advantageous to prepare specimens with a high surface gloss and quality.

Such specimens may be obtained by pressing the sheets in a plate press for no longer that 2 min at 165 °C to max. 170 °C between high gloss chrome steel plates using a spacer frame of 1mm thickness. The pressed sheets shall be cooled rapidly to room temperature.

8.2 Milling at $130\text{ °C} \pm 5\text{ °C}$

The remainder of the milled sheet prepared as specified in 8.1 shall be used for this purpose. The roller gap shall be set, and maintained unchanged during roll milling, such that a milled sheet having a thickness of 0,4 mm to 0,5 mm is produced. The roller temperatures shall be maintained at $130\text{ °C} \pm 5\text{ °C}$.

The milled sheet shall first be passed through the roller gap unfolded, then folded once and passed without delay through the gap again. This procedure (i.e. folded once) shall be repeated ten times. A test specimen having dimensions of 1 mm by at least $50\text{ mm} \times 50\text{ mm}$ shall be prepared by pressing as specified in 8.1.3.

9 Photometric measurement

The colour strength of the test specimens prepared as specified in 8.1 and 8.2 shall be measured as specified in ISO 7724-2:1984, clause 9. These values shall be used to determine the colour strength as specified in EN ISO 787-24:1995, 8.1 and clause 9 for the purposes of the calculation of DH_{PVC-P} .

10 Evaluation

10.1 Evaluation of colouristic properties in a white reduction

For quality control purposes the colouristic properties and colour differences of the test specimens relative to a standard shall be measured as specified in clause 9.

NOTE The colouristic properties in a full-shade system can be carried out in a similar manner but without addition of TiO_2 .

EN 13900-2:2003 (E)

10.2 Evaluation of the ease of dispersion

The ease of dispersion [DH_{PVC-P}] is the percentage increase in colour strength following roll milling at 130 °C. It shall be computed from the F values, using the following equation:

$$DH_{PVC-P} = 100 \times \left(\frac{F_2}{F_1} - 1 \right)$$

where

F_1 is the colour strength value of the test specimen, specified in 8.1;

F_2 is the colour strength value of the test specimen specified in 8.2.

11 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of this European Standard (prEN 13900-2);
- c) designation of the test specimens and their preparation;
- d) description of the basic compound;
- e) concentration of the colouring material under test in the basic compound, for the respective test specimens;
- f) photometric data obtained and where appropriate ease of dispersion [DH_{PVC-P}];
- g) method of colour strength determination;
- h) if colour measurement has been specified: type of photometer, standard illuminant and standard observer used;
- i) any deviation from the test method specified;
- j) the date of the test.

12 Precision

This standard defines the principals of the method and the procedures to be used, but allows variation as regards the dimensions of the machinery and the composition of the PVC compound used. Precision data thus cannot be established for the method itself, precision should be determined by repeatability and reproducibility studies according to the equipment and compound used in the testing laboratory, and according to the pigment under test.

Annex A

(informative)

Description of the basic compound

A.1 PVC-P compound suitable for determining ease of dispersion by two-roll milling

65,00 parts vinyl chloride polymer, suspension PVC (1)

33,50 parts plasticizer - di-iso-decyl phthalate (DIDP) (2)

1,50 parts epoxidized soybean oil (3)

1,30 parts liquid barium zinc stabiliser (4)

0,20 parts lubricant - stearic acid (5)

5,34 parts* titanium dioxide pigment (6)

* equivalent to 5 parts TiO₂ in 100 parts of finished compound

A.2 Specifications

- 1) Suspension PVC

K value 70 ± 1

- 2) Plasticizer - di-iso-decyl phthalate

of a quality recommended for the use in PVC compounds

- 3) Epoxidized soybean oil

of a quality recommended for the use in PVC compounds

- 4) Liquid barium zinc stabiliser

having a barium content of 10,2 to 12,2 and a zinc content of 1,95 to 2,35

NOTE Alternatively barium zinc stabiliser systems resulting in equivalent heat stability can be used.

- 5) Stearic acid

of a quality recommended for the use in PVC compounds

- 6) Titanium dioxide pigment

An easily dispersing powder grade recommended for plastics should be used.

Composition: rutile type with organic and inorganic surface treatment and with minimum 93 % TiO₂.

A.3 Preparation of PVC-P compound

The PVC polymer, stabiliser and lubricant are pre-mixed in a high speed mixer until the mixture reaches a temperature of 70 °C. Titanium dioxide pigment is then added and mixed for about 2 min (there is a danger of greying through metal abrasion if longer mixing times are used). Subsequently the pre-mixed quantities of plasticizer and epoxidized soybean oil are added as a thin stream as mixing continues. The mixture reaches a temperature of about 100 °C during this process, following which the homogeneous compound is cooled with agitation to room temperature.

NOTE PVC-P compounds should be stored in a cool place in a closed container for not longer than 2 years under exclusion of light.

A.4 Assessing the basic compound

It is necessary to assess the basic compound, since the titanium dioxide pigment which it contains can also be further dispersed by the roll milling specified in 8.2. This will result in an increase in the opacity or hiding powder of the basic mixture, leading to a change in the F value of the test specimen prepared by the roll milling specified in 8.2. In determining the ease of dispersion DH_{PVC-P} , the change in the opacity or hiding power of the basic mixture can be disregarded if it is equivalent to less than 3 %. Otherwise, it is necessary to correct the test results.

In order to assess the basic compound, the procedure specified in this part of this European Standard should be carried out as stated in clause 8, and a dyestuff soluble in the basic mixture should be used in place of the pigment under test. It is recommended that a concentration of 0,05 % C.I. Solvent Violet 13 or Solvent Violet 36 be added to the basic compound. This leads to a colouration of approximately 1/25 standard depth of shade. The subsequent procedure is as specified in 8.1 and 8.2. The milled sheets obtained should be used to determine the values F_1 and F_2 as specified in clause 10. These values are used to compute the factor C:

$$C = \frac{F_1^*}{F_2^*}$$

If $C > 1,03$, then the equation in clause 10 should be replaced by the following equation:

$$DH_{PVC-P} = 100 \frac{(C \cdot F_2 - 1)}{F_1}$$

Bibliography

EN 12877-4, *Colouring materials in plastics - Determination of colour stability to heat during processing of colouring materials in plastics - Part 4: Determination by two-roll milling.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.