

Durability of wood and wood-based products — Performance criteria for curative wood preservatives as determined by biological tests

The European Standard EN 14128:2003 has the status of a British Standard

ICS 71.100.50; 79.040

National foreword

This British Standard is the official English language version of EN 14128:2003.

The UK participation in its preparation was entrusted to Technical Committee B/515, Wood preservation, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 23 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 23 January 2004

© BSI 23 January 2004

ISBN 0 580 43313 7

EUROPEAN STANDARD

EN 14128

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2003

ICS 71.100.50; 79.040

English version

Durability of wood and wood-based products - Performance criteria for curative wood preservatives as determined by biological tests

Durabilité du bois et des matériaux dérivés du bois -
Critères de performances des produits curatifs de
préservation du bois établis par des essais biologiques

Dauerhaftigkeit von Holz und Holzprodukten -
Anforderungen an bekämpfend wirkende Holzschutzmittel,
wie sie durch biologische Prüfungen ermittelt werden

This European Standard was approved by CEN on 1 October 2003.

CEN members are bound to comply with the CEN/GENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions.....	6
4 Wood destroying organisms	7
5 Performance requirements for products against beetles (see Table 1).....	8
6 Performance requirements for barrier treatments against dry rot fungus	9
7 Derivation of effective values	9
8 Product identification and labelling	9
Annex A (informative) Guidance on re-testing after making variations in product formulation.....	13
Annex B (normative) Test requirements for curative products against <i>Xestobium rufovillosum</i>	18
Annex C (normative) Test requirements for curative products against <i>Hesperophanes cinnereus</i>	19
Annex D (informative) Recommended system for the classification of the effectiveness of curative wood preservatives	20
Annex E (informative) Guidance for physical chemical properties.....	21
Annex F (informative) Example of a system to describe the effectiveness of a curative wood preservatives against beetles.....	22
Bibliography	23

Foreword

This document (EN 14128:2003) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

This European Standard gives the performance criteria for curative wood preservatives as determined by biological tests. A further European Standard (at present still in preparation) is concerned with criteria for hot air processes for curative uses against wood destroying organisms.

This European Standard is valid for products to eradicate beetles in infested wood and for products to be used in the course of curative actions against the dry rot fungus to prevent its growth through masonry and beyond.

The annexes B and C are normative.

The annexes A, D, E and F are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This European Standard should be used in conjunction with prEN WI 00038084 (at present still in preparation) and with EN 599-1 which describes the performance requirements for preventive wood preservatives as determined by biological tests.

The need to use curative products against wood destroying organisms depends upon a careful diagnosis by expert, qualified specialists to determine the precise causes of the damage to be rectified. This should include the type of wood attacking organisms involved and whether they are active, the environmental circumstances, especially the source and nature of any wetting, the type of wood involved, the nature of the building or construction, and the structural and physical significance of the timber which is damaged or at risk of being damaged.

Curative treatment can be achieved either by chemical wood preservatives as specified in this European Standard or by specific curative processes without using chemicals, like hot air processes, as given in prEN WI 00038084.

Curative wood preservative products should be used in an integrated way as part of a carefully prescribed strategy involving a series of actions appropriate to the particular circumstances of each case. Associated physical measures involving appropriate building works to remedy ingress of moisture and to dry out any dampness can be an essential prerequisite for the use of any curative products. Expert diagnosis should take into account all regional, practical, environmental, economical, safety and any other factors which can be relevant to the prescriptive decisions to be taken.

It is not the purpose of this European Standard to provide a specification, or even guidance in developing specifications for remedial work to eradicate wood destroying organisms. This European Standard also does not give guidance on the methods of application or the precise amounts of products that might be appropriate to apply in specific practical circumstances. It is intended to guide specifiers, users and others in selecting and specifying products on the basis of their effectiveness as demonstrated in accordance with the criteria given.

1 Scope

This European Standard specifies the minimum performance requirements in biological tests for products for curative uses against specific wood destroying organisms. It specifies the biological tests required together with the performance criteria to be achieved in each test.

Chemicals against insects can act according to their specific properties within a short time (fast acting) or only after a long period (slow acting or with a deferred effect). Different tests and performance requirements are needed for these various types of curative wood preservatives.

This European Standard is applicable to all wood preservative products supplied for application in liquid form for curative uses against attack by wood attacking insects, excluding termites. This European Standard is also applicable for products applied to prevent growth of dry rot fungus through masonry.

This European Standard is also applicable to products for curative uses supplied for application as pastes, solids or in capsule form but only where appropriate biological methods of test exist as published European Standards or as normative annexes to this European Standard.

NOTE 1 The nature of the laboratory tests required in this European Standard is such that the time required to generate data is many months sometimes more than one year, depending upon the type of product and the organism(s) it is intended to be used against.

Therefore, at the date of publication of this European Standard, for many products covered under its scope already placed on the market and used lawfully in accordance with local technical traditions, the minimum data specified in this standard may not be available. Accordingly, for a period not exceeding 3 years from the date of publication of this European Standard, national standards organisations, or an organisation nominated by them may declare interim effective values for use within their territories, to apply to products already placed on the market and used lawfully in accordance with local traditions at the date of use of this European Standard.

NOTE 2 For re-testing after making variations in product formulation, guidance is given in annex A.

This European Standard is not applicable to products used as fumigants.

This European Standard is also not applicable for determining whether specific curative products, used alone or in combination, are effective in conferring long-term preventive action against attack by wood destroying organisms in the future. Preventive effectiveness can be determined using EN 599-1 but only for products whose nature allow them to be tested using the methods and interpretative procedures defined in EN 599-1. Amendments of existing test methods cited in EN 599-1 may be used but only when defined in normative annexes to this European Standard.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 22, *Wood preservatives – Determination of eradicant action against *Hylotrupes bajulus* (Linnaeus) larvae (Laboratory method)*.

EN 48, *Wood preservatives – Determination of the eradicant action against larvae of *Anobium punctatum* (De Geer) (Laboratory method)*.

EN 73, *Wood preservatives – Accelerated ageing tests of treated wood prior to biological testing – Evaporative ageing procedure*.

EN 14128:2003 (E)

EN 370, *Wood preservatives – Determination of eradicant efficacy in preventing emergence of Anobium punctatum (De Geer)*.

EN 599-1:1996, *Durability of wood and wood-based products – Performance of preventive wood preservatives as determined by biological tests – Part 1: Specification according to hazard class*.

ENV 1390, *Wood preservatives – Determination of the eradicant action against Hylotrupes bajulus (Linnaeus) larvae – Laboratory method*.

ENV 12404, *Durability of wood and wood-based products – Assessment of the effectiveness of a masonry fungicide to prevent growth into wood of Dry Rot Serpula lacrymans (Schumacher ex Fries) S.F Gray – Laboratory method*.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1 active ingredient

individual chemical compound or compounds included in the wood preservative product to give it a specific activity against the particular biological agencies of deterioration

3.2 barrier treatment

treatment of masonry in case of dry rot fungus to avoid its growth beyond the treated zone

3.3 biological reference value (brv)

amount in grams per square meter or kilograms per cubic meter of the wood preservative product found to be effective in test in eradicating attack by the particular biological agency being tested

3.4 curative efficacy

specific property of a wood preservative to act as an eradicant in infested timber

3.5 deferred effect insecticidal products

insect curative products which are not designed to have an immediate effect on the target organisms but which are designed to have their full eradicant effect at a later stage in the life cycle e.g. at the time of emergence from the wood

3.6 effective value

amount of wood preservative in millilitres per square meter obtained from all biological tests carried out in accordance with this European Standard. It is the highest of the brvs for the curative effectiveness of the product from all the tests carried out to support the claimed activity of the product

3.7 fast acting insecticidal products

insect curative products which achieve the required level of effectiveness within a period of three months using the appropriate standard test method

3.8 maximum application limit

maximum amount in millilitres per square meter of the wood preservative product permitted for application to the wood specimens in the particular biological test

3.9 performance

behaviour of the wood preservative product in terms of its effectiveness in the test

NOTE The term 'performance' applies also to the behaviour in terms of its effectiveness in practice against individual or collective effects of particular biological agencies of deterioration.

3.10 preventive efficacy

property of a wood preservative to avoid infestation of the wood by the particular biological agencies of deterioration

3.11 product

formulated wood preservative product in the form as supplied for sale by the manufacturer

3.12 slow acting insecticidal products

insect curative products which achieve the required level of effectiveness in a period longer than three months but not more than one year using the appropriate standard test method

3.13 wood preservative

active ingredient(s) or preparations containing active ingredient(s) in the form in which they are placed on the market, which are, on the basis of the properties of their active ingredient(s), intended either to prevent wood destroying or wood disfiguring organisms (fungi, insects and marine borers) from attacking wood and wood-based products or to combat an attack by those organisms

NOTE For the purpose of this European standard, the term wood preservatives includes also these products to eradicate an existing infection.

4 Wood destroying organisms

4.1 Insects

Amongst the wood attacking insects considered in this European Standard the following are the most common:

Beetles: *Hylotrupes bajulus* (house longhorn beetle) in the sapwood of softwoods;

Anobium punctatum (common furniture beetle) in softwoods and hardwoods;

Xestobium rufovillosum (deathwatch beetle) in hardwoods and softwoods, mainly in oak;

Lyctus brunneus (powderpost beetle) in the starch containing sapwood of hardwoods;

Hesperophanes cinnereus in the sapwood of hardwoods (occurs only in Mediterranean countries).

4.2 Dry rot fungus

The dry rot fungus (*Serpula lacrymans* = true dry rot fungus) occurs in buildings, causing brown rot in timber. The fungus can develop at relatively low wood moisture contents and is able to penetrate damp masonry over long distances in order to infect further timber or to develop its fruit-bodies.

5 Performance requirements for products against beetles (see Table 1)

5.1 Principle requirements for curative efficacy

The curative wood preservative product shall be tested in accordance with the tests specified in Table 1, taking into consideration the relevant organisms and the type of insecticidal product (see 5.2.2).

5.2 Supplementary requirements for curative efficacy

5.2.1 For *Lyctus brunneus*, *Xestobium rufovillosum* and *Hesperophanes cinnereus* no specific requirements are listed, as no relevant/valid test standards exist.

NOTE In the case of *Lyctus brunneus*, curative treatment takes place only exceptionally so that specific preservatives are placed only very rarely on the market. Due to economical reasons, no specific test procedure will be established. If curative treatment against *Lyctus brunneus* is demanded, a curative wood preservative "for *Hylotrupes* and *Anobium*" should be applied.

In the case of *Xestobium rufovillosum* see annex B.

In the case of *Hesperophanes cinnereus* see annex C.

5.2.2 The following types of insecticidal products have to be considered:

- $\frac{3}{4}$ fast acting products;
- $\frac{3}{4}$ slow acting products;
- $\frac{3}{4}$ products with deferred effect.

5.2.3 Tests of insecticidal activity shall be carried out against one of the following:

- a) "*Hylotrupes bajulus* (C-H)" **and** "*Anobium punctatum* (C-A)" unless b) or c) is applicable and is selected;
or
- b) the more tolerant beetle species, if the product is based on insecticide(s) for which data on curative efficacy already exist which show different activities against *Hylotrupes bajulus* and *Anobium punctatum*, that is the effective value for the less tolerant species is less than 80 % of the effective amount for the more tolerant species;
or
- c) against "*Hylotrupes bajulus* (C-H)" **or** "*Anobium punctatum* (C-A)", if the product is based on insecticide(s) for which data on the curative efficacy already exist which show more or less equal activity against both beetle species, that is the effective value of the least tolerant beetle species is equal to or greater than 80 % of the effective value of the more tolerant beetle species.

5.2.4 New tests shall be carried out against *Hylotrupes bajulus* according to ENV 1390, however, former results from EN 22 tests shall remain valid.

5.2.5 At present no relevant test standards exist for deferred effect products.

5.2.6 The maximum application limit shall not exceed 300 ml per square meter.

NOTE 1 If the curative wood preservative is specified by the manufacturer to be used at a higher application in practice, the manufacturer should define how this amount is to be achieved under practical conditions.

NOTE 2 If the curative wood preservative is already placed on the market on the basis of results from biological tests conducted at a maximum application limit greater than 300 ml per square meter, these test results remain valid and no new tests should be demanded.

5.2.7 For tests according to EN 370 the duration can exceed 1 year.

5.2.8 If the curative wood preservative is designed to be used for the protection of items of cultural heritage for *Anobium punctatum* the mortality at the end of the test shall be 90 %.

5.3 Requirements for preventive efficacy

Where local conditions require the curative wood preservative product to have also preventive efficacy, or to support the claims of manufacturers or the demands of specifiers, the product shall have its preventive efficacy demonstrated from tests in accordance with EN 599-1 at an application limit equal to or lower than that at which test under this curative standard were conducted.

6 Performance requirements for barrier treatments against dry rot fungus

In tests according to ENV 12404 growth through mortar specimens and infection of the wood specimens shall have been prevented by the masonry fungicide. The application rate of the ready to use solution of the fungicide shall be not lower than 500 ml per square meter and not more than 750 ml per square meter.

7 Derivation of effective values

7.1 Effective value against beetles

The effective value is derived from the results of the biological tests and shall be equal to the application rate of the wood preservative tested according to the manufacturer's recommendation (see 5.2.6).

7.2 Effective value against dry rot fungus

The effective value is derived from the results of the biological tests and shall be equal to the application rate of the ready to use formulation of the wood preservative tested according to the manufacturer's recommendation, which prevented any growth through the mortar specimens.

8 Product identification and labelling

8.1 Product identification

Product identification and control shall be designated as described in EN 599-1:1996, clause 9.

8.2 Product classification

Curative wood preservative products shall be classified according to target organism(s) (see clause 4) against which they were tested in accordance with this European Standard and not according to their physical or chemical form and composition.

The classification shall comprise:

- ¾ minimum biological efficacy against the target organism(s);
- ¾ the application procedures;
- ¾ additional biological efficacy if any;
- ¾ effective value .

EN 14128:2003 (E)

NOTE A recommended system of codes for classifying the efficacy of curative wood preservative products is given in annex D.

If relevant, the curative wood preservative against beetles shall be classified to indicate any preventive performance capabilities if it meets the respective requirements of EN 599-1.

8.3 Product description for products against beetles

It shall be mentioned against which type of insect species the curative preservative product shows efficacy.

The curative wood preservative shall be suitable for superficial application processes. It shall be indicated for which type of treatments the product may be used.

The manufacturer shall make available at least the following information:

- a) a unique name and/or code number for the product;
- b) the main ingredient(s) and their quantities or proportions;
- c) the type of curative product: fast acting, slow acting or deferred effect;
- d) the method(s) for analysis of active ingredients in the product in its ready to use form;
- e) the method(s) for the determination of the penetration and quantitative retention of the product in the wood if available;
- f) the effective value in millilitres per square meter, with different amounts for different target organisms if relevant.

NOTE 1 Additional information may be required by European or national regulations.

NOTE 2 Certain physical and chemical properties of the curative wood preservative product can effect its efficacy. Guidance on further information which can be useful is given in annex E.

8.4 Product description for barrier treatments against the dry rot fungus

It shall be mentioned that the product is only designed for treatment of masonry to achieve a barrier against the dry rot fungus.

It shall be indicated for which type of treatment(s) the product may be used.

The manufacturer shall make available at least the following information:

- a) a unique name and/or code number for the product;
- b) the main ingredient(s) and their quantities or proportions;
- c) the method(s) for analysis of active ingredients in the product in its ready to use form;
- d) the effective value in millilitres per square meter.

NOTE 1 Additional information may be required by European or national regulations.

NOTE 2 Certain physical and chemical properties of the product can effect its efficacy. Guidance on further information which can be useful is given in annex E.

8.5 Product labelling for products against beetles

The container for the product shall be marked with or accompanied by the following information:

- | | |
|--|---|
| a) the product name: | XX |
| b) the number of this European Standard: | EN 14128 |
| c) the insect species against which efficacy has been approved: | e.g. <i>Hylotrupes bajulus</i> (C-H) |
| d) the process of application: | e.g. brushing, spraying, injection into drilled holes |
| e) any additional biological efficacy: | e.g. preventive against insects in use class 1 and 2, preventive against fungal attack in use class 2 |
| f) type of wood preservative: | fast acting, slow acting or deferred effect |
| g) the effective value according to the type of organism and additional efficacy if relevant | in millilitres per square meter |
| h) the manufacturer's recommended application rate or retention: | in millilitres per square meter |

NOTE An example of how this information might be presented is given in annex F.

8.6 Product labelling for barrier treatments against the dry rot fungus

The container for the product shall be marked with or accompanied by the following information:

- | | |
|--|---|
| a) the product name: | XY |
| b) the number of this European Standard: | EN 14128 |
| c) the purpose of the product: | Only for treatment of masonry to achieve a barrier against the dry rot fungus |
| d) the process of application: | e.g. brushing, spraying, injection into drilled holes |
| e) the effective value: | in millilitres per square meter |
| f) the manufacturer's recommended application rate or retention: | in millilitres per square meter |

Table 1 — Performance criterion in biological tests for curative wood preservatives against beetles

Requirement	Minimum requirements (5.2.1)					
	Fast acting (5.2.2)		Slow acting (5.2.2)		Deferred effect (5.2.2)	
	<i>Hylotrupes bajulus</i> (C-H) (5.2.3)	<i>Anobium punctatum</i> (C-A) (5.2.3)	<i>Hylotrupes bajulus</i> (C-H) (5.2.3)	<i>Anobium punctatum</i> (C-A) (5.2.3)	<i>Hylotrupes bajulus</i> (C-H)	<i>Anobium punctatum</i> (C-A)
Test	EN 22 / ENV 1390 (5.2.4)	EN 48	EN 22 / ENV 1390 (5.2.4)	EN 48	(5.2.5)	EN 370
Ageing	None	None	None	None	(5.2.5)	EN 73
Maximum application limit	300 ml/m ² (5.2.6)	300 ml/m ² (5.2.6)	300 ml/m ² (5.2.6)	300 ml/m ² (5.2.6)	(5.2.5)	300 ml/m ² (5.2.6)
Duration of test	12 weeks	8 weeks	24 weeks	16 weeks	(5.2.5)	In accordance with test specification (5.2.7)
Criterion for effective value	80 % mortality at end of test	80 % mortality at end of test (5.2.8)	80 % mortality at end of test	80 % mortality at end of test (5.2.8)	(5.2.5)	Maximum emergence 3 out of the 72 larvae inserted

Annex A (informative)

Guidance on re-testing after making variations in product formulation

A.1 Introduction

Manufacturers can wish or be obliged to modify the formulation of a product, due for example to changes in the availability of ingredients or the need to introduce improvements in physical properties. In addition, manufacturers can wish to produce a range of preservatives based on a single formulation having test data to the requirements of Table 1 in this European Standard but with different physical characteristics, for example water repellency and/or colour.

This annex gives guidance on the extent of re-testing that is considered to be appropriate if a product formulation is varied from the original 'type-product' for which full data in accordance with this European Standard are already available. It provides for three levels of variation in formulation which results in:

- a) no requirements for new biological testing;
- b) minimum new biological testing;
- c) full new biological testing.

Within this European Standard there are two distinct types of product recognised:

- a) curative wood preservatives for the control of wood boring insects;
- b) barrier treatments that are applied to masonry to prevent the growth of dry rot.

These two distinct types of product are considered in A.2 and A.3 respectively.

A.2 Guidance on re-testing after making variations to curative wood preservatives for the control of wood boring insects

A.2.1 General

Curative wood preservatives for the control of wood boring insects can also contain a fungicide (or fungicides) for the prevention of wood destroying fungi attack. Where such fungicides are included reference should be made to EN 599-1 for preventive test requirements as given in 5.3. Where a variation in formulation is made to a product for which both curative and preventive claims are made for an insecticide, annex B of EN 599-1:1996 should be consulted for preventive requirements.

A.2.2 No requirements for new biological testing

A.2.2.1 Products having any or all of the variations as given in A.2.2.2 or A.2.2.3 from a "type-product" for which test data in accordance with the requirements of Table 1 of this European Standard exist already, are considered not to require new biological testing.

It should be confirmed:

- a) that the penetration into wood is not adversely affected;
- b) that the stability of the product is not adversely affected.

A.2.2.2 In the case of organic solvent based products (ready for use) no new biological testing is required for:

- a) changes involving substitution of any co-formulant by one which is chemically equivalent, from another supplier;
- b) a change in the aromatic content of hydrocarbon solvent carrier of no greater than 10 % (v/v) of the total aromatic hydrocarbon solvent content;
- c) changes involving the addition or deletion of a soluble dyestuff;
- d) changes in pigments to an equal or lower pigment content of the product;
- e) for products in their ready for use form containing 10 % (m/m) or less of solids containing resins and/or water repellents, relative changes in content of these constituent(s) of no more than ± 20 % (m/m) and for products containing more than 10 % (m/m) solids, relative changes of no more than ± 10 % (m/m) of these constituents;
- f) up to 5 % of the hydrocarbon solvent may be replaced by a solvent miscible co-solvent providing that not less than 90 % (V/V) of the carrier distils below 250 °C;
- g) replacing a co-formulant providing the additive constitutes less than 2 % of the total formulation and providing the physical properties are not affected.

A.2.2.3 In the case of water-soluble preservatives no new biological testing is required for:

- a) changes involving substitution of any co-formulant by one which is chemically equivalent, from another supplier;
- b) changes involving the addition or deletion of a soluble dyestuff;
- c) for inorganic active ingredients, changes in the non-biologically active portion of the ingredients not resulting in a change in the ratio, total content or nature of the active chemical elements;
- d) a change in pigments to an equal or lower pigment content of the product;
- e) for products in their ready for use form containing 10 % (m/m) or less of solids containing resins and/or water repellents, relative changes in content of these constituent(s) of no more than ± 20 % (m/m) and for products containing more than 10 % (m/m) solids, relative changes of no more than ± 10 % (m/m) of these constituents;
- f) a change of the pH is within a range of 0,5
- g) changing or adding a water miscible co-solvent up to 5 % of the total formulation, providing that not less than 90 % (V/V) of the carrier distils below 250 °C;
- h) replacing a co-formulant providing the additive constitutes less than 2 % of the total formulation and providing the physical properties are not affected.

A.2.2.4 In the case of emulsion products no new biological testing is required for:

- a) changes involving substitution of any co-formulant by one which is chemically equivalent from another supplier;
- b) a change of the pH is within a range of 0,5;
- c) replacing or adding a co-solvent up to 5 % the total formulation providing the physical stability does not change;
- d) replacing a co-formulant providing the additive constitutes less than 2 % of the total formulation and providing the physical properties are not affected.

A.2.2.5 Additionally in every case:

It should be confirmed:

- a) by chemical analysis, that the above changes do not alter the content of the active ingredient(s) in the commercial version of the product after storage at 40 °C for 28 days.

A.2.3 Requirements for minimum new biological testing

A.2.3.1 Minimum new biological testing will only reduce the amount of retesting required, following a formulation change, when both *Hylotrupes bajulus* and *Anobium punctatum* claims are made.

Products having any or all of the variations as given in A.2.3.2 or A.2.3.3 from a 'type-product' for which test data in accordance with the requirements of Table 1 of this European Standard exist already, are considered only to require re-testing using the insect test that gave the higher effective value for the original type-product.

A.2.3.2 In the case of organic solvent based products and water-soluble products, minimum new biological tests are required following:

- a) changes involving the incorporation of a water-repellent additive to a formulation;
- b) any other changes in the content or nature of co-formulants not exempted by A.2.2.2 or A.2.2.3;
- c) for products containing both insecticide(s) and fungicide(s) the deletion of fungicide(s) or the replacement of one fungicide with another;
- d) changes involving the addition of fungicide(s) to a product already tested against insects according to this European Standard.

A.2.3.3 In the case of emulsion products, minimum new biological tests are required following:

- a) any other changes in the content or nature of co-formulants not exempted by A.2.2.4 above;
- b) for products containing both insecticide(s) and fungicide(s) the deletion of fungicide(s) or the replacement of one fungicide with another;
- c) changes involving the addition of fungicide(s) to a product already tested against insects according to this European Standard.

A.2.3.4 The minimum new biological tests should be carried out using the test method that gave the higher effective value in the original tests. If the effective value for both *Hylotrupes bajulus* and *Anobium punctatum* was identical in the original tests then testing should be undertaken with *Hylotrupes bajulus*. The application rate and duration of test should be as in the original test.

The product variant when tested in accordance with A.2.3.3 should meet the performance criterion indicated in Table 1 of this European Standard.

A.2.3.5 Additionally, in every case:

It should be confirmed:

- a) that the penetration into wood is not adversely affected;
- b) that the stability of the product is not adversely affected;
- c) by chemical analysis, that the above changes do not alter the content of the active ingredient(s) in the commercial version of the product after storage at 40 °C for 28 days.

A.2.4 Requirement for full new biological testing

Products having any or all of the following variations from a 'type-product' for which test data in accordance with the requirements of Table 1 of this European Standard exist already, are considered to require full relevant re-testing in accordance with Table 1 of this European Standard.

- a) any change(s) in the content of the active ingredient(s) greater than that given in 9.3.1 b) and c) of EN 599-1:1996 or in the nature of the active ingredient(s), with the exception of the provisions of A.2.2.3 d), A.2.3.1 c), and A.2.3.2 b) and c);
- b) any change(s) where the minimum new biological testing as described in A.2.2.1 shows a reduction in toxicity to the relevant beetle;
- c) all other changes not covered in A.2.2 or A.2.3.

A.3 Guidance on re-testing after making variations to barrier treatments that are applied to masonry to prevent the growth of dry rot

A.3.1 No requirements for new biological testing

A.3.1.1 Products having any or all of the variations as given in A.3.1.2 or A.3.1.3 from a 'type-product' for which test data in accordance with the requirements of clause 6 of this European Standard exist already, are considered not to require new biological testing.

A.3.1.2 In the case of water-soluble preservatives no new biological testing is required for:

- a) changes involving substitution of any co-formulant by one which is chemically equivalent, from another supplier;
- b) changes involving the addition or deletion of a soluble dyestuff;
- c) for inorganic active ingredients, changes in the non-biologically active portion of the ingredients not resulting in a change in the ratio, total content or nature of the active chemical elements;
- d) a change in pigments to an equal or lower pigment content of the product;
- e) for products in their ready for use form containing 10 % (m/m) or less of solids containing resins and/or water repellents, relative changes in content of these constituent(s) of no more than ± 20 % (m/m) and for products containing more than 10 % (m/m) solids, relative changes of no more than ± 10 % (m/m) of these constituents;
- f) a change of the pH is within a range of 0,5.

A.3.1.3 In the case of emulsion products no new biological testing is required for:

- a) changes involving substitution of any co-formulant by one which is chemically equivalent from another supplier;
- b) a change of the pH is within a range of 0,5.

A.3.1.4 Additionally in every case:

It should be confirmed:

- a) that the stability of the product is not adversely affected;
- b) by chemical analysis, that the above changes do not alter the content of the active ingredient(s) in the commercial version of the product after storage at 40 °C for 28 days.

A.3.2 Requirements for full new biological testing

Products having any or all of the following variations from a "type product" for which test data in accordance with the requirements of clause 6 of this European Standard exist already, are considered to require full relevant re-testing in accordance with clause 6 of this European Standard.

- a) any change(s) in the content of active ingredient(s) greater than that given in 9.3.1 b) and c) of EN 599-1:1996 or in the nature of the active ingredient(s) with the exception of the provisions of A.3.1.2 d);
- b) all the changes not covered in A.3.1.2 or A.3.1.3.

Annex B (normative)

Test requirements for curative products against *Xestobium rufovillosum*

For curative products to be used against *Xestobium rufovillosum*, no laboratory test method exists and it is unlikely that a method will be developed in near future due to the specific biology of *Xestobium rufovillosum*. For *Xestobium rufovillosum* reference is given to practical field demonstration the results of which should be evaluated by national standards organisations, or an organisation nominated by them, to declare effective values for use within their territories.

Annex C (normative)

Test requirements for curative products against *Hesperophanes cinnereus*

For curative products to be used against *Hesperophanes cinnereus* no specific laboratory method currently exists. However tests may be carried out according to ENV 1390 by replacing pine wood by a suitable hardwood. As *Hesperophanes cinnereus* occurs only in Mediterranean regions regulations may be given by respective local authorities.

Annex D (informative)

Recommended system for the classification of the effectiveness of curative wood preservatives

D.1 Curative wood preservatives against beetles

Marking categories	Symbols
Insect species	
$\frac{3}{4}$ <i>Hylotrupes bajulus</i>	C-H
$\frac{3}{4}$ <i>Anobium punctatum</i>	C-A
$\frac{3}{4}$ <i>Hylotrupes bajulus</i> and <i>Anobium punctatum</i>	C-I
Type of wood preservative	
$\frac{3}{4}$ Fast acting	fast
$\frac{3}{4}$ Slow acting	slow
$\frac{3}{4}$ Deferred effect	deferred

D.2 Barrier treatments against the dry rot fungus

Marking category	Symbol
$\frac{3}{4}$ <i>Serpula lacrymans</i>	S

Annex E (informative)

Guidance for physical chemical properties

The effectiveness of wood preservative products in service and their suitability for particular service situations depends upon many physical and chemical characteristics which are not within the scope of this standard.

In particular, specific wood preservative products often are suitable for the use only in certain service situations. Therefore they may conform to appropriate legislative requirements on fitness for purpose, only if they have an appropriate combination of relevant characteristics, both as made-up fluids or in their form as supplied, as well as once they have been applied to the wood. The characteristics can include one or more of the following:

- ¾ stability "in can";
- ¾ corrosiveness of treatment solution;
- ¾ stability after freezing;
- ¾ stability in water;
- ¾ stability during the impregnation process (not to be destroyed by the application of pressure or vacuum);
- ¾ flash point;
- ¾ properties of treated wood; e.g.:
 - ¾ corrosion of fixings and fittings;
 - ¾ paintability;
 - ¾ mechanical properties;
 - ¾ fire resistance.

NOTE There are no European standard methods for determining such properties but information relevant to a particular product and its intended use is expected to be provided in manufacturer's Technical Data Sheets.

The specifier should seek assurances from the manufacturer and/or supplier of the product as to its suitability in respect of the additional physical and chemical properties which are relevant to its intended use.

Annex F (informative)

Example of a system to describe the effectiveness of a curative wood preservatives against beetles

Preservative name XX

Insect species	<i>Hylotrupes bajulus</i> (C-H) ^a	<i>Anobium punctatum</i> (C-A) ^b	<i>Hylotrupes and Anobium</i> (C-I) ^c
Type of wood preservative:			
Fast acting	○	○	○
Slow acting	○	○	○
Deferred effect	○	○	○
Effective value ml/m ²	XXX	XXX	XXX
<p>^a C-H refers to a Curative product against <i>Hylotrupes bajulus</i>.</p> <p>^b C-A refers to a Curative product against <i>Anobium punctatum</i>.</p> <p>^c C-I refers to a Curative product against Insects in general, that is against <i>Hylotrupes</i> as well as against <i>Anobium</i>.</p>			

Any additional preventive efficacy should be described according to EN 599-2, annex A.

Bibliography

prEN WI 00038084, *Durability of wood and wood-based products – Performance criteria for hot air processes for curative uses against wood destroying organisms.*

EN 599-2:1995, *Durability of wood and wood-based products – Performance of preventive wood preservatives as determined by biological tests—Part 2: Classification and labelling.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.