

Derivatives from coal pyrolysis — Coal tar and pitch based binders and related products: painting tar — Characteristics and test methods

The European Standard EN 14265:2003 has the status of a
British Standard

ICS 75.140

National foreword

This British Standard is the official English language version of EN 14265:2003.

The UK participation in its preparation was entrusted to Technical Committee CII/56, Derivatives from coal pyrolysis, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 8, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, was published under the authority of the Standards Policy and Strategy Committee on 31 October 2003

© BSI 31 October 2003

ISBN 0 580 42853 2

ICS 75.140

English version

Derivatives from coal pyrolysis - Coal tar and pitch based binders and related products : painting tar - Characteristics and test methods

Produits dérivés de la pyrolyse du charbon - Liants à base de goudron et de brais issus de la houille et produits connexes: goudron pour peinture - Caractéristiques et méthodes d'essai

Derivate der Kohlenpyrolyse - Bindemittel aus Steinkohlenteer und Steinkohlenteerpech und verwandte Produkte: Teerpechlack - Anforderungen und Prüfverfahren

This European Standard was approved by CEN on 10 July 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

page

Foreword.....3

1 Scope4

2 Normative references4

3 Terms and definitions.....4

4 Classification.....4

5 Characteristics4

6 Specifications.....5

7 Sampling5

8 Test methods.....5

Annex A (informative) Typical values.....6

Annex B (informative) Warning to use7

B.1 Composition - Data on components7

B.2 First aid measures7

B.3 Handling and storage7

B.4 Disposal considerations8

Foreword

This document (EN 14265:2003) has been prepared by Technical Committee CEN /TC 317, "Derivatives from coal pyrolysis", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2004, and conflicting national standards shall be withdrawn at the latest by March 2004.

In this European Standard the annexes A and B are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the methods of test required to determine the characteristics for "painting tar" used as industrial and domestic varnish.

Depending on the required application and the desired properties of the end product, different grades of painting tars are available.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 13847:2001, *Coal tar and pitch based binders and related products - Terminology and classification*

EN 12846, *Bitumen and bituminous binders - Determination of efflux time of bitumen emulsions by the efflux viscometer*

ISO 6257, *Carbonaceous materials used in the production of aluminium - Pitch for electrodes –Sampling*

ISO 10336, *Crude Petroleum - Determination of water - Potentiometric Karl Fischer titration method*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 13847:2001 apply.

4 Classification

For the purposes of this European Standard, the classification according to EN 13847:2001 applies.

5 Characteristics

The following characteristics shall be determined:

- a) Water content;
- b) Viscosity;
- c) Drying time.

6 Specifications

Specifications requested by the customers shall be applied.

The typical values given in annex A can be used as requirements.

7 Sampling

ISO 6257 specifies methods for sampling and preparing samples for testing of painting tar.

These methods are applicable to all grades of painting tar in liquid form, in bulk, or in a numbers of containers making up one batch at sites of manufacture, storage or delivery.

8 Test methods

For the determination of the characteristics according to clause 5, the methods listed in Table 1 have to be used.

Table 1 — Test methods

Characteristic	Test methods
Water content	ISO 10336
Viscosity	EN 12846
Drying time	Brush on an inoxydable plate 50 g/m ² . At ambient temperature of 20 °C, the sample has to be dry by touch.

Annex A (informative)

Typical values

The typical values in Table A.1 can be used as requirements of the painting tar.

Table A.1 — Typical values

Water content	< 0,5 %
Viscosity (2 mm / 25 °C)	depends on recipe
Drying time	between 3 h and 6 h

Annex B (informative)

Warning to use ¹⁾

B.1 Composition - Data on components

- ¾ Chemical characterization of painting tars
 - ¾ CAS. N° Designation: Void.
 - ¾ Identification number (s): Void.
 - ¾ EINECS Number: Void.
 - ¾ Description: Complex mixture of polynuclear aromatic and heterocyclic hydrocarbons.
 - ¾ Dangerous components: Benzo(d,e,f) chrysene < 1 %

B.2 First aid measures

- ¾ General information: Symptoms of poisoning may even occur after several hours; therefore medical observation for at least 48 h after the accident.
- ¾ After inhalation: Take affected persons into the open air and position comfortably.
- ¾ After skin contact: Instantly wash with water and soap and rinse thoroughly.
If skin irritation continues consult a doctor.
- ¾ After eye contact: Rinse opened eye for several minutes under running water.
- ¾ After swallowing: Instantly call for a doctor.

B.3 Handling and storage

- ¾ Handling:
 - ¾ Information for safe handling: Ensure good ventilation/ exhaustion at the workplace.
Open and handle container with care.
Prevent formation of aerosols
 - ¾ Information about protection against explosions and fires: Keep breathing equipment ready.
Keep ignition sources away- Do not smoke.
The product forms flammable fumes when heated.

1) The latest edition of the publication of the Material Safety Data Sheet of the product applies

¾ Storage

¾ Requirements to be met by storerooms and containers: Provide floor trough without outlet.

¾ Information about storage in one common storage facility: Not required.

¾ Further information about storage conditions: Keep container tightly sealed.

Must be stored in a collecting room

B.4 Disposal considerations

¾ European waste catalogue: The waste code classification is to be carried out according to the European Waste Catalogue (EWC) specifically for each branch of industry and each type of process.

¾ Uncleaned packagings : Disposal must be made according to official regulations.
Must not be disposed of together with household garbage.

¾ Recommandation : Disposal must be made according to official regulations.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.