

Derivatives from coal pyrolysis — Coal tar based oils: fluxings oils — Specifications and test methods

The European Standard EN 14998:2005 has the status of a
British Standard

ICS 75.160.20

National foreword

This British Standard is the official English language version of EN 14998:2005.

The UK participation in its preparation was entrusted to Technical Committee CII/56, Derivatives from coal pyrolysis, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 21 March 2005

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 7 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 21 March 2005

EUROPEAN STANDARD

EN 14998

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2005

ICS 75.160.20

English version

Derivatives from coal pyrolysis - Coal tar based oils: fluxings oils - Specifications and test methods

Produits dérivés de la pyrolyse du charbon - Huiles de
goudron de houille: fluidifiants - Spécifications et méthodes
d'essai

Derivate der Kohlenpyrolyse - Steinkohlenteeröl: Fluxöle -
Anforderungen und Prüfverfahren

This European Standard was approved by CEN on 9 December 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Sampling	4
5 Specifications and test methods	5
Annex A (informative) Warning to use	6

Foreword

This document (EN 14998:2005) has been prepared by Technical Committee CEN/TC 317, "Derivatives from coal pyrolysis", the secretariat of which is held by IBN.

This document is based on NF M 15-003.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2005, and conflicting national standards shall be withdrawn at the latest by July 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This document gives specifications and defines test methods for coal tar fluxing oils. Annex specifies this warning for use for industrial purposes. The main purposes of these oils are to reduce the viscosity of bituminous (carbonaceous) binders used for road construction. They may be used in conjunction with petrochemical feedstocks.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1014-1, *Wood preservatives - Creosote and creosoted timber-Methods of sampling and analysis – Part 1: Procedure for sampling creosote*

EN 1014-3, *Wood preservatives - Creosote and creosoted timber - Methods of sampling and analysis - Part 3: Determination of benzo[a]pyrene content of creosote*

EN 12303:2000, *Coal tar based oils - Terminology*

EN 12846, *Bitumen and bituminous binders. Determination of efflux time of bitumen emulsions by the efflux viscometer*

EN 13847:2001, *Coal tar and pitch based binders and related products - Terminology and classification*

EN 13991, *Derivatives from coal pyrolysis - Coal tar based oils: creosotes - Specifications and test methods*

EN ISO 2719, *Determination of flash point - Pensky-Martens closed cup method (ISO 2719:2002)*

EN ISO 3405, *Petroleum products. Determination of distillation characteristics at atmospheric pressure (ISO 3405:2000)*

EN ISO 3675, *Crude petroleum and liquid petroleum products - Laboratory determination of density - Hydrometer method (ISO 3675:1998)*

ISO 760, *Determination of water - Karl Fischer method (General method)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12303:2000 and EN 13847:2001 apply.

4 Sampling

Samples for the assessment of the characteristics listed in Table 1 shall be taken in accordance with EN 1014-1.

5 Specifications and test methods

Table 1 — Specifications and test methods for fluxing oils grade A, B, C and D

Parameters	Grade A light fluxing oils	Grade B Medium oils fluxing	Grade C Heavy fluxing oils	Grade D	Tests method
Distillation range (°C)					
0 - 185	< 70 %	< 5 %	< 5 %	< 5 %	EN ISO 3405
185 - 270	> 30 %	65 - 85	10 - 25	< 50	
270 - 305		> 15	15 - 25	< 70	
305 - 350			> 10	< 90	
Density at 20°C (kg/m ³)	> 1,000	> 1,000	> 1,000	> 930	ISO 3675
Water content (% m/m)	< 0,5	< 0,5	< 0,5	< 1	ISO 760 *
Crystallization temperature (°C)	< 0	< 0	< 0		EN 13991
Benzo[a]pyrene content (mg/kg)	< 50	< 50	< 50	< 50	EN 1014-3
Flash point (°C)	> 61	> 61	> 101	> 61	EN ISO 2719
Viscosity					EN 12846
STV ϕ 2 mm at 25°C	> 16 s	> 18 s			
at 40°C	> 15 s	> 16 s			
ϕ 4 mm at 25°C			< 30 s.		
<p>* As an alternative, the ISO 3733 may be used</p> <p>Grade A is intended for the preparation of storable cold mix binders and slurry sealings.</p> <p>Grade B and Grade C are devoted to the preparation of binders for surface dressing, respectively in cold and warm weather conditions.</p> <p>Grade D is issued from low temperature coal tar distillation and is intended for the preparation of binders for precoated chippings.</p>					

Annex A (informative)

Warning for use¹⁾

A.1 Composition - Data on components

- **Chemical characterization:**
- **CAS. N° Designation:** not applicable
- **Identification number (s):**
- **EINECS Number:** not applicable.
- **EU Number:** not applicable.
- **Chemical characterization:**
- **Description:** Complex mixture of polynuclear aromatic and heterocyclic hydrocarbons.
- **Dangerous components:** Void.

A.2 First aid measures

- **General information:** instantly remove any clothing spoiled by the product.
- **After inhalation:** Supply fresh air; consult doctor in case of symptoms.
- **After skin contact:** Instantly wash with water and soap and rinse thoroughly.
- **A.2.4 After eye contact:** Rinse opened eye for several minutes under running water.
- **After swallowing:** In case of persistent symptoms consult doctor.

A.3 Handling and storage

- **Handling.**
- **Information for safe handling:** No special measures required; precautions against electrostatic charging.
- **Information about protection against explosions and fires:** No special measures required.
- **Storage**
- **Requirements to be met by storerooms and containers:** No special requirements.
- **Information about storage in one common storage facility:** Keep container tightly sealed.
- **Further information about storage conditions:** None.

A.4 Disposal considerations

- **Product:**
- **European waste catalogue:** The waste code classification is to be carried out according to the European Waste Catalogue (EWC) specifically for each branch of industry and each type of process.
- **Uncleaned packagings**
- **Recommendation:** Disposal should be made according to official regulations.
- **Recommended cleaning agent:** Water, if necessary with cleaning agent.

1) The latest edition of the publication of the Material Safety Data Sheet of the product applies

Bibliography

- [1] ISO 3733, *Petroleum products and bituminous materials - Determination of water - Distillation method*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.