

Solar cells — Datasheet information and product data for crystalline silicon solar cells

The European Standard EN 50461:2006 has the status of a British Standard

ICS 27.160

National foreword

This British Standard was published by BSI. It is the UK implementation of EN 50461:2006.

The UK participation in its preparation was entrusted to Technical Committee GEL/82, Solar photovoltaic energy systems.

A list of organizations represented on GEL/82 can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 September 2006

© BSI 2006

ISBN 0 580 49294 X

Amendments issued since publication

Amd. No.	Date	Comments

EUROPEAN STANDARD

EN 50461

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2006

ICS 27.160

English version

**Solar cells -
Datasheet information and product data
for crystalline silicon solar cells**

Cellules solaires -
Spécifications particulières et données
de produit pour les cellules solaires en
silicium cristallin

Solarzellen -
Datenblattangaben und Angaben zum
Produkt für kristalline Silizium-Solarzellen

This European Standard was approved by CENELEC on 2006-02-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

This European Standard was prepared by the Technical Committee CENELEC TC 82, Solar photovoltaic energy systems. The text of the draft was submitted to the Unique Acceptance Procedure and was approved by CENELEC as EN 50461 on 2006-02-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2007-03-01
 - latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2009-02-01
-

Contents

1	Scope	4
2	Normative references	4
3	Data sheet information	4
3.1	Certificates	4
3.2	Applicable materials and their condition	5
3.3	Process characteristic	5
3.3.1	Solder connection	5
3.3.2	Breaking strength (in work).....	5
3.4	Size	5
3.5	Electrical characteristics.....	5
3.6	Thermal characteristics	6
4	Packaging, marking and storage	6
4.1	Packaging	6
4.2	Marking.....	6
4.3	Storage.....	6
5	Major changes of product and of processes	6
	Bibliography	7

1 Scope

This European Standard describes data sheet and product data information for crystalline silicon solar cells.

The intent of this standard is to provide minimum information required to configure safe and optimal photovoltaic modules.

In this context, data sheet information is a technical description separate from the photovoltaic module.

Product data information concerns the packaging, marking, storage and containing a commitment to inform about major changes on product and on process. These data are needed for further processing of solar cells to photovoltaic modules.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 60068-2-44, Environmental testing - Part 2: Tests - Guidance on test T: Soldering (IEC 60068-2-44)

EN 60904-1, Photovoltaic devices - Part 1: Measurement of photovoltaic current-voltage characteristics (IEC 60904-1)

EN 60904-3, Photovoltaic devices - Part 3: Measurement principles for terrestrial photovoltaic (PV) solar devices with reference spectral irradiance data (IEC 60904-3)

EN 61189 series, Test methods for electrical materials, printed boards and other interconnection structures and assemblies (IEC 61189 series)

EN 61215, Crystalline silicon terrestrial photovoltaic (PV) modules - Design qualification and type approval (IEC 61215)

IEC 60326-2, Printed boards - Part 2: Test methods

DIN 6174, Colorimetric Evaluation of Colour Differences of Surface Colours According to the CIELAB Formula

3 Data sheet information

3.1 Certificates

All relevant certificates must be considered in the datasheet (i.e. certified material test report, certificate of conformance, certified electrical measuring record, certificate to quality management, etc.).

3.2 Applicable materials and their condition

Quotation of the materials which are used in crystalline solar cells:

- wafer specification (standard in work);
- colour (indication of number of colour according to DIN 6174 or a similar specimen);
- indication of basic material of the surface: antireflective coating, metallization (front- and backside).

Adhesive strength examination of all surfaces with the tape test according to IEC 60326-2, test 13a, (for example tape 3M 810) which is specified as follows: removable tape with adhesion force of 2 N/cm to 4 N/cm. Afterwards optical test with human eye. No debonding layer on solar cell identifiable.

3.3 Process characteristic

3.3.1 Solder connection

Inspection of solderability according to EN 60068-2-44.

Adhesive strength of solder connection according to EN 61189-2 Test 2M05. As an alternative to the test equipment described in the standard another suitable construction may be used.

Minimum peel strength 1 N per mm solder tab width.

Soldering conditions: The manufacturer should give details to suitable solder conditions (solder, temperature, solder time, etc.).

3.3.2 Breaking strength (in work)

3.4 Size

Size: the dimensions are nominal values with measuring tolerances in mm.

Surface: declaration in mm².

Thickness: the dimensions are nominal values with measuring tolerances in μm.

Busbar-width: the dimensions are nominal values with measuring tolerances in mm. Front- and backside.

NOTE All measurements at 25 °C ± 2 °C.

A complete dimensioned technical drawing with all measuring tolerances shall be added.

3.5 Electrical characteristics

Values shall be specified for following parameters: 1 000 W/m², 800 W/m² and 200 W/m² (25 ± 2) °C, AM 1.5 in accordance with EN 60904-3:

- Fill factor quantities in % with measuring tolerances in %
- V_{OC} quantities in V with measuring tolerances in %
- I_{SC} quantities in A with measuring tolerances in %
- V_{MPP} quantities in V with measuring tolerances in %
- I_{MPP} quantities in A with measuring tolerances in %
- Power at V_{MPP} quantities in W with measuring tolerances in %
- Efficiency at MPP quantities in % with measuring tolerances in %

NOTE All measurements according to EN 60904-1.

All solar cells shall be measured at STC and sorted corresponding to the classification in power classes or current rates.

3.6 Thermal characteristics

The temperature coefficient of short circuit current (α) in [mA/K], the temperature coefficient of open circuit voltage (β) in [mV/K], and the temperature coefficient of P_{\max} (δ) in [W/K], shall be given.

NOTE All measurements according to EN 61215. Relative temperature coefficients expressed as percentages can be determined by dividing the calculated α , β , and δ by the values of current, voltage and peak power at a selected temperature.

4 Packaging, marking and storage

4.1 Packaging

- Packing unit
- Kind of packaging

4.2 Marking

The smallest package unit should be accompanied by the following information:

- type designation;
- lot numbering;
- quantity.

4.3 Storage

- Data to stack ability
- Ambient conditions
- Maximal storage time

5 Major changes of product and of processes

Commitment to inform about changes as defined in EN 61215.

Bibliography

EN 50380:2003, Datasheet and nameplate information for photovoltaic modules

EN 60891:1994, Procedures for temperature and irradiance corrections to measured I-V characteristics of crystalline silicon photovoltaic devices (IEC 60891:1987 + A1:1992)

EN 60904-2:1993 + A1:1998, Photovoltaic devices – Part 2: Requirements for reference solar cells (IEC 60904-2:1989 + A1:1998)

EN 60904-6:1994 + A1:1998, Photovoltaic devices – Part 6: Requirements for reference solar modules (IEC 60904-6:1994 + A1:1998)

EN 60904-7:1998, Photovoltaic devices – Part 7: Computation of spectral mismatch error introduced in the testing of a photovoltaic device (IEC 60904-7:1998)

EN 60904-8:1998; Photovoltaic devices – Part 8: Measurement of spectral response of a photovoltaic (PV) device (IEC 60904-8:1998)

IEC 60904-9:1995, Photovoltaic Devices — Part 9: Solar simulator performance requirements

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.