

Electrical insulating materials — Thermal endurance properties —

**Part 2: Determination of thermal
endurance properties of electrical
insulating materials — Choice of test
criteria**

The European Standard EN 60216-2:2005 has the status of a
British Standard

ICS 17.220.99; 29.035.01

National foreword

This British Standard is the official English language version of EN 60216-2:2005. It is identical with IEC 60216-2:2005. It supersedes BS 5691-2:1995 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee GEL/15, Insulating material, to Subcommittee GEL/15/5, Methods of test, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled "International Standards Correspondence Index", or by using the "Search" facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 16, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 2 December 2005

Amendments issued since publication

Amd. No.	Date	Comments

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 60216-2

October 2005

ICS 17.220.99; 29.035.01

Supersedes HD 611.2 S1:1992

English version

**Electrical insulating materials –
Thermal endurance properties
Part 2: Determination of thermal endurance properties
of electrical insulating materials –
Choice of test criteria
(IEC 60216-2:2005)**

Matériaux isolants électriques –
Propriétés d'endurance thermique
Partie 2: Détermination des propriétés
d'endurance thermique de matériaux
isolants électriques –
Choix de critères d'essai
(CEI 60216-2:2005)

Elektroisolierstoffe –
Eigenschaften hinsichtlich des
thermischen Langzeitverhaltens
Teil 2: Leitfaden zur Bestimmung
thermischer Langzeiteigenschaften
von Elektroisolierstoffen –
Auswahl der Prüfmerkmale
(IEC 60216-2:2005)

This European Standard was approved by CENELEC on 2005-08-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 15E/257/FDIS, future edition 4 of IEC 60216-2, prepared by SC 15E*, Methods of test, of IEC TC 15, Insulating materials, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 60216-2 on 2005-08-01.

This European Standard supersedes HD 611.2 S1:1992.

The main changes from HD 611.2 S1 are as follows:

- editorial;
- Table 1 has been actualized essentially by Part 3 sheets of IEC/SC 15C publications.

The following dates were fixed:

- latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2006-05-01
- latest date by which the national standards conflicting with the EN have to be withdrawn (dow) 2008-08-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 60216-2:2005 was approved by CENELEC as a European Standard without any modification.

* Subcommittee 15E has been merged with technical committee 98 into the new technical committee 112.

CONTENTS

FOREWORD.....	2
1 Scope	5
2 Normative references	5
3 General considerations.....	7
4 Guide for the choice of properties and end-points.....	7
Annex A (informative) Additional Information on the group to which new or unknown materials should be assigned	11
Annex ZA (normative) Normative references to international publications with their corresponding European publications	14

The text of this standard is based on the following documents:

FDIS	Report on voting
15E/257/FDIS	15E/259/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 60216: *Electrical insulating materials – Properties of thermal endurance*, consists of six parts:

- Part 1: Ageing procedures and evaluation of test results
- Part 2: Choice of test criteria
- Part 3: Instructions for calculating thermal endurance characteristics
- Part 4-1: Ageing ovens – Section 1: Single-chamber ovens
- Part 4-2: Ageing ovens – Precision ovens for use up to 300 °C
- Part 4-3: Ageing ovens – Multi-chamber ovens
- Part 5: Determination of relative thermal endurance index (RTE) of an insulating material
- Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method

NOTE This work may be continued. For revisions and new parts, see the current catalogue of IEC publications for an up-to-date list.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria

1 Scope

This part of IEC 60216 gives guidance for the choice of test criteria for the determination of thermal endurance characteristics. It includes a list of existing published procedures which is however not exhaustive.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60172, *Test procedure for the determination of the temperature index of enamelled winding wires*

IEC 60216-3, *Electrical insulating materials – Thermal endurance properties – Part 3: Instructions for calculating thermal endurance characteristics*

IEC 60216-5, *Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative thermal endurance index (RTE) of an insulating material*

IEC 60216-6, *Electrical insulating materials – Thermal endurance properties – Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method*

IEC 60243-1, *Electrical strength of insulating materials – Test methods – Part 1: Tests at power frequencies*

IEC 60317 (all parts), *Specifications for particular types of winding wires*

IEC 60370, *Test procedure for thermal endurance of insulating varnishes – Electric strength method*

IEC 60371 (all parts), *Specification for insulating materials based on mica*

IEC 60394 (all parts), *Varnished fabrics for electrical purposes*

IEC 60450, *Measurement of the average viscometric degree of polymerization of new and aged cellulosic electrically insulating materials*

IEC 60454 (all parts), *Specifications for pressure-sensitive adhesive tapes for electrical purposes*

- IEC 60455 (all parts), *Resin based reactive compounds used for electrical insulation*
- IEC 60464 (all parts), *Varnishes used for electrical insulation*
- IEC 60554 (all parts), *Specification for cellulosic papers for electrical purposes*
- IEC 60626 (all parts), *Combined flexible materials for electrical insulation*
- IEC 60641 (all parts), *Specification for pressboard and presspaper for electrical purposes*
- IEC 60667 (all parts), *Specification for vulcanized fibre for electrical purposes*
- IEC 60674 (all parts), *Specification for plastic films for electrical purposes*
- IEC 60684 (all parts), *Flexible insulating sleeving*
- IEC 60763 (all parts), *Specification for laminated pressboard*
- IEC 60819 (all parts), *Non-cellulosic papers for electrical purposes*
- IEC 60893 (all parts), *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes*
- IEC 61033, *Test methods for the determination of bond strength of impregnating agents to an enamelled wire substrate*
- ISO 37, *Rubber, vulcanized or thermoplastic – Determination of tensile stress-strain properties*
- ISO 178, *Plastics – Determination of flexural properties*
- ISO 179-1, *Plastics – Determination of Charpy impact properties – Non-instrumented impact test*
- ISO 527-2, *Plastics – Determination of tensile properties – Test conditions for moulding and extrusion plastics*
- ISO 527-3, *Plastics – Determination of tensile properties – Test conditions for films and sheets*
- ISO 1520, *Paints and varnishes – Cupping test*
- ISO 1924 (all parts), *Paper and board – Determination of tensile properties*
- ISO 2759, *Board – Determination of bursting strength*
- ISO 8256, *Plastics – Determination of tensile-impact strength*

3 General considerations

The determination of the thermal endurance of electrical insulating materials is described in IEC 60216-1, IEC 60216-3, IEC 60216-5 and IEC 60216-6. IEC 60216-1 gives experimental details for the ageing of test specimens and determining the gradual deterioration of the property selected as the test criterion. IEC 60216-3 gives details of the procedures for evaluation of the experimental data. IEC 60216-5 gives experimental details for determining the relative thermal endurance of a material and details of the procedures for evaluation of the experimental data. IEC 60216-6 provides an alternate experimental method for determining the thermal endurance of a material and details of the procedures for evaluation of the experimental data. This standard is concerned with the selection of the test properties and end-point levels.

The thermal endurance behaviour of a material cannot be adequately represented by a single number. At least two shall be given:

- temperature index TI (or relative thermal endurance index RTE), and
- halving interval HIC.

Even so, the values of these numbers are highly dependent on the chosen property and end-point, and may be dependent on the dimensions of the test specimen, especially the thickness.

The selection of a property should reflect the function of the material in its application, as stated in IEC 60216-1.

4 Guide for the choice of properties and end-points

Where an international specification exists for a particular insulating material, the property and end-point called for in that specification shall be used to determine the thermal endurance characteristic value(s) needed to claim compliance with the specification. See the current catalogue of IEC publications for an up-to-date list of specifications.

For the choice of properties and end-points, Clause 5 and Table 1 provide guidance. Further advice is given in Annex A. To evaluate thermal endurance characteristics, an end-point of 50 % of the initial value of the property is often used.

Although, on account of the high cost of thermal endurance testing, it is frequently desirable to select a single property and end-point to give a result representative of the thermal endurance behaviour of a material, this information may be inadequate for use in all applications of the material. In such cases, alternative criteria should be chosen that are more appropriate to the application and the function of the material, when, e.g. the 50 % of initial value end-point has no fundamental significance and a 25 % of initial value end-point is more indicative of the application. Alternative end-points considered likely to be valuable in such cases are also indicated in Table 1.

The information in Table 1 is given, for convenience, in relation to materials grouped according to their salient mechanical or chemical features. Annex A explains the main features of each group; this may be helpful to assign a non-listed material to the right group.

Table 1 – Examples of insulating materials, with recommended test properties and end-points

Insulating materials	Material Specification Publication No.	Recommended properties	Recommended end-points			Test method Publication No.
			Preferred	Subsidiary 5)	Type 1)	
Rigid materials A						
Rigid laminates	IEC 60893	Flexural strength	50 %	25 %; 75 %	R	ISO 178 IEC 60243-1
Vulcanized fibre products	IEC 60667	Voltage 1-min proof test	6 kV	3 kV; 10 kV	A	ISO 527-2 IEC 60455-2
Preimpregnated fibre products (prepregs)		Loss of mass	5 %	3 %; 10 %	L	ISO 179-1 IEC 60243-1
Rigid mica or mica-paper products	IEC 60371					
Rigid materials B						
Reinforced/filled thermosetting moulded and cast insulation		Flexural strength	50 %	25 %; 75 %	R	ISO 178 IEC 60243-1
Reinforced/filled thermoplastic moulded and cast insulation		Tensile strength	50 %	25 %; 75 %	R	ISO 527-2 IEC 60455-2
		Loss of mass	3 %	5 %; 10 %	L	ISO 179-1 IEC 60243-1
		Charpy impact strength	50 %	25 %; 75 %	R	
		Breakdown voltage	50 %	25 %; 75 %	R	
Rigid materials C						
Unfilled thermosetting moulded and cast insulation		Flexural strength	50 %	25 %; 75 %	R	ISO 178 IEC 60243-1
Unfilled thermoplastic moulded and cast insulation ⁴⁾		Tensile strength	50 %	25 %; 75 %	R	ISO 527-2 IEC 60455-2
		Loss of mass	3 %	5 %; 10 %	L	ISO 8256 IEC 60243-1
		Tensile impact strength	50 %	25 %; 75 %	R	
		Breakdown voltage	50 %	25 %; 75 %	R	
Elastomers						
Vulcanized natural or synthetic rubber and combinations of them		Tensile stress at 100 % extension	50 %	25 %; 75 %	R	ISO 37 IEC 60243-1
Polyolefins including cross-linked polyethylene		Elongation at break 2)	50 %	25 %; 75 %	R	ISO 37 IEC 60243-1
Silicone rubber		Breakdown voltage	50 %	25 %; 75 %	R	
Semi-rigid sheet materials						
Pressboards and presspapers	IEC 60641	Bursting strength	50 %	25 %; 75 %	R	ISO 2759 ISO 1924
Laminated pressboards	IEC 60763	Tensile strength MD/CD	50 %	25 %; 75 %	R	
Paper, paper-based or woven materials (except: glass textile reinforced)						
Cellulosic paper (all types)	IEC 60554	Tensile strength	50 %	25 %; 75 %	R	IEC 60394 IEC 60450
Non-cellulosic, paper-like materials	IEC 60819	Viscometric degree of polymerization	50 %	25 %; 75 %	R	
Varnished paper		Breakdown voltage			R	IEC 60370
Varnished fabrics						

Table 1 (continued)

1	2	3	4	5
Material Publication No.	Recommended properties	Preferred	Recommended end-points Subsidiary 5)	Type 1) Test method Publication No.
Insulating materials				
Pressure-sensitive adhesive tapes Paper-based tapes Glass fabric-based tapes (Plastic film-based tapes, see the next group)	IEC 60454 IEC 60454	Breakdown voltage Loss of mass	1,0 kV 10 %	5 %; 20 % A L IEC 60454-2 IEC 60454-2
Flexible film and film based materials Plastic films Pressure-sensitive adhesive film tapes	IEC 60674 IEC 60454	Tensile strength Elongation at break Breakdown voltage Loss of mass	30 % 2 % 2,5 kV 10 %	10 %; 50 % 1 %; 4 % 1 kV; 4 kV 5 %; 20 % R A A L ISO 527-3 ISO 527-3 IEC 60454-2 IEC 60454-2
Flexible insulating sleevings Extruded, non-shrinkable sleevings Extruded, heat-shrinkable sleevings Coated or impregnated textile sleevings Coated glass textile sleevings	IEC 60684 IEC 60684 IEC 60684 IEC 60684	Elongation at break Tensile stress at 100 % extension Breakdown voltage	50 % 2 times initial value 50 %	25 %; 75 % ³⁾ R R R IEC 60684-2 IEC 60684-2 IEC 60684
Flexible material combinations Combined flexible materials Flexible laminates Reinforced flexible mica materials	IEC 60626 IEC 60371	Tensile strength Breakdown voltage	50 % 50 %	25 %; 75 % 25 %; 75 % R R ISO 1924 IEC 60243-1
Resin based reactive compounds (embedding compounds, potting compounds, encapsulating compounds) Unfilled epoxy resinous compounds Filled epoxy resinous compounds Unfilled polyurethane compounds Filled polyurethane compounds	IEC 60455 IEC 60455 IEC 60455 IEC 60455	Flexural strength Loss of mass Loss of mass Flexural strength	50 % 10 % 3 % 50 %	3 %; 5 % 5 %; 10 % R L R ISO 178
Impregnating compounds and varnishes Unsaturated polyester based impregnating resins Epoxy-based impregnating resins, unfilled Polyurethane-based impregnating resins, unfilled Hot curing impregnating varnishes	IEC 60455 IEC 60464	Bond strength Proof voltage Breakdown voltage Loss of mass Flexural strength	22 N 0,3 – 1,2 kV 3 kV 10 % 50 %	- - - A A A L R IEC 61033, method B IEC 60172 IEC 60455-2 IEC 60455-2 ISO 178

Table 1 (continued)

1	2	3	4	5
Insulating materials	Material Specification No.	Recommended properties	Recommended end-points	Test method No.
		Preferred	Subsidiary 5)	Type 1)
Coating compounds				
Coating powders	IEC 60455	Loss of mass Breakdown voltage Loss of flexibility	10 % 3 kV 3 kV Cupping 1 mm	5 %; 15 % - 1 kV; 5 kV 0,5 mm
Fusible insulating materials				L A A A
Plastisols and organosols				IEC 60370 ISO 1520
Insulations on conductors				
Enamelled winding wires	IEC 60317	Proof voltage	0,3 – 1,2 kV	- A
Column 1 lists the group of the material to be tested. See also Annex A.				
If in the respective material specification listed in column 2, the property(ies), end-point(s) and test method(s) are prescribed, then these instructions shall be followed. If a material specification or its testing conditions are not listed, select from the recommended properties and end-points those appropriate to the application of the material.				
The test methods in Column 5 are identified by the ISO or IEC publication where they are specified. However, in particular cases where thermal endurance data are of interest for design purposes, other properties applying national or specifically developed test methods may be more useful.				
NOTE Some of the materials listed herein may be grouped differently. In a few cases tests for determination of thermal endurance characteristics according to IEC 60216-1 may not apply to the materials listed below.				
1) Percentage or other values in column 4 ("Recommended end-points") shall be interpreted according to the letter symbol as follows:				
R = abbreviation for retention (if initial tensile strength is, for example, 60 MPa, then 25 % means 15 MPa, 50 % means 30 MPa and so forth).				
L = abbreviation for loss of mass end-points to be understood as the percentage decrease of the mass related to the original organic material content (determined by burning out at approximately 500 °C).				
A = abbreviation for an absolute end-point according to Item b) of 5.2 of IEC 60216-1.				
2) This property may not always be critical because in some applications, once the material is in place, it no longer will be subject to elongation.				
3) Elongation at break may not be relevant for all types of glass sleeving.				
4) Where an excessive reduction of the test specimen thickness is observed on thermoplastic moulded insulation (e.g., due to thermoplastic flow), the voltage breakdown test is not applicable.				
5) Subsidiary end-points to be used in special cases only, where the preferred end-points will not give information appropriate for special applications of the material (see Clause 3).				

Annex A (informative)

Additional information on the group to which new or unknown materials should be assigned

Since it is impossible to list all insulating materials with their preferred diagnostic properties for thermal endurance testing, Table 1 shows typical representatives of each group. The grouping is essentially based on the materials' salient mechanical and chemical features. However, the supply form, the appearance or the predominant application of a material provides additional information on the group to which new or unknown materials should be assigned in order to enable the selection of adequate properties and end-points.

a) Rigid materials

Rigid materials typically exhibit a modulus of elasticity greater than 700 MPa.

Materials of Group A and thermosetting materials of Group B and C are mostly supplied in the form of plates or flat pieces, produced by moulding, pressing from granules or from two- or multi-component compounds.

Rigid thermoplastic materials are delivered as extrusion moulded plates or other semi-finished products; they may also be manufactured to prefabricated parts by injection moulding of granules.

b) Elastomers

Materials of this group are composed from natural rubber or synthetic rubber materials or thermoplastic elastomers to meet specific properties. Compositions of natural or synthetic rubber should be adequately prepared, e.g. by milling, vulcanizing, etc. and pressed or calendered in final form. Thermoplastic elastomers are typically injection or blow moulded into prefabricated parts. Elastomers are often applied in a prefabricated form to a particular part of an electrotechnical product where thermal shock resistance or sealing performance are important material features.

c) Semi-rigid sheet materials

Materials of this group are mostly supplied in sheet form, but also as strips; they have a modulus of elasticity between 70 MPa and 700 MPa. They can be punched or folded without breaking. The thickness of pressboards and presspapers ranges from 0,1 mm up to 5,0 mm. Laminated pressboards may have a thickness up to 200 mm. These materials are often applied for slot insulation.

d) Paper, paper-based or woven materials

Materials of this group are mostly supplied in roll form. The thickness ranges from 0,01 mm to 0,5 mm. Varnished cotton or glass fabrics are designated by the term "woven materials"; the varnish may consist of different kinds of coating including silicones. A significant application of materials of this group is wrapping to insulate conducting elements such as winding coils.

e) Pressure-sensitive adhesive (PSA) tapes

These materials form a separate group due to the adhesive's influence on the performance and on the preparation of endurance test specimens. Since the backing determines the kind of ageing and diagnostics, it is advisable to consider thoroughly the details of a thermal endurance test, depending on whether the tape is paper-based, textile-based or film-based. PSA tapes with film backing are similar to pure films with regard to their diagnostics.

f) Plastic films

Materials of this group consist of a wide range of distinct products with different properties, which are also applied for multiple purposes. The thickness ranges from 0,002 mm to 0,35 mm. A significant aspect of films is their transparency; for designation purposes they are often supplied in various colours.

g) Flexible insulating sleevings

Materials of this group are supplied in tubular form in continuous or cut lengths. They are used in a wide range of applications; therefore, many different compositions and dimensions are available. This is pertinent to the ageing and diagnostics.

h) Flexible material combinations

Materials of this group are supplied in the form of sheets, tapes or full width rolls. The supply form may not be representative of the final application; additional processing is in most cases required such as wrapping and curing, punching, folding, etc. Specimens for thermal endurance testing should be made in a shape or structure representative of the intended part or product.

i) Resin-based reactive compounds (embedding compounds, potting compounds, encapsulating compounds)

Embedding compound:

casting compound poured into a mould completely encasing an electric or electronic component. After subsequent curing, the encased component is removed from the mould.

Potting compound:

casting compound poured into a mould completely encasing an electric or electronic component. After subsequent curing the mould remains attached to the encased component as a permanent part of the unit.

Encapsulating compound:

reactive compound applied without a mould as a protective or insulating coating to enclose an electric or electronic component by suitable means such as brushing, dipping, spraying, or spreading.

j) Impregnating compounds and varnishes

Compounds and varnishes are supplied in liquid form in containers. They may be solventless or contain solvent. Resinous compounds are often supplied as two separate reactive components which have to be mixed prior to application and solidification. Products of this group are suitable to provide adequate impregnation even for fine wire windings.

k) Coating compounds

Coating compounds are supplied as either powders or liquids. Powders of thermoplastic or chemically reactive resins, are applied by coating processes such as the fluidized bed technique, powder spraying or electrostatic coating. Generally, the powder is applied to objects heated to a temperature exceeding the melting or curing point of the powder. For final cure many coatings require post-heating. The coating thickness is normally high, up to 0,5 mm.

Fusible insulating materials, plastiols and organosols are supplied in liquid form. The coating performance depends on the ability of providing a coating on metallic substrates of sufficient integrity to ensure insulation and protection. Some materials cure under room temperature conditions.

l) Insulated conductive elements

Products of this group are composites and should be considered as prefabricated parts. Although the thermal endurance may be governed by the insulation, the performance depends on the entire composite. Consequently, such composites should be submitted to particular methods of thermal endurance testing, with diagnostics and end-points related to the intended technical function.

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE Where an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60172	- ¹⁾	Test procedure for the determination of the temperature index of enamelled winding wires	EN 60172	1994 ²⁾
IEC 60216-3	- ¹⁾	Electrical insulating materials - Thermal endurance properties Part 3: Instructions for calculating thermal endurance characteristics	EN 60216-3	2002 ²⁾
IEC 60216-5	- ¹⁾	Part 5: Determination of relative thermal endurance index (RTE) of an insulating material	EN 60216-5	2003 ²⁾
IEC 60216-6	- ¹⁾	Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method	EN 60216-6	2004 ²⁾
IEC 60243-1	- ¹⁾	Electrical strength of insulating materials - Test methods Part 1: Tests at power frequencies	EN 60243-1	1998 ²⁾
IEC 60317	Series	Specifications for particular types of winding wires	EN 60317	Series
IEC 60370	- ¹⁾	Test procedure for thermal endurance of insulating varnishes - Electric strength method	HD 570 S1	1990 ²⁾
IEC 60371	Series	Specification for insulating materials based on mica	EN 60371	Series
IEC 60394	Series	Varnished fabrics for electrical purposes	-	-

1) Undated reference.

2) Valid edition at date of issue.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60450	- ¹⁾	Measurement of the average viscometric degree of polymerization of new and aged electrical papers	-	-
IEC 60454	Series	Specifications for pressure-sensitive adhesive tapes for electrical purposes	EN 60454	Series
IEC 60455	Series	Resin based reactive compounds used for electrical insulation	EN 60455	Series
IEC 60464	Series	Varnishes used for electrical insulation	EN 60464	Series
IEC 60554	Series	Specification for cellulosic papers for electrical purposes	-	-
IEC 60626	Series	Combined flexible materials for electrical insulation	EN 60626	Series
IEC 60641	Series	Specification for pressboard and presspaper for electrical purposes	EN 60641	Series
IEC 60667	Series	Specification for vulcanized fibre for electrical purposes	HD 416	Series
IEC 60674	Series	Specification for plastic films for electrical purposes	EN 60674	Series
IEC 60684	Series	Flexible insulating sleeving	EN 60684	Series
IEC 60763	Series	Specification for laminated pressboard	EN 60763	Series
IEC 60819	Series	Specification for non-cellulosic papers for electrical purposes	-	-
IEC 60893	Series	Insulating materials - Industrial rigid laminated sheets based on thermosetting resins for electrical purposes	EN 60893	Series
IEC 61033	- ¹⁾	Test methods for the determination of bond strength of impregnating agents to an enamelled wire substrate	-	-
ISO 37	- ¹⁾	Rubber, vulcanized or thermoplastic - Determination of tensile stress-strain properties	-	-
ISO 178	- ¹⁾	Plastics - Determination of flexural properties	EN ISO 178	2003 ²⁾
ISO 179-1	- ¹⁾	Plastics - Determination of Charpy impact properties Part 1: Non-instrumented impact test	EN ISO 179-1	2000 ²⁾
ISO 527-2	- ¹⁾	Plastics - Determination of tensile properties Part 2: Test conditions for moulding and extrusion plastics	EN ISO 527-2	1993 ²⁾

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
ISO 527-3	- ¹⁾	Part 3: Test conditions for films and sheets	EN ISO 527-3	1995 ²⁾
ISO 1520	- ¹⁾	Paints and varnishes - Cupping test	EN ISO 1520	2001 ²⁾
ISO 1924	Series	Paper and board - Determination of tensile properties		-
ISO 2759	- ¹⁾	Board - Determination of bursting strength	EN ISO 2759	2003 ²⁾
ISO 8256	- ¹⁾	Plastics - Determination of tensile-impact strength	EN ISO 8256	2004 ²⁾

blank

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Rewrites

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.