

BS EN 60317-0-4:2016



BSI Standards Publication

Specifications for particular types of winding wires

Part 0-4: General requirements — Glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 60317-0-4:2016. It is identical to IEC 60317-0-4:2015. It supersedes BS EN 60317-0-4:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee L/-/99, Miscellaneous Standards - Electrical.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.

Published by BSI Standards Limited 2016

ISBN 978 0 580 85660 0

ICS 29.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2016.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------

EUROPEAN STANDARD

EN 60317-0-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2016

ICS 29.060.10

Supersedes EN 60317-0-4:1998

English Version

Specifications for particular types of winding wires - Part 0-4:
General requirements - Glass-fibre wound, resin or varnish
impregnated, bare or enamelled rectangular copper wire
(IEC 60317-0-4:2015)

Spécifications pour types particuliers de fils de bobinage -
Partie 0-4: Exigences générales - Fil de section
rectangulaire en cuivre nu ou émaillé, guipé de fibres de
verre imprégnées de vernis ou de résine
(IEC 60317-0-4:2015)

Technische Lieferbedingungen für bestimmte Typen von
Wickeldrähten - Teil 0-4: Allgemeine Anforderungen -
Flachdrähte aus Kupfer, blank oder lackisoliert und umhüllt
mit Glasgewebe, imprägniert mit Harz oder Lack
(IEC 60317-0-4:2015)

This European Standard was approved by CENELEC on 2015-11-27. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

The text of document 55/1550/FDIS, future edition 3 of IEC 60317-0-4, prepared by IEC/TC 55 "Winding wires" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60317-0-4:2016.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2016-08-27
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2018-11-27

This document supersedes EN 60317-0-4:1998.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 60317-0-4:2015 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60264	NOTE	Harmonized in EN 60264 series.
IEC 60317	NOTE	Harmonized in EN 60317 series.

Annex ZA

(normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 When an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60851	series	Winding wires - Test methods	EN 60851	series

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope	7
2 Normative references	7
3 Terms, definitions and general notes on tests and appearance	7
3.1 Terms and definitions	7
3.2 General notes	8
3.2.1 Methods of test	8
3.2.2 Winding wire	8
3.3 Appearance	9
4 Dimensions	9
4.1 Conductor dimensions	9
4.2 Tolerance on conductor dimensions	11
4.3 Rounding of corners	11
4.4 Increase in dimensions due to the insulation	11
4.5 Overall dimensions	13
4.5.1 Nominal overall dimensions	13
4.5.2 Minimum overall dimensions	13
4.5.3 Maximum overall dimensions	13
5 Electrical resistance	13
6 Elongation	13
7 Springiness	13
8 Flexibility and adherence	14
8.1 Mandrel winding test	14
8.2 Adherence test	14
8.2.1 Glass-fibre covered bare wires	14
8.2.2 Glass-fibre covered enamelled wires	14
9 Heat shock	14
10 Cut-through	14
11 Resistance to abrasion	14
12 Resistance to solvents	14
13 Breakdown voltage	14
14 Continuity of insulation	15
15 Temperature index	15
16 Resistance to refrigerants	15
17 Solderability	15
18 Heat or solvent bonding	15
19 Dielectric dissipation factor	15
20 Resistance to transformer oil	15
21 Loss of mass	15
23 Pin hole test	16
30 Packaging	16

Annex A (informative) Nominal cross-sectional areas for preferred and intermediate sizes	17
Bibliography	24
Table 1 – Nominal cross-sectional areas of preferred sizes	10
Table 2 – Conductor tolerances	11
Table 3 – Corner radii	11
Table 4 – Increase in dimensions	12
Table 5 – Elongation	13
Table 6 – Mandrel winding	14
Table 7 – Breakdown voltage	15
Table A.1 – Nominal cross-sectional areas (1 of 7)	17

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –**Part 0-4: General requirements –
Glass-fibre wound, resin or varnish impregnated,
bare or enamelled rectangular copper wire**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-0-4 has been prepared by IEC technical committee 55: Winding wires.

This third edition cancels and replaces the second edition published in 1997, Amendment 1:1999 and Amendment 2:2005. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) addition of dimensional requirements for grade 1 enamelled wire in Table 4;
- b) addition of dielectric breakdown requirements for grade 1 enamelled wire in Table 7.

The text of this standard is based on the following documents:

FDIS	Report on voting
55/1550/FDIS	55/1565/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

This standard is to be read in conjunction with the IEC 60851 series. The clause numbers used in this standard are identical with the respective test numbers of the IEC 60851 series.

In case of inconsistencies between IEC 60851 and this standard, the latter prevails.

The numbering of clauses in this standard is not continuous from Clauses 21 through 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 0-4: General requirements – Glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire

1 Scope

This part of IEC 60317 specifies general requirements of glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire.

The range of nominal conductor dimensions is given in the relevant specification sheet.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60851 (all parts), *Winding wires – Test methods*

3 Terms, definitions and general notes on tests and appearance

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

coating

material which is deposited on a conductor or wire by a suitable means and then dried and/or cured

3.1.2

conductor

bare metal after removal of the insulation

3.1.3

covering

material which is wound, wrapped or braided around a bare or insulated conductor

3.1.4

crack

opening in the insulation which exposes the conductor to view at the stated magnification

3.1.5

enamelled wire

wire coated with an insulation of cured resin

3.1.6

grade

range of thickness of the insulation of a wire

3.1.7**insulation**

coating or covering on the conductor with the specific function of withstanding voltage

3.1.8**nominal conductor dimension**

designation of the conductor size in accordance with IEC 60317

3.1.9**normal vision**

20/20 vision, with corrective lenses if necessary

3.1.10**winding wire**

wire used for winding a coil to provide a magnetic field

3.1.11**wire**

conductor coated or covered with an insulation

3.2 General notes**3.2.1 Methods of test**

All methods of test to be used for this part of IEC 60317 are given in the IEC 60851 series of standards.

The clause numbers used in this part of IEC 60317 are identical with the respective test numbers in the IEC 60851 series of standards.

In case of inconsistencies between the publication on test methods and this part of IEC 60317, the latter shall prevail.

Where no specific range of nominal conductor dimensions is given for a test, the test applies to all nominal conductor dimensions covered by the specification sheet.

Unless otherwise specified, all tests shall be carried out at a temperature from 15 °C to 40 °C and a relative humidity from 45 % to 75 %. Before measurements are made, the specimens shall be preconditioned under these atmospheric conditions for a time sufficient to allow the specimens to reach stability.

The wire to be tested shall be removed from the packaging in such a way that it is not subjected to tension or unnecessary bends. Before each test, sufficient wire should be discarded to ensure that any damaged wire is not included in the test specimens.

3.2.2 Winding wire

When reference is made to a winding wire according to a standard of the IEC 60317 series, the following information is given in the description:

- reference of the IEC specification;
- nominal conductor dimensions in millimetres (width × thickness);
- grade.

EXAMPLE IEC 60317-31 – 4,00 × 1,00 Grade 2GL1

3.3 Appearance

The fibrous covering shall be essentially smooth and continuous, and free from physical damage and foreign material when examined with normal vision, as wound on the original spool or reel.

NOTE Evidence of physical damage includes gashes, broken fibre strands, and the like.

4 Dimensions

4.1 Conductor dimensions

The dimensions for widths and thickness of conductors of winding wires with rectangular cross-section recommended in this part of IEC 60317 shall be in accordance with Table 1, and are taken from the R 20 series according to ISO 3.

Preferred and intermediate sizes are combinations of width and thickness both according to the R 20 series.

This part of IEC 60317 covers:

- widths from 2,00 mm up to and including 16,00 mm;
- thicknesses from 0,80 mm up to and including 5,60 mm.

For thickness over 5,60 mm up to and including 10 mm and for widths over 16 mm up to and including 25 mm where, for technical reasons, additional sizes may be needed, the R 40 series shall be used. The ratio width/thickness shall be within the specified limits and combinations of R 40 and R 40 are not allowed in the case of additional sizes.

The ratio width/thickness shall be greater than or equal to 1,4:1 and shall not exceed 8:1.

The actual values of dimensions are given in Table 1.

The nominal cross-sectional areas for preferred sizes are given in Table 1 and the nominal cross-sectional areas for intermediate sizes are given in Annex A.

Table 1 – Nominal cross-sectional areas of preferred sizes

Thickness mm	Width																	
	0,80	0,90	1,00	1,12	1,25	1,40	1,60	1,80	2,00	2,24	2,50	2,80	3,15	3,55	4,00	4,50	5,00	5,60
	Corner radius (0,5 mm ^a)																	
2,00	1,463	1,626	1,785	2,025	2,285	2,585												
2,24	1,655	1,842	2,205	2,294	2,582	2,921	3,369											
2,50	1,863	2,076	2,285	2,585	2,910	3,285	3,785	4,137										
2,80	2,103	2,346	2,585	2,921	3,285	3,705	4,265	4,677	5,237									
3,15	2,383	2,661	2,935	3,313	3,723	4,195	4,825	5,307	5,937	6,693								
3,55	2,703	3,021	3,335	3,761	4,223	4,755	5,465	6,027	6,737	7,589	8,326							
4,00	3,063	3,426	3,785	4,265	4,785	5,385	6,185	6,831	7,637	8,597	9,451	10,65						
4,50	3,463	3,876	4,285	4,825	5,410	6,085	6,85	7,737	8,631	9,717	10,70	12,05	13,63					
5,00	3,863	4,326	4,785	5,385	6,035	6,785	7,785	8,637	9,637	10,84	12,18	13,45	15,20	17,20				
5,60	4,363	4,866	5,385	6,057	6,785	7,625	8,745	9,717	10,84	12,18	13,45	15,13	17,09	19,33	21,54			
6,30	4,903	5,496	6,085	6,841	7,660	8,605	9,865	10,98	12,24	13,75	15,20	17,09	19,30	21,82	24,34	27,49		
7,10		6,216	6,885	7,737	8,660	9,725	11,15	12,42	13,84	15,54	17,20	19,33	21,82	24,66	27,54	31,09	34,64	
8,00			7,785	8,745	9,785	10,99	12,59	14,04	15,64	17,56	19,45	21,85	24,65	27,85	31,14	35,14	39,14	43,94
9,00				9,865	11,04	12,39	14,19	15,84	17,64	19,80	21,95	24,65	27,80	31,40	35,14	39,64	44,14	49,54
10,0					12,29	13,79	15,79	17,64	19,64	22,04	24,45	27,45	30,95	34,95	39,14	44,14	49,14	55,14
11,2						15,47	17,71	19,80	22,04	24,79	27,46	30,81	34,73	39,21	43,94	49,54	55,14	61,86
12,5	Not recommended						19,79	22,14	24,64	27,64	30,70	34,45	38,83	43,83	49,14	55,39	61,64	69,14
14,0	Ratio width/thickness over 8:1							24,84	27,64	31,00	34,45	38,65	43,55	49,15	55,14	62,14	69,14	77,54
16,0									31,64	35,48	39,45	44,25	49,85	56,25	63,14	71,14	79,14	88,74

^a Nominal thickness

4.2 Tolerance on conductor dimensions

The conductor dimensions shall not differ from the nominal values by more than the tolerance given in Table 2.

Table 2 – Conductor tolerances

Nominal width or thickness of the conductor mm		Tolerance mm
Over	Up to and including	
–	3,15	± 0,030
3,15	6,30	± 0,050
6,30	12,50	± 0,070
12,50	16,00	± 0,100

4.3 Rounding of corners

The arc shall merge smoothly into the flat surfaces of the conductor and the strip shall be free from sharp, rough and projecting edges. The conductor shall have corner radii complying with Table 3. The specified radii shall be maintained within ± 25 %.

Table 3 – Corner radii

Nominal thickness of the conductor mm		Corner radius mm
Over	Up to and including	
–	1,00	0,5 nominal thickness
1,00	1,60	0,50 ^a
1,60	2,24	0,65 ^b
2,24	3,55	0,80
3,55	5,60	1,00
If agreed between purchaser and supplier, the corner radii for wires with a width greater than 4,8 mm may be: ^a 0,5 mm nominal thickness; ^b 0,8 mm.		

4.4 Increase in dimensions due to the insulation

The increase in width or thickness due to the insulation shall be as specified in Table 4.

Table 4 – Increase in dimensions

Nominal width of the conductor mm		Increase in dimensions mm														
		Glass-fibre covering over bare conductor				Glass-fibre covering over grade 1 enamelled wire				Glass-fibre covering over grade 2 enamelled wire						
		Single covering (GL1)		Double covering (GL2)		Single covering (grade 1 GL1)		Double covering (grade 1 GL2)		Single covering (grade 2 GL1)		Double covering (grade 2 GL2)				
Over	Up to and incl.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.			
–	3,15	0,10	0,14	0,18	0,21	0,27	0,33	0,16	0,23	0,30	0,45	0,23	0,29	0,35	0,42	0,49
3,15	6,30	0,12	0,16	0,20	0,23	0,30	0,37	0,18	0,25	0,32	0,49	0,25	0,31	0,37	0,45	0,52
6,30	12,50	0,14	0,19	0,24	0,27	0,35	0,43	0,20	0,28	0,36	0,55	0,27	0,34	0,41	0,50	0,57
12,50	16,00	0,17	0,23	0,29	0,31	0,39	0,47	0,23	0,32	0,41	0,59	0,30	0,38	0,46	0,54	0,62

The maximum increase in thickness or width due to the insulation may be exceeded, provided the overall thickness or width of the insulated wire does not exceed the sum of the maximum thickness or width of the bare wire plus the maximum increase in dimension.

NOTE The minimum increases in dimensions apply only to the increase in thickness.

4.5 Overall dimensions

4.5.1 Nominal overall dimensions

The nominal overall dimensions shall be calculated as the sum of the nominal bare conductor dimension and the nominal increase in dimension due to the insulation.

4.5.2 Minimum overall dimensions

The minimum overall dimensions shall be calculated as the sum of the minimum bare conductor dimension and the minimum increase in dimension due to the insulation.

4.5.3 Maximum overall dimensions

The maximum overall dimensions shall be calculated as the sum of the maximum bare conductor dimension and the maximum increase in dimension due to the insulation.

5 Electrical resistance

The resistance of the wire shall be expressed as the d.c. resistance at 20 °C. The method used shall provide an accuracy of 0,5 %.

The maximum value of resistance shall be not greater than the value calculated for the minimum tolerated cross-sectional area of the conductor resulting from the minimum dimensions in thickness and width and the maximum for the corner radius, and with a maximum resistivity of $1/58,5 \Omega \text{ mm}^2 \text{ m}^{-1}$.

One measurement shall be made.

6 Elongation

The elongation at fracture shall be in accordance with Table 5.

Table 5 – Elongation

Nominal thickness of the conductor mm		Minimum elongation %
Over	Up to and including	
–	2,50	30
2,50	5,60	32

7 Springiness

The wire shall not exceed the maximum springback of:

- 5,0 degrees for glass-fibre covered bare wires;
- 5,5 degrees for glass-fibre covered enamelled wires.

8 Flexibility and adherence

8.1 Mandrel winding test

The covering shall show no crack after the wire has been bent flatwise and edgewise on a mandrel with a diameter as specified in Table 6.

Table 6 – Mandrel winding

Wire bent on		Mandrel diameter
Width	Sizes up to and including 8 mm	10 × width
	Sizes over 8 mm	15 × width
Thickness	All sizes	10 × thickness

Specimens showing no crack or opening shall meet the requirements of Clause 13.

8.2 Adherence test

8.2.1 Glass-fibre covered bare wires

The specimen shall be elongated by 10 %. There shall be no loss of adhesion of the glass-fibre covering.

8.2.2 Glass-fibre covered enamelled wires

The specimen shall be elongated by 10 %. There shall be no loss of adhesion either of the glass-fibre covering or the enamel.

9 Heat shock

Test inappropriate.

10 Cut-through

Test inappropriate.

11 Resistance to abrasion

Test inappropriate.

12 Resistance to solvents

Test inappropriate.

13 Breakdown voltage

The wire shall meet the requirements of Table 7.

Table 7 – Breakdown voltage

Type of insulation		Minimum breakdown voltage (root-mean-square value) (r.m.s.) V
Bare conductor with	Single covering (GL1)	350
	Double covering (GL2)	560
Grade 1 enamelled wire with	Single covering (grade 1 GL1)	1 350
	Double covering (grade 1 GL2)	1 560
Grade 2 enamelled wire with	Single covering (grade 2 GL1)	2 350
	Double covering (grade 2 GL2)	2 560

14 Continuity of insulation

Test inappropriate.

15 Temperature index

The temperature index is dependent on the type of impregnating agent used. The method of test used shall be agreed between purchaser and supplier. The maximum service temperature shall be determined by experience.

16 Resistance to refrigerants

Test inappropriate.

17 Solderability

Test inappropriate.

18 Heat or solvent bonding

Test inappropriate.

19 Dielectric dissipation factor

Test inappropriate.

20 Resistance to transformer oil

Test inappropriate.

21 Loss of mass

Test inappropriate.

23 Pin hole test

Test inappropriate.

30 Packaging

The kind of packaging can influence certain properties of the wire, for example springback. Therefore the kind of packaging, for example the type of spool, shall be agreed between purchaser and supplier.

The wire shall be evenly and compactly wound on spools or placed in containers. In order to reduce the risk of wire damage, the spool with the wire shall be delivered and used with its axis in the horizontal position. No spool or container shall contain more than one length of wire unless agreed between purchaser and supplier. Marking of the label when there is more than one length and/or identification of the separate lengths in the package shall be agreed between purchaser and supplier.

Labels shall be attached to each packaging unit as agreed between supplier and user and shall include the following information:

- a) manufacturer's name and/or trade mark;
- b) type of wire and insulation, for instance trade name and/or IEC specification number;
- c) net mass of wire;
- d) nominal dimension(s) of wire and grade of insulation;
- e) date of manufacture.

Annex A (informative)

Nominal cross-sectional areas for preferred and intermediate sizes

Table A.1 – Nominal cross-sectional areas (1 of 7)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area		
mm	mm	mm	mm ²	mm	mm	mm	mm ²		
2,00	0,80	a	1,463	2,50	1,25	0,5	2,910		
	0,85	a	1,545		1,32	0,5	3,085		
	0,90	a	1,626		1,40	0,5	3,285		
	0,95	a	1,706		1,50	0,5	3,535		
	1,00	a	1,785		1,60	0,5	3,785		
	1,06	0,5	1,905		1,70	0,65	3,887		
	1,12	0,5	2,025		1,80	0,65	4,137		
	1,18	0,5	2,145		2,65	0,80	a	1,983	
	1,25	0,5	2,285			0,90	a	2,211	
	1,32	0,5	2,425			1,00	a	2,435	
	2,12	0,80	a		1,559	2,80	1,12	0,5	2,753
			a		1,734		1,25	0,5	3,098
			a		1,905		1,40	0,5	3,495
1,12		0,5	2,160	1,60	0,5		4,025		
1,25		0,5	2,435	1,80	0,65		4,407		
1,40		0,5	2,753		0,80		a	2,103	
2,24		0,80	a	1,655	0,85		a	2,225	
	0,85	a	1,749	0,90	a	2,346			
	0,90	a	1,842	0,95	a	2,466			
	0,95	a	1,934	1,00	a	2,585			
	1,06	0,5	2,160	1,06	0,5	2,753			
	1,12	0,5	2,294	1,12	0,5	2,921			
	1,18	0,5	2,429	1,18	0,5	3,089			
	1,25	0,5	2,585	1,25	0,5	3,285			
	1,32	0,5	2,742	1,32	0,5	3,481			
	1,40	0,5	2,921	1,40	0,5	3,705			
	1,50	0,5	3,145	1,50	0,5	3,985			
	1,60	0,5	3,369	1,60	0,5	4,265			
	2,36	0,80	a	1,751	1,70	0,65	4,397		
		0,90	a	1,950	1,80	0,65	4,677		
		1,00	a	2,145	1,90	0,65	4,957		
		1,12	0,5	2,429	2,00	0,65	5,237		
1,25		0,5	2,735	3,00	0,80	a	2,263		
1,40		0,5	3,089		0,90	a	2,526		
1,60		0,5	3,561		1,00	a	2,785		
2,50		0,80	a		1,863	1,12	0,5	3,145	
	0,85	a	1,970	1,25	0,5	3,535			
	0,90	a	2,076	1,40	0,5	3,985			
	0,95	a	2,181	1,60	0,5	4,585			
	1,00	a	2,285	1,80	0,65	5,037			
	1,06	0,5	2,435		3,15	0,80	a	2,383	
	1,12	0,5	2,585	0,85		a	2,522		
	1,18	0,5	2,736						

^a 0,5 mm nominal thickness.

Table A.1 (2 of 7)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area		Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area	
mm	mm	mm	mm ²		mm	mm	mm	mm ²	
3,15	0,90	a	2,661		3,75	0,80	a	2,863	
	0,95	a	2,799			0,90	a	3,201	
	1,00	a	2,935			1,00	a	3,535	
	1,06	0,5	3,124			1,12	0,5	3,985	
	1,12	0,5	3,313			1,25	0,5	4,473	
	1,18	0,5	3,502			1,40	0,5	5,035	
	1,25	0,5	3,723			1,60	0,5	5,785	
	1,32	0,5	3,943			4,00	1,80	0,65	6,387
	1,40	0,5	4,195				2,00	0,65	7,137
	1,50	0,5	4,510		2,24		0,65	8,037	
	1,60	0,5	4,825		2,50		0,8	8,826	
	1,70	0,65	4,992		4,00		0,80	a	3,063
	1,80	0,65	5,307				0,85	a	3,245
	1,90	0,65	5,622				0,90	a	3,426
	2,00	0,65	5,937				0,95	a	3,606
	2,12	0,65	6,315				1,00	a	3,785
	2,24	0,65	6,693			1,06	0,5	4,025	
	3,35	0,80	a			2,543	1,12	0,5	4,265
		0,90	a			2,841	1,18	0,5	4,505
1,00		a	3,135	1,25		0,5	4,785		
1,12		0,5	3,537	1,32	0,5	5,065			
1,25		0,5	3,973	1,40	0,5	5,385			
1,40		0,5	4,475	1,50	0,5	5,785			
1,60		0,5	5,145	1,60	0,5	6,185			
1,80		0,65	5,667	1,70	0,65	6,437			
2,00		0,65	6,337	1,80	0,65	6,837			
2,24		0,65	7,141	1,90	0,65	7,237			
3,55		0,80	a	2,703	2,00	0,65	7,637		
		0,85	a	2,862	2,12	0,65	8,117		
		0,90	a	3,021	2,24	0,65	8,597		
		0,95	a	3,179	4,25	2,36	0,8	8,891	
		1,00	a	3,335		2,50	0,8	9,451	
		1,06	0,5	3,548		2,65	0,8	10,05	
		1,12	0,5	3,761		2,80	0,8	10,65	
		1,18	0,5	3,974		4,25	0,80	a	3,263
		1,25	0,5	4,223			0,90	a	3,651
	1,32	0,5	4,471	1,00			a	4,035	
	1,40	0,5	4,755	1,12			0,5	4,545	
	1,50	0,5	5,110	1,25			0,5	5,098	
	1,60	0,5	5,465	1,40	0,5		5,735		
	1,70	0,65	5,672	1,60	0,5		6,585		
	1,80	0,65	6,027	1,80	0,65		7,287		
	1,90	0,65	6,382	2,00	0,65		8,137		
	2,00	0,65	6,737	2,24	0,65	9,157			
	2,12	0,65	7,163	4,25	2,50	0,8	10,08		
	2,24	0,65	7,589		2,80	0,8	11,35		
2,36	0,8	7,829							
2,50	0,8	8,326							

^a 0,5 mm nominal thickness.

Table A.1 (3 of 7)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area		Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area		
mm	mm	mm	mm ²		mm	mm	mm	mm ²		
4,50	0,80	a	3,463		5,00	1,70	0,65	8,137		
	0,85	a	3,670			1,80	0,65	8,637		
	0,90	a	3,876			1,90	0,65	9,137		
	0,95	a	4,081			2,00	0,65	9,637		
	1,00	a	4,285			2,12	0,65	10,24		
							2,24	0,65	10,84	
	1,06	0,5	4,555			5,30	2,36	0,8	11,25	
	1,12	0,5	4,825				2,50	0,8	11,95	
	1,18	0,5	5,095				2,65	0,8	12,70	
	1,25	0,5	5,410				2,80	0,8	13,45	
	1,32	0,5	5,725		3,00		0,8	14,45		
	1,40	0,5	6,085		3,15		0,8	15,20		
	1,50	0,5	6,535		3,35		0,8	16,20		
	1,60	0,5	6,985		3,55		0,8	17,20		
	1,70	0,65	7,287		5,60		0,80	a	4,103	
	1,80	0,65	7,737				0,90	a	4,596	
	1,90	0,65	8,187			1,00	a	5,085		
	2,00	0,65	8,637			1,12	0,5	5,721		
	2,12	0,65	9,177			1,25	0,5	6,410		
	2,24	0,65	9,717			1,40	0,5	7,205		
	2,36	0,8	10,07			1,60	0,5	8,265		
	2,50	0,8	10,70			1,80	0,65	9,177		
	2,65	0,8	11,38			2,00	0,65	10,24		
	2,80	0,8	12,05			2,24	0,65	11,51		
	3,00	0,8	12,95		5,60	2,50	0,8	12,70		
	3,15	0,8	13,63			2,80	0,8	14,29		
	4,75	0,80	a			3,663	3,15	0,8	16,15	
		0,90	a			4,101	3,55	0,8	18,27	
		1,00	a			4,535	5,60	0,80	a	4,343
		1,12	0,5			5,105		0,85	a	4,605
		1,25	0,5			5,723		0,90	a	4,866
		1,40	0,5			6,435		0,95	a	5,126
		1,60	0,5			7,385		1,00	a	5,385
1,80		0,65	8,188	1,06		0,5		5,721		
2,00		0,65	9,137	1,12	0,5	6,057				
2,24		0,65	10,28	1,18	0,5	6,393				
2,50	0,8	11,33	1,25	0,5	6,785					
2,80	0,8	12,75	1,32	0,5	7,177					
3,15	0,8	14,41	1,40	0,5	7,625					
5,00	0,80	a	3,863	1,50	0,5	8,185				
	0,85	a	4,095	1,60	0,5	8,745				
	0,90	a	4,326	5,60	1,70	0,65	9,157			
	0,95	a	4,556		1,80	0,65	9,717			
	1,00	a	4,785		1,90	0,65	10,28			
	1,06	0,5	5,085		2,00	0,65	10,84			
	1,12	0,5	5,385		2,12	0,65	11,51			
	1,18	0,5	5,685		2,24	0,65	12,18			
	1,25	0,5	6,035		5,60	2,36	0,8	12,67		
	1,32	0,5	6,385			2,50	0,8	13,45		
1,40	0,5	6,785	2,65			0,8	14,29			
1,50	0,5	7,285	2,80			0,8	15,13			
1,60	0,5	7,785								

^a 0,5 mm nominal thickness.

Table A.1 (4 of 7)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area		Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area
mm	mm	mm	mm ²		mm	mm	mm	mm ²
5,60	3,00	0,8	16,25		6,30	3,75	1,0	22,77
	3,15	0,8	17,09			4,00	1,0	24,34
	3,35	0,8	18,21			4,25	1,0	25,92
	3,55	0,8	19,33			4,50	1,0	27,49
	3,75	1,0	20,14	6,70	0,90	a	5,856	
	4,00	1,0	21,54		1,00	a	6,485	
	6,00	0,80	a	4,663	7,10	1,12	0,5	7,289
		0,90	a	5,226		1,25	0,5	8,160
1,00		a	5,785	1,40		0,5	9,165	
				1,60		0,5	10,51	
1,12		0,5	6,505					
1,25		0,5	7,285	1,80		0,65	11,70	
1,40		0,5	8,185	2,00		0,65	13,04	
1,60		0,5	9,385	2,24		0,65	14,65	
1,80		0,65	10,44	2,50		0,8	16,20	
2,00		0,65	11,64	2,80		0,8	18,21	
2,24		0,65	13,08	3,15		0,8	20,56	
				3,55		0,8	23,24	
2,50		0,8	14,45					
2,80		0,8	16,25	4,00		1,0	25,94	
3,15		0,8	18,35	4,50		1,0	29,29	
3,55	0,8	20,75						
4,00	1,0	23,14	6,30	0,90	a	6,216		
				0,95	a	6,551		
				1,00	a	6,885		
0,80	a	4,903		1,06	0,5	7,311		
0,85	a	5,200		1,12	0,5	7,737		
0,90	a	5,496		1,18	0,5	8,163		
0,95	a	5,791		1,25	0,5	8,660		
1,00	a	6,085		1,32	0,5	9,157		
				1,40	0,5	9,725		
1,06	0,5	6,463		1,50	0,5	10,44		
1,12	0,5	6,841		1,60	0,5	11,15		
1,18	0,5	7,219						
1,25	0,5	7,660		1,70	0,65	11,71		
1,32	0,5	8,101		1,80	0,65	12,42		
1,40	0,5	8,605		1,90	0,65	13,13		
1,50	0,5	9,235	2,00	0,65	13,84			
1,60	0,5	9,865	2,12	0,65	14,69			
			2,24	0,65	15,54			
1,70	0,65	10,35						
1,80	0,65	10,98	2,36	0,8	16,21			
1,90	0,65	11,61	2,50	0,8	17,20			
2,00	0,65	12,24	2,65	0,8	18,27			
2,12	0,65	12,99	2,80	0,8	19,33			
2,24	0,65	13,75	3,00	0,8	20,75			
			3,15	0,8	21,82			
2,36	0,8	14,32	3,35	0,8	23,24			
2,50	0,8	15,20	3,55	0,8	24,66			
2,65	0,8	16,15						
2,80	0,8	17,09	3,75	1,0	25,77			
3,00	0,8	18,35	4,00	1,0	27,54			
3,15	0,8	19,30	4,25	1,0	29,32			
3,35	0,8	20,56						
3,55	0,8	21,82						

^a 0,5 mm nominal thickness.

Table A.1 (5 of 7)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area			
mm	mm	mm	mm ²	mm	mm	mm	mm ²			
7,10	4,50	1,0	31,09	8,50	1,12	0,5	9,305			
	4,75	1,0	32,87		1,25	0,5	10,41			
	5,00	1,0			34,64	1,40	0,5	11,69		
1,60						0,5	13,39			
7,50	1,00	a	7,285	1,80	0,65	14,94				
	1,12	0,5	8,185	2,00	0,65	16,64				
				2,24	0,65	18,68				
				2,50	0,8	18,20	2,80	0,8	20,45	
							3,15	0,8	23,08	
							3,55	0,8	26,08	
				4,00	1,0	29,14	4,50	1,0	32,89	
	5,00	1,0	36,64							
	8,00	1,00	a				7,785	1,06	0,5	8,265
								1,12	0,5	8,745
								1,18	0,5	9,225
1,25	0,5	9,785								
1,32	0,5	10,35								
1,40	0,5	10,99								
1,50	0,5	11,79								
1,60	0,5	12,59								
1,70	0,65	13,24								
1,80	0,65	14,04								
1,90	0,65	14,84								
2,00	0,65	15,64								
2,12	0,65	16,60								
2,24	0,65	17,56								
2,36	0,8	18,33								
2,50	0,8	19,45								
2,65	0,8	20,65								
2,80	0,8	21,85								
3,00	0,8	23,45								
3,15	0,8	24,65								
3,35	0,8	26,25								
3,55	0,8	27,85								
3,75	1,0	29,14								
4,00	1,0	31,14								
4,25	1,0	33,14								
4,50	1,0	35,14								
4,75	1,0	37,14								
5,00	1,0	39,14								
5,30	1,0	41,54								
5,60	1,0	43,94								
9,00	1,00	a	7,785	1,12	0,5	9,865				
				1,18	0,5	10,41				
				1,25	0,5	11,04				
				1,32	0,5	11,67				
				1,40	0,5	12,39				
				1,50	0,5	13,29				
				1,60	0,5	14,19				
				1,70	0,65	14,94				
				1,80	0,65	15,84				
				1,90	0,65	16,74				
				2,00	0,65	17,64				
2,12	0,65	18,72								
2,24	0,65	19,80								
2,36	0,8	20,69								
2,50	0,8	21,95								
2,65	0,8	23,30								
2,80	0,8	24,65								
3,00	0,8	26,45								
3,15	0,8	27,80								
3,35	0,8	29,60								
3,55	0,8	31,40								
3,75	1,0	32,89								
4,00	1,0	35,14								
4,25	1,0	37,39								
4,50	1,0	39,64								
4,75	1,0	41,89								
5,00	1,0	44,14								
5,30	1,0	46,84								
5,60	1,0	49,54								
9,50	1,00	a	7,785	1,25	0,5	11,66				
				1,40	0,5	13,09				
				1,60	0,5	14,99				
				1,80	0,65	16,74				
				2,00	0,65	18,64				
2,24	0,65	20,92								

^a 0,5 mm nominal thickness.

Table A.1 (7 of 7)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-sectional area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
12,50	4,50	1,0	55,39	14,00	4,75	1,0	65,64
	4,75	1,0	58,52		5,00	1,0	69,14
	5,00	1,0	61,64		5,30	1,0	73,34
	5,30	1,0	65,39		5,60	1,0	77,54
	5,60	1,0	69,14		15,00	2,00	0,65
13,20	1,80	0,65	23,40	2,24		0,65	33,24
	2,00	0,65	26,04	2,50		0,8	36,95
	2,24	0,65	29,21	2,80		0,8	41,45
	2,50	0,8	32,45	3,15		0,8	46,70
	2,80	0,8	36,41	3,55		0,8	52,70
	3,15	0,8	41,03	4,00		1,0	59,14
	3,55	0,8	46,31	4,50		1,0	66,64
	4,00	1,0	51,94	5,00		1,0	74,14
	4,50	1,0	58,54	5,60		1,0	83,14
	5,00	1,0	65,14	16,00	2,00	0,65	31,64
5,60	1,0	73,06	2,12		0,65	33,56	
14,00	1,80	0,65	24,84		2,24	0,65	35,48
	1,90	0,65	26,24		2,36	0,8	37,21
	2,00	0,65	27,64		2,50	0,8	39,45
	2,12	0,65	29,32		2,65	0,8	41,85
	2,24	0,65	31,00		2,80	0,8	44,25
	2,36	0,8	32,49		3,00	0,8	47,45
	2,50	0,8	34,45		3,15	0,8	49,85
	2,65	0,8	36,55		3,35	0,8	53,05
	2,80	0,8	38,65		3,55	0,8	56,25
	3,00	0,8	41,45		3,75	1,0	59,14
3,15	0,8	43,55	4,00		1,0	63,14	
3,35	0,8	46,35	4,25		1,0	67,14	
3,55	0,8	49,15	4,50		1,0	71,14	
3,75	1,0	51,64	4,75	1,0	75,14		
4,00	1,0	55,14	5,00	1,0	79,14		
4,25	1,0	58,64	5,30	1,0	83,94		
4,50	1,0	62,14	5,60	1,0	88,74		

Bibliography

IEC 60264 (all parts), *Packaging of winding wires*

IEC 60317 (all parts), *Specifications for particular types of winding wires*

ISO 3:1973, *Preferred numbers – Series of preferred numbers*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK