

BS EN 60317-0-9:2015



BSI Standards Publication

Specifications for particular types of winding wires

Part 0-9: General requirements — Enamelled rectangular aluminium wire

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 60317-0-9:2015. It is identical to IEC 60317-0-9:2015.

The UK participation in its preparation was entrusted to Technical Committee L/-/99, Miscellaneous Standards - Electrical.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 83231 4
ICS 29.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2015.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------

EUROPEAN STANDARD

EN 60317-0-9

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 29.060.10

English Version

Specifications for particular types of winding wires - Part 0-9:
General requirements - Enamelled rectangular aluminium wire
(IEC 60317-0-9:2015)

Spécifications pour types particuliers de fils de bobinage -
Partie 0-9: Exigences générales - Fil de section
rectangulaire émaillé en aluminium
(IEC 60317-0-9:2015)

Technische Lieferbedingungen für bestimmte Typen von
Wickeldrähten - Teil 0-9: Allgemeine Anforderungen -
Flachdrähte aus Aluminium, lackisoliert
(IEC 60317-0-9:2015)

This European Standard was approved by CENELEC on 2015-06-09. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

The text of document 55/1519/FDIS, future edition 1 of IEC 60317-0-9, prepared by IEC/TC 55 "Winding wires" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60317-0-9:2015.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2016-06-04
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2018-06-09

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 60317-0-9:2015 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

- | | | |
|------------------|------|--------------------------------|
| IEC 60264 series | NOTE | Harmonized in EN 60264 series. |
| IEC 60317 series | NOTE | Harmonized in EN 60317 series. |

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 When an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60172	2015	Test procedure for the determination of the temperature index of enamelled and tape wrapped winding wires	EN 60172	2015
IEC 60317-0-1	-	Specifications for particular types of winding wires -- Part 0-1: General requirements - Enamelled round copper wire	EN 60317-0-1	-
IEC 60851	series	Winding wires - Test methods	EN 60851	series
ISO 3	-	Preferred numbers; Series of preferred numbers	-	-

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope	7
2 Normative references	7
3 Terms, definitions, general notes and appearance	7
3.1 Terms and definitions	7
3.2 General notes	7
3.2.1 Methods of test	7
3.2.2 Winding wire	8
3.3 Appearance	8
4 Dimensions	8
4.1 Conductor dimensions	8
4.2 Tolerance on conductor dimensions	9
4.3 Rounding of corners	9
4.4 Increase in dimensions due to the insulation	11
4.5 Overall dimensions	11
4.5.1 Nominal overall dimensions	11
4.5.2 Minimum overall dimensions	11
4.5.3 Maximum overall dimensions	11
5 Electrical resistance	12
6 Elongation	12
7 Springiness	12
8 Flexibility and adherence	12
8.1 Mandrel winding test	12
8.2 Adherence test	12
9 Heat shock	12
10 Cut-through	12
11 Resistance to abrasion	13
12 Resistance to solvents	13
13 Breakdown voltage	13
14 Continuity of insulation	13
15 Temperature index	13
16 Resistance to refrigerants	13
17 Solderability	14
18 Heat or solvent bonding	14
19 Dielectric dissipation factor	14
20 Resistance to transformer oil	14
21 Loss of mass	14
23 Pin hole test	14
30 Packaging	14
Annex A (informative) Nominal cross-sectional areas for preferred and intermediate sizes	15
Annex B (informative) Special tolerances	24

Bibliography..... 25

Table 1– Conductor tolerances 9

Table 2 – Nominal cross-sectional areas of preferred sizes..... 10

Table 3 – Corner radii 11

Table 4 – Increases in dimensions 11

Table 5 – Mandrel winding 12

Table 6 – Breakdown voltage 13

Table A.1 – Nominal cross-sectional areas (*1 of 9*) 15

Table B.1 – Overall dimensional tolerances for grade 2 24

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –**Part 0-9: General requirements – Enamelled rectangular aluminium wire**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-0-9 has been prepared by IEC technical committee 55: Winding wires.

The text of this standard is based on the following documents:

FDIS	Report on voting
55/1519/FDIS	55/1525/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The numbering of clauses in this standard is not continuous from Clauses 21 through 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851 series);
- 2) Specifications for particular types of winding wires (IEC 60317 series);
- 3) Packaging of winding wires (IEC 60264 series).

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 0-9: General requirements – Enamelled rectangular aluminium wire

1 Scope

This part of IEC 60317 specifies the general requirements of enamelled rectangular aluminium winding wires.

The range of nominal conductor dimensions is given in the relevant specification sheet.

When reference is made to a winding wire according to a standard of the IEC 60317 series mentioned under Clause 2, the following information is given in the description:

- reference to IEC specification;
- nominal conductor dimensions in millimetres (width × thickness);
- grade.

EXAMPLE IEC 60317-16 – 4,00 x 1,00 Grade 1

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60172¹, *Test procedure for the determination of the temperature index of enamelled and tape wrapped winding wires*

IEC 60317-0-1, *Specifications for particular types of winding wires – Part 0-1: General requirements – Enamelled round copper wire*

IEC 60851 (all parts), *Winding wires – Test methods*

ISO 3, *Preferred numbers – Series of preferred numbers*

3 Terms, definitions, general notes and appearance

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60317-0-1 apply.

3.2 General notes

3.2.1 Methods of test

All methods of test to be used for this standard are given in IEC 60851.

¹ Fourth edition to be published.

The clause numbers used in this standard are identical to the corresponding test numbers in the IEC 60851 series of standards.

In case of inconsistencies between the publication on methods of test and this standard, IEC 60317-0-9 shall prevail.

Where no specific range of nominal conductor dimensions is given for a test, the test applies to all nominal conductor dimensions covered by the specification sheet.

Unless otherwise specified, all tests shall be carried out at a temperature from 15 °C to 35 °C and a relative humidity from 45 % to 75 %. Before measurements are made, the specimens shall be preconditioned under these atmospheric conditions for a time sufficient to allow the specimens to reach stability.

The wire to be tested shall be removed from the packaging in such a way that the wire will not be subjected to tension or unnecessary bends. Before each test, sufficient wire should be discarded to ensure that any damaged wire is not included in the test specimens.

3.2.2 Winding wire

When reference is made to a winding wire according to a standard of the IEC 60317 series mentioned under Clause 2, the following information is given in the description:

- reference to IEC specification;
- nominal conductor dimensions in millimetres (width × thickness);
- grade.

EXAMPLE IEC 60317-18 – 4,00 × 1,00 Grade 1

3.3 Appearance

The film coating shall be smooth and continuous, free from streaks, blisters and foreign material when examined with normal vision, as wound on the original spool or reel.

4 Dimensions

4.1 Conductor dimensions

The dimensions for widths and thickness of conductors of winding wires with rectangular cross-section recommended in this standard are taken from the R 20 and R 40 series according to ISO 3.

Preferred sizes are combinations of width and thickness both according to the R 20 series.

Intermediate sizes are combinations of width or thickness according to the R 20 series with the other dimension according to the R 40 series.

This standard covers:

- widths from 2,00 mm up to and including 16,00 mm;
- thicknesses from 0,80 mm up to and including 5,60 mm.

For thicknesses over 5,600 mm up to and including 10 mm and for widths over 16 mm up to and including 25 mm where, for technical reasons, additional sizes may be needed, the R 40 series shall be used. The ratio width/thickness shall be within the specified limits and combinations of R 40 by R 40 are not allowed in the case of additional sizes.

The ratio width/thickness shall be greater than or equal to 1,4:1 and shall not exceed 8:1.

The actual values of dimensions are given in Table 2.

The nominal cross-sectional areas for preferred sizes are given in Table 2, and the nominal cross-sectional areas for intermediate sizes are given in Table A.1.

4.2 Tolerance on conductor dimensions

The conductor dimensions shall not differ from the nominal values by more than the tolerance given in Table 1.

Table 1– Conductor tolerances

Nominal width or thickness of the conductor		Tolerance
mm		
Over	Up to and including	± mm
–	3,15	0,030
3,15	6,30	0,050
6,30	12,50	0,070
12,50	16,00	0,100

4.3 Rounding of corners

The arc shall merge smoothly into the flat surfaces of the conductor and the strip shall be free from sharp, rough and projecting edges. The conductor shall have radiused corners complying with Table 3. The specified radii shall be maintained within $\pm 25\%$.

Table 2 – Nominal cross-sectional areas of preferred sizes

Width	Thickness →																	
	0,80	0,90	1,00	1,12	1,25	1,40	1,60	1,80	2,00	2,24	2,50	2,80	3,15	3,55	4,00	4,50	5,00	5,60
	Corner radius (0,5 mm*)																	
2,00	1,463	1,626	1,785	2,025	2,285	2,585												
2,24	1,655	1,842	2,205	2,294	2,582	2,921	3,369											
2,50	1,863	2,076	2,285	2,585	2,910	3,285	3,785	4,137										
2,80	2,103	2,346	2,585	2,921	3,285	3,705	4,265	4,677	5,237									
3,15	2,383	2,661	2,935	3,313	3,723	4,195	4,825	5,307	5,937	6,693								
3,55	2,703	3,021	3,335	3,761	4,223	4,755	5,465	6,027	6,737	7,589	8,326							
4,00	3,063	3,426	3,785	4,265	4,785	5,385	6,185	6,831	7,637	8,597	9,451	10,65						
4,50	3,463	3,876	4,285	4,825	5,410	6,085	6,85	7,737	8,631	9,717	10,70	12,05	13,63					
5,00	3,863	4,326	4,785	5,385	6,035	6,785	7,785	8,637	9,637	10,84	12,18	13,45	15,20	17,20				
5,60	4,363	4,866	5,385	6,057	6,785	7,625	8,745	9,717	10,84	12,18	13,45	15,13	17,09	19,33	21,54			
6,30	4,903	5,496	6,085	6,841	7,660	8,605	9,865	10,98	12,24	13,75	15,20	17,09	19,30	21,82	24,34	27,49		
7,10		6,216	6,885	7,737	8,660	9,725	11,15	12,42	13,84	15,54	17,20	19,33	21,82	24,66	27,54	31,09	34,64	
8,00			7,785	8,745	9,785	10,99	12,59	14,04	15,64	17,56	19,45	21,85	24,65	27,85	31,14	35,14	39,14	43,94
9,00				9,865	11,04	12,39	14,19	15,84	17,64	19,80	21,95	24,65	27,80	31,40	35,14	39,64	44,14	49,54
10,0					12,29	13,79	15,79	17,64	19,64	22,04	24,45	27,45	30,95	34,95	39,14	44,14	49,14	55,14
11,2						15,47	17,71	19,80	22,04	24,79	27,46	30,81	34,73	39,21	43,94	49,54	55,14	61,86
12,5							19,79	22,14	24,64	27,64	30,70	34,45	38,83	43,83	49,14	55,39	61,64	69,14
14,0								24,84	27,64	31,00	34,45	38,65	43,55	49,15	55,14	62,14	69,14	77,54
16,0									31,64	35,48	39,45	44,25	49,85	56,25	63,14	71,14	79,14	88,74

* Nominal thickness

Not recommended
Ratio width-thickness smaller than 1,4:1Not recommended
Ratio width-thickness over 8:1

Table 3 – Corner radii

Nominal thickness of conductor mm		Corner radius ± mm
Over	Up to and including	
–	1,00	0,50 nominal thickness
1,00	1,60	0,50*
1,60	2,24	0,65**
2,24	3,55	0,80
3,55	5,60	1,00

NOTE If agreed between purchaser and supplier, the corner radii for wires with a width greater than 4,8 mm may be:

* 0,50 nominal thickness

** 0,80 mm

4.4 Increase in dimensions due to the insulation

The increase in width or thickness due to the insulation shall be as given in Table 4.

Table 4 – Increases in dimensions

Grade	Increase in dimensions mm		
	Minimum	Nominal	Maximum
1	0,06	0,085	0,11
2	0,12	0,145	0,17

4.5 Overall dimensions

4.5.1 Nominal overall dimensions

The nominal overall dimensions shall be calculated as the sum of the nominal bare conductor and the nominal increase in dimension due to the insulation.

4.5.2 Minimum overall dimensions

The minimum overall dimensions shall be calculated as the sum of the minimum bare conductor and the minimum increase in dimension due to the insulation. See also note under 4.5.3.

4.5.3 Maximum overall dimensions

The maximum overall dimensions shall be calculated as the sum of the maximum bare conductor and the maximum increase in dimension due to the insulation.

NOTE When agreed between purchaser and supplier, special tolerances for grade 2 as given in Annex B have been established to calculate special maximum and minimum dimensions.

5 Electrical resistance

The resistance of the wire shall be expressed as the d.c. resistance at 20 °C. The method used shall provide an accuracy of 0,5 %.

The maximum value of resistance shall be not greater than the value calculated for the minimum tolerated cross-sectional area of the conductor resulting from the minimum dimensions in thickness and width and the maximum for the corner radius, and with a resistivity of 1/35,85 (0,027 894) $\Omega \cdot \text{mm}^2 \cdot \text{m}^{-1}$.

One measurement shall be made.

6 Elongation

The minimum elongation at fracture shall be 15 %.

7 Springiness

Test appropriate but no requirements specified.

8 Flexibility and adherence

8.1 Mandrel winding test

The coating shall show no crack after the wire has been bent flatwise and edgewise on a mandrel with a diameter as specified in Table 5.

Table 5 – Mandrel winding

Wire bent on		Mandrel diameter
Width	Sizes up to and including 10 mm	4width
	Sizes over 10 mm	5 × width
Thickness	All sizes	4 × thickness

8.2 Adherence test

The wire shall be stretched by 15 %. The distance of loss of adhesion shall be less than one time the width.

9 Heat shock

The coating shall show no crack after the wire has been bent flatwise on a mandrel with a diameter of six times the thickness.

The minimum heat shock temperature is given in the relevant specification sheet.

10 Cut-through

Test inappropriate.

11 Resistance to abrasion

Test inappropriate.

12 Resistance to solvents

Following immersion in standard solvent, the coating shall not be removed using a pencil of hardness "H".

13 Breakdown voltage

When tested at room temperature at least four of the five specimens tested shall not break down at a voltage less than or equal to that given in Table 6, and the fifth shall not break down at less than 50 % of the values specified.

When required by the purchaser, the wire shall be tested at elevated temperature.

The elevated temperature is given in the relevant specification sheet.

Table 6 – Breakdown voltage

Grade	Minimum breakdown voltage (r.m.s.) V	
	Room temperature	Elevated temperature
1	1 000	750
2	2 000	1 500

14 Continuity of insulation

Test inappropriate.

15 Temperature index

The test shall be carried out on a rectangular wire according to IEC 60172, unless otherwise agreed between purchaser and supplier.

When required by a purchaser, the supplier of the enamelled wire shall supply evidence that the wire meets the requirements for the temperature index.

NOTE 1 The temperature index requirement based on an extrapolated life of 20 000 h relates to enamelled wires tested unvarnished and not as part of an insulation system.

NOTE 2 Temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.

16 Resistance to refrigerants

Test inappropriate.

17 Solderability

Test inappropriate.

18 Heat or solvent bonding

Test inappropriate.

19 Dielectric dissipation factor

For requirements, see the relevant specification sheet.

20 Resistance to transformer oil

For requirements, see the relevant specification sheet.

21 Loss of mass

Test inappropriate.

23 Pin hole test

Test inappropriate.

30 Packaging

The kind of packaging may influence certain properties of the wire, for example springback. Therefore the kind of packaging for example, the type of spool, shall be agreed between purchaser and supplier.

The wire shall be evenly and compactly wound on spools or placed in containers. No spool or container shall contain more than one length of wire unless agreed to by purchaser and supplier. Marking of the label when there is more than one length and/or identification of the separate lengths in the package shall be agreed to by purchaser and supplier.

Where wires are delivered in coils, the dimensions and the maximum weights of such coils shall be agreed between purchaser and supplier. Any additional protection for coils shall also be agreed between purchaser and supplier.

Labels shall be attached to each packaging unit as agreed between supplier and user and shall include the following information:

- a) manufacturer name and/or trade mark;
- b) type of wire and insulation, for instance trade name and/or IEC specification number;
- c) net mass of wire;
- d) nominal dimension(s) of wire and grade of insulation;
- e) date of manufacture.

Annex A (informative)

Nominal cross-sectional areas for preferred and intermediate sizes

Table A.1 provides nominal cross-sectional areas for preferred and intermediate sizes of rectangular aluminium bare conductors, from which the user may select intermediate sizes only for technical reasons.

Table A.1 – Nominal cross-sectional areas (1 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
2,00	0,80	*	1,463	2,50	1,25	0,5	2,910
	0,85	*	1,545		1,32	0,5	3,085
	0,90	*	1,626		1,40	0,5	3,285
	0,95	*	1,706		1,50	0,5	3,535
	1,00	*	1,785		1,60	0,5	3,785
	1,06	0,5	1,905	1,70	0,65	3,887	
	1,12	0,5	2,025	1,80	0,65	4,137	
	1,18	0,5	2,145	2,65	0,80	*	1,983
	1,25	0,5	2,285		0,90	*	2,211
	1,32	0,5	2,425		1,00	*	2,435
1,40	0,5	2,585	1,12		0,5	2,753	
1,40	0,5	2,585	1,25		0,5	3,098	
2,12	0,80	*	1,559	1,40	0,5	3,495	
	0,90	*	1,734	1,60	0,5	4,025	
	1,00	*	1,905	1,80	0,65	4,407	
	1,12	0,5	2,160	2,80	0,80	*	2,103
	1,25	0,5	2,435		0,85	*	2,225
	1,40	0,5	2,753		0,90	*	2,346
	0,80	*	1,655		0,95	*	2,466
2,24	0,85	*	1,749	1,00	*	2,585	
	0,90	*	1,842	1,06	0,5	2,753	
	0,95	*	1,934	1,12	0,5	2,921	
	1,00	*	2,025	1,18	0,5	3,089	
	1,06	0,5	2,160	1,25	0,5	3,285	
	1,12	0,5	2,294	1,32	0,5	3,481	
	1,18	0,5	2,429	1,40	0,5	3,705	
	1,25	0,5	2,585	1,50	0,5	3,985	
	1,32	0,5	2,742	1,60	0,5	4,265	
	1,40	0,5	2,921	1,70	0,65	4,397	
	1,50	0,5	3,145	1,80	0,65	4,677	
	1,60	0,5	3,369				
	2,36	0,80	*	1,751			

Table A.1 (2 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
2,50	0,90	*	1,950	3,00	1,90	0,65	4,957
	1,00	*	2,145		2,00	0,65	5,237
	1,12	0,5	2,429		0,80	*	2,263
	1,25	0,5	2,735		0,90	*	2,526
	1,40	0,5	3,089		1,00	*	2,785
	1,60	0,5	3,561		1,12	0,5	3,145
	0,80	*	1,863		1,25	0,5	3,535
	0,85	*	1,970		1,40	0,5	3,985
	0,90	*	2,076		1,60	0,5	4,585
	0,95	*	2,181		1,80	0,65	5,037
	1,00	*	2,285		2,00	0,65	5,637
	3,15	1,06	0,5		2,435	3,15	0,80
1,12		0,5	2,585	0,85	*		2,522
1,18		0,5	2,736	3,75	0,80	*	2,863
0,90		*	2,661		0,90	*	3,201
0,95		*	2,799		1,00	*	3,535
1,06		0,5	3,124		1,12	0,5	3,985
1,12		0,5	3,313		1,25	0,5	4,473
1,18		0,5	3,502		1,40	0,5	5,035
1,25		0,5	3,723		1,60	0,5	5,785
1,32		0,5	3,943		1,80	0,65	6,387
1,40		0,5	4,195		2,00	0,65	7,137
1,50		0,5	4,510		2,24	0,65	8,037
1,60	0,5	4,825	2,50		0,8	8,826	
3,35	1,70	0,65	4,992		4,00	0,80	*
	1,80	0,65	5,307	0,85		*	3,245
	1,90	0,65	5,622	0,90		*	3,426
	2,00	0,65	5,937	0,95		*	3,606
	2,12	0,65	6,315	1,00		*	3,785
	2,24	0,65	6,693	1,06		0,5	4,025
	0,80	*	2,543	1,12	0,5	4,265	
	0,90	*	2,841	1,18	0,5	4,505	
	1,00	*	3,135	1,25	0,5	4,785	
	1,12	0,5	3,537	1,32	0,5	5,065	
	1,25	0,5	3,973	1,40	0,5	5,385	
	1,40	0,5	4,475	1,50	0,5	5,785	
	1,60	0,5	5,145	1,60	0,5	6,185	
	1,80	0,65	5,667				

Table A.1 (3 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
3,55	2,00	0,65	6,337	4,25	1,70	0,65	6,437
	2,24	0,65	7,141		1,80	0,65	6,837
	0,80	*	2,703		1,90	0,65	7,237
	0,85	*	2,862		2,00	0,65	7,637
	0,90	*	3,021		2,12	0,65	8,117
	0,95	*	3,179		2,24	0,65	8,597
	1,00	*	3,335		2,36	0,8	8,891
	1,06	0,5	3,548		2,50	0,8	9,451
	1,12	0,5	3,761		2,65	0,8	10,05
	1,18	0,5	3,974		2,80	0,8	10,65
	1,25	0,5	4,223		0,80	*	3,263
	1,32	0,5	4,471		0,90	*	3,651
	1,40	0,5	4,755		1,00	*	4,035
	1,50	0,5	5,110		1,12	0,5	4,545
	1,60	0,5	5,465		1,25	0,5	5,098
	1,70	0,65	5,672		1,40	0,5	5,735
	1,80	0,65	6,027		1,60	0,5	6,585
	1,90	0,65	6,382		1,80	0,65	7,287
	2,00	0,65	6,737		2,00	0,65	8,137
	2,12	0,65	7,163		2,24	0,65	9,157
2,24	0,65	7,589	2,50	0,8	10,08		
2,36	0,8	7,829	2,80	0,8	11,35		
2,50	0,8	8,326	5,00	1,70	0,65	8,137	
0,80	*	3,463		1,80	0,65	8,637	
0,85	*	3,670		1,90	0,65	9,137	
0,90	*	3,876		2,00	0,65	9,637	
0,95	*	4,081		2,12	0,65	10,24	
1,00	*	4,285		2,24	0,65	10,84	
1,06	0,5	4,555		2,36	0,8	11,25	
1,12	0,5	4,825		2,50	0,8	11,95	
1,18	0,5	5,095		2,65	0,8	12,70	
1,25	0,5	5,410		2,80	0,8	13,45	
1,32	0,5	5,725		3,00	0,8	14,45	
1,40	0,5	6,085		3,15	0,8	15,20	
1,50	0,5	6,535		3,35	0,8	16,20	
1,60	0,5	6,985		3,55	0,8	17,20	
1,70	0,65	7,287		5,30	0,80	*	4,103
1,80	0,65	7,737			0,90	*	4,596
1,90	0,65	8,187			1,00	*	5,085
2,00	0,65	8,637					
2,12	0,65	9,177					

Table A.1 (4 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
4,75	2,24	0,65	9,717	5,60	1,12	0,5	5,721
	2,36	0,8	10,07		1,25	0,5	6,410
	2,50	0,8	10,70		1,40	0,5	7,205
	2,65	0,8	11,38		1,60	0,5	8,265
	2,80	0,8	12,05		1,80	0,65	9,177
	3,00	0,8	12,95		2,00	0,65	10,24
	3,15	0,8	13,63		2,24	0,65	11,51
	0,80	*	3,663		2,50	0,8	12,70
	0,90	*	4,101		2,80	0,8	14,29
	1,00	*	4,535		3,15	0,8	16,15
	1,12	0,5	5,105		3,55	0,8	18,27
	1,25	0,5	5,723		0,80	*	4,343
	1,40	0,5	6,435		0,85	*	4,605
	1,60	0,5	7,385		0,90	*	4,866
	1,80	0,65	8,188		0,95	*	5,126
	2,00	0,65	9,137		1,00	*	5,385
2,24	0,65	10,28	1,06	0,5	5,721		
2,50	0,8	11,33	1,12	0,5	6,057		
2,80	0,8	12,75	1,18	0,5	6,393		
3,15	0,8	14,41	1,25	0,5	6,785		
5,00	0,80	*	3,863	1,32	0,5	7,177	
	0,85	*	4,095	1,40	0,5	7,625	
	0,90	*	4,326	1,50	0,5	8,185	
	0,95	*	4,556	1,60	0,5	8,745	
	1,00	*	4,785	1,70	0,65	9,157	
	1,06	0,5	5,085	1,80	0,65	9,717	
	1,12	0,5	5,385	1,90	0,65	10,28	
	1,18	0,5	5,685	2,00	0,65	10,84	
	1,25	0,5	6,035	2,12	0,65	11,51	
	1,32	0,5	6,385	2,24	0,65	12,18	
	1,40	0,5	6,785	2,36	0,8	12,67	
	1,50	0,5	7,285	2,50	0,8	13,45	
	1,60	0,5	7,785	2,65	0,8	14,29	
	3,00	0,8	16,25	2,80	0,8	15,13	
	3,15	0,8	17,09	6,30	3,75	1,0	22,77
	3,35	0,8	18,21		4,00	1,0	24,34
3,55	0,8	19,33	4,25		1,0	25,92	
3,75	1,0	20,14	4,50		1,0	27,49	
5,60	4,00	1,0	21,54	6,70	0,90	*	5,856
					1,00	*	6,485

Table A.1 (5 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
6,00	0,80	*	4,663	7,10	1,12	0,5	7,289
	0,90	*	5,226		1,25	0,5	8,160
	1,00	*	5,785		1,40	0,5	9,165
					1,60	0,5	10,51
	1,12	0,5	6,505				
	1,25	0,5	7,285		1,80	0,65	11,70
	1,40	0,5	8,185		2,00	0,65	13,04
	1,60	0,5	9,385		2,24	0,65	14,65
	1,80	0,65	10,44		2,50	0,8	16,20
	2,00	0,65	11,64		2,80	0,8	28,21
	2,24	0,65	13,08		3,15	0,8	20,56
					3,55	0,8	23,24
	2,50	0,8	14,45				
	2,80	0,8	16,25		4,00	1,0	25,94
	3,15	0,8	18,35		4,50	1,0	29,29
	3,55	0,8	20,75				
4,00	1,0	23,14	0,90	*	6,216		
			0,95	*	6,551		
			1,00	*	6,885		
6,30	0,80	*	4,903	1,06	0,5	7,311	
	0,85	*	5,200	1,12	0,5	7,737	
	0,90	*	5,496	1,18	0,5	8,163	
	0,95	*	5,791	1,25	0,5	8,660	
	1,00	*	6,085	1,32	0,5	9,157	
				1,40	0,5	9,725	
	1,06	0,5	6,463	1,50	0,5	10,44	
	1,12	0,5	6,841	1,60	0,5	11,15	
	1,18	0,5	7,219				
	1,25	0,5	7,660	1,70	0,65	11,71	
	1,32	0,5	8,101	1,80	0,65	12,42	
	1,40	0,5	8,605	1,90	0,65	13,13	
	1,50	0,5	9,235	2,00	0,65	13,84	
	1,60	0,5	9,865	2,12	0,65	14,69	
				2,24	0,65	15,54	
	1,70	0,65	10,35				
	1,80	0,65	10,98	2,36	0,8	16,21	
	1,90	0,65	11,61	2,50	0,8	17,20	
	2,00	0,65	12,24	2,65	0,8	18,27	
	2,12	0,65	12,99	2,80	0,8	19,33	
	2,24	0,65	13,75	3,00	0,8	20,75	
			3,15	0,8	21,82		
2,36	0,8	14,32	3,35	0,8	23,24		
2,50	0,8	15,20	3,55	0,8	24,66		
2,65	0,8	16,15					
2,80	0,8	17,09	3,75	1,0	25,77		
3,00	0,8	18,35					

Table A.1 (6 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
7,10	3,15	0,8	19,30	8,50	4,00	1,0	27,54
	3,35	0,8	20,56		4,25	1,0	29,32
	3,55	0,8	21,82		1,12	0,5	9,305
	4,50	1,0	31,09		1,25	0,5	10,41
	4,75	1,0	32,87		1,40	0,5	11,69
	5,00	1,0	34,64		1,60	0,5	13,39
7,50	1,00	*	7,285		1,80	0,65	14,94
	1,12	0,5	8,185		2,00	0,65	16,64
	1,25	0,5	9,160		2,24	0,65	18,68
	1,40	0,5	10,29		2,50	0,8	20,70
	1,60	0,5	11,79		2,80	0,8	23,25
	1,80	0,65	13,14		3,15	0,8	26,23
	2,00	0,65	14,64	3,55	0,8	29,63	
	2,24	0,65	16,44	4,00	1,0	33,14	
	2,50	0,8	18,20	4,50	1,0	37,39	
	2,80	0,8	20,45	5,00	1,0	41,64	
	3,15	0,8	23,08	5,60	1,0	46,74	
	3,55	0,8	26,08	9,00	1,12	0,5	9,865
4,00	1,0	29,14	1,18		0,5	10,41	
4,50	1,0	32,89	1,25		0,5	11,04	
5,00	1,0	36,64	1,32		0,5	11,67	
8,00	1,00	*	7,785		1,40	0,5	12,39
	1,06	0,5	8,265		1,50	0,5	13,29
	1,12	0,5	8,745		1,60	0,5	14,19
	1,18	0,5	9,225		1,70	0,65	14,94
	1,25	0,5	9,785		1,80	0,65	15,84
	1,32	0,5	10,35		1,90	0,65	16,74
	1,40	0,5	10,99		2,00	0,65	17,64
	1,50	0,5	11,79		2,12	0,65	18,72
	1,60	0,5	12,59	2,24	0,65	19,80	
	1,70	0,65	13,24	2,36	0,8	20,69	
	1,80	0,65	14,04	2,50	0,8	21,95	
	1,90	0,65	14,84	2,65	0,8	23,30	
2,00	0,65	15,64	2,80	0,8	24,65		
2,12	0,65	16,60	3,00	0,8	26,45		
2,24	0,65	17,56	3,15	0,8	27,80		
2,36	0,8	18,33	3,35	0,8	29,60		
2,50	0,8	19,45	3,55	0,8	31,40		
				3,75	1,0	32,89	

Table A.1 (7 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	
mm	mm	mm	mm ²	mm	mm	mm	mm ²	
9,50	2,65	0,8	20,65	9,50	4,00	1,0	35,14	
	2,80	0,8	21,85		4,25	1,0	37,39	
	3,00	0,8	23,45		4,50	1,0	39,64	
	3,15	0,8	24,65		4,75	1,0	41,89	
	3,35	0,8	26,25		5,00	1,0	44,14	
	3,55	0,8	27,85		5,30	1,0	46,84	
					5,60	1,0	49,54	
	3,75	1,0	29,14		9,50	1,25	0,5	11,66
	4,00	1,0	31,14			1,40	0,5	13,09
	4,25	1,0	33,14			1,60	0,5	14,99
	4,50	1,0	35,14	11,20		1,80	0,65	16,74
	4,75	1,0	37,14		2,00	0,65	18,64	
	5,00	1,0	39,14		2,24	0,65	20,92	
	5,30	1,0	41,54		1,70	0,65	18,68	
	5,60	1,0	43,94		1,80	0,65	19,80	
	2,50	0,8	23,20		1,90	0,65	20,92	
	2,80	0,8	26,05		2,00	0,65	22,04	
	3,15	0,8	29,38		2,12	0,65	23,38	
	3,55	0,8	33,18		2,24	0,65	24,73	
	4,00	1,0	37,14		2,36	0,8	25,88	
4,50	1,0	41,89	2,50	0,8	27,45			
5,00	1,0	46,64	2,65	0,8	29,13			
5,60	1,0	52,34	2,80	0,8	30,81			
10,00	1,25	0,5	12,29	3,00	0,8	33,05		
	1,32	0,5	12,99	3,15	0,8	34,73		
	1,40	0,5	13,79	3,35	0,8	36,97		
	1,50	0,5	14,79	3,55	0,8	39,21		
	1,60	0,5	15,79	11,80	3,75	1,0	41,14	
	1,70	0,65	16,64		4,00	1,0	43,94	
	1,80	0,65	17,64		4,25	1,0	46,74	
	1,90	0,65	18,64		4,50	1,0	49,54	
	2,00	0,65	19,64		4,75	1,0	52,34	
	2,12	0,65	20,84		5,00	1,0	55,14	
	2,24	0,65	22,04		5,30	1,0	58,50	
	2,36	0,8	23,05		5,60	1,0	61,86	
	2,50	0,8	24,45		11,80	1,60	0,5	18,67
	2,65	0,8	25,95			1,80	0,65	20,88
	2,80	0,8	27,45	2,00		0,65	23,24	
	3,00	0,8	29,45	2,24		0,65	26,07	
	3,15	0,8	30,95	2,50		0,8	28,95	
	3,35	0,8	32,95	2,80		0,8	32,49	
	3,55	0,8	34,95					
	3,75	1,0	36,64					

Table A.1 (8 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area		
mm	mm	mm	mm ²	mm	mm	mm	mm ²		
10,60	4,00	1,0	39,14	12,50	3,15	0,8	36,62		
	4,25	1,0	41,64		3,55	0,8	41,34		
	4,50	1,0	44,14		4,00	1,0	46,34		
	4,75	1,0	46,64			1,0	52,24		
	5,00	1,0	49,14			1,0	58,14		
	5,30	1,0	52,14			1,0	65,22		
	5,60	1,0	55,14			1,60	0,5	19,79	
	1,40	0,5	14,63				0,65	20,89	
	1,60	0,5	16,75		1,80		0,65	22,14	
	1,80	0,65	18,72		1,90		0,65	23,39	
		0,65	20,84		2,00		0,65	24,64	
		0,65	23,38		2,12		0,65	26,14	
		2,50	0,8		25,95		2,24	0,65	27,64
			0,8		29,13		2,36	0,8	28,95
		3,15	0,8		32,84			0,8	30,70
		3,55	0,8		37,08			0,8	32,58
4,00		1,0	41,54	0,8	34,45				
		1,0	46,84	0,8	36,95				
		1,0	52,14	0,8	38,83				
	1,0	58,50	0,8	41,33					
	11,20	1,40	0,5	15,47	0,8	43,83			
		1,50	0,5	16,59	3,75	1,0		46,02	
1,60		0,5	17,71	1,0		49,14			
12,50	4,50	1,0	55,39	1,0		52,27			
	4,75	1,0	58,52	14,00	4,75	1,0	65,64		
	5,00	1,0	61,64		5,00	1,0	69,14		
	5,30	1,0	65,39		5,30	1,0	73,34		
	5,60	1,0	69,14		5,60	1,0	77,54		
13,20	1,80	0,65	23,40		15,00	2,00	0,65	29,64	
	2,00	0,65	26,04	2,24		0,65	33,24		
	2,24	0,65	29,21	2,50	0,8	36,95			
	2,50	0,8	32,45		0,8	41,45			
		0,8	36,41		0,8	46,70			
		0,8	41,03		0,8	52,70			
	3,15	0,8	46,31		4,00	1,0	59,14		
	4,00	1,0	51,94			1,0	66,64		
		1,0	58,54			1,0	74,14		
		1,0	65,14			1,0	83,14		

Table A.1 (9 of 9)

Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area	Nominal width	Nominal thickness	Radius on corners	Nominal cross-section area
mm	mm	mm	mm ²	mm	mm	mm	mm ²
14,00	5,60	1,0	73,06	16,00	2,00	0,65	31,64
					2,12	0,65	33,56
	1,80	0,65	24,84		2,24	0,65	35,48
	1,90	0,65	26,24				
	2,00	0,65	27,64		2,36	0,8	37,21
	2,12	0,65	29,32		2,50	0,8	39,45
	2,24	0,65	31,00		2,65	0,8	41,85
					2,80	0,8	44,25
	2,36	0,8	32,49		3,00	0,8	47,45
	2,50	0,8	34,45		3,15	0,8	49,85
	2,65	0,8	36,55		3,35	0,8	53,05
	2,80	0,8	38,65		3,55	0,8	56,25
	3,00	0,8	41,45				
	3,15	0,8	43,55		3,75	1,0	59,14
	3,35	0,8	46,35		4,00	1,0	63,14
	3,55	0,8	49,15		4,25	1,0	67,14
					4,50	1,0	71,14
	3,75	1,0	51,64		4,75	1,0	75,14
	4,00	1,0	55,14		5,00	1,0	79,14
	4,25	1,0	58,64		5,30	1,0	83,94
4,50	1,0	62,14	5,60	1,0	88,74		

* 0,5 mm nominal thickness.

Annex B (informative)

Special tolerances

Table B.1 gives the special tolerances used for measuring overall dimensions of grade 2 rectangular aluminium winding wire.

Table B.1 – Overall dimensional tolerances for grade 2

Nominal width or thickness of the conductor mm		Tolerances on nominal overall dimensions for grade 2 ± mm	
Over	Up to and including	Width	Thickness
–	2,00	–	0,03
2,00	3,15	0,06	0,03
3,15	5,60	0,06	0,05
5,60	6,30	0,06	–
6,30	12,50	0,08	–
12,50	16,00	0,10	–

Bibliography

IEC 60264 (all parts), *Packaging of winding wires*

IEC 60317 (all parts), *Specifications for particular types of winding wires*



British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™