

Specification of technical grade sulfur hexafluoride (SF₆) for use in electrical equipment —

The European Standard EN 60376:2005 has the status of a
British Standard

ICS 29.040.20; 29.130

National foreword

This British Standard is the official English language version of EN 60376:2005. It is identical with IEC 60376:2005. It supersedes BS 5207:1975 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee GEL/10, Fluids for electrotechnical applications, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 12, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 2 December 2005

© BSI 2 December 2005

EUROPEAN STANDARD

EN 60376

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2005

ICS 29.040.20; 29.130

English version

**Specification of technical grade sulfur hexafluoride (SF₆)
for use in electrical equipment
(IEC 60376:2005)**

Spécifications de la qualité technique
de l'hexafluorure de soufre (SF₆)
pour utilisation dans les appareils
électriques
(CEI 60376:2005)

Bestimmung für Schwefelhexafluorid
(SF₆) von technischem Reinheitsgrad
zur Verwendung in elektrischen
Betriebsmitteln
(IEC 60376:2005)

This European Standard was approved by CENELEC on 2005-09-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 10/620/FDIS, future edition 2 of IEC 60376, prepared by IEC TC 10, Fluids for electrotechnical applications, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 60376 on 2005-09-01.

The following dates were fixed:

- latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2006-06-01
- latest date by which the national standards conflicting with the EN have to be withdrawn (dow) 2008-09-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 60376:2005 was approved by CENELEC as a European Standard without any modification.

CONTENTS

INTRODUCTION.....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions.....	5
4 General properties of SF ₆	6
4.1 Electrical properties.....	6
4.2 Compatibility.....	7
5 Maximum acceptable impurity levels for technical grade SF ₆	7
6 Environmental, health and safety aspects.....	8
6.1 Environmental aspects.....	8
6.1.1 Introductory remarks.....	8
6.1.2 Environmental characteristics of SF ₆	8
6.1.3 Environmentally compatible use of SF ₆	9
6.2 Health and safety.....	9
6.2.1 Introduction.....	9
6.2.2 Toxicity.....	9
6.2.3 Oxygen depletion.....	9
6.2.4 Mechanical.....	9
6.2.5 Freezing.....	10
7 Handling, storage and transportation.....	10
7.1 Gas handling procedures.....	10
7.2 Gas handling.....	10
7.3 Storage.....	10
7.4 Transportation.....	10
Bibliography.....	11
Table 1 – Maximum acceptable impurity levels.....	7

INTRODUCTION

Sulfur hexafluoride, SF₆, is an essential gas for electrical equipment.

The available commercial gas contains impurities.

It is necessary to define a high purity level sulfur hexafluoride, referred to as technical grade sulfur hexafluoride.

This International Standard does not purport to address all the safety problems associated with its use. It is the responsibility of the user of the standard to establish appropriate health and safety practices and to determine the applicability of regulatory limitations prior to use (see IEC 61634).

This International Standard gives rise to sulfur hexafluoride, chemicals, and used sample containers. The disposal of these items should be carried out according to local regulations with regard to the impact on the environment. Every precaution is taken to prevent the release into the environment of sulphur hexafluoride (see IEC 61634).

SPECIFICATION OF TECHNICAL GRADE SULFUR HEXAFLUORIDE (SF₆) FOR USE IN ELECTRICAL EQUIPMENT

1 Scope

This International Standard defines the quality requirements and properties for technical grade sulfur hexafluoride (SF₆) for use in electrical equipment. It covers the properties and methods of test applicable to SF₆ when this substance is supplied for use in connection with any electrical equipment.

NOTE Throughout this standard, the term SF₆ stands for technical grade sulfur hexafluoride.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050(191), *International Electrotechnical Vocabulary (IEV) – Chapter 191: Dependability and quality of service*

IEC 60050(212), *International Electrotechnical Vocabulary (IEV) – Chapter 212: Insulating solids, liquids and gases*

IEC 60050(441), *International Electrotechnical Vocabulary (IEV) – Chapter 441: Switchgear, controlgear and fuses*

IEC 60050(826), *International Electrotechnical Vocabulary (IEV) – Chapter 826: Electrical installations*

IEC 60480, *Guidelines for the checking and treatment of sulfur hexafluoride (SF₆) taken from electrical equipment and specification for its re-use*

IEC 61634, *High-voltage switchgear and controlgear – Use and handling of sulfur hexafluoride (SF₆) in high-voltage switchgear and controlgear*

ISO 14040, *Environmental management – Life cycle assessment – Principles and framework*

3 Terms and definitions

For the purposes of this document, the terms and definitions of IEC 60050(191), IEC 60050(212), IEC 60050(441) and IEC 60050(826) apply.

Some of the more important ones are listed here for easy reference.

3.1

electrical equipment

item used for such purposes as generation, conversion, transmission, distribution or utilization of electrical energy, such as electric machines, transformers, switchgear and controlgear, measuring instruments, protective devices, wiring systems, current-using equipment

[IEV 826-16-01]

3.2

technical grade SF₆

SF₆ gas having a very low level of impurities in accordance with Table 1

3.3

container

any kind of cylinder suitable for pressurized SF₆

NOTE This general term will be used throughout the text.

4 General properties of SF₆

Sulfur hexafluoride is a compound having the formula SF₆. At normal room temperatures and pressures (20 °C and 100 kPa) [1]¹ it is gaseous and has a density of 6,07 kg/m³ (about five times the density of air). Since its critical temperature is 45,54 °C, it can be liquefied by compression [2]. The pressure/temperature/density curves are given in IEC 61634.

SF₆ is colourless, odourless and non-toxic. It is normally transported as a liquefied gas in containers

Caution Although the gas is non-toxic, it will not support life, and equipment containing sulfur hexafluoride must not be entered without adequate ventilation. Similarly, since the gas has a much greater density than air, low lying areas, e.g. trenches, may contain high concentrations of the gas and the necessary precautions shall be taken to avoid asphyxiation.

SF₆ is used in electrical equipment for the transmission and distribution of electricity (gas insulated substations, ring main units, circuit breakers, transformers, cables, etc.). It is also used for non-electric purposes, such as metallurgy, electronics, scientific equipment, etc.

4.1 Electrical properties

The gas is strongly electronegative (i.e. tends to attract free electrons). It has a unique combination of physical properties: high dielectric strength 89 V/m/Pa at 20 °C (about three times higher than air), high interruption capabilities (about ten times higher than air) and high heat transfer characteristics (about two times higher than air) [2].

It has been successfully used for current interruption and insulation in both HV power transmission and MV distribution equipment since the 1960s.

¹ Figures in square brackets refer to the bibliography.

4.2 Compatibility

Technical grade sulphur hexafluoride is chemically inert and thermally stable [2] at normal temperatures.

At temperatures up to about 180 °C the gas has a compatibility with metals used in electrical construction, similar to that of nitrogen. Operation at higher temperatures is possible, but SF₆ can decompose in these conditions, particularly in the presence of catalytic material and the by-products may be incompatible with some constructional materials. Individual cases need to be assessed separately.

5 Maximum acceptable impurity levels for technical grade SF₆

The available commercial gas contains impurities. The maximum impurity levels present in sulfur hexafluoride referred to in this standard as technical grade sulfur hexafluoride are given in Table 1. This table also lists appropriate analytical methods for the determination of impurity levels and the corresponding acceptable accuracy of measurement.

NOTE Further handling and storage of the gas and operation of equipment may introduce additional quantities of impurities. This situation is covered in IEC 60480.

Table 1 – Maximum acceptable impurity levels

Content	Specification	Analytical methods (for indication only, not exhaustive)	Precision
Air	2 g/kg [note 1]	Infrared absorption method	35 mg/kg
		Gas-chromatographic method	3 – 10 mg/kg
		Density method	10 mg/kg
CF ₄	2 400 mg/kg [note 2]	Gas-chromatographic method	9 mg/kg
H ₂ O	25 mg/kg [note 3]	Gravimetric method	0,5 mg/kg[note 5]
		Electrolytic method	2 – 15 mg/kg
		Dew point method	1 °C
Mineral oil	10 mg/kg	Photometric method	< 2 mg/kg
		Gravimetric method	0,5 mg/kg [note 5]
Total acidity expressed in HF	1 mg/kg [note 4]	Titration	0,2 mg/kg
NOTE 1 2 g/kg is equivalent to 1 % vol under ambient conditions (100 kPa and 20 °C [1]). NOTE 2 2 400 mg/kg is equivalent to 4 000 µl/l under ambient conditions (100 kPa and 20 °C [1]). NOTE 3 25 mg/kg (25 mg/kg) is equivalent to 200 µl/l and to a dew point of -36 °C, measured at ambient conditions (100 kPa and 20 °C [1]). NOTE 4 1 mg/kg is equivalent to 7,3 µl/l under ambient conditions (100 kPa and 20 °C [1]). NOTE 5 Depending on the sample size.			

Due to the maximum impurity levels that can be present in SF₆, the SF₆ amount in a container (measured in the liquid phase), shall be higher than 99,7 % in weight. There exist other methods giving this value, without separating the different impurities that cannot be considered as analytical methods (e.g. the measurement of the speed of sound).

6 Environmental, health and safety aspects

6.1 Environmental aspects

6.1.1 Introductory remarks

Human activities have an effect on the environment. The impact of a given activity depends on its scale and on the materials involved. SF₆ has certain environmental characteristics as described below. Due to these characteristics, SF₆ has to be used avoiding any deliberate release into the atmosphere, and in an environmentally compatible way.

Nevertheless the real impact of SF₆ used in electrical equipment shall be considered by taking into account the entire functionality of the electrical equipment, i.e. the full power system environmental load. This can be evaluated via life cycle assessment (see ISO 14040).

6.1.2 Environmental characteristics of SF₆

6.1.2.1 Impact on the ecosystem

SF₆ is an inert gas. As its solubility in water is very low, it presents no danger to surface and ground water or the soil. A biological accumulation in the nutrition cycle does not occur.

6.1.2.2 Ozone depletion

SF₆ does not contribute to the destruction of stratospheric ozone.

6.1.2.3 Greenhouse effect

SF₆ persists in the atmosphere for a long time and has a high global warming potential (GWP). The values reported are dependent on the evaluation methods. It is recommended that reference be made to IPCC (International panel for climate change) updated documents.

Due to these characteristics, SF₆ has to be used in a way so as to avoid any deliberate release into the atmosphere, and in an environmentally compatible way, during the development, designing, production, filling and refilling, servicing, maintenance, recovering and end of life.

However, the GWP of SF₆ alone is not adequate to measure the environmental impact of electric power equipment based on SF₆ technology. The environmental impact has to be evaluated from the global point of view, accounting for all components as well as the system design solutions (ISO 14040).

6.1.2.4 End of life of SF₆

At its end of life (i.e. when it is no longer technically and economically recyclable), SF₆ can be destroyed by incineration in compliance with local regulations.

6.1.3 Environmentally compatible use of SF₆

6.1.3.1 Handling

Proper handling procedures shall be defined and implemented to limit any release of SF₆ into the environment wherever possible (see IEC 61634).

6.1.3.2 Tightness of the equipment

Gas tightness of equipment shall be proven according to the relevant IEC product standards.

6.1.3.3 Reclaiming/recycling

Reclaiming and recycling of sulfur hexafluoride shall be carried out according to IEC 60480 and IEC 61634.

6.1.3.4 End of life of equipment

Refer to IEC 61634 (Clause 6).

6.2 Health and safety

6.2.1 Introductory remark

SF₆ is odourless, tasteless, colourless and non-toxic. It is chemically stable at room temperature and is non-flammable.

A material safety data sheet (MSDS) shall be provided by the supplier.

6.2.2 Toxicity

It is the supplier's responsibility to guarantee that the SF₆ supplied is non-toxic, taking into account the local regulations and state-of-the-art knowledge.

6.2.3 Oxygen depletion

SF₆ gas is about five times heavier than air and, if released in large quantities into the working environment may accumulate in low-lying areas. In doing so the air is displaced and consequently, the quantity of available oxygen will fall.

If the oxygen concentration falls below 16 % (IEC 61634), a danger of asphyxiation will exist for any personnel working in these areas. Particularly sensitive areas are those below ground level, poorly or not ventilated, such as cable ducts, trenches, inspection pits and drainage systems.

However, after a period of time, depending upon air movement and ventilation, the SF₆ will become mixed with the working environment air and its local concentration will fall to acceptable levels.

6.2.4 Mechanical

In many electrical applications the pressure of SF₆ gas employed is above atmospheric pressure. This implies that special precautions have to be taken when handling the equipment, to avoid exposing workers to the risks associated with mechanical failure. Local safety regulation of pressure vessels shall be applied.

6.2.5 Freezing

If compressed SF₆ is released rapidly, the sudden expansion reduces its temperature. The gas temperature may fall to well below 0 °C. A worker accidentally subjected to a jet of gas during equipment filling, for example, runs a risk of serious freezing burns, if he is not equipped with protective clothing such as overalls, boots and gloves as well as goggles for eye protection.

7 Handling, storage and transportation

7.1 Gas handling procedures

The need to handle SF₆ arises when

- a) the gas is introduced in an electrical equipment,
- b) the gas pressure is topped up in closed pressure systems,
- c) a sample is taken for analysis.

When the gas has to be removed from an enclosure, a proper handling procedure shall be defined and implemented to limit any release of SF₆ into the environment wherever possible (see IEC 61634).

7.2 Gas handling

A particular care shall be paid to prevent contamination of SF₆ when it is transferred to the electrical equipment.

7.3 Storage

Containers are used for storage and transportation of the SF₆. It is the responsibility of the supplier to provide gas in the appropriate containers, according to local regulations and international transport regulations.

Nevertheless, containers shall have valves properly protected. The mass of sulfur hexafluoride (in kg) has to be stated on each cylinder.

Gas containers shall be stored in cool and well ventilated areas. Attention shall be paid to the filling factor of the containers, taking into account their design pressure and the maximum ambient temperature to which they will be subjected.

7.4 Transportation

Transport of SF₆ shall be carried out in accordance with national and international regulations. Nevertheless it is recommended to legibly mark the containers at the valve end and preferably on the cylindrical part of the body.

Specific labelling of containers shall be effected in accordance with the mode of transport and the national and international regulations.

Bibliography

- [1] Gas encyclopaedia, Elsevier editor, pp. 7, 8
 - [2] Gmelin handbook of inorganic chemistry, 8th Edition, Behrendt *et al.*, Springer-verlag Berlin 1978
 - [3] IEC 60694, *Common specifications for high-voltage switchgear and controlgear standards*
 - [4] ISO 14050:2002, *Environmental management – Vocabulary*
-

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE Where an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050-191	- ¹⁾	International Electrotechnical Vocabulary (IEV) Chapter 191: Dependability and quality of service	-	-
IEC 60050-212	- ¹⁾	Chapter 212: Insulating solids, liquids and gases	-	-
IEC 60050-441	- ¹⁾	Chapter 441: Switchgear, controlgear and fuses	-	-
IEC 60050-826	- ¹⁾	Chapter 826: Electrical installations	-	-
IEC 60480	- ¹⁾	Guidelines for the checking and treatment of sulphur hexafluoride (SF ₆) taken from electrical equipment and specification for its re-use	EN 60480	2004 ²⁾
IEC/TS 61634	- ¹⁾	High-voltage switchgear and controlgear – Use and handling of sulfur hexafluoride (SF ₆) in high-voltage switchgear and controlgear	-	-
ISO 14040	- ¹⁾	Environmental management - Life cycle assessment - Principles and framework	-	-

1) Undated reference.

2) Valid edition at date of issue.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.