

BS EN 60811-509:2012



BSI Standards Publication

Electric and optical fibre cables — Test methods for non-metallic materials

Part 509: Mechanical tests — Test for resistance of insulations and sheaths to cracking (heat shock test)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 60811-509:2012. It is identical to IEC 60811-509:2012.

In the UK, the relationship between the supersessions of BS EN 60811 series can be summarized as follows.

BS EN 60811-100 together with	Supersedes -
-201, -202, -203, -501	BS EN 60811-1-1:1995
-301, -302, -411, -601, -602, -603, -604	BS EN 60811-5-1:2000
-401, -412	BS EN 60811-1-2:1995
-402, -502, -503, -606	BS EN 60811-1-3:1995
-403, -404, -507	BS EN 60811-2-1:1998
-405, -409	BS EN 60811-3-2:1995
-406, -511, -605, -607	BS EN 60811-4-1:2004
-407, -408, -410, -510, -512, -513	BS EN 60811-4-2:2004
-504, -505, -506	BS EN 60811-1-4:1995
-508, -509	BS EN 60811-3-1:1995

Superseded standards are withdrawn

The UK participation in its preparation was entrusted by Technical Committee GEL/20, Electric cables, to Subcommittee GEL/20/17, Electric Cables - Low voltage.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

Published by BSI Standards Limited 2012

ISBN 978 0 580 65333 9

ICS 29.035.01; 29.060.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2012.

Amendments issued since publication

Amd. No.	Date	Text affected
<hr/>		

English version

**Electric and optical fibre cables -
Test methods for non-metallic materials -
Part 509: Mechanical tests -
Test for resistance of insulations and sheaths to cracking
(heat shock test)
(IEC 60811-509:2012)**

Câbles électriques et à fibres optiques -
Méthodes d'essai pour les matériaux
non-métalliques -
Partie 509: Essais mécaniques -
Essai de résistance à la fissuration
des enveloppes isolantes et des gaines
(essai de choc thermique)
(CEI 60811-509:2012)

Kabel, isolierte Leitungen
und Glasfaserkabel -
Prüfverfahren für nichtmetallene
Werkstoffe -
Teil 509: Mechanische Prüfungen -
Prüfung der Rissbeständigkeit
von Isolierhüllen und Mänteln
(IEC 60811-509:2012)

This European Standard was approved by CENELEC on 2012-04-17. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of document 20/1305/FDIS, future edition 1 of IEC 60811-509, prepared by IEC/TC 20 "Electric cables" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60811-509:2012.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2013-01-17
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2015-04-17

This document supersedes Clause 9 of EN 60811-3-1:1995 + A1:1996 + A2:2001 (partially). Full details of the replacements are shown in Annex A of EN 60811-100:2012.

There are no specific technical changes with respect to EN 60811-3-1:1995, but see the Foreword to EN 60811-100:2012.

This standard is to be read in conjunction with EN 60811-100.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

This standard covers the Principle Elements of the Safety Objectives for Electrical Equipment Designed for Use within Certain Voltage Limits (LVD - 2006/95/EC).

Endorsement notice

The text of the International Standard IEC 60811-509:2012 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following note has to be added for the standard indicated :

IEC 60811-3-1:1985 NOTE Harmonized as EN 60811-3-1:1995 (not modified).

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60811-100	2012	Electric and optical fibre cables - Test methods for non-metallic materials - Part 100: General	EN 60811-100	2012

CONTENTS

INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Test method	6
4.1 General	6
4.2 Apparatus.....	6
4.3 Sample and test piece preparation for insulations.....	7
4.3.1 General	7
4.3.2 Procedure.....	7
4.3.3 Expression of results	8
4.4 Sample and test piece preparation for sheaths	8
4.4.1 General	8
4.4.2 Procedure.....	8
4.4.3 Measurements.....	9
4.4.4 Expression of the results	9
5 Test report.....	9
Annex A (informative) Recommended performance requirement	10
Bibliography.....	11

Table 1 – Diameter of mandrel and number of turns for cores with overall diameter not exceeding 12,5 mm..... 7

Table 2 – Diameter of mandrel and number of turns for cores with overall diameter exceeding 12,5 mm..... 8

INTRODUCTION

The IEC 60811 series specifies the test methods to be used for testing non-metallic materials of all types of cables. These test methods are intended to be referenced in standards for cable construction and for cable materials.

NOTE 1 Non-metallic materials are typically used for insulating, sheathing, bedding, filling or taping within cables.

NOTE 2 These test methods are accepted as basic and fundamental and have been developed and used over many years principally for the materials in all energy cables. They have also been widely accepted and used for other cables, in particular optical fibre cables, communication and control cables and cables for ships and offshore applications.

ELECTRIC AND OPTICAL FIBRE CABLES – TEST METHODS FOR NON-METALLIC MATERIALS –

Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)

1 Scope

This Part 509 of IEC 60811 gives the procedure for the test for resistance of insulations and sheaths to cracking at an elevated temperature.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60811-100:2012, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 100: General*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60811-100 apply.

4 Test method

4.1 General

This part of IEC 60811 shall be used in conjunction with IEC 60811-100.

All the tests shall be carried out not less than 16 h after the extrusion of the insulating or sheathing compounds

Unless otherwise specified, tests shall be carried out at room temperature.

NOTE In the absence of any requirement in the relevant cable standard, Annex A in this standard gives a recommendation for the test conditions and test requirements.

4.2 Apparatus

The apparatus consists of the following parts:

- a) an air oven capable of maintaining the temperature and tolerance specified;
- b) mandrels of sufficient length made of metal or other suitable material.

4.3 Sample and test piece preparation for insulations

4.3.1 General

Each core to be tested shall be represented by two samples of suitable length taken from two places separated by at least 1 m. External coverings, if any, shall be removed from the insulation.

The test pieces shall be prepared in one of the three following ways:

- a) For cores with an overall diameter not exceeding 12,5 mm, each test piece shall consist of a piece of core.
- b) For cores with an overall diameter exceeding 12,5 mm and having an insulation thickness not exceeding 5 mm, and for all sector-shaped cores, each test piece shall consist of a strip taken from the insulation whose width shall be at least 1,5 times its thickness, but not less than 4 mm. The strip shall be cut in the direction of the axis of the conductor. In the case of sector-shaped cores, it shall be cut out of the “back” of the core.
- c) For cores with an overall diameter exceeding 12,5 mm and a wall thickness exceeding 5,0 mm, each test piece shall consist of a strip cut in accordance with item b) and then ground or cut (avoiding heating) on the outer surface, to a thickness between 4,0 mm and 5,0 mm. This thickness shall be measured on the thicker part of the strip, whose width shall be at least 1,5 times the thickness.

4.3.2 Procedure

Each test piece shall be tautly wound and fixed, at ambient temperature, on a mandrel to form a close helix, as given below:

- a) For test pieces prepared in accordance with 4.3.1 a), and for flat cables, the diameter of the mandrel and the number of turns shall be as given below in Table 1. The mandrel diameter shall be based on the minor dimension of the core which is wound on with its minor axis perpendicular to the mandrel.

**Table 1 – Diameter of mandrel and number of turns
for cores with overall diameter not exceeding 12,5 mm**

External diameter of test piece mm	Mandrel diameter (maximum) mm	Number of turns
Up to and including 2,5	5	6
Over 2,5 up to and including 4,5	9	6
Over 4,5 up to and including 6,5	13	6
Over 6,5 up to and including 9,5	19	4
Over 9,5 up to and including 12,5	40	2

- b) For test pieces prepared in accordance with 4.3.1 b) and c), the diameter of the mandrel and the number of turns shall be as given below in Table 2. In this case, the inner surface of the test piece shall be in contact with the mandrel.

**Table 2 – Diameter of mandrel and number of turns
for cores with overall diameter exceeding 12,5 mm**

Thickness of test piece mm	Mandrel diameter (maximum) mm	Number of turns
Up to and including 1	2	6
Over 1 up to and including 2	4	6
Over 2 up to and including 3	6	6
Over 3 up to and including 4	8	4
Over 4 up to and including 5	10	2

For the application of Tables 1 and 2, the diameter or thickness of each test piece shall be measured by means of callipers or any other suitable measuring instrument.

Each test piece, on its mandrel, shall be placed in the oven, pre-heated to the temperature specified in the relevant cable standard or, if no other is specified in the cable standard, to that given in Annex A of this standard.

The test pieces shall be removed from the oven and allowed to attain approximately ambient temperature. They shall then be examined while still on the mandrel.

4.3.3 Expression of results

The test pieces shall show no cracks when examined with normal or corrected vision without magnification. Cracks at the fixing points shall not be recorded as a fault.

A crack is considered to be a crack if it goes through the whole insulation and/or sample thickness.

4.4 Sample and test piece preparation for sheaths

4.4.1 General

Each sheath to be tested shall be represented by two samples of cable of suitable length taken from two places, separated by at least 1 m. Any external coverings shall be removed.

- a) For sheaths with an overall diameter not exceeding 12,5 mm, each test piece shall consist of a piece of cable, except for polyethylene-insulated PVC sheathed cables.
- b) For sheaths with an overall diameter exceeding 12,5 mm and with a wall thickness not exceeding 5,0 mm, and for sheaths of polyethylene-insulated cables, each test piece shall consist of a strip taken from the sheath, whose width shall be at least 1,5 times its thickness but not less than 4 mm; the strip shall be cut in the direction of the axis of the cable.
- c) For sheaths with an overall diameter exceeding 12,5 mm and a wall thickness exceeding 5,0 mm, each test piece shall consist of a strip cut in accordance with item b) and then ground or cut (avoiding heating) on the outer surface, to a thickness between 4,0 mm and 5,0 mm. This thickness shall be measured on the thicker part of the strip, whose width shall be at least 1,5 times the thickness.
- d) For flat cables, if the width of the cable does not exceed 12,5 mm, each test piece shall be a piece of complete cable. If the width of the cable exceeds 12,5 mm, each test piece shall consist of a strip taken from the sheath as specified in item b).

4.4.2 Procedure

Each test piece shall be tautly wound and fixed, at ambient temperature, on a mandrel to form a close helix, as given below:

- a) For test pieces prepared in accordance with 4.3.1 a), and flat cables of width not exceeding 12,5 mm in accordance with 4.4.1 d), the diameter of the mandrel and the number of turns shall be as given in 4.4.1 a). The mandrel diameter shall be based on the minor dimensions of the cable which is wound on with its minor axis perpendicular to the mandrel.
- b) For test pieces prepared in accordance with 4.3.1 b) and c), and flat cables wider than 12,5 mm in accordance with 4.4.1 d), the diameter of the mandrel and the number of turns shall be as given in 4.4.1 b). In this case, the inner surface of the test piece shall be in contact with the mandrel.

The diameter or thickness of each test piece shall be measured by means of calipers or any other suitable measuring instrument.

4.4.3 Measurements

In accordance with 4.3.2 of this standard.

A crack is considered to be a crack if it goes through the whole sheath and/or sample thickness.

4.4.4 Expression of the results

In accordance with 4.3.3 of this standard.

5 Test report

The test report shall be in accordance with that given in IEC 60811-100.

Annex A (informative)

Recommended performance requirement

The performance requirements for a particular type or class of insulated conductor or cable should preferably be given in the individual cable standard.

In the absence of any given requirement, it is recommended that the following values are adopted for any cable tested against this standard:

- test temperature: (150 ± 3) °C
- test time: 1 h
- requirement: no cracks going through the sample of the insulation or sheath.

Bibliography

IEC 60811-3-1:1985, *Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section One – Pressure test at high temperature – Tests for resistance to cracking*
(withdrawn)

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



...making excellence a habit.™