BS EN 60819-3-3:2011

BSI Standards Publication

Non-cellulosic papers for electrical purposes

Part 3: Specifications for individual materials — Sheet 3: Unifilled aramid (aromatic polyamide) papers

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN 60819-3-3:2011. It is identical to IEC 60819-3-3:2011. It supersedes BS EN 60819-3-3:2006, which will be withdrawn on 18 October 2014.

The UK participation in its preparation was entrusted by Technical Committee GEL/15, Solid electrical insulating materials, to Subcommittee GEL/15/10, Combined flexible materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Published by BSI Standards Limited 2012

ISBN 978 0 580 65891 4

ICS 29.035.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2012.

Amendments issued since publication

Date	Text affected

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN 60819-3-3

October 2011

ICS 29.035.10

Supersedes EN 60819-3-3:2006

English version

Non-cellulosic papers for electrical purposes - Part 3: Specifications for individual materials - Sheet 3: Unfilled aramid (aromatic polyamide) papers

(IEC 60819-3-3:2011)

Papiers non cellulosiques pour usages électriques -
Partie 3: Spécifications pour matériaux particuliers -
Feuille 3: Papiers en aramide non chargé (polyamide aromatique)
(CEI 60819-3-3:2011)

Zellulosefreie Papiere für elektrotechnische Zwecke -
Teil 3: Bestimmungen für einzelne Materialien -
Blatt 3: Ungefüllte Aramid-(aromatische Polyamid-)Papiere
(IEC 60819-3-3:2011)

This European Standard was approved by CENELEC on 2011-10-18. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of document 15/619/CDV, future edition 3 of IEC 60819-3-3, prepared by IEC TC 15, "Solid electrical insulating materials", was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60819-3-3:2011.

The following dates are fixed:

• latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement	(dop)	2012-07-18
• latest date by which the national standards conflicting with the document have to be withdrawn	(dow)	2014-10-18

This document supersedes EN 60819-3-3:2006.

EN 60819-3-3:2011 includes the following significant technical changes with respect to EN 60819-3-3:2006:

– normative references change: all the requirements are now determined according the clauses of test methods from EN 60819-2 specific for non cellulosic papers, instead of EN 60554-2:2002 generally valid for cellulosic papers;

– some new, very thin thicknesses, of type 4, calendered paper with lower density for laminating, were added.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 60819-3-3:2011 was approved by CENELEC as a European Standard without any modification.

Annex ZA
(normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

Publication	Year	Title	EN/HD	Year
IEC 60819-1	-	Non-cellulosic papers for electrical purposes - Part 1: Definitions and general requirements	EN 60819-1	-
IEC 60819-2	2001	Non-cellulosic papers for electrical purposes - Part 2: Methods of test	EN 60819-2	2001
ISO 186	2002	Paper and board - Sampling to determine average quality	EN ISO 186	2002

INTRODUCTION

This International Standard is one of a series which deals with non-cellulosic papers for electrical purposes.

The series consists of three parts:

– Part 1: Definitions and general requirements (IEC 60819-1).
– Part 2: Methods of test (IEC 60819-2).
– Part 3: Specifications for individual materials (IEC 60819-3).

This standard is one of the sheets comprising Part 3:

Sheet 3: Unfilled aramid (aromatic polyamide) papers

NON-CELLULOSIC PAPERS FOR ELECTRICAL PURPOSES –

Part 3: Specifications for individual materials – Sheet 3: Unfilled aramid (aromatic polyamide) papers

1 Scope

This sheet of IEC 60819-3 specifies requirements for four types of unfilled aramid papers:

Type 1: calendered paper;

Type 2: calendered paper, with improved tearing resistance and conformability;

Type 3: uncalendered paper;

Type 4: calendered paper, with lower density for laminating.

Materials which conform to this specification meet established levels of performance. However, the selection of material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

SAFETY WARNING: It is the responsibility of the user of the methods contained or referred to in this document to ensure that they are used in a safe manner.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60819-1, *Non-cellulosic papers for electrical purposes – Part 1: Definitions and general requirements*

IEC 60819-2: 2001, *Non-cellulosic papers for electrical purposes – Part 2: Methods of test*

IS0 186:2002, *Paper and board – Sampling to determine average quality*

3 Requirements

Papers shall satisfy the general requirements in IEC 60819-1, and shall in addition comply with the requirements specified in Table 1 of this part. In assessing conformity with the requirements in Table 1, the sampling procedures used shall be in accordance with ISO 186. In all cases, the values given in Table 1 are the central values, with the number of test pieces to be in accordance with the reference test methods.

Table 1 – Requirements

Properties	Method (see IEC 60819-2 clause/ subclause)	Units	Requirements							
Thickness	4	μm	Nominal thickness	Permissible deviation of central value from nominal value						
				Type 1		Type 2		Type 3		Type 4	
			≤50 >50	± 20 % ± 15 %		± 15 %		± 25 % ± 25 %		± 20% ± 15 %	
Grammage	5	g/m^2	Nominal thickness μm	Type 1		Type 2		Type 3		Type 4	
				Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.
			38	–	–	–	–	–	–	21	30
			50	35	46	–	–	–	–	30	44
			65	–	–	–	–	–	–	41	59
			80	45	75	–	–	–	–	52	74
			100	–	–	–	–	–	–	60	90
			130	100	130	–	–	34	47	100	130
			180	150	200	150	200	54	71	–	–
			250	220	280	220	280	71	88	–	–
			300	270	340	270	340	–	–	–	–
			380	350	430	350	430	120	140	–	–
			510	490	600	–	–	–	–	–	–
			580	–	–	–	–	180	220	–	–
			610	630	750	–	–	–	–	–	–
			760	750	880	–	–	–	–	–	–
Apparent density	4 and 5	g/cm^3	Nominal thickness μm	Type 1		Type 2		Type 3		Type 4	
				Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.
			38	–	–	–	–	–	–	0,50	0,80
			50	0,64	0,88	–	–	–	–	0,55	0,85
			65	–	–	–	–	–	–	0,56	0,87
			80	0,71	0,97	–	–	–	–	0,66	0,96
			100	–	–	–	–	–	–	0,66	0,96
			130	0,79	1,02	–	–	0,28	0,38	0,74	0,99
			180	0,87	1,09	0,85	1,07	0,28	0,38	–	–
			250	0,88	1,08	0,85	1,09	0,28	0,38	–	–
			300	0,92	1,10	0,85	1,09	–	–	–	–
			380	0,93	1,13	0,85	1,09	0,28	0,38	–	–
			510	0,97	1,17	–	–	–	–	–	–
			580			–	–	0,28	0,38	–	–
			610	1,04	1,26	–	–	–	–	–	–
			760	1,00	1,25	–	–	–	–	–	–
Minimum tensile strength	7	Width N/mm	Nominal thickness μm	Type 1		Type 2		Type 3		Type 4	
				MD	CD	MD	CD	MD	CD	MD	CD
			38	–	–	–	–	–	–	2,0	1,0
			50	2,8	1,4	–	–	–	–	2,4	1,2
			65	–	–	–	–	–	–	3,0	1,5
			80	4,7	2,2	–	–	–	–	4,6	2,2
			100	–	–	–	–	–	–	6,0	3,2
			130	9,5	5,2	–	–	1,2	0,5	9,0	4,6
			180	16,0	8,5	11,0	5,5	1,8	0,9	–	–
			250	22,0	12,0	19,0	8,5	2,0	1,0	–	–
			300	30,0	17,0	24,0	11,0	–	–	–	–
			380	36,0	22,0	27,0	14,0	3,5	1,8	–	–
			510	52,0	30,0	–	–	–	–	–	–
			580	–	–	–	–	5,3	3,0	–	–
			610	63,0	36,0	–	–	–	–	–	–
			760	79,0	47,0	–	–	–	–	–	–

Table 1 *(continued)*

	Properties	Units	Requirements							
Minimum elongation at break	7	%	Nominal thickness μm	Type 1		Type 2		Type 3		Type 4	
				MD	CD	MD	CD	MD	CD	MD	CD
			38	–	–	–	–	–	–	5	3
			50	6	5	–	–	–	–	5	3
			65	–	–	–	–	–	–	5	3
			80	7	6	–	–	–	–	6	4
			100	–	–	–	–	–	–	7	4
			130	11	9	–	–	2,5	2,5	10	6
			180	13	11	7	7	2,5	2,5	–	–
			250	13	11	11	11	2,5	2,5	–	–
			300	13	12	11	11	–	–	–	–
			380	13	12	11	11	2,5	2,5	–	–
			510	13	12	–	–	–	–	–	–
			580	–	–	–	–	2,5	2,5	–	–
			610	13	12	–	–	–	–	–	–
			760	13	10	–	–	–	–	–	–
Minimum edge tearing resistance	8 [a]	N	Nominal thickness μm	Type 1		Type 2		Type 3		Type 4	
				MD	CD	MD	CD	MD	CD	MD	CD
			38	–	–	–	–	–	–	21	8
			50	48	24	–	–	–	–	34	14
			65	–	–	–	–	–	–	37	14
			80	100	44	–	–	–	–	70	30
			100	–	–	–	–	–	–	120	40
			130	200	80	–	–	20	11	180	50
			180	300	130	320	160	36	20	–	–
			250	400	160	520	280	50	27	–	–
			300	460	180	600	300	–	–	–	–
			380	480	180	800	440	90	50	–	–
			510	520	200	–	–	–	–	–	–
			580	–	–	–	–	150	90	–	–
			610	520	240	–	–	–	–	–	–
			760	640	240	–	–	–	–	–	–
Minimum electric strength	10	kV/mm	Nominal thickness μm	Type 1		Type 2		Type 3		Type 4	
			38	–		–		–		10	
			50	15		–		–		10	
			65	–		–		–		12	
			80	18		–		–		15	
			100	–		–		–		15	
			130	21		–		9		17	
			180	27		25		9		–	
			250	27		25		9		–	
			300	27		25		–		–	
			380	25		23		9		–	
			510	25		–		–		–	
			580	–		–		9		–	
			610	23		–		–		–	
			760	21		–		–		–	

Table 1 *(continued)*

Properties	Method (see IEC 60819-2 clause/ subclause)	Units	Requirements						
Maximum shrinkage on heating	9 [b]	%	Nominal thickness μm	Type 1		Type 2		Type 3	Type 4	
				MD	CD	MD	CD		MD	CD
			38	–	–	–	–	No requirement	4,0	2,0
			50	4,0	2,0	–	–		4,0	2,0
			65	–	–	–	–		4,0	2,0
			80	3,0	2,0	–	–		3,0	2,0
			100	–	–	–	–		3,0	2,0
			130	3,0	2,0	–	–		2,0	2,0
			180	2,0	2,0	3,0	3,0		–	–
			250	2,0	2,0	3,0	3,0		–	–
			300	2,0	2,0	3,0	3,0		–	–
			380	2,0	2,0	3,0	3,0		–	–
			510	1,5	1,5	–	–		–	–
			580	–	–	–	–		–	–
			610	1,5	1,5	–	–		–	–
			760	1,5	1,5	–	–		–	–

MD = Machine direction

CD = Cross machine direction

[a] The thickness of the plate, rate of loading, and the width and thickness of the test piece shall be reported.

[b] Three test pieces 250 mm × 250 mm to be heated in an oven at 300 °C ± 5 K for 40 min to 45 min. Pieces to be suspended vertically, with damps or light weights on bottom edge to prevent curling during heating. Condition in accordance with Clause 3 of IEC 60819-2, before and after heating, and make measurements on conditioned pieces. Calculate the percentage shrinkage in each direction and report the central values.

This page deliberately left blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

Useful Contacts:

Customer Services
Tel: +44 845 086 9001
Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions
Tel: +44 845 086 9001
Email: subscriptions@bsigroup.com

Knowledge Centre
Tel: +44 20 8996 7004
Email: knowledgecentre@bsigroup.com

Copyright & Licensing
Tel: +44 20 8996 7070
Email: copyright@bsigroup.com

bsi.

...making excellence a habit.™