

BS EN 60836:2015



BSI Standards Publication

Specifications for unused silicone insulating liquids for electrotechnical purposes

bsi.

...making excellence a habit.TM

National foreword

This British Standard is the UK implementation of EN 60836:2015. It is identical to IEC 60836:2015. It supersedes BS EN 60836:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee GEL/10, Fluids for electrotechnical applications.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.

Published by BSI Standards Limited 2015

ISBN 978 0 580 80171 6

ICS 29.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2015.

Amendments/corrigenda issued since publication

| Date | Text affected |
|------|---------------|
|------|---------------|

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 60836

September 2015

ICS 29.040.10

Supersedes EN 60836:2005

English Version

**Specifications for unused silicone insulating liquids
for electrotechnical purposes
(IEC 60836:2015)**

Spécifications pour liquides isolants silicoines neufs
pour usages électrotechniques
(IEC 60836:2015)

Anforderungen an ungebrauchte Silikonisolierflüssigkeiten
für elektrotechnische Anwendungen
(IEC 60836:2015)

This European Standard was approved by CENELEC on 2015-08-20. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

The text of document 10/961/FDIS, future edition 3 of IEC 60836, prepared by IEC/TC 10 "Fluids for electrotechnical applications" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60836:2015.

The following dates are fixed:

- latest date by which the document has to be implemented at (dop) 2016-05-20 national level by publication of an identical national standard or by endorsement
- latest date by which the national standards conflicting with (dow) 2018-08-20 the document have to be withdrawn

This document supersedes EN 60836:2005.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 60836:2015 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

| | | |
|----------------|------|------------------------------|
| IEC 60076-14 | NOTE | Harmonized as EN 60076-14. |
| IEC 60695-1-40 | NOTE | Harmonized as EN 60695-1-40. |

Annex ZA
(normative)

**Normative references to international publications
with their corresponding European publications**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 When an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

| <u>Publication</u> | <u>Year</u> | <u>Title</u> | <u>EN/HD</u> | <u>Year</u> |
|--------------------|-------------|--|--------------|-------------|
| IEC 60156 | 1995 | Insulating liquids - Determination of the breakdown voltage at power frequency - Test method | EN 60156 | 1995 |
| IEC 60247 | - | Insulating liquids - Measurement of relative permittivity, dielectric dissipation factor ($\tan \delta$) and d.c. resistivity | EN 60247 | - |
| IEC 60296 | - | Fluids for electrotechnical applications - Unused mineral insulating oils for transformers and switchgear | EN 60296 | - |
| IEC 60475 | - | Method of sampling insulating liquids | EN 60475 | - |
| IEC 60628 | - | Gassing of insulating liquids under electrical stress and ionization | HD 488 S1 | - |
| IEC 60814 | - | Insulating liquids - Oil-impregnated paper and pressboard - Determination of water by automatic coulometric Karl Fischer titration | EN 60814 | - |
| IEC 60944 | - | Guide for maintenance of silicone transformer liquids | - | - |
| IEC 61039 | 2008 | Classification of insulating liquids | EN 61039 | 2008 |
| IEC 62021-3 | - | Insulating liquids - Determination of acidity - Part 3: Test methods for non-mineral insulating oils | EN 62021-3 | - |
| ISO 2211 | - | Liquid chemical products - Measurement of colour in Hazen units (platinum-cobalt scale) | - | - |
| ISO 2592 | - | Determination of flash and fire points - Cleveland open cup method | EN ISO 2592 | - |
| ISO 2719 | - | Determination of flash point - Pensky-Martens closed cup method | EN ISO 2719 | - |

EN 60836:2015

| <u>Publication</u> | <u>Year</u> | <u>Title</u> | <u>EN/HD</u> | <u>Year</u> |
|--------------------|-------------|---|--------------|-------------|
| ISO 3016 | - | Petroleum products - Determination of pour point | - | - |
| ISO 3104 | - | Petroleum products - Transparent and opaque liquids - Determination of kinematic viscosity and calculation of dynamic viscosity | EN ISO 3104 | - |
| ISO 3675 | - | Crude petroleum and liquid petroleum products - Laboratory determination of density - Hydrometer method | EN ISO 3675 | - |
| ISO 5661 | - | Petroleum products - Hydrocarbon liquids - Determination of refractive index | - | - |
| ISO 12185 | - | Crude petroleum and petroleum products - Determination of density - Oscillating U-tube method | EN ISO 12185 | - |

CONTENTS

| | |
|--|----|
| FOREWORD | 3 |
| 1 Scope | 5 |
| 2 Normative references | 5 |
| 3 Terms and definitions | 6 |
| 4 Properties | 6 |
| 4.1 General properties | 6 |
| 4.2 Properties relating to health, safety and environment (HSE) | 7 |
| 4.2.1 Handling | 7 |
| 4.2.2 Disposal | 7 |
| 5 General delivery requirements and identification | 7 |
| 6 Storage and maintenance | 7 |
| 7 Sampling | 7 |
| 8 Properties and test methods | 8 |
| 8.1 Colour and appearance | 8 |
| 8.1.1 Colour | 8 |
| 8.1.2 Appearance | 8 |
| 8.2 Density | 8 |
| 8.3 Kinematic viscosity | 8 |
| 8.4 Flash point | 8 |
| 8.5 Fire point | 8 |
| 8.6 Refractive index | 8 |
| 8.7 Pour-point | 8 |
| 8.8 Water content | 8 |
| 8.9 Acidity | 8 |
| 8.10 Breakdown voltage | 8 |
| 8.11 Dielectric dissipation factor, permittivity, d.c. resistivity | 8 |
| 8.12 Gassing under electrical stress and ionization | 8 |
| 8.13 Flammability | 9 |
| 9 Individual specifications | 9 |
| 9.1 General | 9 |
| 9.2 Silicone transformer liquid | 9 |
| 9.3 Other silicone liquids for electrotechnical purposes | 10 |
| Bibliography | 11 |
| Table 1 – Specification of silicone transformer liquid | 9 |
| Table 2 – Minimum requirements for silicone liquids | 10 |

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR UNUSED SILICONE INSULATING LIQUIDS FOR ELECTROTECHNICAL PURPOSES**FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The International Standard IEC 60836 has been prepared by IEC technical committee 10: Fluids for electrotechnical applications.

This third edition cancels and replaces the second edition published in 2005. This edition constitutes a technical revision.

This edition includes the following major technical changes with regard to the second edition:

- a) classification of liquids according to IEC 61039 have been adapted with respect to the latest edition of IEC 61039:2008;
- b) classification of liquids according to IEC 61100:1992 have been removed as IEC 61100 has been withdrawn;
- c) minimum requirements for other silicone liquids for electrotechnical purposes have been added.

The text of this standard is based on the following documents:

| FDIS | Report on voting |
|------------|------------------|
| 10/961FDIS | 10/968/RVD |

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

SPECIFICATIONS FOR UNUSED SILICONE INSULATING LIQUIDS FOR ELECTROTECHNICAL PURPOSES

1 Scope

This International Standard covers specifications and test methods for unused silicone liquids intended for use in transformers and other electrotechnical equipment.

The specified characteristics of silicone transformer liquid classified as L-NTUK-8360300 (in accordance with IEC 61039) are described in Table 1.

Besides the standard transformer applications there are other applications of silicone liquids, such like cable accessories, capacitors, electrical magnets etc. The specified characteristics and minimum requirements for these liquids are described in Table 2.

NOTE Maintenance of used silicone liquid in electrotechnical equipment is covered in a separate publication IEC 60944.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60156:1995, *Insulating liquids – Determination of the breakdown voltage at power frequency – Test method*

IEC 60247, *Insulating liquids – Measurement of relative permittivity, dielectric dissipation factor ($\tan \delta$) and d.c. resistivity*

IEC 60296, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

IEC 60475, *Method of sampling insulating liquids*

IEC 60628, *Gassing of insulating liquids under electrical stress and ionization*

IEC 60814, *Insulating liquids – Oil-impregnated paper and pressboard – Determination of water by automatic coulometric Karl Fischer titration*

IEC 60944, *Guide for the maintenance of silicone transformer liquids*

IEC 61039:2008, *Classification of insulating liquids*

IEC 62021-3, *Insulating liquids – Determination of acidity – Part 3: Test methods for non-mineral insulating oils*

ISO 2211, *Liquid chemical products – Measurement of colour in Hazen units (platinum-cobalt scale)*

ISO 2592, *Determination of flash and fire points – Cleveland open cup method*

ISO 2719, *Determination of flash point – Pensky Martens closed cup method*

ISO 3016, *Petroleum products – Determination of pour point*

ISO 3104, *Petroleum products – Transparent and opaque liquids – Determination of kinematic viscosity and calculation of dynamic viscosity*

ISO 3675, *Crude petroleum and liquid petroleum products – Laboratory determination of density – Hydrometer method*

ISO 5661, *Petroleum products – Hydrocarbon liquids – Determination of refractive index*

ISO 12185, *Crude petroleum and petroleum products – Determination of density – Oscillating U-tube method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

silicone insulating liquids

liquid organopolysiloxanes whose molecular structure consists mainly of linear chains of alternating silicon and oxygen atoms, with hydrocarbon groups attached to the silicon atoms

3.2

silicone transformer liquid

polydimethyl siloxane, without additives, primarily for use in transformers

Note 1 to entry: According to IEC 61039, this type is classified as L-NTUK-8360300.

3.3

other silicone liquids for electrotechnical purposes

polydimethyl siloxane, without additives, applied for electrotechnical purposes

Note 1 to entry: Classification of other fluids for electrotechnical purposes according to IEC 61039 shall be made in relation to their main application and their fire point, e.g. a liquid for capacitors with a fire point of less than 300 °C is classified as L-NCUO-8360300.

4 Properties

4.1 General properties

As defined in 3.2, silicone liquid for transformers has high flash and fire points and is therefore difficult to ignite. If combustion occurs, heat release rate is much lower than that of hydrocarbon oils.

In addition to use at similar working temperatures to those of transformers containing mineral transformer oil, silicone insulating liquids may also be used in appropriately designed electrotechnical equipment operating at higher temperatures.

The solubility of water in silicone liquids is greater than in mineral oils. Other physical characteristics which are important for the design of electrotechnical equipment, e.g. heat transfer, may also be different from those of mineral transformer oil and will need to be taken fully into account by the designer.

4.2 Properties relating to health, safety and environment (HSE)

4.2.1 Handling

Silicone liquids ultimately degrade in nature to simple, naturally occurring substances. Their handling is not hazardous to health.

Direct contact with the eyes may cause slight irritation. Safety glasses should be worn to avoid splashing the eyes. In the case of eye contact, irrigation with large quantities of clean running water should relieve any irritation. If irritation persists, seek medical advice.

Detailed information on safe handling of these liquids can be obtained from manufacturers or suppliers.

4.2.2 Disposal

Local regulations shall be complied with. The preferred means of disposal is recycling by a qualified contractor. Waste liquid may be incinerated. Spillages should be cleaned using adsorbent media. Small quantities of liquid entering the environment present no special hazard.

5 General delivery requirements and identification

Transport of silicone insulating liquid shall be in clean hermetically sealed containers whose lining does not interact with the contents.

Each container shall display the following information:

- number of this standard;
- supplier's designation;
- batch number;
- any notices required by local regulatory authorities.

Electrotechnical equipment filled with silicone insulating liquid should be labelled for identification with respect to the insulation used.

6 Storage and maintenance

Storage should preferably be indoors and shall be in sealed containers to prevent ingress of moisture and dirt. If accidentally contaminated by water and/or solid particles during storage, the liquid can usually be restored to acceptable quality by the procedures described in IEC 60944.

7 Sampling

The liquid shall be sampled in accordance with IEC 60475, using the procedure consistent with the density of the liquid being sampled. Isopropyl alcohol is suitable for cleaning the sampling equipment.

8 Properties and test methods

8.1 Colour and appearance

8.1.1 Colour

This property shall be measured according to ISO 2211.

8.1.2 Appearance

This property shall be evaluated by examining a representative sample of approximately 100 mm in thickness, in transmitted light and at ambient temperature.

8.2 Density

This property shall be measured at 20 °C according to ISO 3675 but measurement according to ISO 12185 is accepted as well.

8.3 Kinematic viscosity

This property shall be measured at 40 °C according to ISO 3104.

8.4 Flash point

This property shall be measured according to ISO 2719.

8.5 Fire point

This property shall be measured according to ISO 2592.

8.6 Refractive index

This property shall be measured according to ISO 5661.

8.7 Pour-point

This property shall be measured according to ISO 3016.

8.8 Water content

This property shall be measured according to IEC 60814.

8.9 Acidity

This property shall be measured according to IEC 62021-3.

8.10 Breakdown voltage

This property shall be measured according to IEC 60156 and with particular attention to IEC 60156:1995, 3.4.2.

8.11 Dielectric dissipation factor, permittivity, d.c. resistivity

These properties shall be determined at 90 °C by the methods described in IEC 60247. Isopropyl alcohol or acetone are suitable for cleaning the test cell.

8.12 Gassing under electrical stress and ionization

This property shall be measured according to IEC 60628.

8.13 Flammability

Fire hazard measurement of insulating liquids is now studied by IEC technical committee 89.

9 Individual specifications

9.1 General

The specifications given in Table 1 and Table 2 applies only to unused silicone liquids intended for use in electrotechnical equipment, as received from the supplier and before any treatment or introduction into electrotechnical equipment. The liquid sampled in accordance with Clause 7 shall be tested in accordance with the appropriate test methods given in Clause 8. The characteristics of the liquid when tested shall comply with the requirements given in Table 1 and Table 2.

9.2 Silicone transformer liquid

This liquid is polydimethyl siloxane without additives, primarily for use in transformers. According to IEC 61039, it is classified as L-NTUK-8360300.

When tested in accordance with the methods specified in Clause 8, the properties of silicone transformer liquid shall meet the requirements given in Table 1.

Table 1 – Specification of silicone transformer liquid

| Property | Test method (clause or subclause) | Permissible values | Notes |
|--|---|--|----------|
| Colour | 8.1.1 | Max.35 | |
| Appearance | 8.1.2 | Clear, free from suspended matter and sediment | |
| Density at 20 °C (kg/dm ³) | 8.2 | 0,955 to 0,970 | |
| Kinematic viscosity at 40 °C (mm ² /s) | 8.3 | 40 ± 4 | |
| Flash point (°C) | 8.4 | Min. 240 | |
| Fire point (°C) | 8.5 | Min. 340 | |
| Refractive index at 20 °C | 8.6 | 1,404 ± 0,002 | |
| Pour point (°C) | 8.7 | Max. -50 | |
| Water content (mg/kg) | 8.8 | Max. 50 | see NOTE |
| Acidity (mg KOH/g) | 8.9 | Max. 0,01 | see NOTE |
| Breakdown voltage (kV) | 8.10 | Min. 40 | see NOTE |
| Dielectric dissipation factor (DDF) at 90 °C and 50 Hz | 8.11 | Max. 0,001 | see NOTE |
| Permittivity at 90 °C | 8.11 | 2,55 ± 0,05 | see NOTE |
| DC resistivity at 90 °C (GΩ × m) | 8.11 | Min. 100 | see NOTE |
| NOTE For untreated liquid, as received. | | | |

9.3 Other silicone liquids for electrotechnical purposes

Other silicone liquids are available and may be used for electrotechnical purposes. These liquids are polydimethyl siloxanes without additives and may have either a higher or a lower viscosity than liquids as per 9.2.

When tested in accordance with the methods specified in Clause 8, the properties of these liquids shall meet the minimum requirements given in Table 2.

Table 2 – Minimum requirements for silicone liquids

| Property | Test method (clause or subclause) | Permissible values | Notes |
|--|-----------------------------------|---|----------|
| Fire point (°C) ^a | 8.5 | As a function of the target classification according to IEC 61039 | |
| Pour point (°C) | 8.7 | < -50 | |
| Water content (mg/kg) | 8.8 | Max. 50 | see NOTE |
| Acidity (mg KOH/g) | 8.9 | Max. 0,01 | see NOTE |
| Breakdown voltage (kV) | 8.10 | Min. 40 | see NOTE |
| Dielectric dissipation factor (DDF) at 90 °C and 50 Hz | 8.11 | Max. 0,001 | see NOTE |
| DC resistivity at 90 °C (GΩ × m) | 8.11 | Min. 100 | see NOTE |
| NOTE For untreated liquid, as received. | | | |
| ^a The minimum value of the fire point shall be selected as a function of the target classification according to IEC 61039. If classification "class K" is required the fire point shall be above 300 °C; fluids with a fire point of less than or equal to 300 °C shall be classified "class O"; silicone liquids with a lower viscosity exhibit a lower fire point; selection shall be made with respect to local standards and minimum requirements for the intended application of the liquid; the minimum flash point of the chosen liquid shall be in accordance with IEC 60296. | | | |

Bibliography

IEC 60076-14, *Power transformers – Part 14: Liquid-immersed power transformers using high-temperature insulation materials*

IEC 60695-1-40, *Fire hazard testing – Part 1-40: Guidance for assessing the fire hazard of electrotechnical products – Insulating liquids*

IEC TS 60695-8-3, *Fire hazard testing – Part 8-3: Heat release – Heat release of insulating liquids used in electrotechnical products*

This page deliberately left blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Rewvisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.TM