

50 g/m² nylon parachute fabric

ICS 49.025.60

Committees responsible for this British Standard

The preparation of this British Standard was entrusted to Technical Committee ACE/54, Wide fabrics and coated fabrics for aerospace purposes, upon which the following bodies were represented:

British Rubber Manufacturers' Association Ltd.

Ministry of Defence

Society of British Aerospace Companies Ltd.

Textile Finishers' Association

This British Standard, having been prepared under the direction of the Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 22 May 2002

© BSI 22 May 2002

First published February 1964
Second edition August 1978
Third edition September 1980
Fourth edition September 1990
Fifth edition May 2002

Amendments issued since publication

Amd. No.	Date	Comments

The following BSI references relate to the work on this British Standard:

Committee reference ACE/54
Draft for comment 00/706576 DC

Contents

	Page
Committees responsible	Inside front cover
Foreword	ii
<hr/>	
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General requirements	1
5 Yarn	2
6 Manufacture	3
7 Finish	3
8 Construction and properties of finished fabric	4
9 Permeability	4
10 Water extractable matter	4
11 Identification	4
<hr/>	
Annex A (informative) Information to be supplied by the purchaser	5
Annex B (normative) Heat ageing test	5
<hr/>	
Bibliography	7
<hr/>	
Table 1 — General requirements (given in BS F 100)	2
Table 2 — Yarn twist	3
Table 3 — Construction and properties of finished fabric	4
Table 4 — Permeability requirements	4
<hr/>	

Foreword

This British Standard, prepared by Technical Committee ACE/54, Wide fabrics and coated fabrics for aerospace purposes, is one of a series of specifications for textiles of a quality suitable for aerospace purposes, and is a revision of BS 4F 118:1990, which is withdrawn.

This revision updates the standard, introduces intermingled yarns and deletes the imperial units for air permeability. Quality requirements, as defined in the latest edition of BS F 100, are also included, as are details of information to be supplied by the purchaser.

NOTE The latest revision of an aerospace series standard is indicated by a prefix number.

Annex A is informative and Annex B is normative.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 7 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

1 Scope

This British Standard specifies the requirements for a range of nylon fabrics, of nominal mass per unit area of 50 g/m², for aerospace purposes, primarily for parachute canopies.

NOTE The information to be supplied by the purchaser in the contract or order should be as listed in Annex A.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

BS F 100, *Procedure for inspection and testing of textiles for aerospace purposes*.

BS EN ISO 7500-1:1999, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*.

BS EN ISO 2061:1996, *Textiles — Determination of twist in yarns — Direct counting method*.

BS EN ISO 2062:1995, *Textiles — Yarns from packages — Determination of single-end breaking force and elongation at break*.

3 Terms and definitions

For the purposes of this British Standard, the following terms and definitions apply.

3.1

heat ageing

breaking strength lost after a specified heat treatment

NOTE This is usually expressed as a percentage of the original strength.

3.2

intermingle

impart cohesion to the filament bundle of a multifilament yarn by entwining the filaments

4 General requirements

4.1 In addition to the requirements specified in Clause 4 to Clause 11 of this standard, the requirements and tests of the latest edition of BS F 100 as specified in Table 1 shall apply.

4.2 The breaking force and elongation at break of the yarn (see 5.2) shall be determined in accordance with BS EN ISO 2062:1995, Method A or B, except that the number of packages to be tested shall be a minimum of five, and the number of tests required to produce a package mean shall be five.

4.3 The yarn twist shall be determined in accordance with BS EN ISO 2061, except that the number of packages to be tested shall be a minimum of five, and the number of tests required to produce a package mean shall be five.

Table 1 — General requirements (given in BS F 100)

Section of BS F 100	Section title	Requirements and tests in BS F 100
1	General	All requirements
2	Quality requirements	Requirements for the manufacture of wide fabrics Requirements for dyed textiles Requirements for dimensions and tolerances, general and wide fabrics Requirements for freedom from corrosive impurities (see also section 4) Requirements for freedom from faults in wide fabrics
3	Physical tests	Test for the determination of the number of threads in woven fabrics Test for the determination of mass of wide fabrics Tests for breaking strength and extension under force of wide fabrics Test for tearing strength Test for air permeability of parachute fabrics
4	Chemical tests	Test for water extractable matter If required by section 2 — test for pH value of aqueous extract — test for water-soluble chloride — test for water-soluble sulfate

5 Yarn

5.1 Type

The fabric shall be woven from continuous-filament, round cross-section, high-tenacity nylon 6.6 yarn manufactured from bright, heat-resistant polymer.

5.2 Properties

5.2.1 The yarn prior to twisting shall have the following properties:

- a) a nominal linear density of 50 dtex¹⁾ and contain 15 filaments;
- b) a mean breaking force per package of not less than 260 cN, and a mean elongation at break per package not exceeding 30 %.

5.2.2 The yarn prior to twisting shall not lose more than 20 % of its original strength, when tested in accordance with the heat ageing test described in Annex B.

5.2.3 Yarn twist shall comply with the values stated in Table 2.

¹⁾ 1 tex = 10⁻⁶ kg/m.

Table 2 — Yarn twist

Fabric designation	Yarn twist turns/m	
	Warp	Weft
556	160 ± 15	Intermingled
	295 ± 30	Intermingled
854	160 ± 15	295 ± 30
	295 ± 30	160 ± 15
	295 ± 30	295 ± 30
1302	160 ± 15	Intermingled
	295 ± 30	Intermingled
1307	160 ± 15	Intermingled
	295 ± 30	Intermingled

6 Manufacture

6.1 The weave shall be plain.

6.2 In fabric 1302 a single black thread, the same count as the warp ends, shall be included in the fabric not less than 50 mm in from each finished edge, to distinguish this fabric from fabrics 556 and 854.

6.3 When fabric woven as 1302 is used to produce fabric 1307, the black identifying thread shall also be present in fabric 1307.

7 Finish

7.1 General

7.1.1 Except for fabric 1307, the fabric shall not be pressed or calendered, and shall be supplied scoured and either:

- a) undyed; or
- b) dyed (see 7.2).

7.1.2 Fabric 1307 shall be supplied scoured, calendered on both sides, and either:

- a) undyed; or
- b) dyed (see 7.2).

7.2 Dyeing

Where dyeing is required, the colour of the fabric shall be specified either by reference to a British Standard or otherwise by pattern.

NOTE An appropriate British Standard would be BS 381C:1996.

NOTE The requirement for dyed or undyed fabric should be specified by the purchaser in the contract or order (see Annex A).

7.3 Calendering

Where calendering is required, the method of calendering shall be at the discretion of the finisher provided that the finished fabric complies with Table 3 and clause 9, and has a similar appearance on both faces.

8 Construction and properties of finished fabric

8.1 When tested in accordance with 4.1, the fabric in the finished state shall comply with the requirements of Table 3.

8.2 The minimum usable width of the finished fabric shall be 920 mm unless otherwise stated by the purchaser in the contract or order (see Annex A).

NOTE The fabric may be woven in multiple widths with leno weave selvages, and slit to yield finished fabric of the minimum usable width stipulated.

Table 3 — Construction and properties of finished fabric

Designation	Minimum number of threads per centimetre ^a		Maximum mass per unit area g/m ²	Minimum average breaking strength		Minimum breaking extension		Minimum tearing strength ^b	
	Warp	Weft		N/50 mm		%		N	
				Warp	Weft	Warp	Weft	Warp	Weft
556	39.5	39.5	50	510	510	22	22	30	25
854	39.5	38.0	50	475	475	22	22	30	30
1302	41.5	41.5	52	510	510	22	22	32	27
1307	39.5	39.5	52	510	510	22	22	30	25

^a Calculated from the number of threads in a measured length of not less than 2 mm.
^b Warp tear means tearing across warp threads. Weft tear means tearing across weft threads.

9 Permeability

When tested in accordance with 4.1, each piece of finished fabric shall have a mean permeability as shown in Table 4.

NOTE It is most desirable that the mean permeability of the fabric should be as near as possible to the relevant mean figure shown in Table 4, and that the variation between the individual readings should be as low as possible.

Table 4 — Permeability requirements

Fabric	Mean permeability ^a
556	3 800 ± 800
854	7 000 ± 800
1302	2 150 ± 460
1307	760 ± 460

^a Mean permeability readings refer to $l/(m^2 \cdot s)$, i.e. volume of air in litres passing through 1 m² of fabric in 1 s at 2.5 kN/m² (25.4 cm water gauge).

10 Water extractable matter

When tested in accordance with 4.1, the amount of water extractable matter in the finished fabric shall not exceed 1.0 % by mass.

11 Identification

The fabric shall be identified for ordering purposes by the number and date of this British Standard, i.e. BS 5F 118:2002²⁾, together with the relevant designation given in Table 3 and, if required dyed, the colour.

NOTE This identification may be codified, e.g. fabric 854 required dyed olive drab may be identified as BS 5F 118:2002/854/BS 381C:1996 No. 298.

²⁾ Marking BS 5F 118:2002 on or in relation to a product represents a manufacturer's declaration of conformity, i.e. a claim by or on behalf of the manufacturer that the product meets the requirements of the standard. The accuracy of the claim is therefore solely the responsibility of the person making the claim. Such a declaration is not to be confused with third-party certification of conformity.

Annex A (informative)

Information to be supplied by the purchaser

The following information should be stated by the purchaser in the contract or order:

- a) the number of this British Standard, i.e. BS 5F 118;
- b) the fabric designation from Table 3;
- c) whether the fabric is required dyed or undyed (see Clause 7);
- d) the minimum usable width required (see Clause 8).

Annex B (normative)

Heat ageing test

B.1 Principle

Specimens of yarn are heated in an oven for a specified time and temperature. The specimens are then removed from the oven, conditioned, and the breaking strength is determined. The strength lost during treatment is expressed as a percentage of the unheated yarn breaking strength as determined from unheated comparison specimens.

B.2 Apparatus

B.2.1 *Tensile testing machine*, to BS EN ISO 7500-1:1999 (Class 1 or better) and fitted with the appropriate load cell and clamps.

B.2.2 *Laboratory oven*, of suitable size, capable of providing temperatures within the range 150 °C to 250 °C, with control of the selected temperature to ± 2 °C.

NOTE To ensure uniform temperature distribution the oven should preferably be fitted with a fan. It is important that the oven regains the set temperature within 3 min of shutting the door, without any appreciable overshoot (not greater than 2 °C).

B.2.3 *Suitable timer*.

B.2.4 *Wrap wheel*, of 1 m circumference.

B.2.5 *Heat-resistant gloves*.

B.2.6 *Means of suspending the yarn samples in the oven*, e.g. a frame or metal rod fitted with bulldog clips.

B.2.7 *Tie-on labels*.

B.3 Conditioning and testing atmosphere

Condition all samples and carry out all tests in the standard atmosphere for testing, as defined in BS F 100.

B.4 Test specimens

B.4.1 Unwrap and discard the surface layers from each package to be tested.

B.4.2 Using the wrap wheel, run off from each package sufficient yarn to carry out five tests.

B.4.3 Tie the free ends together to form a skein, release the retractable arm of the wrap wheel, and remove the skein, taking care not to damage the yarn.

B.4.4 Double the skein and attach a label noting the specimen reference.

B.4.5 Repeat **B.4.2**, **B.4.3** and **B.4.4** for the unheated samples and place in the conditioning atmosphere while the first samples are heated.

B.5 Procedure

B.5.1 Set the oven temperature to (180 ± 2) °C.

B.5.2 For the yarn that is to be heated, suspend each folded skein from a bulldog clip on the rod, or from a hook on the frame.

B.5.3 When the oven is at the required temperature, open the oven door, immediately insert the rod or hook frame and close the door.

B.5.4 Start the timer.

B.5.5 After (60 ± 1) min, put on heat-resistant gloves, open the oven door and remove the rod or frame.

B.5.6 Hang the skeins to condition in the standard atmosphere for testing defined in **B.3**. Condition for a minimum of 2 h.

B.5.7 Using one of the following sets of conditions, determine the breaking strength of the unheated and the heated specimens:

- a) gauge length of (250 ± 1) mm, a cross-head speed of 100 mm/min;
- b) gauge length of (500 ± 1) mm, a cross-head speed of 200 mm/min.

B.5.8 Record the breaking strength in newtons to the nearest 0.1 N.

B.6 Calculation and expression of results

B.6.1 Calculate the mean breaking strength for the unheated control sample and for the heated sample in newtons.

B.6.2 Calculate the percentage strength loss as follows:

$$S_L = \frac{S_u - S_h}{S_u} \times 100$$

where

- S_L is the percentage strength loss;
- S_u is the mean breaking strength of unheated sample;
- S_h is the mean breaking strength of heated sample.

B.7 Report

B.7.1 Report the percentage strength loss of the material tested to the nearest 0.1 %.

B.7.2 Report the test conditions used (see **B.5.7**).

Bibliography

Standards publication

BS 381C:1996, *Specification for colours for identification, coding and special purposes.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.