



BSI Standards Publication

AEROSPACE SERIES

Specification for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy billets, bars, forgings and parts (Ni/Co 42.5, Cr 12.5, Mo 5.8, Ti 3.0, Fe remainder)

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

raising standards worldwide[™]

Copyright British Standards Institution
Provided by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Not for Resale

Publishing and copyright information

The BSI copyright notice displayed in this document indicates when the document was last issued.

© BSI 2010

ISBN 978 0 580 67438 9

ICS 49.025.10

The following BSI references relate to the work on this standard:

Committee reference ACE/61

Draft for comment 09/30201781 DC

Publication history

First published March 1973

Second (present) edition, January 2010

Amendments issued since publication

Date	Text affected
-------------	----------------------

Contents

Foreword *ii*

1 Scope 1

2 Normative references 1

3 Technical requirements 1

Bibliography 10

List of tables

Table 1 – Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy bars for machining 2

Table 2 – Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy extruded section for subsequent forming 4

Table 3 – Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy billets and bars for forging 6

Table 4 – Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy forgings 8

Summary of pages

This document comprises a front cover, an inside front cover, pages i to ii, pages 1 to 10, an inside back cover and a back cover.

Foreword

Publishing information

This British Standard is published by BSI and came into effect on 31 January 2010. It was prepared by Panel ACE/61/-/48, *Heat resisting alloys*, under the authority of Technical Committee ACE/61, *Metallic materials for aerospace purposes*. A list of organizations represented on this committee can be obtained on request to its secretary.

Supersession

This standard supersedes BS HR 53:1973, which is withdrawn.

Information about this document

This is a full revision of BS HR 53. The principal change from the previous edition is that the requirements are stated in tabular format in accordance with EN 4500-1 and EN 4500-3.

Hazard warnings

WARNING. This British Standard calls for the use of substances and/or procedures that can be injurious to health if adequate precautions are not taken. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

Use of this document

It has been assumed in the preparation of this British Standard that the execution of its provisions will be entrusted to appropriately qualified and experienced people, for whose use it has been produced.

Presentational conventions

The provisions of this standard are presented in roman (i.e. upright) type. Its requirements are expressed in sentences in which the principal auxiliary verb is "shall".

Commentary, explanation and general informative material is presented in smaller italic type, and does not constitute a normative element.

Contractual and legal considerations

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

1 Scope

This British Standard specifies requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy supplied in the following forms, and as parts.

- a) Bars for machining: solution treated, designation HR 53A.
- b) Extruded section for subsequent forming: solution treated, designation HR 53B.
- c) Billets and bars for forging: hot or cold worked and subsequently machined or ground, designation HR 53C.
- d) Forgings: solution treated and precipitation treated, designation HR 53D.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

BS HR 100, *Procedure for inspection, testing and acceptance of wrought heat-resisting alloys*

3 Technical requirements

3.1 Material to this standard shall conform to Table 1, Table 2, Table 3 and Table 4.

NOTE The format and symbols used in Table 1, Table 2, Table 3 and Table 4 are derived from EN 4500-1 and EN 4500-3.

3.2 Parts finally heat-treated after machining shall conform to Section 1 and Section 8 of BS HR 100.

3.3 Parts shall be supplied in the solution treated and precipitation treated condition.

Table 1 Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy bars for machining

1	Material designation		BS HR 53								
2	Chemical composition %	Element	C	Si	Mn	P	S	Ag	Al	B	Bi
		Min.	0.020	—	—	—	—	—	—	0.010	—
		Max.	0.06	0.4	0.5	0.020	0.008 0	5 ppm	0.3	0.020	1 ppm
		Element	Co	Cr	Cu	Mo	Ni + Co	Pb	Ti	Fe	
		Min.	—	11.0	—	5.0	40	—	2.8	Base	
Max.	1.0	14.0	0.2	6.5	45	10 ppm	3.1				
3	Method of melting		Air melted, vacuum refined and consumable electrode melted; vacuum melted and consumable electrode melted								
4.1	Form		Bars for machining (HR 53A)								
4.2	Method of production		—								
4.3	Limit dimension(s)	mm	—								
5	Technical specification		Sections 1 and 2 of BS HR 100								

6.1	Delivery condition		Solution treated								
	Heat treatment		$\theta = (1090 \pm 10) ^\circ\text{C} / t = 3 \text{ h} / \text{AC or OQ or WQ}$								
6.2	Delivery condition code		W								
7	Use condition		Solution treated + precipitation treated								
	Heat treatment		Delivery condition + $\theta = (775 \pm 5) ^\circ\text{C} / 2 \text{ h} \leq t \leq 4 \text{ h} / \text{AC} + 705 ^\circ\text{C} \leq \theta \leq 720 ^\circ\text{C} / t = 24 \text{ h} / \text{AC}$								

Characteristics

8.1	Test sample(s)		See Section 2 of BS HR 100										
8.2	Test piece(s)		See Section 2 of BS HR 100										
8.3	Heat treatment		Delivery condition						Use condition				
9	Dimensions concerned	mm	—										
10	Thickness of cladding on each face	%	—										
11	Direction of test piece		—						L				
12	Temperature	θ	$^\circ\text{C}$	Ambient						575			
13	T	Proof stress	$R_{p0.2}$	MPa	—						≥ 690		
14		Strength	R_m	MPa	—						≥ 960		
15		Elongation	A	%	—						≥ 8		
16		Reduction of area	Z	%	—								
17	Hardness		HBW ≤ 230						HBW ≥ 341				
18	Shear strength	R_c	MPa	—									
19	Bending	κ	—	—									
20	Impact strength		—										
21	C	Temperature	θ	$^\circ\text{C}$	—						575		
22		Time	h		—						t = 100		
23		Stress	σ_a	MPa	—						590		
24		Elongation	a	%	—						Total plastic strain ≤ 0.10		
25		Rupture stress	σ_R	MPa	—								
26		Elongation at rupture	A	%	—								
27	Notes (see line 98)		—										

Table 2 Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy extruded section for subsequent forming

1	Material designation		BS HR 53								
2	Chemical composition %	Element	C	Si	Mn	P	S	Ag	Al	B	Bi
		Min.	0.020	—	—	—	—	—	—	0.010	—
		Max.	0.06	0.4	0.5	0.020	0.008 0	5 ppm	0.3	0.020	1 ppm
		Element	Co	Cr	Cu	Mo	Ni + Co	Pb	Ti	Fe	
		Min.	—	11.0	—	5.0	40	—	2.8	Base	
Max.	1.0	14.0	0.2	6.5	45	10 ppm	3.1				
3	Method of melting		Air melted, vacuum refined and consumable electrode melted; vacuum melted and consumable electrode melted								
4.1	Form		Extruded section for subsequent forming (HR 53B)								
4.2	Method of production		Extruded								
4.3	Limit dimension(s)	mm	—								
5	Technical specification		Sections 1 and 2 of BS HR 100								

6.1	Delivery condition		Solution treated								
	Heat treatment		$\theta = (1090 \pm 10) ^\circ\text{C} / t = 3 \text{ h} / \text{AC or OQ or WQ}$								
6.2	Delivery condition code		W								
7	Use condition		Delivery condition								
	Heat treatment		—								

Characteristics

8.1	Test sample(s)		See Section 2 of BS HR 100										
8.2	Test piece(s)		See Section 2 of BS HR 100										
8.3	Heat treatment		Delivery condition						Reference (see line 29)				
9	Dimensions concerned	mm	—										
10	Thickness of cladding on each face	%	—										
11	Direction of test piece		—						L				
12	T	Temperature	θ	$^\circ\text{C}$	Ambient			575					
13		Proof stress	$R_{p0.2}$	MPa	—			≥ 690					
14		Strength	R_m	MPa	—			≥ 960					
15		Elongation	A	%	—			≥ 8					
16		Reduction of area	Z	%	—								
17	Hardness		HBW ≤ 230						HBW ≥ 341				
18	Shear strength	R_c	MPa	—									
19	Bending	κ	—	—									
20	Impact strength		—										
21	C	Temperature	θ	$^\circ\text{C}$	—			575					
22		Time		h	—			t = 100					
23		Stress	σ_a	MPa	—			590					
24		Elongation	a	%	—			Total plastic strain ≤ 0.10					
25		Rupture stress	σ_R	MPa	—								
26		Elongation at rupture	A	%	—								
27	Notes (see line 98)		—										

Table 3 Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy billets and bars for forging

1	Material designation		BS HR 53								
2	Chemical composition %	Element	C	Si	Mn	P	S	Ag	Al	B	Bi
		Min.	0.020	—	—	—	—	—	—	0.010	—
		Max.	0.06	0.4	0.5	0.020	0.008 0	5 ppm	0.3	0.020	1 ppm
		Element	Co	Cr	Cu	Mo	Ni + Co	Pb	Ti	Fe	
		Min.	—	11.0	—	5.0	40	—	2.8	Base	
Max.	1.0	14.0	0.2	6.5	45	10 ppm	3.1				
3	Method of melting		Air melted, vacuum refined and consumable electrode melted; vacuum melted and consumable electrode melted								
4.1	Form		Billets and bars for forging (HR 53C)								
4.2	Method of production		—								
4.3	Limit dimension(s)	mm	—								
5	Technical specification		Sections 1 and 3 of BS HR 100								

6.1	Delivery condition		Hot or cold worked and subsequently machined or ground								
	Heat treatment		—								
6.2	Delivery condition code		F								
7	Use condition		Delivery condition								
	Heat treatment		—								

Characteristics

8.1	Test sample(s)		See Section 3 of BS HR 100										
8.2	Test piece(s)		See Section 3 of BS HR 100										
8.3	Heat treatment		Delivery condition						Reference (see line 29)				
9	Dimensions concerned	mm	—										
10	Thickness of cladding on each face	%	—										
11	Direction of test piece		—						L				
12	T	Temperature	θ	°C	—			575					
13		Proof stress	$R_{p0.2}$	MPa	—			≥ 690					
14		Strength	R_m	MPa	—			≥ 960					
15		Elongation	A	%	—			≥ 8					
16		Reduction of area	Z	%	—								
17	Hardness		—						HBW ≥ 341				
18	Shear strength	R_c	MPa	—									
19	Bending	κ	—	—									
20	Impact strength		—										
21	C	Temperature	θ	°C	—			575					
22		Time		h	—			t = 100					
23		Stress	σ_a	MPa	—			590					
24		Elongation	a	%	—			Total plastic strain ≤ 0.10					
25		Rupture stress	σ_R	MPa	—								
26		Elongation at rupture	A	%	—								
27	Notes (see line 98)		—										

Table 4 Technical requirements for nickel-iron-chromium-molybdenum-titanium heat-resisting alloy forgings

1	Material designation		BS HR 53								
2	Chemical composition %	Element	C	Si	Mn	P	S	Ag	Al	B	Bi
		Min.	0.020	—	—	—	—	—	—	0.010	—
		Max.	0.06	0.4	0.5	0.020	0.008 0	5 ppm	0.3	0.020	1 ppm
		Element	Co	Cr	Cu	Mo	Ni + Co	Pb	Ti	Fe	
		Min.	—	11.0	—	5.0	40	—	2.8	Base	
Max.	1.0	14.0	0.2	6.5	45	10 ppm	3.1				
3	Method of melting		Air melted, vacuum refined and consumable electrode melted; vacuum melted and consumable electrode melted								
4.1	Form		Forgings (HR 53D)								
4.2	Method of production		Forged from HR 53C stock								
4.3	Limit dimension(s)	mm	—								
5	Technical specification		Sections 1 and 4 of BS HR 100								
6.1	Delivery condition		Solution treated + precipitation treated								
	Heat treatment		$\theta = (1090 \pm 10)^\circ\text{C} / t = 3 \text{ h} / \text{AC or OQ or WQ} + \theta = (775 \pm 5)^\circ\text{C} / 2 \text{ h} \leq t \leq 4 \text{ h} / \text{AC} + 705^\circ\text{C} \leq \theta \leq 720^\circ\text{C} / t = 24 \text{ h} / \text{AC}$								
6.2	Delivery condition code		U								
7	Use condition		Delivery condition								
	Heat treatment		—								
Characteristics											
8.1	Test sample(s)		See Section 4 of BS HR 100								
8.2	Test piece(s)		See Section 4 of BS HR 100								
8.3	Heat treatment		Use condition								
9	Dimensions concerned	mm	—								
10	Thickness of cladding on each face	%	—								
11	Direction of test piece		L								
12	Temperature	θ	$^\circ\text{C}$	575							
13	T	Proof stress	$R_{p0.2}$	MPa	≥ 690						
14		Strength	R_m	MPa	≥ 960						
15		Elongation	A	%	≥ 8						
16		Reduction of area	Z	%	—						
17	Hardness		HBW ≥ 341								
18	Shear strength	R_c	MPa	—							
19	Bending	κ	—	—							
20	Impact strength		—								
21	C	Temperature	θ	$^\circ\text{C}$	575						
22		Time		h	$t = 100$						
23		Stress	σ_a	MPa	590						
24		Elongation	a	%	Total plastic strain ≤ 0.10						
25		Rupture stress	σ_R	MPa	—						
26		Elongation at rupture	A	%	—						
27	Notes (see line 98)		—								

Bibliography

Standards publications

For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 4500-1, *Metallic materials – Rules for the drafting and presentation of material standards – Part 1: General rules*¹⁾

EN 4500-3, *Metallic materials – Rules for the drafting and presentation of material standards – Part 3: Specific rules for heat-resisting alloys*¹⁾

¹⁾ Published as ASD-STAN Prestandard at the date of publication of this standard.

British Standards Institution (BSI)

BSI is the independent national body responsible for preparing British Standards and other standards-related publications, information and services.

It presents the UK view on standards in Europe and at the international level.

It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001

BSI offers Members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Tel: +44 (0)20 8996 7669 Fax: +44 (0)20 8996 7001

Email: plus@bsigroup.com

Buying standards

You may buy PDF and hard copy versions of standards directly using a credit card from the BSI Shop on the website www.bsigroup.com/shop. In addition all orders for BSI, international and foreign standards publications can be addressed to BSI Customer Services.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001

Email: orders@bsigroup.com

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Knowledge Centre.

Tel: +44 (0)20 8996 7004 Fax: +44 (0)20 8996 7005

Email: knowledgecentre@bsigroup.com

Various BSI electronic information services are also available which give details on all its products and services.

Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048

Email: info@bsigroup.com

BSI Subscribing Members are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.

Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001

Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at www.bsigroup.com/BSOL

Further information about BSI is available on the BSI website at www.bsigroup.com/standards

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. This does not preclude the free use, in the course of implementing the standard of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained. Details and advice can be obtained from the Copyright & Licensing Manager.

Tel: +44 (0)20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Tel +44 (0)20 8996 9001

Fax +44 (0)20 8996 7001

www.bsigroup.com/standards

raising standards worldwide™

Copyright British Standards Institution
Provided by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Not for Resale

