BS ISO 125:2011



BSI Standards Publication

Natural rubber latex concentrate — Determination of alkalinity



BS ISO 125:2011 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of ISO 125:2011. It supersedes BS ISO 125:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 74668 0

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2011.

Amendments issued since publication

Date Text affected

INTERNATIONAL STANDARD

ISO 125:2011 ISO 125

Sixth edition 2011-11-15

Natural rubber latex concentrate — Determination of alkalinity

Latex concentré de caoutchouc naturel — Détermination de l'alcalinité



BS ISO 125:2011 ISO 125:2011(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

ii

Contents Page Forewordiv 1 Scope ______1 2 3 Principle1 4 Reagents 1 5 Apparatus ______2 6 Sampling 2 7 Procedure 2 7.1 General 2 Potentiometric titration 2 7.2 7.3 Titration using a visual indicator ______2 8 Expression of results ______2 9 Precision 3 10 Test report ______3 Annex A (informative) Precision statement 4 Bibliography 5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 125 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry.*

This sixth edition cancels and replaces the fifth edition (ISO 125:2003), which has been technically revised. The main changes are the following:

- instructions have been included in Clause 4 for standardizing the HCl solution used;
- more detailed instructions have been included in Clause 7 for the titration using a visual indicator;
- the precision data have been moved to an informative annex.

Natural rubber latex concentrate — Determination of alkalinity

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies a method for the determination of the alkalinity of natural rubber latex concentrate.

The method is not necessarily suitable for latices from natural sources other than *Hevea brasiliensis* or for synthetic rubber latices, compounded latex, vulcanized latex or artificial dispersions of rubber.

NOTE A method for the determination of the alkalinity of polychloroprene latex is specified in ISO 13773 (see the Bibliography).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, Rubber latex — Sampling

ISO 976, Rubber and plastics — Polymer dispersions and rubber latices — Determination of pH

3 Principle

A test portion of latex concentrate is titrated with acid to pH 6 in the presence of a stabilizer to prevent coagulation, either electrometrically or with methyl red as a visual indicator. The alkalinity is calculated from the quantity of acid required.

4 Reagents

Distilled water or water of equivalent purity shall be used wherever water is specified.

4.1 Stabilizer solution: 5 % (by mass) solution of a non-ionic stabilizer of the alkyl phenol polyethylene oxide condensate type. Before use, the pH of the solution shall be adjusted to a value of 6.0 ± 0.05 .

The following reagents shall be of recognized analytical quality:

4.2 Sulfuric acid, $c(H_2SO_4) = 0.05 \text{ mol/dm}^3$, or hydrochloric acid, $c(HCI) = 0.1 \text{ mol/dm}^3$, standard volumetric solution.

Standardize the 0,1 mol/dm³ HCl by pipetting 10 ml of 0,05 mol/dm³ Na₂CO₃ solution (4.4) into a flask and titrating with the 0,1 mol/dm³ HCl, using methyl orange (4.5) as indicator.

4.3 Methyl red, 0,1 % solution in ethanol of minimum purity 95 % (by volume).

4.4 Sodium carbonate solution, $c(Na_2CO_3) = 0.05 \text{ mol/dm}^3$.

Dry the Na₂CO₃ used to prepare this solution at 120 °C \pm 5 °C for 2 h before preparing the solution.

4.5 Methyl orange, 0,1 % solution in ethanol of minimum purity 95 % (by volume).

5 Apparatus

Standard laboratory equipment together with:

- **5.1 Electric stirrer**, with earthed (grounded) motor and non-metallic propeller-type blade, or **magnetic stirrer**.
- **5.2 pH-meter**, equipped with a combined electrode suitable for use in solutions up to pH 12, as specified in ISO 976, and capable of being read to 0,02 pH-units.
- **5.3 Balance**, capable of being read to 0,01 g.

6 Sampling

Carry out sampling in accordance with one of the methods specified in ISO 123.

7 Procedure

7.1 General

Carry out the determination in duplicate.

To about 200 cm³ of water in a 400 cm³ beaker add, while stirring, 10 cm³ of stabilizer solution (4.1).

Weighing to the nearest 10 mg, add by difference from a weighing bottle between 5 g and 10 g of the latex concentrate and stir until thoroughly mixed.

Ensure that the latex is added so that none runs down the side of the beaker (which could result in loss of ammonia) or down the side of the weighing bottle.

Titrate the resulting mixture either by the method described in 7.2 or by that described in 7.3.

7.2 Potentiometric titration

Insert the electrode of the pH-meter and, with continual stirring, add from a burette sulfuric acid or hydrochloric acid solution (4.2), adding the acid drop by drop on approaching the end point of pH 6,0 \pm 0,05.

7.3 Titration using a visual indicator

Add 2 or 3 drops of methyl red (4.3) to the mixture and titrate with 0,1 mol/dm³ HCl (see 4.2), taking as the end point the colour change from yellow to pink.

8 Expression of results

8.1 Depending on whether the latex concentrate has been preserved with ammonia or potassium hydroxide, calculate the alkalinity as specified in 8.2 or 8.3, respectively.

8.2 If the latex concentrate is preserved with ammonia, calculate the alkalinity as the percentage (by mass) of ammonia (NH₃) in the latex concentrate, as follows:

Alkalinity (as NH₃) =
$$\frac{F_1 cV}{m}$$

where

 F_1 is a factor: 1,7 for hydrochloric acid or 3,4 for sulfuric acid;

- c is the actual concentration, expressed in moles of HCl or H₂SO₄ per cubic decimetre of acid used;
- V is the volume, in cubic centimetres, of acid used;
- *m* is the mass, in grams, of the test portion.

Report the result as the mean of the duplicate determinations. If the individual results differ by more than 0,01 units from the mean where the actual alkalinity is above 0,5 units, or by more than 0,005 units from the mean where the actual alkalinity is 0,5 units or less, repeat the determination.

8.3 If the latex is preserved with potassium hydroxide, calculate the alkalinity as the percentage (by mass) of potassium hydroxide in the latex concentrate, as follows:

Alkalinity (as KOH) =
$$\frac{F_1 cV}{m}$$

where

 F_1 is a factor: 5,61 for hydrochloric acid or 11,22 for sulfuric acid;

c, V and m are as defined in 8.2.

Report the result as the mean of the duplicate determinations. If the individual results differ by more than 0,015 units from the mean, repeat the determination.

9 Precision

See Annex A.

10 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary to identify the test sample;
- c) the mean of the determinations, and the units in which it is expressed;
- d) full details of any incident likely to have affected the result;
- e) full details of any operation not included in this International Standard or in any of the International Standards to which reference is made, together with details of any operation regarded as optional;
- f) the date of the test.

Annex A

(informative)

Precision statement

- **A.1** The precision of this method has been determined in accordance with ISO/TR 9272. Refer to ISO/TR 9272 for terminology and other statistical details.
- **A.2** The precision data are given in Table A.1. The precision parameters shall not be used for acceptance or rejection of any group of materials without documentation stating that the parameters are applicable to those particular materials and specific test protocols that include these test methods. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability r and reproducibility R.
- **A.3** The results contained in Table A.1 are average values and give an estimate of the precision of this test method as determined in an interlaboratory test programme carried out in 2001 and including 13 laboratories performing triplicate analyses on two samples A and B which were prepared from high-ammonia latex. Before the bulk was subsampled into 1 I bottles labelled A and B, it was filtered and homogenized by thorough stirring. Thus, essentially, samples A and B were the same and were treated as such in the statistical computations. Each participating laboratory was required to carry out the test, using these two samples, on the dates given to them.
- **A.4** A Type 1 precision was evaluated based on the method of preparation of the latex samples used for the interlaboratory test programme.
- **A.5** Repeatability: The repeatability r (in measurement units) of the test method has been established as the appropriate value tabulated in Table A.1. Two single test results, obtained in the same laboratory under normal test method procedures, that differ by more than the tabulated r (for any given level) shall be considered to have come from different, or non-identical, sample populations.
- **A.6** Reproducibility: The reproducibility R (in measurement units) of the test method has been established as the appropriate value tabulated in Table A.1. Two single test results, obtained in different laboratories under normal test method procedures, that differ by more than the tabulated R (for any given level) shall be considered to have come from different, or non-identical, sample populations.
- **A.7 Bias:** In test method terminology, bias is the difference between an average test value and the reference (or true) test property value.

Reference values do not exist for this test method since the value (of the test property) is exclusively defined by the test method. Bias cannot therefore be determined for this particular method.

Table A.1 — Precision data

Average results	Within-laboratory		Between laboratories	
	S_{r}	r	s_R	R
0,64	0,007	0,02	0,013	0,04

 $r = 2.83 \times s_r$

where r is the repeatability (in measurement units) and s_r is the within-laboratory standard deviation.

 $R = 2,83 \times s_R$

where R is the reproducibility (in measurement units) and s_R is the between-laboratory standard deviation.

Bibliography

- [1] ISO/TR 9272, Rubber and rubber products Determination of precision for test method standards
- [2] ISO 13773, Rubber Polychloroprene latex Determination of alkalinity



British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

