

BS ISO 334:2013



BSI Standards Publication

Solid mineral fuels — Determination of total sulfur — Eschka method

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 334:2013. It supersedes BS 1016-106.4.1:1993 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PTI/16, Solid mineral fuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 81995 7

ICS 73.040; 75.160.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2013.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
334

Third edition
2013-10-15

**Solid mineral fuels — Determination
of total sulfur — Eschka method**

*Combustibles minéraux solides — Dosage du soufre total —
Méthode Eschka*



Reference number
ISO 334:2013(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
4.1 Eschka mixture.....	1
4.2 Hydrochloric acid.....	1
4.3 Potassium sulfate solution.....	2
4.4 Barium chloride, approximately 85 g/l solution.....	2
4.5 Methyl red indicator solution.....	2
4.6 Ammonia.....	2
4.7 Silver nitrate, 17 g/l solution.....	2
5 Apparatus	2
5.1 Analytical balance.....	2
5.2 Graduated glassware.....	2
5.3 Electrically heated muffle furnace.....	2
5.4 Crucible.....	2
5.5 Flat plate.....	2
5.6 Gooch crucible.....	2
5.7 Air oven.....	2
6 Preparation of test sample	3
7 Procedure	3
7.1 Test portion.....	3
7.2 Charging the crucible.....	3
7.3 Ignition.....	4
7.4 Recovering the residue.....	4
7.5 Extraction.....	4
7.6 Precipitation of barium sulfate.....	4
7.7 Blank testing.....	5
8 Expression of results	5
9 Precision	6
9.1 Repeatability limit.....	6
9.2 Reproducibility limit.....	6
10 Test report	6
Annex A (informative) Derivation of factors used in the calculation in Clause 8	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 334:1992), of which it constitutes a minor revision.

Introduction

An alternative reference method to that specified in this International Standard is given in ISO 351:1996.

Instrumental methods for a more rapid determination of total sulfur are now available. If such a method is to be used, it is important to demonstrate that the method is free from bias, when compared to this reference method, and will give levels of repeatability and reproducibility which are the same as, or better than, those quoted for the reference method (see [Clause 9](#)).

Solid mineral fuels — Determination of total sulfur — Eschka method

1 Scope

This International Standard specifies a reference method for determining the total sulfur content of hard coal, brown coals and lignites, and coke by the Eschka method.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 687, *Solid mineral fuels — Coke — Determination of moisture in the general analysis test sample*

ISO 1170, *Coal and coke — Calculation of analyses to different bases*

ISO 5068-1, *Brown coals and lignites — Determination of moisture content — Part 1: Indirect gravimetric method for total moisture*

ISO 5069-2, *Brown coals and lignites — Principles of sampling — Part 2: Sample preparation for determination of moisture content and for general analysis*

ISO 11722, *Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen*

ISO 13909-4, *Hard coal and coke — Mechanical sampling — Part 4: Coal — Preparation of test samples*

3 Principle

A test portion is ignited in intimate contact with the Eschka mixture in an oxidizing atmosphere at 800 °C to remove combustible matter and to convert the sulfur to sulfate. This is then extracted with hydrochloric acid solution and determined gravimetrically by precipitation with barium chloride.

4 Reagents

WARNING — Care should be exercised when handling the reagents, many of which are toxic and corrosive.

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Eschka mixture

Mix two parts by mass of light calcined magnesium oxide with one part by mass of anhydrous sodium (or potassium) carbonate. The mixture shall entirely pass a test sieve of 212 µm nominal size of openings.

4.2 Hydrochloric acid

Concentrated ρ approximately 1,18 g/ml, approximately 36 % (m/m).

4.3 Potassium sulfate solution

Weigh, to the nearest 0,1 mg, about 2 g of potassium sulfate, previously dried at a temperature of 105 °C to 110 °C. Dissolve in water and dilute to 1 l.

4.4 Barium chloride, approximately 85 g/l solution

Dissolve 100 g of barium chloride dihydrate in water and dilute to 1 l. Filter before use through a close-textured, doubly acid-washed filter paper or filter-paper pad.

4.5 Methyl red indicator solution

Dissolve 1 g of 2-(4-dimethylaminophenylazo) benzoic acid sodium salt (methyl red) in 1 l of water.

4.6 Ammonia

Concentrated solution, not less than 25 % (*m/m*).

4.7 Silver nitrate, 17 g/l solution

Dissolve 17 g of silver nitrate in water and dilute to 1 l. Store in a dark, glass bottle.

5 Apparatus

5.1 Analytical balance

Capable of weighing to the nearest 0,1 mg.

5.2 Graduated glassware

Conforming to the requirements for class A in the International Standards prepared by ISO/TC 48.

5.3 Electrically heated muffle furnace

Capable of being maintained at a temperature of 800 °C ± 25 °C. The ventilation through the muffle furnace shall be such as to give about five air changes per minute.

5.4 Crucible

Of platinum, silica, or glazed porcelain, of capacity approximately 25 ml.

5.5 Flat plate

6 mm thick, of silica (or other suitable refractory material) which fits easily into the muffle furnace (5.3).

5.6 Gooch crucible

Of glazed porcelain or sintered glass.

5.7 Air oven

Capable of being maintained at a temperature of 130 °C ± 10 °C.

6 Preparation of test sample

The test sample is the general analysis test sample prepared in accordance with ISO 13909-4 or ISO 5069-2, as appropriate. Expose the sample, in a thin layer, for the minimum time required for the moisture content to reach approximate equilibrium with the laboratory atmosphere (this is particularly important for brown coals and lignites).

Before commencing the determination, thoroughly mix the test sample for at least 1 min, preferably by mechanical means.

If the results are to be calculated other than on an “air-dried” basis (see [Clause 8](#)), then, after weighing the test portion (see [7.1](#)), determine the moisture content using a further portion of the test sample by the method described in ISO 11722, ISO 687, or ISO 5068-1, as appropriate.

7 Procedure

7.1 Test portion

7.1.1 For coal

Take a test portion of the mass given in [Table 1](#) (for the expected total sulfur content), weighing to the nearest 0,1 mg.

Table 1 — Test portion for coal

Expected total sulphur content % (m/m)	Mass of test portion g
<5	1,0
5 to 10	0,5
>10	0,25

7.1.2 For coke

Take a test portion of 1 g, weighing to the nearest 0,1 mg.

7.2 Charging the crucible

Cover the bottom of the crucible ([5.4](#)) uniformly with 0,5 g of the Eschka mixture ([4.1](#)), weighed to the nearest 0,1 mg. Mix the test portion intimately with 2,5 g of the Eschka mixture, weighed to the nearest 0,1 mg, in a suitable vessel. Transfer the mixture to the 25 ml crucible. Level the contents by tapping the crucible gently on the bench and cover the contents uniformly with 1,0 g of the Eschka mixture, weighed to the nearest 0,1 mg.

The entire 4 g of the Eschka mixture should be weighed out and the 0,5 g and 1 g portions, required for the bottom and top layers, should be extracted from this. For this purpose, it is convenient to calibrate a small glass tube for each bath of the Eschka mixture to deliver 0,5 g and 1 g without weighing. The bottom layer of the Eschka mixture below the test portion mixture reduces attack on the porcelain surface so that the extraction of sulfate with hot water is complete even when the surface deteriorates.

7.3 Ignition

7.3.1 For coal

Place the charged crucible (and any others up to the limit of the muffle furnace capacity) in the cold muffle furnace (5.3) and raise the temperature to $800\text{ °C} \pm 25\text{ °C}$ in about 1 h, maintaining this temperature for at least a further 1,5 h. Withdraw the crucible (or crucibles) and allow to cool.

NOTE The cracking of porcelain crucibles can be prevented if they are slowly cooled by insertion in supports of light porous firebrick on removal from the muffle furnace.

7.3.2 For coke

Place the charged crucible (or crucibles) on the cold insulating plate (5.5) and insert into the muffle furnace (5.3) at a temperature of $800\text{ °C} \pm 25\text{ °C}$, maintaining this temperature for at least a further 1,5 h. Withdraw the crucible (or crucibles) and allow to cool. See Note in 7.3.1.

7.4 Recovering the residue

Transfer the ignited mixture from the crucible to a 400 ml beaker containing 25 ml to 30 ml of water. If unburnt particles are present, the determination shall be stopped and the test repeated. Wash the crucible thoroughly with about 50 ml of hot water and add the washings to the contents of the beaker.

7.5 Extraction

Place a watch glass on the beaker and then, while tilting the watch glass, carefully add enough hydrochloric acid (4.2) to dissolve the solid matter (17 ml will normally be required), warming the contents of the beaker to effect solution. Boil for 5 min to expel carbon dioxide and filter, collecting the filtrate in a 400 ml conical beaker.

NOTE A medium-textured, doubly acid-washed filter paper or a filter-paper pad is recommended for speed of filtration.

To prepare the filter-paper pad, shake doubly acid-washed filter-paper clippings, in pieces with areas of approximately 1 cm^2 , with water in a bottle until the paper is thoroughly disintegrated. Place a porcelain filter cone of 25 mm in a 75 mm funnel, close the stem of the funnel with a finger, and add water until the cone is immersed and the funnel stem is full. Shake, onto the cone, sufficient paper pulp to form a pad 5 mm thick, and level it with a flat-ended glass rod. Allow the excess water to drain away by removing the finger from the stem and as drainage ceases, lightly tamp the pad around the edges with the glass rod. A final wash with water renders the filter ready for use.

Wash the filter with five 20 ml portions of hot water.

Add two or three drops of the methyl red indicator solution (4.5) to the combined filtrate and washings, and then cautiously add the ammonia solution (4.6) until the colour of the indicator changes and a trace of precipitate is formed. Add enough hydrochloric acid (4.2) to just redissolve the precipitate and then add 1 ml in excess.

7.6 Precipitation of barium sulfate

After extraction, dilute the solution, if necessary, to approximately 200 ml and cover the beaker containing the solution with a watch glass. Heat the covered beaker until the solution boils and then reduce the heating slightly until ebullition of the solution ceases. Then add 10 ml of the cold barium chloride solution (4.4) from a pipette with a delivery time of approximately 20 s so that the barium chloride solution falls into the centre of the hot solution while it is being agitated. Keep the solution just below boiling point for 30 min.

Filter the solution using one of the following techniques.

- a) By gravity through an ashless, close-textured, doubly acid-washed filter paper of diameter 100 mm to 125 mm. Carefully fold the filter paper and fit it into a fluted, long-stemmed 60° funnel so that the stem remains full of liquid during the filtration.
- b) By gravity through a filter-paper pad prepared from ashless, doubly acid-washed filter paper (see Note in 7.5).
- c) By suction through a pad of filtration mineral fibre in a Gooch crucible (5.6). Before commencing the filtration, dry the Gooch crucible and pad for 1 h at a temperature of 130 °C ± 10 °C and weigh, to the nearest 0,1 mg.

Wash the precipitate with hot water, using not more than 250 ml, until the last 20 ml of the washings give not more than a faint opalescence with the silver nitrate solution (4.7).

If technique a) or b) is used, place the wet filter paper or pad in the previously ignited and weighed crucible (5.4) on the cold flat plate (5.5).

If technique b) is used, after transferring the filter-paper pad to the crucible, wipe the funnel successively with two halves of an ashless filter paper and place this paper in the crucible with the pad. Insert the crucible slowly into the muffle furnace (5.3), at a temperature of 800 °C ± 25 °C, and then heat for 15 min. Cool in a desiccator and reweigh, to the nearest 0,1 mg.

If technique c) is used, dry the Gooch crucible (5.6) and pad for 1 h at a temperature of 130 °C ± 10 °C, cool in a desiccator, and reweigh, to the nearest 0,1 mg.

7.7 Blank testing

Carry out a blank test using the same procedure as for the determination, but omitting the test portion (as described in 7.2, 7.3, 7.4, 7.5, and 7.6). Using a one-mark pipette, add 25,0 ml of the potassium sulfate solution (4.3) to the filtrate before adding the methyl red indicator solution (4.5), as described in 7.5.

8 Expression of results

The sulfur content, w_S , of the sample, expressed as a percentage by mass, is given by Formula (1)

$$w_S = \frac{13,74(m_2 - m_3 + 0,033\,48\rho_{K_2SO_4})}{m_1} \quad (1)$$

where

m_1 is the mass, expressed in grams, of the test portion;

m_2 is the mass, expressed in grams, of barium sulfate found in the determination;

m_3 is the mass, expressed in grams, of barium sulfate found in the blank test;

$\rho_{K_2SO_4}$ is the mass concentration, expressed in grams per litre, of the potassium sulfate solution (4.3).

NOTE The derivation of the factors used in Formula (1) is given in Annex A.

Report the result, as the mean of duplicate determinations, to the nearest 0,1 % (m/m).

The results of the determination described in this International Standard are reported on the "air-dried" basis. Calculation of the results on other bases is dealt with in ISO 1170.

9 Precision

9.1 Repeatability limit

The results of duplicate determinations, carried out at different times, in the same laboratory, by the same operator with the same apparatus on representative portions taken from the same test sample, should not differ by more than 0,05 % absolute.

9.2 Reproducibility limit

The means of the results of duplicate determinations, carried out in each of two laboratories on representative portions taken from the same sample after the last stage of sample preparation, should not differ by more than 0,1 % absolute, at a 95 % confidence level.

10 Test report

The test report shall include the following particulars:

- a) the identification of the sample;
- b) the method used by reference to this International Standard (i.e. ISO 334);
- c) the results and the form in which they are expressed.

Annex A (informative)

Derivation of factors used in the calculation in [Clause 8](#)

In this annex, relative atomic masses and relative molecular masses are represented by the chemical formulae in square brackets. The relative atomic masses given in [Table A.1](#) were used in the calculations.

Table A.1 — Relative atomic mass

Element	Symbol	Relative atomic mass
Barium	Ba	137,33
Oxygen	O	15,999
Potassium	K	39,098
Sulfur	S	32,06

The mass, expressed in grams, of barium sulfate equivalent to 25 ml of potassium sulfate solution is given by Formula (A.1)

$$\frac{[BaSO_4]}{[K_2SO_4]} \times \frac{25\rho_{K_2SO_4}}{1000} \quad (A.1)$$

where $\rho_{K_2SO_4}$, is the mass concentration, expressed in grams per litre, of the potassium sulfate solution.

Thus, the sulfur content, w_S , of the sample, expressed as a percentage by mass, is given by Formula (A.2)

$$w_S = \frac{100}{m_1} \left(\frac{[S]}{[BaSO_4]} \times m_2 - \frac{[S]}{[BaSO_4]} \times \left(m_3 - \frac{[BaSO_4]}{[K_2SO_4]} \times \frac{25\rho_{K_2SO_4}}{1000} \right) \right) \quad (A.2)$$

where

m_1 is the mass, expressed in grams, of the test portion;

m_2 is the mass, expressed in grams, of barium sulfate found in the determination;

m_3 is the mass, expressed in grams, of barium sulfate found in the blank test.

Hence

$$w_S = \frac{13,74(m_2 - m_3 + 0,03348\rho_{K_2SO_4})}{m_1} \quad (A.3)$$

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™