

BS ISO 699:2015



BSI Standards Publication

# Pulps — Determination of alkali resistance

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 699:2015. It supersedes BS 4499:1984 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 86893 1

ICS 85.040

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2015.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

BS ISO 699:2015

**ISO**  
**699**

Third edition  
2015-04-01

---

---

**Pulps — Determination of alkali  
resistance**

*Pâtes — Détermination de la résistance aux solutions d'hydroxyde de sodium*



Reference number  
ISO 699:2015(E)

© ISO 2015



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagents</b> .....	<b>1</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Preparation of the test sample</b> .....	<b>2</b>
<b>8 Procedure</b> .....	<b>3</b>
8.1 Test portion.....	3
8.2 Determination.....	3
<b>9 Expression of results</b> .....	<b>4</b>
9.1 Method of calculation and formula.....	4
9.2 Precision and expression of results.....	4
<b>10 Test report</b> .....	<b>4</b>
<b>Bibliography</b> .....	<b>5</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 699:1982), of which it constitutes a minor revision.

## Introduction

The object of both this International Standard and ISO 692, *Pulps — Determination of alkali solubility*, is to permit the study of the behaviour of pulps in the presence of alkali solutions, but their fields of application are different. While this International Standard describes the gravimetric determination of the alkali insoluble constituents of the pulp and applies to all categories of pulps, ISO 692 describes the volumetric determination of the alkali soluble constituents of the pulp and is applied preferably to the control of bleached pulps.





# Pulps — Determination of alkali resistance

**WARNING** — The method specified in this International Standard involves the use of hazardous chemicals. Appropriate precautions are to be taken to ensure the proper use and disposal of these chemicals.

## 1 Scope

This International Standard specifies a method for the determination of the alkali-insoluble fraction of pulps using sodium hydroxide solution of fixed concentration. The sodium hydroxide concentrations most frequently used are 18, 10, and 5 % (*m/m*).

The method is applicable to all kinds of pulp.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*

ISO 4793, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **R-value**

alkali resistance; the insoluble fraction expressed as a percentage by mass of the oven-dry pulp

### 3.2

#### **R<sub>18</sub>, R<sub>10</sub>, R<sub>5</sub>, or R<sub>c</sub>**

R-values in which the indices 18, 10, 5, or *c* refer to the chosen concentration in grams of sodium hydroxide per 100 g of solution

## 4 Principle

Defibreing of the pulp under specified conditions in sodium hydroxide solution of chosen concentration.

Filtering of the insoluble fraction, washing with sodium hydroxide solution of the same concentration, and temperature as that used for defibreing and acidification, washing, drying, and weighing.

## 5 Reagents

Use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

**5.1 Sodium hydroxide**, solution of known concentration containing less than 1 g of sodium carbonate per litre (see the notes), for example:

- (5,39 ± 0,03) mol/l solution, containing (18,0 ± 0,1) g of sodium hydroxide per 100 g of solution ( $\rho_{20} = 1,197\ 2$  g/ml), equivalent to (215,5 ± 1,0) g of sodium hydroxide per litre;

- $(2,77 \pm 0,03)$  mol/l solution, containing  $(10,0 \pm 0,1)$  g of sodium hydroxide per 100 g of solution ( $\rho_{20} = 1,1089$  g/ml), equivalent to  $(110,9 \pm 1,0)$  g of sodium hydroxide per litre;
- $(1,31 \pm 0,03)$  mol/l solution, containing  $(5,0 \pm 0,1)$  g of sodium hydroxide per 100 g of solution ( $\rho_{20} = 1,0538$  g/ml), equivalent to  $(52,7 \pm 1,0)$  g of sodium hydroxide per litre.

NOTE 1 The sodium hydroxide solution can be conveniently prepared as follows: dissolve a quantity of solid sodium hydroxide in an equal mass of water and allow the suspended sodium carbonate to settle. Decant the supernatant liquid and dilute with carbon dioxide-free water to the appropriate concentration. Check by titration with standard acid solution.

NOTE 2 Although sodium hydroxide solution generally possesses the maximum dissolving power at a concentration of about 10 % (*m/m*), certain pulps show maximum solubility at some lower or higher alkali concentration. If the *R*-value of an unknown pulp or of a new type of pulp is to be determined with the sodium hydroxide solution of maximum dissolving power for this pulp, it is necessary to establish a solubility diagram using several different concentrations in order to determine the sodium hydroxide concentration of maximum dissolving power.

**5.2 Acetic acid**, 1,7 mol/l solution, corresponding to 100 ml of  $\text{CH}_3\text{COOH}$  ( $\rho_{20} = 1,055$  to  $1,058$  g/ml) per litre.

## 6 Apparatus

**6.1 Beaker**, of capacity 250 ml, flat-bottomed, made of alkali-resistant material.

**6.2 Stirring rod**, of diameter 15 mm, with a flat end, made of a non-brittle alkali-resistant material, preferably hard plastics.

**6.3 Filtering device**, of capacity 80 to 100 ml, internal diameter about 30 mm, with a bottom made of sintered glass, of porosity grade P 250 (porosity 0) in accordance with ISO 4793.

**6.4 Weighing bottle**, with a lid.

**6.5 Constant temperature bath**, capable of maintaining a temperature of  $(20 \pm 0,2)$  °C.

## 7 Preparation of the test sample

If the pulp is in slush form, remove the water by suction taking precautions to avoid the loss of fine fibres, press between blotters, and dry at a maximum temperature of 60 °C.

If the pulp is in the form of wet sheets or rolls, dry the sample at a maximum temperature of 60 °C.

Tear the sample into pieces of size approximately 5 mm x 5 mm. If the pulp is difficult to defibre, split the sample by means of tweezers (see Note 1).

Check that the pulp contains not more than 0,1 % ash (see Note 2). Before weighing, condition the sample for not less than 20 min in the atmosphere near the balance.

NOTE 1 Dry disintegration, for example with a Wiley-mill, or wet disintegration, for example with a high-speed stirrer, are not permitted.

NOTE 2 If the pulp to be tested contains more than 0,1 % ash, determine the ash content of the alkali-insoluble fraction. Calculate the *R*-value on the basis of the ash-free pulp and the ash-free insoluble fraction.

## 8 Procedure

### 8.1 Test portion

Weigh, to the nearest 1 mg, about 2,5 g of the test sample. Then immediately weigh two separate test portions for the determination of the dry matter content in accordance with ISO 638.

### 8.2 Determination

Transfer the test portion to the beaker (6.1), add 25 ml of the sodium hydroxide solution (5.1) adjusted to  $(20 \pm 0,2)$  °C (see 5.1, Note 1 and Note 2), place the beaker in the constant temperature bath (6.5), and allow the pulp to swell for 3 min.

Thoroughly defibre the pulp by stirring and macerating with the stirring rod (6.2) for at least 3 min, macerating at a rate of two strokes per second. Add another 25 ml of the sodium hydroxide solution at 20 °C, stir until the suspension is uniform, and dilute by adding 100 ml of the sodium hydroxide solution at 20 °C. Cover the beaker with a watch-glass and leave in the constant temperature bath.

60 minutes after the first addition of the sodium hydroxide solution, stir the fibre suspension again and transfer it to the filtering device (6.3) fitted on a dry suction flask, adjusted to a temperature of  $(20 \pm 0,2)$  °C in the constant temperature bath.

Apply suction only as long as the fibre mat is still covered with liquid in order that no air is sucked through the mat. Use the filtrate for rinsing the beaker and filter again through the slightly pressed fibre mat in order to collect all fibres. Finally, apply full suction briefly. The time for filtering and washing shall not exceed 20 min.

Compact the fibre mat, especially at the edges, cover with the acetic acid (5.2) and allow 200 ml to pass through slowly without suction. Drain completely and wash with hot water until the filtrate is free from acid.

Cover the filtering device with the hand during the last washing in order that a vacuum is formed above the fibre mat. Then quickly release the vacuum in the suction flask in order to lift the fibre mat. Transfer the fibre mat together with any remaining fibres adhering to the filtering device by means of stainless steel tweezers to the weighing bottle (6.4).

Place the open weighing bottle together with its lid in a drying oven and dry to constant mass at a temperature of  $(105 \pm 2)$  °C (normally for 6 h). Allow the closed weighing bottle to cool in a desiccator and determine the mass of the alkali-insoluble fraction to the nearest 1 mg, after briefly raising the lid to allow equalization of pressure.

Carry out at least two parallel determinations on each test sample.

NOTE 1 In certain cases, for example, straw pulps, it is advisable to add initially only 15 ml or 20 ml of the sodium hydroxide solution to the pulp in order to facilitate defibreing. The volume of alkali for the second addition has then to be increased to 35 ml or 30 ml respectively.

The solubility in 18 % (*m/m*) sodium hydroxide solution is not affected by variations of a few degrees in temperature. At this concentration, the temperature may be kept at  $(20 \pm 2)$  °C.

The solubility in sodium hydroxide solution of lower concentration (for example, 10 % (*m/m*)) is much more dependent on temperature. At this lower concentration, the temperature should be kept at  $(20 \pm 0,2)$  °C.

## 9 Expression of results

### 9.1 Method of calculation and formula

The alkali resistance,  $R_c$ , expressed as a percentage by mass, is given by the formula

$$\frac{m_1 \times 100}{m_0} \quad (1)$$

where

$m_0$  is the mass, in grams, of the test portion calculated on an oven-dry basis;

$m_1$  is the oven-dry mass, in grams, of the alkali-insoluble fraction.

### 9.2 Precision and expression of results

The results of the parallel determinations should agree to within 0,3 %.

Report the mean alkali resistance to one decimal place using the symbols  $R_{18}$ ,  $R_{10}$ , etc.

NOTE For pulps containing less than 0,1 % ash, and other noncarbohydrate materials, the value  $(100 - R_c)$  approaches the value ( $S_c$ ) determined by the method for alkali solubility of pulps described in ISO 692.

## 10 Test report

The test report shall include the following particulars:

- a) a reference to this International Standard, i.e. ISO 699;
- b) the results and the method of expression used;
- c) any unusual features noted during the determination;
- d) any operation not specified in this International Standard, or regarded as optional.

## Bibliography

- [1] ISO 692, *Pulps — Determination of alkali solubility*





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™