

BS ISO 776:2011



BSI Standards Publication

Pulps — Determination of acid-insoluble ash

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 776:2011. It supersedes BS 4496:1984, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 68302 2

ICS 85.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2011.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

BS ISO 776:2011

ISO
776

Third edition
2011-08-15

Pulps — Determination of acid- insoluble ash

Pâtes — Détermination des cendres insolubles dans l'acide



Reference number
ISO 776:2011(E)

© ISO 2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 776 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 776:1982), which has been technically revised. The ignition temperature has been changed from 575 °C to 525 °C to be consistent with the temperature specified in ISO 1762. The method also requires that the minimum mass of acid-insoluble residue be 10 mg instead of 1 mg, in order to improve the accuracy of the test.

Introduction

Acid-insoluble ash consists primarily of silica and silicates. This material, when present in the finished paper or paperboard, can have an abrasive effect on punches, knives, slitters and dies which come into contact with paper during finishing operations. Paper made from pulps with more than 400 mg/kg (based on oven-dried mass) of acid-insoluble ash can cause premature dulling of such equipment. The level of silica in pulp can vary significantly depending on several factors, including wood type, water quality, and the presence of silicate-based additives, such as clay and talc. For example, in bleached kraft pulps, the silica mass fraction can range from under 100 mg/kg to over 1 000 mg/kg.

Pulps — Determination of acid-insoluble ash

1 Scope

This International Standard specifies a method for the determination of the acid-insoluble ash of pulp. It is applicable to all types of pulps.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*

ISO 1762, *Paper, board and pulps — Determination of residue (ash) on ignition at 525 °C*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

acid-insoluble ash

insoluble residue remaining after a pulp sample is ignited in a furnace at $525\text{ °C} \pm 25\text{ °C}$ and the ash treated with hydrochloric acid as specified in this International Standard

4 Principle

A test specimen is weighed in a heat-resistant container, ignited in a muffle furnace at $525\text{ °C} \pm 25\text{ °C}$, and the residue is treated with hydrochloric acid. The insoluble residue after acid treatment is filtered, washed, ignited at 525 °C and weighed. The moisture content of a separate test portion is also measured. The acid-insoluble ash is then determined, in milligrams per kilogram, on an oven-dry basis, from the mass of the insoluble residue after ignition and the dry matter content of the sample.

5 Reagent

Use only analytical grade reagent and distilled water or water of equivalent purity.

5.1 Hydrochloric acid, 6 mol/l solution.

Carefully, in a fume hood, dilute 500 ml of hydrochloric acid (density at $20\text{ °C} = 1,19\text{ kg/l}$) to 1 000 ml with water.

6 Apparatus

6.1 Heat-resistant evaporating dishes, of capacity 50 ml to 100 ml, and **crucibles** with a capacity of 20 ml. Platinum containers are preferred, but porcelain or silica may be used.

6.2 Steam bath or electric hotplate, capable of maintaining a surface temperature of 110 °C to 130 °C .

6.3 Analytical balance, of capacity 100 g, accurate to 0,1 mg.

6.4 Desiccator.

6.5 Muffle furnace, capable of maintaining a temperature of $525\text{ °C} \pm 25\text{ °C}$.

6.6 Filter paper, quantitative, ashless, double acid-washed, of a type recommended for fine precipitates (e.g. Whatman No. 42¹⁾ or equivalent).

6.7 Drying oven, capable of maintaining an air temperature of $105\text{ °C} \pm 2\text{ °C}$ and suitably ventilated.

7 Sampling and preparation of test specimen

If the analysis is done in order to evaluate a pulp lot, obtain a representative pulp sample as described in ISO 7213. If it is not, report the source of the sample and, if possible, the sampling procedure used. Sufficient sample shall be collected to allow for at least duplicate determinations and for the determination of moisture content.

Obtain a test specimen consisting of small pieces, not larger than 1 cm^2 , from various parts of the sample in such a manner as to be thoroughly representative of it. The mass of the test portion shall be such that the mass of the acid-insoluble residue is greater than 10 mg. A test portion weighing 25 g is sufficient in most cases.

NOTE In samples with very low levels of acid-insoluble residue, it might be necessary to obtain a larger test specimen and to ignite it in more than one portion.

8 Procedure

Carry out the procedure in duplicate.

Condition the test specimens and moisture specimens in the laboratory atmosphere until they reach equilibrium moisture.

Determine the moisture content of the sample as described in ISO 638. Weigh this test portion at the same time as the test portion used for ash determination.

Ash the test specimens as described in ISO 1762, in a dish previously ignited in the muffle furnace, to a constant mass (to the nearest 0,1 mg). If the dish is too small to hold the entire specimen, the specimen shall be ashed in portions. Place a portion of the specimen in the dish and burn it gently to avoid any loss. Then add the next portion to the dish and burn it gently. Continue this process until the entire specimen has been carbonized, as indicated by the absence of black carbon particles.

Cool the dish to room temperature in a fume hood, add 5 ml of 6 mol/l HCl (5.1), and evaporate carefully to dryness on a steam bath or hotplate (6.2). Repeat the treatment. Add a third 5 ml aliquot of 6 mol/l HCl (5.1) to the residue, heat for 2 min on the steam bath or hotplate, and dilute with 20 ml of water.

Quantitatively transfer the residue by filtering through the filter paper (6.6), being careful to remove all the residue from the dish with water. Wash the residue several times with hot water until the filtrate is free of chloride ions.

The absence of chloride ions in the filtrate may be confirmed with a few drops of 5 % silver nitrate. The filtrate should not produce a white precipitate or opalescence.

Carefully place the filter paper and residue into a tared 20 ml crucible or heat-resistant evaporating dish (6.1). Heat gently until dry, then ignite at $525\text{ °C} \pm 25\text{ °C}$ until the entire specimen has been ashed, as indicated by the absence of black carbon particles. Cool the crucible in a desiccator and weigh to the nearest 0,1 mg. Repeat the ignition until a constant mass is obtained.

1) Whatman No. 42 is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

9 Calculation

Calculate the mass fraction of acid-insoluble ash according to Equation (1):

$$w_a = 1\,000 \times \frac{m_1}{m_2} \quad (1)$$

where

w_a is the mass fraction of acid-insoluble ash, expressed as milligrams per kilogram of the oven-dry sample;

m_1 is the mass of insoluble residue after ignition at $525\text{ °C} \pm 25\text{ °C}$, in milligrams;

m_2 is the mass of the sample, on an oven-dry basis, in grams.

Report the mean of duplicate determinations to the nearest 5 mg/kg.

10 Test report

The test report shall include the following information:

- a) a reference to this International Standard (ISO 776:2011);
- b) the date and place of testing;
- c) a complete identification of the sample tested;
- d) the result, expressed as indicated in Clause 9;
- e) any departure from the procedure described in this International Standard or any other circumstances which may have affected the result.

Annex A (informative)

Precision

A.1 General

In August 2009, an international round robin was performed in which eight laboratories from five different countries participated.

Three samples of different types of pulp were tested. Each sample was disintegrated, to ensure its homogeneity, and made into handsheets. Several handsheets from each sample were submitted to the participating laboratories for testing according to this International Standard. For the two hardwood bleached kraft pulp samples, the data from two of the eight laboratories were considered as outliers and were not included in the precision statement.

The calculations were made according to ISO/TR 24498, *Paper, board and pulps — Estimation of uncertainty for test methods*.

The repeatability and reproducibility limits reported are estimates of the maximum difference which should be expected in 19 of 20 instances, when comparing two test results for material similar to those described under similar test conditions. These estimates may not be valid for different materials or different test conditions.

NOTE Repeatability and reproducibility limits are calculated by multiplying the repeatability and reproducibility standard deviations by 2,77, where $2,77 = 1,96 \times \sqrt{2}$.

A.2 Repeatability

Table A.1 — Estimation of the repeatability of the test method

Sample	Number of laboratories	Mean value mg/kg	Standard deviation s_r mg/kg	Coefficient of variation $C_{V,r}$ %	Repeatability limit r mg/kg
Hardwood bleached kraft pulp (low ash)	6	1 368	72,6	5,3	201
Hardwood bleached kraft pulp (high ash)	6	2 909	72,4	2,5	201
Clay-filled mechanical pulp furnish	8	112 955	4 611	4,1	12 781

A.3 Reproducibility

Table A.2 — Estimation of the reproducibility of the test method

Sample	Number of laboratories	Mean value	Standard deviation	Coefficient of variation	Reproducibility limit
		mg/kg	s_R mg/kg	$C_{V,R}$ %	R mg/kg
Hardwood bleached kraft pulp (low ash)	6	1 368	112	8,2	311
Hardwood bleached kraft pulp (high ash)	6	2 909	165	5,7	458

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™