

BS ISO 975:2013



BSI Standards Publication

**Brown coals and lignites —  
Determination of yield of  
benzene-soluble extract —  
Semi-automatic method**

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 975:2013.

The UK participation in its preparation was entrusted to Technical Committee PTI/16, Solid mineral fuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 81214 9

ICS 73.040

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2013.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

BS ISO 975:2013

**ISO**  
**975**

Fourth edition  
2013-05-01

---

---

**Brown coals and lignites —  
Determination of yield of benzene-  
soluble extract — Semi-automatic  
method**

*Charbons bruns et lignites — Détermination du rendement en extrait  
de benzène soluble — Méthode semi-automatique*



Reference number  
ISO 975:2013(E)

© ISO 2013



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Principle</b> .....	<b>1</b>
<b>4 Reagent</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>1</b>
<b>6 Preliminary adjustment of instrument</b> .....	<b>2</b>
6.1 Adjustment of the extraction temperature.....	2
6.2 Selection of periods of extraction, rinsing and evaporation.....	2
6.3 Procedure.....	2
<b>7 Expression of results</b> .....	<b>3</b>
<b>8 Precision of the method</b> .....	<b>3</b>
8.1 Repeatability limit.....	3
8.2 Reproducibility critical difference.....	3
<b>9 Test report</b> .....	<b>4</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 975 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This fourth edition cancels and replaces the third edition (ISO 975:2000), of which this constitutes a minor revision.

## Introduction

The determination of yield of benzene-soluble extract is carried out using a semi-automatic instrument; a system combining extraction, rinsing and evaporation. As long as the sample is put in the extraction chamber of the instrument, the test can be done automatically.





# Brown coals and lignites — Determination of yield of benzene-soluble extract — Semi-automatic method

## 1 Scope

This International Standard specifies a semi-automatic method for determination of the yield of benzene-soluble extract in brown coals and lignites.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5068-2, *Brown coals and lignites — Determination of moisture content — Part 2: Indirect gravimetric method for moisture in the analysis sample*

## 3 Principle

A test portion of the brown coal or lignite is extracted with benzene in a semi-automatic extraction instrument. The solvent is then removed by evaporation and the soluble residue dried to constant mass. The percentage of benzene-soluble extract is calculated from the mass of residue after drying and is reported on the dry basis.

## 4 Reagent

**4.1 Benzene**, of analytical reagent grade,  $\rho_{20} = 0,876$  g/ml, distillation range 80 °C to 81 °C. At least 95 % shall distil within this range.

**WARNING — Benzene is flammable and toxic by inhalation, ingestion or skin absorption. The test must be carried out in a hood and the benzene must be recovered as completely as possible.**

## 5 Apparatus

**5.1 Semi-automatic extraction instrument**, containing mainly two units: the continuous extraction-evaporation device and the controller. The continuous extraction-evaporation device consists of a 100 ml conical flask, an extraction chamber and a condenser. The extraction chamber is 180 mm long and 30 mm in internal diameter and is provided with a water jacket through which the bath water is circulated in order to maintain the extraction temperature around the extraction chamber.

**5.2 Extraction thimble**, 25 mm × 80 mm. Cellulose or other thimbles are purchased or made as follows.

Cut filter paper into pieces of 75 mm × 75 mm and 25 mm × 25 mm. Moisten one large piece of the filter paper with distilled water and roll it snugly onto the external wall of a test tube of 25 mm diameter with a small hole pierced at the bottom. A small piece of filter paper is next moistened and rolled onto the bottom. Three large pieces and two small pieces are then rolled alternately onto the test tube. Remove the formed moist thimble by blowing at the mouth of the test tube and dry it in air or in an oven at 100 °C.

**5.3 Air oven**, capable of maintaining a temperature between 105 °C and 110 °C, or **vacuum oven**, electrically heated, in which a temperature of 80 °C ± 2 °C and a pressure of about 50 kPa can be maintained.

5.4 **Analytical balance**, accurate to 0,1 mg.

## 6 Preliminary adjustment of instrument

### 6.1 Adjustment of the extraction temperature

Place an extraction thimble with about 2 g of coal sample in the extraction chamber. Add 60 ml to 70 ml of benzene to the conical flask. Connect the flask to the extraction chamber. Switch on the electrical power and push down the programme button. The extraction-evaporation device will then be automatically lowered until the flask is immersed in the water bath and the water bath starts heating. As the first drop of condensed benzene drips from the condenser, adjust the temperature of the water bath so that the dripping rate of benzene is about 4 ml/min to 5 ml/min and the sample is completely immersed in benzene in the thimble. Record the temperature and fix the position of the temperature controller. This temperature should be readjusted for changed ambient temperature.

### 6.2 Selection of periods of extraction, rinsing and evaporation

In general, the suitable periods of the above three steps are, respectively, 180 min, 10 min and 50 min. They can be readily adjusted with the corresponding timers. In the case of a high content of benzene-soluble constituents in the sample or excessively low barometric pressure, etc., readjustment of the extraction period may be necessitated in order to ensure the correct end-point of extraction, which is to be judged by the colourlessness of the last drops of extract solution.

### 6.3 Procedure

Weigh, to the nearest 0,2 mg, about 2 g of general analysis test sample, transfer to the extraction thimble (5.2) and cover with a pad of absorbent cotton, which is fitted snugly on the wall of the thimble.

Place the extraction thimble with sample in the extraction chamber (see 5.1).

Add 60 ml to 70 ml of benzene to a previously dried and accurately weighed flask.

Assemble the instrument.

Switch on the electrical power. Push down the programme button. The instrument will automatically perform the experiment in accordance with the following sequence:

The extraction-evaporation device is lowered until the flask is immersed in the water bath as in the preliminary adjustment and the condenser is in an inclined position permitting refluxing. The heating of the water bath is started simultaneously.

When the extraction temperature previously set is reached, the pump begins to circulate the hot water between the bath and the jacket of the extraction chamber. The benzene vapour from the flask passes through the extraction chamber and reaches the condenser, where it is condensed and drips onto the thimble. The extraction stage is thus in progress.

After 180 min, or an otherwise set time, the pump stops and extraction is finished. Hot water flows back to the bath. The temperature of the extraction chamber drops to a temperature at which the benzene vapour can only reach the extraction chamber and condenses there. Thus a rinsing action is achieved, by means of which the benzene-soluble extract adhered to the wall is washed down into the flask by the condensed benzene. This is the rinsing stage.

After 10 min, rinsing is finished. The condenser is automatically changed to an inverted position permitting distillation. The pump works again so as to resume hot-water circulation. The benzene vapour condenses in the condenser and flows to the receiver. The stage of evaporation starts.

After 50 min of evaporation is finished, the extraction-evaporation system is elevated to the original position, permitting the flask to be detached from the extraction chamber. The programme is thus terminated.

Detach the flask with soluble residue. Dry it in the air oven (5.3) maintained at 105 °C to 110 °C or in the vacuum oven (5.3) maintained at 80 °C ± 2 °C and about 50 kPa to constant mass.

NOTE Constancy in mass is considered to have been achieved when the difference between successive dryings does not exceed 0,001 g.

Carry out a moisture determination on a separate test portion by the method specified in ISO 5068-2.

## 7 Expression of results

The yield of benzene-soluble extract,  $w_{E,ad}$ , in the general analysis test sample, expressed as a percentage by mass, is given by the formula

$$w_{E,ad} = \frac{m_1 \times 100}{m_2}$$

where

$m_1$  is the mass, in grams, of benzene-soluble extract;

$m_2$  is the mass, in grams, of the test portion.

The yield, expressed on the dry basis, is given by the formula

$$w_{E,d} = \frac{100}{100 - w_M} \times w_{E,ad}$$

where  $w_M$  is the mass fraction of moisture, in percent, of the general analysis test sample.

The result (the mean of duplicate determinations, see 8.1) shall be reported on the dry basis to the nearest 0,1 %.

## 8 Precision of the method

### 8.1 Repeatability limit

The results of duplicate determinations, carried out at different times within a short interval, in the same laboratory, by the same operator, with the same apparatus, on two representative test portions taken from the same analysis sample, should not differ by more than the values shown in [Table 1](#).

### 8.2 Reproducibility critical difference

The means of the results of duplicate determinations, carried out in each of two different laboratories, on representative test portions taken from the same sample after the last stage of sample preparation, should not differ by more than the values shown in [Table 1](#).

**Table 1**

Yield of benzene-soluble extract % (m/m)	Repeatability limit (air-dried basis)	Reproducibility critical difference (dry basis)
less than 5	0,3 % absolute	0,5 % absolute
5 to 10 inclusive	0,5 % absolute	0,7 % absolute
more than 10	5 % of the mean result	7 % of the mean result

## 9 Test report

The test report shall include the following information:

- a) a reference to this International Standard including year of publication;
- b) identification of the sample tested;
- c) the results of the determination, together with the analysis basis;
- d) any unusual features noted during the determination.







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™