

BS ISO 1125:2015



BSI Standards Publication

# Rubber compounding ingredients — Carbon black — Determination of ash

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 1125:2015. It supersedes BS ISO 1125:1999+A1:2011 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 89095 6

ICS 83.040.20

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2015.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

BS ISO 1125:2015

**ISO**  
**1125**

Fourth edition  
2015-08-15

---

---

**Rubber compounding ingredients —  
Carbon black — Determination of ash**

*Ingrédients de mélange du caoutchouc — Noir de carbone —  
Détermination du taux de cendres*



Reference number  
ISO 1125:2015(E)

© ISO 2015



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Principle</b> .....	<b>1</b>
<b>4 Apparatus</b> .....	<b>1</b>
<b>5 Sampling</b> .....	<b>1</b>
<b>6 Procedure</b> .....	<b>2</b>
<b>7 Expression of results</b> .....	<b>2</b>
<b>8 Precision</b> .....	<b>2</b>
<b>9 Test report</b> .....	<b>3</b>
<b>Annex A (informative) Precision data</b> .....	<b>4</b>
<b>Bibliography</b> .....	<b>6</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fourth edition cancels and replaces the third edition (ISO 1125:1999), of which it constitutes a minor revision. It also incorporates ISO 1125:1999/Amd.1:2011.

The modifications include updating the normative references (in Clause 2 and throughout the text), moving precision data in an informative annex and adding a Bibliography.

# Rubber compounding ingredients — Carbon black — Determination of ash

**WARNING** — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

## 1 Scope

This International Standard specifies a method for determining the ash of all types of carbon black for use in the rubber industry.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1124, *Rubber compounding ingredients — Carbon black shipment sampling procedures*

## 3 Principle

An accurately weighed portion of dried sample is ignited in a crucible until all the carbonaceous material is oxidized. The crucible is cooled in a desiccator, weighed, and the percentage of ash calculated.

## 4 Apparatus

**4.1 Muffle furnace**, capable of maintaining a temperature of  $550\text{ °C} \pm 25\text{ °C}$  (or other required temperature).

NOTE The use of a vented furnace would decrease the time of heating to constant mass (see 6.3).

**4.2 Porcelain crucible**, tall form, diameter 35 mm, height 30 mm, with lid.

The use of the lid on the crucible is optional. If it is not used, this shall be mentioned in the test report.

**4.3 Analytical balance**, accurate to 0,1 mg.

**4.4 Desiccator**.

**4.5 Oven**, preferably of the gravity-convection type, capable of temperature regulation to within  $\pm 1\text{ °C}$  at  $125\text{ °C}$  and temperature uniformity to within  $\pm 5\text{ °C}$ .

## 5 Sampling

Carry out sampling in accordance with ISO 1124.

## 6 Procedure

**6.1** Heat the crucible (4.2), with its lid (if used), in the muffle furnace (4.1) at a temperature of  $550\text{ °C} \pm 25\text{ °C}$  for 1 h. Place the crucible (and lid) in the desiccator (4.4). Cool to ambient temperature and reweigh to the nearest 0,1 mg.

**NOTE** If, after cleaning, drying and reweighing at the end of the determination (see 6.4), the crucible is stored in a desiccator, step 6.1 is needed only for new crucibles.

**6.2** Dry a little more than 2 g of furnace carbon black or a little more than 5 g of thermal or channel carbon black in the oven (4.5) at a temperature of  $125\text{ °C}$  for 1 h. Allow to cool to room temperature.

**6.3** Weigh, to the nearest 0,1 mg, about 2 g of dried furnace carbon black or 5 g of dried thermal or channel black into the crucible tared in 6.1, place in the furnace at a temperature of  $550\text{ °C} \pm 25\text{ °C}$  and heat uncovered until constant mass is obtained.

Cover with the lid (if used), remove to the desiccator, and allow to cool to ambient temperature. Weigh to the nearest 0,1 mg. To avoid repeated handling of the crucible, an adequate ashing time shall be established at each test site.

**IMPORTANT — Take the following precautions:**

**a) keep the door of the furnace open about 0,5 cm to admit air to support the combustion of organic material;**

**b) after the test portion has cooled in the desiccator, admit air slowly to avoid loss of ash from the crucible due to air currents.**

By mutual agreement between the interested parties, it is permissible to use another ashing temperature such as  $750\text{ °C} \pm 25\text{ °C}$  or  $825\text{ °C} \pm 25\text{ °C}$  (4.1, 6.1 and 6.3 would have to be adapted accordingly).

However, this temperature leads to lower ash contents than the ones obtained at  $550\text{ °C}$ , and shall not be used for reference purposes.

**6.4** Clean the crucible (and lid), dry in the oven (4.5) at  $125\text{ °C}$  and reweigh to the nearest 0,1 mg.

## 7 Expression of results

The ash  $A$  is given, as a percentage by mass, by the following equation.

$$A = \frac{m_2 - m_3}{m_1 - m_0} \times 100$$

where

$m_0$  is the mass, in grams, of the crucible (and lid) before the determination;

$m_1$  is the mass, in grams, of the crucible (and lid) plus the test portion;

$m_2$  is the mass, in grams, of the crucible (and lid) plus the ash;

$m_3$  is the mass, in grams, of the crucible (and lid) after the determination (should be the same as  $m_0$ ).

## 8 Precision

See [Annex A](#).



## 9 Test report

The test report shall include the following particulars:

- a) a reference to this International Standard;
- b) all details necessary for complete identification of the sample;
- c) the results and the units in which they have been expressed;
- d) any unusual features noted during the determination;
- e) any operation not included in this International Standard, or any operation regarded as optional such as the ashing temperature if different from the specified one or the omission of the crucible lid;
- f) the date of the test.

## Annex A (informative)

### Precision data

**A.1** The precision of the method was determined in accordance with ISO/TR 9272. Refer to this document for terminology and other statistical details.

**A.2** The precision data given below merely give an estimate of the precision. The precision parameters shall not therefore be used for acceptance/rejection testing of any group of materials without documentation that they are applicable to those particular materials and the specific test protocols that include this method.

**A.3** A type 1 interlaboratory precision programme was conducted. Both repeatability and reproducibility were measured under short-term testing conditions. Ten laboratories tested five carbon black samples (A, B, C, D and E) twice on two different days.

Difference values were not measured.

**A.4** The results of the precision calculations are given in Table A.1, with the materials arranged in ascending order of the mean ash value.

**Table A.1 — Precision data**

Material	Mean ash %	Within laboratory			Between laboratories		
		$s_r$	$r$	( $r$ )	$s_R$	$R$	( $R$ )
Black A	0,17	0,016	0,045	25,497	0,021	0,060	35,188
Black E	0,35	0,020	0,057	16,121	0,037	0,014	29,663
Black B	0,45	0,030	0,085	18,919	0,043	0,122	27,067
Black C	0,61	0,027	0,076	12,483	0,037	0,106	17,445
Black D	0,83	0,016	0,045	5,620	0,023	0,066	7,961
Pooled or averaged values	0,48	0,02	0,06	13,25	0,03	0,09	19,63

$p = 10$ ,  $q = 5$  and  $n = 4$

$s_r$  is the within-laboratory standard deviation

$r$  is the repeatability (in measurement units)

( $r$ ) is the repeatability (in percent)

$s_R$  is the between-laboratory standard deviation

$R$  is the reproducibility (in measurement units)

( $R$ ) is the reproducibility (in percent)

**A.5** The precision for the pooled values for the ash may be expressed as follows:

- a) **Repeatability:** The repeatability  $r$  of the result has been established as 0,06 % ash. Two individual test results (or determinations) that differ from each other by more than 0,06 % ash shall be considered suspect and dictate that some appropriate investigative action be taken.

b) **Reproducibility:** The reproducibility R of the result has been established as 0,09 % ash. Two individual test results (or determinations) produced in separate laboratories that differ by more than 0,09 % ash shall be considered suspect and dictate that some appropriate investigative action be taken.

**A.6 Bias:** In test method terminology, bias is the difference between an average test value and the reference (true) test property value. Reference values do not exist for this test method since the value of the test property is exclusively defined by the test method. Bias, therefore, cannot be determined.

## Bibliography

- [1] ISO/TR9272:2005, *Rubber and rubber products — Determination of precision for test method standards*







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™