BS ISO 1144:2016



BSI Standards Publication

Textiles — Universal system for designating linear density (Tex System)



BS ISO 1144:2016 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of ISO 1144:2016.

The UK participation in its preparation was entrusted to Technical Committee TCI/24, Physical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 93540 4

ICS 59.080.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2016.

Amendments/corrigenda issued since publication

Date Text affected

INTERNATIONAL STANDARD

ISO 1144:2016 ISO 1144

Second edition 2016-09-15

Textiles — Universal system for designating linear density (Tex System)

Textiles — Système universel de désignation de la masse linéique (système Tex)



BS ISO 1144:2016 ISO 1144:2016(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Con	itents	Page
Forev	word	iv
Intro	duction	v
1	Scope	1
2	Normative references	1
3	Characteristics of the system	1
4	Units	1
5	Notation	2
Anne	x A (informative) Conversion and rounding	3
Anne	x B (informative) Implementation of the tex system in trade and industry	9
Biblio	ography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This second edition cancels and replaces the first edition (ISO 1144:1973), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- a) the content structure has been updated;
- b) some printing errors in <u>Table A.3</u> (previously Table 4) have been corrected.

Introduction

It has long been customary to designate the coarseness or the fineness of textile yarns by numbering or counting systems. Many branches of the textile industry employ systems of their own for this purpose, and those in current use may be classified in two groups.

- a) Direct systems, in which the coarseness or the fineness of the yarn is expressed in terms of the mass of yarn per unit length (linear density, often called yarn number or yarn *titre*).
- b) Indirect systems, in which the coarseness or the fineness of the yarn is expressed in terms of the length of yarn per unit mass (usually called yarn *count*).

With the growing use of yarns containing more than one kind of fibre, and of fabrics containing these yarns, it became increasingly evident that the general adoption of a single system of numbering or counting would avoid confusion and save time.

In 1956, after detailed studies, it was agreed that the Tex System be recommended for international adoption in place of the various traditional methods of numbering or counting. That system is direct and based on metric units: originally grams per kilometre (tex), milligrams per kilometre (millitex), and kilograms per kilometre (kilotex), with the addition of decigrams per kilometre (decitex) agreed in 1967.

Textiles — Universal system for designating linear density (Tex System)

1 Scope

This International Standard gives the principles and recommended units of the Tex System for the expression of linear density and includes conversion tables for calculating the tex values of numbers or counts in other systems together with a statement of the procedure for the implementation of the Tex System in trade and industry.

The Tex System is applicable to all kinds of textile fibres, intermediate products (for example tops, slivers and rovings), yarns and similar structures.

2 Normative references

There are no normative references in this document.

3 Characteristics of the system

- **3.1** This system, called the Tex System, is a direct system. It expresses the linear density, that is to say the mass of a certain length of the textile material.
- **3.2** The system is decimal and employs metric units.
- **3.3** The basic unit is the "tex". The linear density in "tex" expresses the mass, in grams, of one kilometre of $yarn^{1}$.

It is realized that, at present, usage of the term linear density is limited to scientific and laboratory application but every effort should be made to ensure greater currency of it.

4 Units

The multiple and sub-multiples of the tex unit recommended for use in preference to other possible combinations are

- kilogram per kilometre, designated kilotex;
- decigram per kilometre, designated decitex;
- milligram per kilometre, designated millitex.

Table 1 — Tex system—Recommended units

Name	Symbol	Definition
millitex	mtex	1 mtex = 1 mg/km = 1 μ g/m
decitex	dtex	1 dtex = 1 dg/km = 0,1 mg/m
tex	tex	1 tex = 1 g/km = 1 mg/m
kilotex	ktex	1 ktex = 1 kg/km = 1 g/m

¹⁾ The term "yarn", which is used here for simplicity, is as defined in ISO 1139. It does not exclude the other textile applications mentioned in scope.

BS ISO 1144:2016 ISO 1144:2016(E)

To indicate linear density in the Tex System as a quantity in formulae, tables and preprinted forms, irrespective of units, the symbol Tt is used. It should never be used with a numerical value of linear density because it is not a unit. It is equivalent in fact to the expression "linear density expressed in the Tex System". In a general formula, without a numerical value in which the linear density of a yarn (or other product) occurs, the symbol Tt serves to indicate that in a numerical application of the formula, this linear density is expressed in a unit of the Tex System.

5 Notation²⁾

The linear density in the Tex System is indicated by the numerical value followed by the name of the unit used.

EXAMPLE 100 mtex; 60 dtex; 20 tex; 15 ktex

²⁾ More detailed specifications for the designation of folded and cabled yarns are given in ISO 1139.

Annex A

(informative)

Conversion and rounding

A.1 Introduction

This annex is intended to facilitate the implementation of the Tex System by describing the rational development of tex equivalents and giving guidance on the choice of rounded tex values.

Three possibilities are given for the choice of tex equivalent:

- calculated tex equivalent;
- rounded tex value:
- recommended tex value.

The recommended tex values given in <u>Table A.1</u> will serve as guide and should be used whenever practicable.

A.2 Calculation of tex equivalents

Counts and numbers (titres), as expressed in other counting or numbering systems, are converted into tex values as set out below. The multiplying factors in $\underline{\text{Table A.1}}$ and the constants in $\underline{\text{Table A.2}}$ are expressed to four significant figures to give an accuracy of 0,05 %.

The equivalent values, calculated to four significant figures, are rounded to three significant figures to obtain an accuracy within $0.5\,\%$ with respect to the value in the traditional system.

A.2.1 Conversion from direct systems

In direct systems, the coarseness or fineness of yarn (linear density) equals mass of yarn per unit of length.

<u>Table A.1</u> gives the multiplying factors for multiplying the known number (or titre).

EXAMPLE The equivalent of 840 denier in tex is

 840×0 , 1111 = 93,32 tex or 933,2 dtex = 933 dtex to three significant figures.

Table A.1 — Multiplying factors for direct systems

Yarn number system	Symbolic abbreviation	Unit of mass used	Unit of length used	Unit of yarn number	Multiplying factor, yarn number to tex value
Tex	Tt	1 g	1 km	g/km	-
Denier	Td	1 g	9 000 m	g/9 000 m	0,111 1
Linen dry spun Hemp Jute	Tj	1 pound	14 400 yards (spindle unit)	lb/14 400 yd	34,45

Table A.1 (continued)

Yarn number system	Symbolic abbreviation	Unit of mass used	Unit of length used	Unit of yarn number	Multiplying factor, yarn number to tex value
Número en cuartos de onza	То	1/4 onza	500 cañas	0,25 onza/ 500 cañas	10,71
Woollen (Aberdeen)	Та	1 pound	14 400 yards	lb /14 400 yd	34,45
Woolen (Catalonian)	Tc _w	1 g	504 m	g/504 m	1,984

A.2.2 Conversion from indirect systems

In indirect systems, coarseness or fineness of yarn equals length of yarn per unit of mass.

<u>Table A.2</u> gives the constants which are to be divided by the count in the indirect system.

EXAMPLE The equivalent of yarn count Ne_w 20 in tex is

$$\frac{885,8}{20} = 44,29$$
= 44,3 tex to three significant figures

 ${\bf Table~A.2-Constants~for~conversion~of~indirect~systems}$

Yarn count system	Symbolic abbreviation	Unit of length used	Unit of mass used	Unit of yarn count	Constant for conversion to tex values
Asbestos (American)	Na _A	100 yards(cut)	1 pound	100 yd/ lb	4 961
Asbestos (English)	Ne _A	50 yards	1 pound	50 yd/lb	9 921
Cotton bump yarn	N_{B}	1 yard	1 ounce	yd/oz	31 000
Cotton (English)	Ne _C	840 yards (hank)	1 pound	840 yd/lb	590,5
Cotton (Catalonian)	Ncc	500 cañas	1,1 libra catalana	500 cañas/1,1 lb cat.	565,9
Glass (U.S.A and UK)	N _G	100 yards	1 pound	100 yd/lb	4 961
Linen (wet or dry spun)	Ne _L	300 yards(lea)	1 pound	300 yd/lb	1 654
Metric	Nm	1 km	1 kg	km/kg	1000
Numero en puntos	Np	1 320 m	1 libra de Alcoy	1 320 m/lb de Alc.	358,7
Spun silk	Ns	840 yards	1 pound	840 yd/lb	590,5
Турр	Nt	1 000 yards	1 pound	1 000 yd/lb	496,1
Woolen (Alloa)	Nal	11 520 yards (spindle)	24 pounds	11 520 yd/24 lb	1 033
Woollen (American cut)	Nac	300 yards	1 pound	300 yd/lb	1 654
Woolen (American run)	Nar	100 yards	1 ounce	100 yd/oz	310
Woolen (Cardado Covilhã)	NpW	1 m	5 g	m/5 g	5 000
Woolen (Dewsbury)	Nd	1 yard	1 ounce	yd/oz	31 000

Table A.2 (c	ontinued)
---------------------	-----------

Yarn count system	Symbolic abbreviation	Unit of length used	Unit of mass used	Unit of yarn count	Constant for conversion to tex values
Woolen (Galashiels)	Ng	300 yards(cut)	24 ounces	300 yd/24 oz	2 480
Woolen (Hawick)	Nh	300 yards(cut)	26 ounces	300 yd/26 oz	2 687
Woolen (Irish)	Ni _W	1 yard	0.25 ounce	yd/0.25 oz	7 751
Woolen (West of England)	Nwe	320 yards(snap)	1 pound	320 yd/lb	1 550
Woolen (Yorkshire)	Ny	256 yards(skein)	1 pound	256 yd/lb	1 938
Woolen (Yorkshire)	Ny	1 yard	1 dram	yd/dram	1 938
Worsted	New	560 yards(hank)	1 pound	560 yd/lb	885,8

A.3 Choice of rounded tex values

When counts and numbers (titres) are converted into tex, decimal values are usually obtained, which may be used as they are or rounded for practical purposes.

Where trade authorities concerned with each type of product have not published agreed lists in tex values of the yarns and fibres to be produced, the values in tex to three significant figures obtained according to <u>A.2</u> and rounded using one of the alternatives given in <u>A.3.1</u> may be used. Examples of the rounded values are given in <u>Table A.3</u>.

- **A.3.1** For selecting rounded tex values, two possibilities are given:
- a) Rounding to the nearest two significant figures;
- b) Rounding in the direction of the recommended values of <u>Table A.4</u>, using two significant figures or three significant figures when the last figure is 5.

[See the example in a) and b) of column 3 in Table A.3.]

- **A.3.2** Care should be taken to ensure that rounding is applied consistently so that the rounded tex values for two traditional counts of which one is 10 times the other should consist of the same digits and vary only in the position of the decimal point.
- **A.3.3** When rounded values are chosen certain cases will arise where the difference between a yarn according to a traditional count and according to the value of the corresponding rounded tex values will be sufficient to necessitate some adjustment to the yarn being spun.

Table A.3 — Choice of rounded values

1		2	3	3	4
Traditional yarn count		Equivalent tex value in three	Rounded	tex value	Recommended tex value according to
system	value	figures	a) ^a	b) a	Table A.4
Nm	15	66,7	67	67	68
Nm	30	33,3	33	33,5	34
Nm	60	16,7	17	17	17
Nec	12	49,2	49	49,5	50
Ne _C	24	24,6	25	25	25

NOTE This table can be extended in national standards by including figures from lists published by accepted trade authorities.

a See <u>A.3.1</u>

Table A.3 (continued)

Ne _C	48	12,3	12	12,5	12,5
Nec	120	4,92	4,9	4,9	5
Td	60	6,67	6,7	6,7	6,8
Td	120	13,3	13	13	13
Td	480	53,3	53	53	52
Td	600	66,7	67	67	68
New	18	49,2	49	49,5	50
Ny	24	80,7	81	80,5	80
Ne _L	25	66,1	66	66,5	68
N_G	75	66,1	66	66,5	68
Na _A	75	66,1	66	66,5	68

NOTE This table can be extended in national standards by including figures from lists published by accepted trade authorities.

A.4 Choice of recommended values

The decision to use recommended tex values may be taken before changing over to the Tex System or deferred until after the Tex System has come into use.

The use of recommended values is not obligatory: <u>Table A.4</u> is only intended to provide a rational system of selecting rounded values, based on a nearly equal increase of the linear density of yarns and with the additional objective of arriving in the future at a systematic reduction in the total range of linear densities. The recommended values are listed in column 2 of <u>Table A.4</u>. The range of exact values represented by each recommended value is also given in <u>Table A.4</u>. The list of recommended values includes a minimum of decimals and uses even numbers as far as possible.

Use the following procedure to determine the recommended tex value corresponding to a yarn count or linear density expressed in any other system or corresponding with the rounded values of column 3 of Table A.3.

- **A.4.1** Determine the calculated tex equivalent of the nominal count or number by means of the appropriate multiplying factor or constant given in <u>Table A.1</u> and <u>A.2</u>.
- EXAMPLE 1 Nm17 corresponds to 58,82 tex.
- EXAMPLE 2 1,5 denier corresponds to 166,7 mtex.
- **A.4.2** Find the range of values in column 1 of <u>Table A.4</u> which contains the tex value determined in accordance with <u>A.4.1</u> or values already rounded, in accordance with <u>A.3.1</u>.
- EXAMPLE 1 58,82 tex is contained in the range 58 to 62.
- EXAMPLE 2 Multiplying by 10 the values in <u>Table A.4</u>, 166,7 mtex is contained in the range 165 to 175 (corresponding to the range 16,5 to 17,5 of the same Table).
- **A.4.3** Read off the recommended tex value given in column 2 of <u>Table A.4</u> for the range of values selected in accordance with A.4.2.
- EXAMPLE 1 For the range 58 to 62, the recommended tex value is 60.
- EXAMPLE 2 For the range 165 to 175, the recommended tex value is 170 mtex (corresponding to 17 in Table A.4).

a See <u>A.3.1</u>

The values in <u>Table A.4</u> are valid for the unit tex and for its multiples and sub-multiples, including kilotex, decitex and millitex units. The scope of the table may be extended for coarser and finer values by multiplying or dividing the values given by 10 or 100.

	tex values		
	1	4	
Val	ue range	Recommended tex value	
over	up to and including		
9,4	9,8	9,6	
9,8	10,25	10	
10,25	10,75	10,5	
10,75	11,25	11	
11,25	11,75	11,5	
11,75	12,25	12	
12,25	12,75	12,5	
12,75	13,5	13	
13,5	14,5	14	
14,5	15,5	15	
15,5	16,5	16	
16,5	17,5	17	
17,5	18,5	18	
18,5	19,5	19	
19,5	20,5	20	
20,5	21,5	21	
21,5	22,5	22	
22,5	23,5	23	
23,5	24,5	24	
24,5	25,5	25	
25,5	27	26	
27	29	28	
29	31	30	
31	33	32	
33	35	34	
35	37	36	
37	39	38	
39	41	40	
41	43	42	
43	45	44	
45	47	46	
47	49	48	
49	51	50	
51	54	52	
54	58	56	
58	62	60	
62	66	64	

Table A.4 (continued)

	4		
Val	Recommended tex value		
over	up to and including	kecommended tex value	
66	70	68	
70	74	72	
74	78	76	
78	82	80	
82	86	84	
86	90	88	
90	94	92	
94	98	96	
98	102,5	100	
102,5	107,5	105	

Annex B

(informative)

Implementation of the tex system in trade and industry

B.1 Introduction

This annex is intended to facilitate the implementation of the Tex System in trade and industry. For this purpose, three stages may be used, but the several units or sections of industry are free to omit the first and/or the second stage if they wish.

No procedure is given as obligatory for the kind of tex value to be used (equivalent, rounded, or recommended tex value).

However, it is recommended that, in the first and second stages, the same numerical value for tex, mtex, dtex or ktex be used as is intended to be used in the third stage.

B.2 Preparatory steps

The trade authorities concerned with each type of product should, as quickly as possible, publish agreed lists in tex units of the yarns and fibres which are to be produced, and give some indication of the timetable for the adoption of the three stages. The tex values of these lists may be equivalent, rounded, or recommended values.

B.3 First stage

While the tables are being prepared and the existing yarn counting and numbering systems continue in use, the equivalent, rounded, or recommended tex value (see B.2) is put in brackets after the count or number in the traditional system. The inclusion of the tex value does not affect commercial tolerances in any way, and every contract or commercial agreement will still refer to the count or number in the traditional system and not to the value in brackets. During this stage, the tex values will facilitate comparison of counts and linear densities designated in different systems.

```
EXAMPLE Ne<sub>L</sub> 25 (68 tex) Nm 4 500 (220 mtex)

Ne<sub>C</sub> 18 (30,5 tex) Td 840 (940 dtex)

Ne<sub>W</sub> 48 (18 tex) Tj 192 (6,6 ktex)
```

B.4 Second stage

The tex value of linear density in tex is now put first and the original nominal number or count is put in brackets after it.

If necessary, spinners will now adjust their production from the traditional counting system to the Tex System in accordance with the appropriate list (see <u>B.2</u>).

Contracts or commercial agreements will now refer specifically to the value of the linear density in tex and not to the traditional figure given in brackets.

```
EXAMPLE 68 tex (Ne<sub>L</sub> 25) 220 mtex (Nm 4 500)
30,5 tex (Ne<sub>C</sub> 18) 940 dtex (Td 840)
18 tex (Ne<sub>W</sub> 48) 6,6 ktex (Tj 192)
```

B.5 Third stage

The designation in brackets is deleted and the Tex System is the only system used.

Bibliography

[1] ISO 1139, Textiles — Designation of yarns



British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible
 by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced in any format to create an additional copy.
 This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com **Email (enquiries):** cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

 $\textbf{Email:} \ knowledge centre @bsigroup.com$

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

