

BS ISO 1171:2010



BSI Standards Publication

# Solid mineral fuels — Determination of ash

**bsi.**

...making excellence a habit.™

Version correct as of 03/01/2015. (c) The British Standards Institution 2013 Licensed copy: Lee Shau Kee Library, HKUST. Version correct as of 03/01/2015. (c) The British Standards Institution 2013 Licensed copy: Lee Shau Kee Library, HKUST.

**National foreword**

This British Standard is the UK implementation of ISO 1171:2010. It supersedes BS 1016-104.4:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PTI/16, Solid mineral fuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 70436 9

ICS 73.040; 75.160.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2010.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

# INTERNATIONAL STANDARD

BS ISO 1171:2010

**ISO**  
**1171**

Fourth edition  
2010-06-15

---

---

## Solid mineral fuels — Determination of ash

*Combustibles minéraux solides — Détermination des cendres*



Reference number  
ISO 1171:2010(E)

© ISO 2010

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Principle</b> .....	<b>1</b>
<b>3</b> <b>Apparatus</b> .....	<b>1</b>
<b>4</b> <b>Preparation of test sample</b> .....	<b>1</b>
<b>5</b> <b>Procedure</b> .....	<b>1</b>
<b>6</b> <b>Expression of results</b> .....	<b>2</b>
<b>7</b> <b>Precision</b> .....	<b>2</b>
<b>8</b> <b>Test report</b> .....	<b>3</b>
<b>Bibliography</b> .....	<b>4</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 562 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This fourth edition cancels and replaces the third edition (ISO 1171:1997), of which it constitutes a minor revision. (It also incorporates the Technical corrigendum ISO 1171:1997/Cor.1:1998.)

## Introduction

The ash remaining after coal or coke has been incinerated in air is derived from inorganic complexes present in the original coal substance and from associated mineral matter. Therefore, the result of the determination is “ash” and not “ash content” as coal does not contain any ash.

The amount of sulfur retained in the ash is in part dependent on the conditions of ashing and, in order to obtain values for the ash on a comparable basis, it is necessary to adhere strictly to the conditions specified.





# Solid mineral fuels — Determination of ash

## 1 Scope

This International Standard specifies a method for the determination of the ash of all solid mineral fuels.

## 2 Principle

The test portion is heated in air at a specified rate up to a temperature of  $815\text{ °C} \pm 10\text{ °C}$  and maintained at this temperature until constant in mass.

The ash is calculated from the mass of the residue after incineration.

## 3 Apparatus

**3.1 Balance**, capable of weighing to the nearest 0,1 mg.

**3.2 Furnace**, capable of giving a zone of substantially uniform temperature at the levels required by the procedure and reaching these levels in the specified times.

The ventilation through the furnace shall be such as to give five to ten air changes per minute.

**NOTE** The number of air changes per minute can be assessed by the measurement of the air flow in the furnace flue with a pitot-static tube and a suitable manometer.

Alternatively, two furnaces may be used, one capable of achieving an adequate zone at a uniform temperature of approximately  $500\text{ °C}$  and the second capable of maintaining a temperature of  $815\text{ °C} \pm 10\text{ °C}$ .

**3.3 Dish**, of silica, porcelain or platinum, 8 mm to 15 mm deep, of such a size that the sample loading does not exceed  $0,15\text{ g/cm}^2$  for coal and  $0,10\text{ g/cm}^2$  for coke.

**3.4 Plate**, for use with coke samples, made from silica or heat-resistant steel, 6 mm thick and of such a size as to be an easy sliding fit into the furnace (3.2).

**3.5 Desiccator or other closed container.**

## 4 Preparation of test sample

The coal or coke used for the determination of ash is the general analysis test sample (ground to pass a sieve of  $212\text{ }\mu\text{m}$  aperture).

The sample shall be well mixed and in moisture equilibrium with the laboratory atmosphere.

## 5 Procedure

Weigh to the nearest 0,1 mg, the clean, dry dish (3.3) (see next paragraph), spread approximately 1 g of the sample (Clause 4) evenly in the dish and reweigh.

If a silica or porcelain dish is used, before its initial mass is determined, it should be heated to  $815\text{ °C} \pm 10\text{ °C}$ , maintained at this temperature for 15 min and then cooled under conditions specified for the actual determination.

Insert the dish in the furnace (3.2) at room temperature. Raise the furnace temperature evenly to  $500\text{ °C}$  over a period of 60 min and hold at this temperature for 30 min. For brown coals, a holding period of 60 min at  $500\text{ °C}$  is necessary.

Continue heating to  $815\text{ °C} \pm 10\text{ °C}$  in the same furnace or, alternatively, transfer the dish to a second furnace, previously heated to  $815\text{ °C} \pm 10\text{ °C}$ . (See 3.2, last paragraph). Maintain this temperature for at least 60 min.

Alternatively for coke, the dish placed on the plate (3.4) may be inserted directly in a furnace at  $815\text{ °C} \pm 10\text{ °C}$ . Maintain at this temperature for at least 60 min.

When the incineration period is complete, remove the dish from the furnace and allow to cool on a thick metal plate for 10 min. At the end of the 10 min cooling period, transfer the dish to a desiccator or other closed container without desiccant and allow to cool to room temperature. When cool, weigh to the nearest 0,1 mg.

The container may be flushed with dry gas in order to reduce the pick-up of moisture during cooling. In this case, the dish should be covered with a lid.

If there is any doubt that incineration is incomplete (e.g. unburned carbon particles are visible), reheat at  $815\text{ °C} \pm 10\text{ °C}$  for further 15 min periods until the change in mass does not exceed 1 mg.

## 6 Expression of results

The ash,  $A$ , of the sample as analysed, expressed as a percentage mass fraction, is given by Equation (1):

$$A = \frac{m_3 - m_1}{m_2 - m_1} \times 100 \quad (1)$$

where

$m_1$  is the mass, expressed in grams, of the empty dish;

$m_2$  is the mass, expressed in grams, of dish plus test portion;

$m_3$  is the mass, expressed in grams, of dish plus ash.

Report the result, as a mean of duplicate determinations, to the nearest 0,1 % mass fraction.

The results of the determination described in this International Standard are reported on the air-dried basis. Calculation of results to other bases is dealt with in ISO 1170.

## 7 Precision

### 7.1 Repeatability limit

The results of duplicate determinations (carried out over a short period of time, but not simultaneously) in the same laboratory by the same operator with the same apparatus on two representative portions taken from the same analysis sample, shall not differ by more than the values given in Table 1.

**Table 1 — Repeatability and reproducibility limits for ash**

Ash % mass fraction	Maximum acceptable difference between results (calculated to the same moisture content)	
	Repeatability limit	Reproducibility limit
< 10 %	0,2 % absolute	0,3 % absolute
> 10 %	2,0 % of the mean result	3,0 % of the mean result

## 7.2 Reproducibility limit

The means of the results of duplicate determinations performed in each of two laboratories, on representative portions taken from the same analysis sample, shall not differ by more than the values given in Table 1.

## 8 Test report

The test report shall include the following information:

- a) reference to this International Standard, i.e. ISO 1171;
- b) identification of the sample;
- c) date of the determination;
- d) results and the calculation basis in which they are expressed.

## Bibliography

- [1] ISO 687, *Solid mineral fuels — Coke — Determination of moisture in the general analysis test sample*
- [2] ISO 1170, *Coal and Coke — Calculation of analyses to different bases*
- [3] ISO 1213-2, *Solid mineral fuels — Vocabulary — Part 2: Terms relating to sampling, testing and analysis*
- [4] ISO 5068 (all parts), *Brown coals and lignites — Determination of moisture content — Indirect gravimetric method*
- [5] ISO 11722, *Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen*



---

---

**ICS 75.160.10**

Price based on 4 pages



# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

...making excellence a habit.™