

BS ISO 1437:2017



BSI Standards Publication

Rubber compounding ingredients — Carbon black — Determination of sieve residue

National foreword

This British Standard is the UK implementation of ISO 1437:2017. It supersedes BS ISO 1437:2007 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Raw materials (including latex) for use in the rubber industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017.
Published by BSI Standards Limited 2017

ISBN 978 0 580 92847 5

ICS 83.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 1437:2017

ISO
1437

Fifth edition
2017-01

**Rubber compounding ingredients —
Carbon black — Determination of
sieve residue**

*Ingrédients de mélange du caoutchouc — Noir de carbone —
Détermination du refus sur tamis*



Reference number
ISO 1437:2017(E)

© ISO 2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Procedure	3
6.1 Precautions	3
6.2 Determination	3
7 Expression of results	4
8 Precision and bias	4
9 Test report	4
Annex A (informative) Precision and bias	5
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fifth edition cancels and replaces the fourth edition (ISO 1437:2007), which has been technically revised. The main changes compared to the previous edition are as follows:

- in the list of apparatus (see [Clause 5](#)), a rubber hose has been added in [5.1.6](#);
- [Figure 1](#) has been revised to include a rubber hose;
- precision data have been moved in [Annex A](#).

Rubber compounding ingredients — Carbon black — Determination of sieve residue

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This document specifies a method for determining the water-wash sieve residue from regular, untreated carbon black for the rubber industry. It may not be applicable to oil-treated blacks because the oil could prevent proper wetting of the black by water.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

A known mass of carbon black is washed through a test sieve by a controlled flow of water, and the residue dried and weighed. The test sieve aperture is chosen from the range given in the appropriate material specification.

5 Apparatus

5.1 Sieving apparatus ([Figure 1](#)), comprising the following main items.

5.1.1 Test sieve, on which the residue is retained. Test sieves shall be of phosphor bronze or stainless steel, according to the characteristics given in ISO 565. Typical nominal apertures are 500 µm, 125 µm and 45 µm.

NOTE By mutual agreement between the interested parties, it is permissible to use sieves with a different aperture size.

5.1.2 Funnel or container, into the bottom of which the test sieve fits.

5.1.3 Nozzle, fed with clean water under controlled pressure by which the carbon black is washed through the sieve.


5.1.4 Water pressure regulating device.

5.1.5 Filter, in the water supply line, incorporating a wire screen at least as fine as that in the test sieve.

The tubing downstream of the filter shall not be liable to corrosion by tap water (use copper or stainless steel, for example).

5.1.6 Rubber hose, to supply water to wash down the funnel or container sides.

An example is given in [Figure 1](#).



Key

- | | |
|--------------------------------|------------------|
| 1 valve A | 8 pressure gauge |
| 2 valve B | 9 nozzle |
| 3 filter | 10 nozzle tip |
| 4 valve C | 11 funnel |
| 5 rubber hose | 12 sieve |
| 6 water pressure control valve | 13 carbon black |
| 7 valve D | |

Figure 1 — Schematic diagram of sieving apparatus¹⁾

5.2 Balance, with an accuracy of 0,1 g.

5.3 Analytical balance, with an accuracy of 0,1 mg.

1) Suitable apparatus includes the Gallie-Porrit type of apparatus and the one described in ASTM D1514-15. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of these products.

5.4 Weighing dishes.

5.5 **Oven**, gravity-convection type, capable of temperature regulation within ± 1 °C at 125 °C and temperature uniformity of ± 5 °C.

6 Procedure

6.1 Precautions

6.1.1 Keep the apparatus clean at all times to prevent contamination.

6.1.2 Examine the sieve each time it is used to make sure no cracks or holes develop.

6.1.3 Examine the wire screen in the filter periodically to ascertain if the filter screen is in good condition.

6.2 Determination

6.2.1 Clean the filter used in the water line before starting a test.

6.2.2 Regulate the water pressure to the recommended pressure of $(0,2 \pm 0,04)$ MPa. Attach a sieve (5.1.1) of the specified aperture to the funnel or container (5.1.2) and allow water to flow through it for 3 min. Examine the sieve for particles. If none are observed, the apparatus is ready for use.

6.2.3 Weigh, to the nearest 0,1 g, a test portion of carbon black of at least 100 g.

6.2.4 Start the water flow. Carefully add carbon black to the funnel or container, taking care to prevent plugging of the sieve.

A wetting agent may be used before starting the water flow.

6.2.5 Wash down the carbon black from the funnel or container sides with water from the rubber hose (5.1.6). Continue to wash the residue on the sieve until the wash water coming through the sieve is clear.

6.2.6 Remove the sieve and rub the residue lightly with the finger to break up any agglomerates of carbon black which have not been thoroughly wetted by the water. Do not exert so much pressure with the finger that the sieve mesh is distorted.

6.2.7 Replace the sieve and wash for an additional 2 min.

6.2.8 Remove the sieve and dry in the oven (5.5) at 125 °C for 1 h.

6.2.9 Transfer the dried residue to a piece of smooth, white bond paper and rub gently to remove any carbon black remaining in the residue. Rub until the white paper no longer shows any smears.

6.2.10 Transfer the residue to a tared weighing dish (5.4) and weigh to the nearest 0,1 mg.

7 Expression of results

Either calculate the sieve residue, R , expressed in mg/kg (parts per million) using [Formula \(1\)](#):

$$R = \frac{m_1}{m_0} \times 10^6 \quad (1)$$

Or calculate the sieve residue, R , expressed as a percentage (%) using [Formula \(2\)](#):

$$R = \frac{m_1}{m_0} \times 100 \quad (2)$$

where

m_0 is the mass of the test portion, in grams (g);

m_1 is the mass of the residue retained on the sieve, in grams (g).

8 Precision and bias

See [Annex A](#).

9 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 1437;
- b) all details necessary for the identification of the sample;
- c) the nominal values of the sieve apertures;
- d) the type of apparatus used and the water pressure;
- e) the results and the units in which the results were expressed;
- f) the date of the test.

Annex A (informative)

Precision and bias

A.1 Precision

A.1.1 The precision of this test method was determined in accordance with ISO/TR 9272:2005, level 2 method. Refer to ISO/TR 9272 for terminology and other statistical details.

A.1.2 The precision results give an estimate of the precision to be expected. The precision parameters are not intended to be used for acceptance/rejection testing of any group of materials without documentation that they are applicable to those particular materials and the specific testing protocols that include this test method.

A.1.3 A type 1 precision interlaboratory-trials programme was conducted. Both the repeatability and the reproducibility determined represent short-term testing conditions. 16 laboratories tested two carbon blacks, twice on each of two different days: one with a considerable level and one with a very high level of sieve residue. Therefore, $p = 16$, $q = 2$ and $n = 4$. A test result is the value obtained from a single determination. Acceptable difference values were not measured.

A.1.4 The results of the precision calculations are given in [Table A.1](#), with the materials arranged in descending order of mean sieve residue. Outliers have been removed. The number of laboratories remaining after outlier deletion is given in [Table A.1](#).

Table A.1 — Precision calculations

Material	Number of laboratories	Mean sieve residue mg/kg (ppm)	Within-laboratory			Between laboratories		
			s_r	r	(r)	s_R	R	(R)
A	13	98,6	10,14	28,69	29,09	30,10	89,85	91,11
B	15	362,0	55,88	158,04	43,66	194,37	572,02	158,01
Average	14	230,3						
Pooled values			40,16	113,58	37,10	139,08	409,44	128,97

s_r is the within-laboratory standard deviation;

r is the repeatability (in measurement units);

(r) is the repeatability (in percent);

s_R is the between-laboratory standard deviation;

R is the reproducibility (in measurement units);

(R) is the reproducibility (in percent).

A.1.5 The precision for the pooled values of the sieve residue may be expressed as follows.

- a) Repeatability: the repeatability (r) for the sieve residue has been established as 37,1 %. Two single test results (or determinations) that differ by more than 37,1 %, should be considered suspect and dictate that some appropriate investigative action be taken.
- b) Reproducibility: the reproducibility (R) for the sieve residue has been established as 129,0 %. Two single test results (or determinations), produced in separate laboratories, that differ by

more than 129,0 %, should be considered suspect and dictate that some appropriate investigative action be taken.

A.2 Bias

In test method terminology, bias is the difference between an average test value and a reference (true) test property value. Reference values do not exist for this test method since the value of the test property is exclusively defined by the test method. Bias, therefore, cannot be determined.

Bibliography

- [1] ISO/TR 9272:2005, *Rubber and rubber products — Determination of precision for test method standards*
- [2] ASTM D 1514-15, *Standard Test Method for Carbon Black — Sieve Residue*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK