

BS ISO 1887:2014



BSI Standards Publication

# Textile glass — Determination of combustible-matter content

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 1887:2014. It supersedes BS ISO 1887:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/42, Fibre reinforced thermosetting plastics and prepregs.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 74660 4

ICS 59.100.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2014.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

BS ISO 1887:2014

**ISO**  
**1887**

Fourth edition  
2014-09-01

---

---

**Textile glass — Determination of  
combustible-matter content**

*Verre textile — Détermination de la teneur en matières combustibles*



Reference number  
ISO 1887:2014(E)

© ISO 2014



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Terms and definitions .....</b>	<b>1</b>
<b>3 Principle .....</b>	<b>1</b>
<b>4 Apparatus .....</b>	<b>1</b>
<b>5 Test specimens .....</b>	<b>2</b>
5.1 Selection of test specimens .....	2
5.2 Number of test specimens .....	3
<b>6 Procedure .....</b>	<b>3</b>
6.1 Precautions to be taken during test .....	3
6.2 Weighing the specimen holder .....	3
6.3 Weighing the dried test specimen plus holder .....	4
6.4 Weighing the calcinated test specimen plus holder .....	4
<b>7 Expression of results .....</b>	<b>5</b>
<b>8 Precision .....</b>	<b>5</b>
<b>9 Test report .....</b>	<b>5</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

This fourth edition cancels and replaces the third edition (ISO 1887:1995), which has been technically revised.

# Textile glass — Determination of combustible-matter content

## 1 Scope

This International Standard specifies a method for the determination of the combustible-matter content of products made from textile glass, such as continuous-filament yarns, staple-fibre yarns, rovings, chopped strands, milled fibres, fabrics, chopped-strand and continuous-filament mats, and other glass reinforcements.

## 2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 2.1

#### **combustible-matter content**

ratio of the mass of material removed on calcination from a dried textile glass product to the mass of the dried product

Note 1 to entry: This ratio is expressed as a percentage in this International Standard. It is equal to the content of size or finish on the textile glass product when the size or finish is completely combustible without significant residue (i.e. primarily organic products).

## 3 Principle

Test specimens, dried under prescribed conditions, are weighed before and after calcination at a temperature of  $625\text{ °C} \pm 20\text{ °C}$  or, with types of glass which are unstable at this temperature, at a temperature between  $500\text{ °C}$  and  $600\text{ °C}$ , also kept constant to within  $20\text{ °C}$ .

## 4 Apparatus

**4.1 Air-circulation oven**, for drying specimens, capable of being maintained at  $105\text{ °C} \pm 5\text{ °C}$  or the chosen drying temperature and maintained to within  $\pm 5\text{ °C}$  (see 6.3).

**4.2 Muffle furnace**, capable of being maintained, with a tolerance of  $\pm 20\text{ °C}$ , at any desired temperature up to  $625\text{ °C}$ , the temperature being measured at the centre of the muffle furnace with the door closed.

**4.3 Desiccator**, containing a suitable desiccant, for example silica gel, calcium chloride, phosphorous(V) oxide.

**4.4 Specimen holder**, made from a material stable at the test temperature, allowing the best possible air circulation around the test specimen and designed to prevent loss of material. The holder may be a porcelain crucible, a basket made of stainless-steel gauze, etc.

**4.5 Stainless-steel tongs**, for handling test specimens and holders.

**4.6 Balance**, accurate to 0,1 mg.

**4.7 Polished-metal templates**, for the preparation of test specimens.

**4.8 Suitable cutting tool**, for cutting mat or fabric, for example a knife, scissors, or a cutting disc.

**4.9 Suitable wrap-reel**, for taking yarn and roving test specimens.

## 5 Test specimens

### 5.1 Selection of test specimens

Unless stated to the contrary in the product specification or by the person requesting the test, the test specimens shall be selected as specified in [5.1.1](#) to [5.1.4](#).

#### 5.1.1 Yarns and rovings

[Table 1](#) gives the length of yarn to be taken as a function of the linear density of the yarn. The test specimen shall not be unduly compressed, in order to ensure that the air will circulate as freely as possible and that drying and calcination will therefore be complete.

**Table 1**

Linear density, Tt tex	Length of yarn m
$Tt \leq 25$	500
$25 < Tt \leq 45$	200
$45 < Tt \leq 280$	100
$280 < Tt \leq 650$	50
$650 < Tt \leq 2\,000$	10
$2\,000 < Tt$	5

#### 5.1.2 Chopped strands and milled fibres

Each specimen shall have a mass of not less than 5 g, but preferably between 15 g and 30 g.

#### 5.1.3 Fabrics

Each specimen shall have a mass of not less than 5 g.

The recommended specimen shape is a rectangle measuring 150 mm × 80 mm. Cut the specimen out using the template ([4.7](#)) and the cutting tool ([4.8](#)) and fray out the edges over about 5 mm to prevent any subsequent loss of yarns.

If it is necessary to use more than one rectangle to achieve the required minimum specimen mass, these shall be taken along the length of the roll, in the same lane.

The test-specimen dimensions shall be compatible with the apparatus (muffle furnace, balance). If for this reason it has not been possible to comply with the specified dimensions or the 5 g minimum mass, this shall be mentioned in the test report (see also [5.2](#)).

#### 5.1.4 Mats

The test specimen shall have a mass of at least 5 g. The recommended specimen shape is a square measuring 316 mm × 316 mm (0,1 m<sup>2</sup>). However, other shapes may be used provided that the area is approximately 0,1 m<sup>2</sup>. In this case, it is necessary to modify slightly the preparation procedure described below.



If it is necessary to use more than one square to achieve the required minimum specimen mass, these shall be taken along the length of the roll, in the same lane.

Cut a strip of width at least 316 mm from across the whole width of the mat. Using the template (4.7) and the cutting tool (4.8), cut from this strip:

- a) at each end (in the case of mats with trimmed edges, at least 10 mm inside the edges), a test specimen measuring 316 mm × 316 mm;
- b) between these end specimens, as many test specimens measuring 316 mm × 316 mm as the remaining width allows (these test specimens shall be evenly distributed).

## 5.2 Number of test specimens

Unless stated to the contrary or in more detail (i.e. number and location) in the specification or by the person requesting the test, the number of test specimens taken per elementary unit shall be as specified in Table 2.

**Table 2**

Type of product	Number of test specimens
Yarns, roving	1
Chopped strands, milled fibres	1
Fabrics, mats	3 for each metre of width, repeated regularly across the full width

NOTE The number of test specimens used for each determination of the combustible-matter content can be modified depending on the type of elementary unit, which can come in very different forms. In addition, a determination might have to be repeated at one or more locations in the elementary unit depending on the mass (chopped strands, milled fibre) or the length (fabrics, mats) of the elementary unit being tested. The additional information concerning the number and location of these specimens can be given in the product specification or by the person requesting the test.

## 6 Procedure

### 6.1 Precautions to be taken during test

- 6.1.1 Ensure that the test specimen does not come into contact with the furnace during the carbonization stage.
- 6.1.2 Always transfer the test specimen plus holder with care to prevent loss of material.
- 6.1.3 Never touch the test specimen with the bare hands.

### 6.2 Weighing the specimen holder

Stabilize the mass of the specimen holder (4.4) by placing it in the muffle furnace (4.2), maintained at 625 °C ± 20 °C or, if the type of glass being tested is unstable at this temperature, at a temperature between 500 °C and 600 °C, also maintained to within ±20 °C. The temperature between 500 °C and 600 °C shall be chosen either on the basis of the specification for the glass or by agreement between the interested parties.

Allow the holder to cool in the desiccator (4.3), to ambient temperature.

Weigh the holder and note the mass to the nearest 0,1 mg ( $m_0$ ).

Repeat the heating, cooling and weighing operations until constant mass is reached (see, however, note 3 in 6.4).

### 6.3 Weighing the dried test specimen plus holder

Place the holder with a specimen in the oven (4.1), maintained at  $105\text{ °C} \pm 5\text{ °C}$  or, in the case of products containing components which are volatile, or susceptible to change, at this temperature, a lower temperature chosen by agreement between the interested parties and also maintained to within  $\pm 5\text{ °C}$ .

NOTE For fabrics and mats, the specimens can be cut and stacked rather than folded, in order to put them in a holder which fits into the apparatus (muffle furnace, balance).

Heat the specimen for at least 30 min.

Remove the holder plus specimen from the drying oven and allow to cool in the desiccator (4.3) for 30 min.

Weigh the holder plus dried specimen and note the mass to the nearest 0,1 mg ( $m_1$ ).

Repeat the heating, cooling and weighing operations until constant mass is reached (see, however, note 3 in 6.4).

### 6.4 Weighing the calcinated test specimen plus holder

Place the holder plus dried specimen in the muffle furnace (4.2), maintained at  $625\text{ °C} \pm 20\text{ °C}$  or at the chosen temperature between  $500\text{ °C}$  and  $600\text{ °C}$  (see 6.2).

Allow the specimen to burn for 5 min with the door of the furnace open (see notes 1 and 2). Then close the door of the furnace and heat for a further more than 10 min or, if a temperature lowers than  $625\text{ °C}$  is used, for at least a further 1 h.

Remove the holder plus specimen from the furnace and transfer to the desiccator (4.3). Allow to cool to ambient temperature.

Weigh the holder plus calcinated specimen and note the mass to the nearest 0,1 mg ( $m_2$ ).

Repeat the heating, cooling, and weighing operations until constant mass is reached (see, however, note 3).

NOTE 1 The door is left open to allow volatile products to escape from the furnace, thus preventing condensable materials being redeposited on the specimen or on the holder.

NOTE 2 If a ventilated furnace is used, this open-door time is not necessary.

NOTE 3 The test method requires that all weighings be confirmed to be to constant mass by repetition of the drying and calcination stages. In cases in which known materials are being tested regularly, the user of this International Standard is permitted to define, by experimentation, a minimum time for the drying and calcination stages to ensure that constant mass has been obtained.

## 7 Expression of results

The combustible-matter content of a test specimen, expressed as a percentage by mass of the dried product, is given by the formula:

$$H_1 = \frac{m_1 - m_2}{m_1 - m_0} \times 100$$

where

$H_1$  is the combustible-matter content;

$m_0$  is the mass, in grams, of the holder;

$m_1$  is the mass, in grams, of the holder plus the dried specimen;

$m_2$  is the mass, in grams, of the holder plus the dried and calcinated specimen.

Take as the result of the determination of the combustible-matter content either the result obtained with the single test specimen if only one was used or the average of the results obtained, if more than one specimen was used, and express the result to two places of decimals.

If this determination is repeated for several locations in the elementary unit, the person requesting the test shall stipulate if each determination is to be reported separately or if the average of the different determinations is to be calculated to obtain the test result for the whole elementary unit.

## 8 Precision

The precision of this test method is not known because inter-laboratory data are not available. Inter-laboratory data are being obtained and a precision statement will be added at the following revision.

## 9 Test report

The test report shall include the following particulars:

- a) a reference to this International Standard (i.e. ISO 1887);
- b) all details necessary for the complete identification of the textile glass product tested;
- c) the temperature of the muffle furnace, if different from 625 °C;
- d) the temperature of the drying oven, if different from 105 °C;
- e) the number of test specimens used and the dimensions and mass of each;
- f) the result or results obtained for each elementary unit sampled, and the arithmetic mean of all the results obtained for each elementary unit sampled (sample average);
- g) any operational details not specified in this International Standard and any circumstances liable to have had an influence upon the results.





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™