

BS ISO 2028:2015



BSI Standards Publication

Synthetic rubber latex — Preparation of dry polymer

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 2028:2015. It supersedes BS ISO 2028:1999 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 89094 9
ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 2028:2015

ISO
2028

Fifth edition
2015-06-01

**Synthetic rubber latex — Preparation
of dry polymer**

Latex de caoutchouc synthétique — Préparation du polymère sec



Reference number
ISO 2028:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Procedure	3
6.1 General.....	3
6.2 Styrene-butadiene (SBR) latices (of less than 55 % solids content).....	3
6.3 Carboxylated (X-SBR and X-NBR) latices.....	3
6.4 Nitrile (NBR) latices.....	4
6.5 Concentrated latices (more than 55 % solids content).....	4
7 Report	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fifth edition cancels and replaces the fourth edition (ISO 2028:1999), which has been technically revised with the following modifications.

- [Clause 2](#) "Normative references" has been updated.
- In [4.1](#), the note giving information on which company may provide polyamine polyelectrolytes, has been deleted.

Synthetic rubber latex — Preparation of dry polymer

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies four methods for the isolation of dry polymer from synthetic polymer latices containing anionic surfactants, for the purpose of subsequent testing. Tests to be performed include the determination of the Mooney viscosity, the bound-styrene or acrylonitrile content in the polymer chain or the mill shrinkage.

Because of the wide variety of surfactants and stabilizers used in the manufacture of synthetic rubber latices, there is not one method suitable for all latices. The methods given in this International Standard are suitable for a wide variety of latices, but their applicability is to be confirmed for individual types. Latices containing non-ionic stabilizers, in particular, may be resistant to coagulation.

These methods are not necessarily suitable, without modification, for latices containing polymers having high tack.

The dry polymer as isolated may contain residual organic acids or their aluminium salts which may affect the properties of the polymer and which are to be taken into account when performing analytical tests.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 124, *Latex, rubber — Determination of total solids content*

3 Principle

The latex is coagulated in the presence of an antioxidant, using different procedures depending on the type of latex. The resultant crumb is washed with water and dried in a ventilated oven at 70 °C to constant mass.

NOTE Freezing is also a suitable method for the isolation of some latices; sufficient details of the method are not available for inclusion in this edition of ISO 2028.

4 Reagents

During the preparation of the reagent solutions and the isolation of the polymer, use only distilled water or water of equivalent purity.

4.1 Coagulant A

Coagulant A is an aqueous solution of a polyamine polyelectrolyte, prepared by dissolving 2,5 g of polyamine polyelectrolyte in 1 dm³ of hot, 50 °C water and then diluting the resultant solution to 10 dm³.

NOTE Any residues of polyamine electrolyte left in the polymer following isolation are likely to interfere in the determination of bound acrylonitrile.

4.2 Coagulant B

Coagulant B is a solution of aluminium sulfate in dilute sulfuric acid. Prepare dilute sulfuric acid by slowly and cautiously adding 82 cm³ of concentrated sulfuric acid to 1 dm³ of water and cooling. Separately, prepare a solution of aluminium sulfate by adding 200 cm³ of 500 g/dm³ aluminium sulfate solution to 200 cm³ of water and straining through a piece of gauze. Add the diluted aluminium sulfate solution to the diluted sulfuric acid and adjust the volume to 1,5 dm³ with water.

4.3 Antioxidant, for example trinonyl phenyl phosphite (TNPP).

Prepare an aqueous emulsion of antioxidant containing 25 g of antioxidant in 100 cm³ of emulsion.

The antioxidant chosen should preferably be one known to be suitable for use with the polymer to be isolated.

4.4 Aluminium sulfate solution, prepared by dissolving 4 g of aluminium sulfate in water and diluting the resultant solution to 100 cm³.

4.5 Ethanol, minimum purity 99 %.

5 Apparatus

Standard laboratory equipment plus the following.

5.1 Stainless-steel beaker, 5 dm³ capacity.

5.2 Graduated cylinders, 10 cm³, 500 cm³ and 1 000 cm³ capacity.

5.3 Electric stirrer, with two propeller-type blades of approximately 35 mm diameter, mounted 50 mm apart at right angles to the shaft.

5.4 Magnetic stirrer.

5.5 Suitable device for injecting steam, fed from a low-pressure source.

NOTE Steam is the most efficient method of heating liquids rapidly.

5.6 Gauze filter, e.g. cheese cloth.

5.7 Drying pan, aluminium or enamel-lined pan with a suitable surface area (approximately 500 cm²) on which to spread out the crumb for drying. The pan should be relatively light in weight.

5.8 Ventilated oven, capable of being maintained at 70 °C ± 5 °C.

5.9 Balance, capable of being read to 0,1 g.

6 Procedure

6.1 General

Use a test sample of the latex prepared by one of the methods described in ISO 123.

If the solids content of the latex is not known, determine it in accordance with ISO 124.

6.2 Styrene-butadiene (SBR) latices (of less than 55 % solids content)

6.2.1 If it is not known whether or not the latex contains an antioxidant, transfer a portion of the test sample containing approximately 100 g of dry polymer to a clean, dry beaker and add 10 cm³ of the antioxidant emulsion (4.3). Stir well.

6.2.2 Transfer 2 dm³ ± 50 cm³ of coagulant A (4.1) to a 5 dm³ stainless-steel beaker (5.1) and heat to 65 °C ± 5 °C by injecting steam (see 5.5).

Introduce the electric stirrer and stir at approximately 105 rad/s (1 000 r/min) while adding, in a slow stream, a quantity of latex containing approximately 100 g of dry polymer with antioxidant (see 6.2.1).

Continue stirring for 1 min to ensure uniform mixing, then slowly add 15 cm³ of coagulant B (4.2) dropwise. If complete precipitation is not achieved with the formation of fine crumbs and a clear serum, add a further 1 cm³ of coagulant B.

6.2.3 Strain through a clean gauze (5.6) and wash the residue of precipitated rubber particles with water at 50 °C ± 5 °C for 120 s ± 15 s.

Allow the gauze to drain, then wrap it around the precipitated rubber and transfer it to a beaker containing water at 40 °C ± 5 °C.

Allow to soak for a further 120 s ± 15 s while holding the gauze under the water and squeezing gently with the fingers.

Remove the gauze containing the crumbs from the water and squeeze to eliminate as much water as is practical.

6.2.4 Transfer the damp polymer crumbs to a suitable pan (5.7) lined with a double layer of clean gauze and ensure that they are well spread out over the whole surface area.

Dry in a ventilated oven (5.8) at 70 °C ± 5 °C for 5 h. Using a balance (5.9), weigh the container and dried crumbs. Record the mass to 0,1 g.

Return the container to the oven for a further 1 h and re-weigh. Continue to dry in the oven for 1 h periods until the loss in mass between successive weightings is less than 0,5 g.

6.3 Carboxylated (X-SBR and X-NBR) latices

6.3.1 If it is not known whether or not the latex contains an antioxidant, transfer a portion of the test sample containing approximately 100 g of dry polymer to a clean, dry beaker and add 10 cm³ of the antioxidant emulsion (4.3). Stir well.

6.3.2 Take a portion of latex containing approximately 100 g of dry polymer with antioxidant (see 6.3.1) in a 1 dm³ beaker and add 500 cm³ of water. Stir well. Proceed as described in 6.2.2, 6.2.3 and 6.2.4.

6.4 Nitrile (NBR) latices

6.4.1 If it is not known whether or not the latex contains an antioxidant, transfer a portion of the test sample containing approximately 100 g of dry polymer to a clean, dry beaker and add 10 cm³ of the antioxidant emulsion (4.3). Stir well.

6.4.2 Transfer 2 dm³ of the diluted aluminium sulfate solution (4.4) to a 5 dm³ stainless-steel beaker (5.1) and raise the temperature to 65 °C ± 5 °C by passing in steam (see 5.5).

Remove the steam injector and introduce the electric stirrer (5.3). Stir at approximately 105 rad/s (1 000 r/min) while adding, in a slow stream, a portion of the latex containing approximately 100 g of dry polymer together with antioxidant (see 6.4.1).

Continue stirring for a further 5 min, then proceed as described in 6.2.3 and 6.2.4.

6.5 Concentrated latices (more than 55 % solids content)

6.5.1 If it is not known whether or not the latex contains an antioxidant, transfer a 200 g portion of the test sample to a clean, dry beaker and add 10 cm³ of the antioxidant emulsion (4.3). Stir until thoroughly mixed.

6.5.2 Transfer 2 dm³ of ethanol (4.5) into a 5 dm³ stainless-steel beaker equipped with a magnetic stirrer (5.4). While stirring slowly, add, in a steady stream, 200 g ± 5 g of the latex containing antioxidant (see 6.5.1).

Continue stirring until the latex has completely precipitated and the serum is clear. Continue as described in 6.2.3 and 6.2.4.

7 Report

The report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 2028;
- b) all details necessary for complete identification of the test sample;
- c) whether or not an antioxidant was added, and if so its identity;
- d) which method (i.e. 6.2, 6.3, 6.4 or 6.5) was used;
- e) any unusual features noted during the test;
- f) full details of any operation not included in this International Standard or in any of the International Standards to which reference is made, together with any operation regarded as optional;
- g) the date of the test.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™