

BS ISO 2476:2014



BSI Standards Publication

# Butadiene rubber (BR) — Solution-polymerized types — Evaluation procedures

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 2476:2014. It supersedes BS ISO 2476:2009 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 79384 4

ICS 83.060

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

**ISO**  
**2476**

Sixth edition  
2014-03-01

---

---

**Butadiene rubber (BR) — Solution-  
polymerized types — Evaluation  
procedures**

*Caoutchouc butadiène (BR) — Types polymérisés en solution —  
Méthodes d'évaluation*



Reference number  
ISO 2476:2014(E)



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Sampling and further preparative procedures</b> .....	<b>1</b>
<b>4 Physical and chemical tests on raw rubber</b> .....	<b>2</b>
4.1 Mooney viscosity.....	2
4.2 Volatile matter.....	2
4.3 Ash.....	2
<b>5 Preparation of test mixes for evaluation of butadiene rubbers</b> .....	<b>2</b>
5.1 Standard test formulations.....	2
5.2 Procedure.....	3
<b>6 Conditioning of batches</b> .....	<b>8</b>
<b>7 Evaluation of vulcanization characteristics</b> .....	<b>8</b>
7.1 Using an oscillating-disc curemeter.....	8
7.2 Using a rotorless curemeter.....	8
<b>8 Evaluation of tensile stress-strain properties of vulcanized test mixes</b> .....	<b>9</b>
<b>9 Precision</b> .....	<b>9</b>
<b>10 Test report</b> .....	<b>9</b>
<b>Annex A (informative) Precision</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>15</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This sixth edition cancels and replaces the fifth edition (ISO 2476:2009), which has been technically revised with the following changes:

- ISO 2476 has been aligned with ISO 2393:2014;
- [5.2.2.1](#) states that the laboratory internal mixer procedure is the preferred method.

# Butadiene rubber (BR) — Solution-polymerized types — Evaluation procedures

**WARNING** — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

## 1 Scope

This International Standard specifies:

- physical and chemical tests on raw rubbers;
- standard materials, standard test formulations, equipment, and processing methods for evaluating the vulcanization characteristics of solution-polymerized butadiene rubbers (BR), including oil-extended types (OEBR), and the tensile stress-strain properties of vulcanized mixes.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 247:2006, *Rubber — Determination of ash*

ISO 248-1, *Rubber, raw — Determination of volatile-matter content — Part 1: Hot-mill method and oven method*

ISO 248-2, *Rubber, raw — Determination of volatile-matter content — Part 2: Thermogravimetric methods using an automatic analyser with an infrared drying unit*

ISO 289-1, *Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Part 1: Determination of Mooney viscosity*

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

ISO 2393, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures*

ISO 3417, *Rubber — Measurement of vulcanization characteristics with the oscillating disc curemeter*

ISO 6502, *Rubber — Guide to the use of curemeters*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Sampling and further preparative procedures

**3.1** Take a laboratory sample of approximately 1,5 kg by the method described in ISO 1795.

**3.2** Prepare test samples in accordance with ISO 1795.

## 4 Physical and chemical tests on raw rubber

### 4.1 Mooney viscosity

Determine the Mooney viscosity in accordance with ISO 289-1 on a test sample prepared as indicated in ISO 1795 (preferably without milling). If milling is necessary, maintain the mill roll surface temperature at  $35\text{ °C} \pm 5\text{ °C}$ . Record the result as ML(1 + 4) at 100 °C.

### 4.2 Volatile matter

Determine the volatile-matter content in accordance with ISO 248-1 and ISO 248-2.

### 4.3 Ash

Determine the ash in accordance with ISO 247.

## 5 Preparation of test mixes for evaluation of butadiene rubbers

### 5.1 Standard test formulations

Two standard test formulations are given in [Table 1](#). The materials used shall be national or International Standard reference materials (or, if no standard reference material is available, as agreed by the interested parties).

**Table 1 — Standard test formulations**

Material	Parts mass fraction	
	Non-oil-extended	Oil-extended
Butadiene rubber	100,00	100,00 + Y <sup>a</sup>
Zinc oxide	3,00	3,00
IRB <sup>b</sup>	60,00	0,6 × (100 + Y)
Stearic acid	2,00	2,00
ASTM 103 oil <sup>c</sup>	15,00	—
Sulfur	1,50	1,50
TBBS <sup>d</sup>	0,90	0,009 × (100 + Y)
Total	182,40	167,40 + 1,609Y
Calculated density, g/cm <sup>3</sup>	1,11	—

<sup>a</sup> Y = parts of oil, mass fraction, per 100 parts of base polymer in the oil-extended rubber.

<sup>b</sup> Use the current industrial reference black. Dry the material for 1 h at  $125\text{ °C} \pm 3\text{ °C}$  and store in a tightly closed container.

<sup>c</sup> This oil, density 0,92 g/cm<sup>3</sup>, is produced by the Sun Refining and Marketing Company and distributed by R.E. Carroll, Inc., 1570 North Olden Avenue Ext, Trenton, NJ 08638-3204, USA. Overseas requests should be directed to Sunoco Overseas, Inc., 1801 Market Street, Philadelphia, PA 19103-1699, USA. This is an example of a suitable product available commercially. This information is given for convenience of users of this document and does not constitute an endorsement by ISO of this product. Alternative oils can be used, but might give slightly different results.

<sup>d</sup> N-tert-butylbenzothiazole-2-sulfenamide. This is supplied in powder form having an initial insoluble-matter content, determined in accordance with ISO 11235, of less than 0,3 %. The material shall be stored at room temperature in a closed container and the insoluble matter checked every 6 months. If this is found to exceed 0,75 %, the material shall be discarded or recrystallized.



## 5.2 Procedure

### 5.2.1 General

The equipment and procedure for the preparation, mixing, and vulcanization shall be in accordance with ISO 2393.

### 5.2.2 Mixing procedures

#### 5.2.2.1 General

Five mixing procedures are specified, a procedure using a laboratory internal mixer is preferred.

- method A1: single-stage mixing using a laboratory internal mixer;
- method A2: two-stage mixing using a laboratory internal mixer for both initial and final mixing;
- method B: two-stage mixing using a laboratory internal mixer for initial mixing and a mill for final mixing.

The smaller laboratory internal mixers do not provide enough compound for the final mill mixing since a batch mass of four times the formula mass is required. In these cases, the laboratory internal mixer should be used for the final mixing. The mixer head starting temperature or the batch mass can be adjusted, so that the final temperature of the discharged batch does not exceed 120 °C.

- method C1 and C2: mill mixing.

NOTE 1 These procedures can give different results.

NOTE 2 Mill mixing of solution-polymerized butadiene rubbers is more difficult than with other rubbers, and mixing is best accomplished by using an internal mixer. With some types of butadiene rubber, it is not possible to obtain a satisfactory mix using a mill-mixing procedure.

#### 5.2.2.2 Method A1 — Single-stage mixing using a laboratory internal mixer

For laboratory internal mixers having nominal capacities of 65 cm<sup>3</sup> to about 2 000 cm<sup>3</sup>, the batch mass shall be equal to the nominal mixer capacity, in cubic centimetres, multiplied by the density of the compound. For each batch mixed, the laboratory internal mixer conditions shall be the same during the preparation of a series of identical mixes. At the beginning of each series of test mixes, a machine-conditioning batch shall be mixed using the same formulation as the mixes under test. The laboratory internal mixer shall be allowed to cool down to a specified temperature (60 °C has been found to be suitable) between the end of one test batch and the start of the next. The temperature control conditions shall not be altered during the mixing of a series of test batches.

The mixing technique shall be such as to obtain a good dispersion of all the ingredients.

The temperature of the batch discharged on completion of mixing shall not exceed 120 °C. If necessary, adjust the batch mass or the mixer head starting temperature so that this condition is met.

NOTE 1 The mixing conditions given in [Table A.7](#) for various sizes of laboratory internal mixer might be helpful.

NOTE 2 A general mixing procedure for the laboratory internal mixer is as follows:

	Duration (min)	Cumulative time (min)
a) Charge the chamber with the rubber. Lower the ram.	—	—
b) Masticate the rubber.	1,0	1,0
c) Raise the ram and add the zinc oxide, the oil, the stearic acid, and half of the carbon black. Then sweep the orifice and lower the ram.	1,0	2,0
d) Raise the ram and add the TBBS, the sulfur, and the rest of the carbon black. Then sweep the orifice and lower the ram.	1,0	3,0
e) Allow the batch to mix.	6,0	9,0
f) Turn off the motor, raise the ram, remove or open the mixing chamber, and discharge the batch. Record the maximum batch temperature.		

With some types of mixer, the rotors might need to be turning in order to discharge the batch.

Immediately after discharging the mixed batch, pass it through a mill at  $50\text{ °C} \pm 5\text{ °C}$  once at a 0,5 mm mill opening, and then twice at a 3,0 mm mill opening.

Determine the batch mass and record it. If it differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch.

Prepare a test piece for determining the vulcanization characteristics in accordance with ISO 3417 or ISO 6502, if required. Condition the test piece for 2 h to 24 h, if possible at a standard temperature and humidity as defined in ISO 23529 before testing.

If required, sheet the batch to approximately 2,2 mm for preparing test sheets or the appropriate thickness for preparing ring pieces in accordance with ISO 37. To obtain a grain effect, pass the lengthwise-folded batch in the same direction four times between mill rolls set at an opening between 2,1 mm and 2,5 mm and a temperature of  $50\text{ °C} \pm 5\text{ °C}$ .

### 5.2.2.3 Method A2 — Two-stage mixing using a laboratory internal mixer for both initial and final mixing

#### 5.2.2.3.1 Stage 1 — Initial mixing procedure

See [5.2.2.2](#).

The final temperature of the batch shall not exceed 170 °C. If necessary, adjust the batch mass or the mixer head starting temperature so that this condition is met.

NOTE A general mixing procedure for initial mixing using a laboratory mixer is as follows:

	Duration (min)	Cumulative time (min)
a) Adjust the temperature to $50\text{ °C} \pm 5\text{ °C}$ and the rotor speed and ram pressure of the laboratory internal mixer so that the batch will be discharged under the conditions outlined in e) below. Close the discharge gate, start the motor, and raise the ram.	—	—
b) Load one-half of the rubber, followed by the zinc oxide, the carbon black, the oil (omit from oil-extended BR), the stearic acid, and the balance of the rubber. Lower the ram.	0,5	0,5
c) Allow the batch to mix.	3,0	3,5
d) Raise the ram and clean the mixer throat and the top of the ram. Lower the ram.	0,5	4,0
e) Discharge the batch at a temperature of $170\text{ °C}$ or after a total time of 6 min, whichever occurs first.	2,0	6,0

Immediately after discharging the batch, pass it three times through a laboratory mill with a mill opening of 5,0 mm and at a temperature of  $50\text{ °C} \pm 5\text{ °C}$ . Check-weigh the batch in accordance with ISO 2393. If the mass of the batch differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch and remix.

#### 5.2.2.3.2 Stage 2 — Final mixing procedure

The mixing technique shall be such as to obtain a good dispersion of all the ingredients.

The final temperature of the batch shall not exceed  $120\text{ °C}$ . If necessary, adjust the batch mass or the mixer head starting temperature, so that this condition is met.

NOTE A general mixing procedure for final mixing using a laboratory mixer is as follows.

	Duration (min)	Cumulative time (min)
a) Cool the internal mixer to a temperature of $40\text{ °C} \pm 5\text{ °C}$ , with full cooling water on the rotors. Start the motor and raise the ram.	—	—
b) Leave the cooling water on and the steam off. Roll all the sulfur and the TBBS into one-half of the masterbatch and load into the mixer. Add the remaining portion of the masterbatch. Lower the ram.	0,5	0,5
c) Allow the batch to mix until a temperature of $110\text{ °C}$ or a total time of 3 min is reached, whichever occurs first.	2,5	3,0

Immediately after discharging the batch, pass it through a laboratory mill with the mill opening set at 0,8 mm and at a temperature of  $50\text{ °C} \pm 5\text{ °C}$ .

Pass the rolled batch endwise through the rolls six times.

Sheet the batch to approximately 6 mm. Check-weigh the batch in accordance with ISO 2393. If the mass of the batch differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch and remix. Remove sufficient material for curemeter testing.

Sheet the batch to approximately 2,2 mm for preparing test sheets or to the appropriate thickness for preparing ISO ring specimens in accordance with ISO 37.

#### 5.2.2.4 Method B — Two-stage mixing using a laboratory internal mixer for initial mixing and a mill for final mixing

##### 5.2.2.4.1 Stage 1 — Initial mixing procedure

Proceed in accordance with [5.2.2.3.1](#).

##### 5.2.2.4.2 Stage 2 — Final mill-mixing procedure

The standard laboratory mill batch mass, in grams, shall be based on four times the formula mass.

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified hereunder, make small adjustments to the mill openings.

	Duration (min)	Cumulative time (min)
a) Set and maintain the mill roll temperature at $35\text{ °C} \pm 5\text{ °C}$ and the mill opening at 1,5 mm. Band the masterbatch around the front roll.	1,0	1,0
b) Add the sulfur and the TBBS slowly to the batch. Sweep up any material which has fallen into the mill pan and add it to the mix.	1,0	2,0
c) Make six 3/4 cuts from each side.	1,5	3,5
d) Cut the batch from the mill. Set the mill opening to 0,8 mm and pass the rolled batch endwise through the rolls six times.	1,5	5,0
e) Sheet the batch to approximately 6 mm. Check-weigh the batch in accordance with ISO 2393. If the mass of the batch differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch and remix. Remove sufficient material for curemeter testing.		
f) Sheet the batch to approximately 2,2 mm for preparing test sheets or to the appropriate thickness for preparing ISO ring specimens in accordance with ISO 37.		

#### 5.2.2.5 Methods C1 and C2 — Mill-mixing procedure

##### 5.2.2.5.1 General

Solution-polymerized butadiene rubbers are difficult to process on a mill. Methods A1, A2, and B, which give better dispersion of the ingredients, are preferred. If a laboratory internal mixer is not available, a mill mixing procedure can be used:

- method C1, which can be used for all solution-polymerized butadiene rubbers, whether oil-extended or not;
- method C2, which is limited to non-oil-extended rubbers, but gives easier mixing and leads to better dispersion of the ingredients.

Methods C1 and C2 do not necessarily give identical results for non-oil-extended solution-polymerized butadiene rubbers. In laboratory cross-checks or in a series of evaluations, the same procedure shall therefore be used in all cases.

##### 5.2.2.5.2 Method C1

The standard laboratory batch mass, in grams, shall be based on three times the formulation mass (i.e.  $3 \times 182,40\text{ g} = 547,20\text{ g}$  or  $3 \times 167,40\text{ g} = 502,20\text{ g}$ ). Adjust the mill roll cooling conditions to maintain a temperature of  $35\text{ °C} \pm 5\text{ °C}$  throughout the mixing.

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified hereunder, make small adjustments to the mill openings.

	Duration (min)	Cumulative time (min)
a) Band the rubber with the mill opening set at 1,3 mm.	1,0	1,0
NOTE Non-oil-extended rubbers might require longer milling to achieve a good band.		
b) Add the zinc oxide and the stearic acid evenly across the rolls. Make two 3/4 cuts from each side.	2,0	3,0
c) Add the carbon black evenly across the rolls at a uniform rate. When about half the black has been incorporated, open the rolls to 1,8 mm and then add the remainder of the black. Make two 3/4 cuts from each side, allowing 30 s between each cut. Be certain to add any black that has dropped into the mill pan.	15,0 to 18,0	18,0 to 21,0
d) Add the oil (omit from oil-extended BR) very slowly drop by drop.	8,0 to 10,0	26,0 to 31,0
e) Add the sulfur and the TBBS. Sweep up any material which has fallen into the mill pan and add it to the mix.	2,0	28,0 to 33,0
f) Make six successive 3/4 cuts from each side.	2,0	30,0 to 35,0
g) Cut the batch from the mill. Set the mill opening to 0,8 mm and pass the rolled batch endwise through the rolls six times.	2,0	32,0 to 37,0
h) Sheet the batch to approximately 6 mm. Check-weigh the batch in accordance with ISO 2393. If the mass of the batch differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch and remix. Remove sufficient material for curemeter testing.		
i) Sheet the batch to approximately 2,2 mm for preparing test sheets or to the appropriate thickness for preparing ISO ring specimens in accordance with ISO 37.		

### 5.2.2.5.3 Method C2

The standard laboratory batch mass, in grams, shall be based on two times the formulation mass (i.e.  $2 \times 182,40 \text{ g} = 364,80 \text{ g}$ ). Adjust the mill roll cooling conditions to maintain a temperature of  $35 \text{ }^\circ\text{C} \pm 5 \text{ }^\circ\text{C}$  throughout the mixing. Add the ingredients to the batch slowly and evenly across the rolls. Do not cut the batch before all the ingredients have been incorporated.

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified hereunder, make small adjustments to the mill openings.

	Duration (min)	Cumulative time (min)
a) Pass the rubber twice through the rolls with the mill opening set at $0,45 \text{ mm} \pm 0,01 \text{ mm}$ and then band it. Make two successive 3/4 cuts from each side.	2,0	2,0
b) Add the stearic acid and the zinc oxide. Make three successive 3/4 cuts from each side.	2,0	4,0

	Duration (min)	Cumulative time (min)
c) Add successively half of the oil and half of the carbon black. Make seven successive 3/4 cuts from each side.	12,0	16,0
d) Add successively the remainder of the oil and the remainder of the carbon black. Add any black that has dropped into the mill pan. Make seven 3/4 cuts from each side.	12,0	28,0
e) Add the TBBS and the sulfur. Make six 3/4 cuts from each side.	4,0	32,0
f) Cut the batch from the mill. Set the mill opening to 0,7 mm to 0,8 mm and pass the rolled batch endwise through the rolls six times.	3,0	35,0
g) Sheet the batch to approximately 6 mm and check-weigh the batch in accordance with ISO 2393. If the mass of the batch differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch and remix. Remove sufficient material for curemeter testing.		
h) Sheet the batch to approximately 2,2 mm for preparing test sheets or to the appropriate thickness for preparing ISO ring specimens in accordance with ISO 37.		

## 6 Conditioning of batches

Condition all batches produced for 2 h to 24 h after mixing and prior to vulcanizing, if possible at standard temperature and humidity as defined in ISO 23529.

## 7 Evaluation of vulcanization characteristics

### 7.1 Using an oscillating-disc curemeter

Measure the following standard test parameters:

$M_L$ ,  $M_H$  at defined time,  $t_{s1}$ ,  $t'_c(50)$ , and  $t'_c(90)$

in accordance with ISO 3417, using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute);
- amplitude of oscillation: 1° of arc;
- selectivity: to be chosen to give at least 75 % of full-scale deflection at  $M_H$  (note that, with some rubbers, 75 % might not be attainable);
- die temperature: 160 °C ± 0,3 °C;
- pre-heat time: none.

### 7.2 Using a rotorless curemeter

Measure the following standard test parameters:

$M_L$ ,  $M_H$  at defined time,  $t_{s1}$ ,  $t'_c(50)$ , and  $t'_c(90)$

in accordance with ISO 6502, using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute);
- amplitude of oscillation: 0,5° of arc;
- selectivity: to be chosen to give at least 75 % of full-scale deflection at  $M_H$  (note that, with some rubbers, 75 % might not be attainable);
- die temperature: 160 °C ± 0,3 °C;
- pre-heat time: none.

## 8 Evaluation of tensile stress-strain properties of vulcanized test mixes

Vulcanize sheets at 145 °C for 25 min, 35 min, and 50 min or, alternatively, at 150 °C for 20 min, 30 min, and 50 min. The three periods of cure shall be chosen to cover the undercure, optimum cure, and overcure of the material under test.

Condition the vulcanized sheets for 16 h to 96 h, if possible at standard temperature and humidity as defined in ISO 23529.

Measure the stress-strain properties in accordance with ISO 37.

## 9 Precision

See [Annex A](#).

## 10 Test report

The test report shall include the following:

- a) a reference to this International Standard (i.e. ISO 2476);
- b) all details necessary for the identification of the sample;
- c) the method used for the volatile-matter determination (mill or oven);
- d) the method used for the ash determination (method A or method B of ISO 247:2006);
- e) the reference materials used;
- f) the standard test formulation used;
- g) the mixing procedure used in [5.2.2](#);
- h) the curemeter test used in [Clause 7](#) (ISO 3417 or ISO 6502);
- i) the time at which  $M_H$  was determined in the curemeter test;
- j) the vulcanization temperature and times used in [Clause 8](#);
- k) any unusual features noted during the determinations;
- l) any operation not included in this International Standard or in the International Standards to which reference is made, as well as any operation regarded as optional;
- m) the results and the units in which they have been expressed;
- n) the date of the test.

## Annex A (informative)

### Precision

#### A.1 General

Two interlaboratory test programmes (ITPs) were organized in 1987 and in 2004. The 1987 ITP was conducted with mill mixing. The other was conducted with mill mixing and laboratory internal mixer mixing.

The precision results as determined by these ITPs may not be applied to acceptance or rejection testing of any group of materials or products without documentation that the results of the precision determination actually apply to the products or materials tested.

#### A.2 Precision obtained for mill mixing in the 1987 ITP

##### A.2.1 Details of the ITP

**A.2.1.1** Formulations containing two types of BR were selected and mixes were prepared in each of the 17 laboratories that participated in the programme on each of two days approximately one week apart. Formulation 1 contained a non-oil-extended BR, while Formulation 2 contained an oil-extended BR.

Only method C1 of this International Standard (mill mixing) was used for preparing the mixes.

The mixes were prepared from special samples of all the necessary materials, sent to each laboratory prior to the actual testing. For each material, the samples were drawn from a homogeneous lot. Stress-strain tests were conducted on cured sheets of each of the mixes or compounds as specified by the test programme.

**A.2.1.2** Determinations of modulus (stress at 300 % strain), tensile strength, and percent elongation were made, taking as the result the median of five individual determinations, as specified in ISO 37. All 17 laboratories performed the test using dumb-bell test pieces. Five of the laboratories also performed the test using ring test pieces. The precision thus evaluated is a type 2 precision, and the time period for repeatability and reproducibility is on a scale of days.

##### A.2.2 Precision results

The precision calculations to express repeatability and reproducibility were performed in accordance with ISO/TR 9272:1986.

The precision results are given in [Table A.1](#) for dumb-bell test pieces and in [Table A.2](#) for ring test pieces.

The symbols used in [Tables A.1](#) and [A.2](#) are defined as follows.

- $r$  = repeatability, in measurement units. This is the value below which the absolute difference between two within-laboratory test results can be expected to lie with a specified probability.
- $(r)$  = repeatability, in per cent (relative).



The two within-laboratory test results are obtained with the same method on nominally identical test material under the same conditions (same operator, apparatus, and laboratory) and within a specified time period. Unless stated otherwise, the specified probability is 95 %.

- $R$  = reproducibility, in measurement units. This is the value below which the absolute difference between two between-laboratory test results can be expected to lie with a specified probability.
- $(R)$  = reproducibility, in percent (relative).

The two between-laboratory test results are obtained using the same method on nominally identical test materials under different conditions (different operators, apparatus, and laboratories) and within a specified time period. Unless stated otherwise, the specified probability is 95 %.

It shall be borne in mind that these precision results apply only to the mill-mixing procedure of method C1 of this International Standard.

**Table A.1 — Type 2 precision for dumb-bell test pieces**

Formulation	Average value	Within-laboratory		Between laboratories	
		$r$	$(r)$	$R$	$(R)$
<b>Modulus (at 300 % strain), MPa</b>					
Formulation 1	10,9	1,37	12,6	2,61	23,8
Formulation 2	13,0	1,66	12,8	2,90	22,3
<b>Tensile strength, MPa</b>					
Formulation 1	16,5	1,23	7,47	3,13	18,9
Formulation 2	17,7	1,82	10,3	3,93	22,3
<b>Percent elongation</b>					
Formulation 1	367	35,1	9,55	76,6	20,8
Formulation 2	424	57,8	13,6	127	29,9

**Table A.2 — Type 2 precision for ring test pieces**

Formulation	Average value	Within-laboratory		Between laboratories	
		$r$	$(r)$	$R$	$(R)$
<b>Modulus (at 300 % strain), MPa</b>					
Formulation 1	10,3	0,82	7,98	4,13	40,2
Formulation 2	11,9	0,82	6,93	4,73	39,7
<b>Tensile strength, MPa</b>					
Formulation 1	14,4	0,98	6,81	3,03	21,1
Formulation 2	15,8	1,40	8,88	4,36	27,6
<b>Percent elongation</b>					
Formulation 1	362	62,1	17,2	62,1	17,2
Formulation 2	433	51,7	11,9	51,7	11,9

### A.3 Precision obtained for both mill and internal mixer in the 2004 ITP

#### A.3.1 Details of the ITP

The ITP to determine the precision using a laboratory mill and various sizes of internal mixer was conducted on compounds which were based on the formulation for non-oil-extended BR in [Table 1](#),

using Neocis BR40, an Nd-catalysed high-cis 1,4-polybutadiene with a cis content of 97 %. The ITP was conducted as part of the revision of ISO 2393:1994.

NOTE The internal mixers used covered those types often described as “miniature”, “internal”, and “laboratory”.

The ITP was carried out using the precision procedures and guidelines described in the newly revised ISO/TR 9272:2005. This revised Technical Report, which replaces ISO/TR 9272:1986, was under ballot review at the time of the ITP. Reference should be made to ISO/TR 9272:2005 for other details and terminology on precision evaluation.

Two types of measurement were used to evaluate each type of mixing procedure: stress-strain testing and curemeter testing. Stress-strain property precision was determined for stress (modulus) at 100 %, 200 %, and 300 % elongation, elongation at break and tensile strength. Curemeter precision was determined for  $M_H$  (maximum torque),  $M_L$  (minimum torque),  $t_{s1}$  (scorch time or time to a 1 dN·m rise),  $t'_c(50)$  (time to 50 % of full torque), and  $t'_c(90)$  (time to 90 % of full torque). A type 2 precision was determined. The compounds were prepared and tested on a day 1/day 2 basis one week apart.

On each day, homogeneous materials were used to prepare a separate mix for each type of compound, and the appropriate testing (stress-strain and curemeter) was conducted on each of these mixes for each of the two test days. The test result was taken as the average of two replicate test values obtained on each of the two separate test days and the precision was calculated from these test results.

For the internal mixer testing, 10 laboratories participated in the test programme. However, each laboratory did not have the same type or size of mixer. The sizes of the mixers used in the ITP were 75 cm<sup>3</sup>, 80 cm<sup>3</sup>, 270 cm<sup>3</sup>, 379 cm<sup>3</sup>, 422 cm<sup>3</sup>, 588 cm<sup>3</sup>, 1 500 cm<sup>3</sup>, 1 580 cm<sup>3</sup>, 1 600 cm<sup>3</sup>, and 3 322 cm<sup>3</sup>. Some laboratories submitted data from more than one size of mixer, and the data from these separate mixers were incorporated into the ITP as data from individual laboratories. This gave a database equivalent to 17 laboratories. Each of the mixer-laboratory combinations was designated as a pseudo-laboratory.

### A.3.2 Precision results

The precision results for both types of mixing, for both stress-strain and curemeter testing, are given in [Tables A.3](#) to [A.6](#). These results were obtained using the option 1 outlier deletion procedures described in ISO/TR 9272:2005. General statements for the use of the precision results are given below. These are given in terms of both the absolute precision,  $r$  and  $R$ , and also for relative precision,  $(r)$  and  $(R)$  (see additional discussion below).

*Repeatability* — the repeatability, or local domain precision, for each of the test methods has been established as the values given in [Tables A.3](#) to [A.6](#) for each measurement parameter listed in the tables. Two individual test results obtained in the same laboratory (by the proper use of this International Standard) that differ by more than the tabulated values for  $r$ , in measurement units, or  $(r)$ , in percent, should be considered as suspect, i.e. to have come from different populations. Such a situation should suggest that some appropriate investigative action be taken.

*Reproducibility* — the reproducibility, or global domain precision, for each of the test methods has been established as the values given in [Tables A.3](#) to [A.6](#) for each measurement parameter listed in the tables. Two individual test results obtained in different laboratories (by the proper use of this International Standard) that differ by more than the tabulated values for  $R$ , in measurement units, or  $(R)$ , in percent, should be considered as suspect, i.e. to have come from different populations. Such a situation should suggest that some appropriate investigative action be taken.

### A.3.3 Comparison of relative reproducibility

The grand average or overall relative reproducibility,  $(R)$ , values in [Tables A.3](#) to [A.6](#) give an indication of the difference in relative reproducibility between mill and internal mixer mixing.

The overall ( $R$ ) values in [Tables A.3](#) and [A.4](#) for mill-mixing stress-strain and curemeter properties are 23,2 % and 18,1 %, respectively, and those in [Tables A.5](#) and [A.6](#) for internal mixer stress-strain and curemeter properties are 23,0 % and 38,5 %, respectively.

For the stress-strain properties, the overall relative reproducibility is essentially the same for mill mixing and internal mixer mixing: 23,2 % and 23,0 %, respectively. For curemeter testing, however, the relative reproducibility for mill mixing is different from that for internal mixer mixing: 18,1 % versus 38,5 %, respectively. This higher between-laboratory variation is no doubt primarily attributable to the differences between the internal mixers used in the various laboratories.

### A.3.4 Bias

Bias is the difference between a measured average test result and a reference or true value for the measurement in question. Reference values do not exist for this test method and therefore bias cannot be evaluated.

### A.3.5 Internal mixer operating conditions

[Table A.7](#) gives the mixing conditions utilized with each laboratory internal mixer used in the 2004 ITP.

**Table A.3 — Precision (type 2) for mill mixing — Stress-strain properties**

Parameter measured	Mean	Within-laboratory			Between laboratories			Number of laboratories <sup>a</sup>
		$s_r$	$r$	( $r$ )	$s_R$	$R$	( $R$ )	
$S_{100}$ , MPa	2,15	0,094	0,26	12,2	0,100	0,28	13,0	6
$S_{200}$ , MPa	5,43	0,130	0,37	6,86	0,42	1,19	21,9	6
$S_{300}$ , MPa	10,81	0,136	0,38	3,52	1,02	2,86	26,4	6
Elongation at break, %	417	11,4	31,9	7,66	30,2	84,5	20,3	8
Tensile strength, MPa	17,42	0,344	0,96	5,53	2,14	5,98	34,4	7
	Grand average			7,2			23,2	

$s_r$  is the within-laboratory standard deviation (in measurement units)  
 $r$  is the repeatability (in measurement units)  
( $r$ ) is the repeatability (in percent of mean level)  
 $s_R$  is the between-laboratory standard deviation (for total between-laboratory variation in measurement units)  
 $R$  is the reproducibility (in measurement units)  
( $R$ ) is the reproducibility (in percent of mean level)  
<sup>a</sup> Final number of laboratories remaining in the ITP after deletion of outliers (using option 1).

**Table A.4 — Precision (type 2) for mill mixing — Curemeter properties**

Parameter measured	Mean	Within-laboratory			Between laboratories			Number of laboratories <sup>a</sup>
		$s_r$	$r$	( $r$ )	$s_R$	$R$	( $R$ )	
$M_H$ , dN·m	18,3	0,293	0,82	4,48	0,937	2,62	14,3	5
$M_L$ , dN·m	2,83	0,130	0,35	12,4	0,230	0,64	22,5	7
$t_{s1}$ , min	2,87	0,135	0,38	13,2	0,196	0,55	19,1	6
$t'_c$ (50), min	6,91	0,130	0,36	5,3	0,293	0,82	11,9	5
$t'_c$ (90), min	11,1	0,150	0,43	3,9	0,900	2,53	22,8	5
	Grand average			7,9			18,1	

NOTE For definitions of the precision symbols, see [Table A.3](#).  
<sup>a</sup> Final number of laboratories remaining in the ITP after deletion of outliers (using option 1).

**Table A.5 — Precision (type 2) for internal mixer — Stress-strain properties**

Parameter measured	Mean	Within-laboratory			Between laboratories			Number of laboratories <sup>a</sup>
		$s_r$	$r$	$(r)$	$s_R$	$R$	$(R)$	
$S_{100}$ , MPa	2,33	0,086	0,240	10,3	0,203	0,570	24,4	12
$S_{200}$ , MPa	5,82	0,210	0,59	10,1	0,470	1,31	22,6	12
$S_{300}$ , MPa	11,1	0,346	0,97	8,76	0,838	2,35	21,2	13
Elongation at break, %	415	12,02	33,7	8,10	40,60	113,6	27,4	15
Tensile strength, MPa	17,0	0,835	2,34	13,8	1,17	3,28	19,3	15
	Grand average			10,2			23,0	

NOTE For definitions of the precision symbols, see [Table A.3](#).

<sup>a</sup> Final number of laboratories remaining in the ITP after deletion of outliers (using option 1).

**Table A.6 — Precision (type 2) for internal mixer — Curemeter properties**

Parameter measured	Mean	Within-laboratory			Between laboratories			Number of laboratories <sup>a</sup>
		$s_r$	$r$	$(r)$	$s_R$	$R$	$(R)$	
$M_H$ , dN·m	18,55	0,196	0,550	2,97	1,051	2,94	15,9	10
$M_L$ , dN·m	2,97	0,054	0,150	5,04	0,665	1,86	62,6	13
$t_{s1}$ , min	2,84	0,066	0,185	6,53	0,587	1,64	57,9	13
$t'_c(50)$ , min	6,63	0,087	0,240	3,68	0,661	1,85	27,9	12
$t'_c(90)$ , min	10,5	0,177	0,500	4,73	1,051	2,94	28,1	14
	Grand average			4,6			38,5	

NOTE For definitions of the precision symbols, see [Table A.3](#).

<sup>a</sup> Final number of laboratories remaining in the ITP after deletion of outliers (using option 1).

**Table A.7 — Brief details of the mixing conditions used in the 2004 ITP**

Initial head temperature, °C	50	40	60	88	60	60	60	60	60
Rotor speed, r/min	60	120/80	60	60	60	60	60	60	60
Rotor type	Cam	Banbury	4 wings	Banbury	Banbury	Banbury	Banbury	Banbury	6 wings
Free volume, cm <sup>3</sup>	75	80	80	75	270	379	379	379	422
Loading, %	76,7	70	81	75	60	60	60	60	60
Cycle, min	5	6+3	9	12	9	9	9	9	9
Initial head temperature, °C	60	60	90	90	50	40	40	50	
Rotor speed, r/min	60	60	75	75	77	70/40	90/40	50	
Rotor type	Banbury	Banbury	2 wings	2 wings	Banbury	Banbury	Banbury	4 wings	
Free volume, cm <sup>3</sup>	588	1 200	1 500	1 500	1 500	1 580	1 600	3 322	
Loading, %	60	70	80	80	77	55	70	72	
Cycle, min	9	6+3	6+3	6+3	6+3	6+3	6+3	6+3	

## Bibliography

- [1] ISO/TR 9272:1986<sup>1)</sup>, *Rubber and rubber products — Determination of precision for test method standards*
- [2] ISO/TR 9272:2005, *Rubber and rubber products — Determination of precision for test method standards*
- [3] ISO 11235, *Rubber compounding ingredients — Sulfenamide accelerators — Test methods*

---

1) Withdrawn document.





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™