

BS ISO 4195:2012



BSI Standards Publication

# Conveyor belts with heat-resistant rubber covers — Heat resistance of covers — Requirements and test methods

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 4195:2012. It supersedes BS ISO 4195:2007 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/67, Conveyor belts.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 77354 9

ICS 53.040.20

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2012.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

# INTERNATIONAL STANDARD

**ISO**  
**4195**

Second edition  
2012-11-01

---

---

## **Conveyor belts with heat-resistant rubber covers — Heat resistance of covers — Requirements and test methods**

*Courroies transporteuses avec revêtements caoutchouc résistant à la  
chaleur — Résistance à la chaleur des revêtements — Exigences et  
méthodes d'essai*



Reference number  
ISO 4195:2012(E)

© ISO 2012



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Performance requirements</b> .....	<b>1</b>
<b>4 Test method</b> .....	<b>2</b>
4.1 Principle.....	2
4.2 Classification.....	2
4.3 Procedure.....	2
4.4 Expression of results.....	4
<b>5 Test report</b> .....	<b>4</b>
<b>Bibliography</b> .....	<b>5</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4195 was prepared by Technical Committee ISO/TC 41, *Pulleys and belts (including veebelts)*, Subcommittee SC 3, *Conveyor belts*.

This second edition cancels and replaces the first edition (ISO 4195:2007), of which it constitutes a minor revision. It also incorporates ISO 4195:2007/Cor 1:2008.

# Conveyor belts with heat-resistant rubber covers — Heat resistance of covers — Requirements and test methods

## 1 Scope

This International Standard specifies requirements and test methods for the relative level of heat resistance of conveyor belt covers made of rubber. It gives the permissible variations of hardness, elongation at break and tensile strength after exposure to heat. It is applicable only to those conveyor belts having a cover thickness greater than or equal to 4 mm. It is not suitable or valid for light conveyor belts as described in ISO 21183-1<sup>[1]</sup>.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 18573, *Conveyor belts — Test atmospheres and conditioning periods*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Performance requirements

When tested in accordance with the method specified in Clause 4, the permissible variations in hardness, elongation at break and tensile strength shall be in accordance with Table 1.

**Table 1 — Permissible variations**

Cover characteristic	Variation for belt class		
	1	2	3
<b>Hardness (IRHD)</b>			
— variation of initial value	+ 20	+ 20	+ 20
— maximum value	85	85	85
<b>Elongation at break (%)</b>			
— variation in percentage of initial value	– 50 200	– 50 200	– 55 180
— minimum value			
<b>Tensile strength (N/mm<sup>2</sup>)</b>			
— variation in percentage of initial value	– 25 12	– 30 10	– 40 5
— minimum value			

## 4 Test method

### 4.1 Principle

The following properties are measured, before and after exposure to heat according to 4.3.1:

- hardness of covers in accordance with ISO 48;
- elongation at break of covers in accordance with ISO 37;
- tensile strength of covers in accordance with ISO 37.

NOTE The temperatures selected for the tests are usually not those corresponding to the temperature of the product to be transported; they are generally lower to take account of:

- the possibility of the conveyor belt cooling, and
- the fact that contact between the product and the conveyor belt will not equalize the temperature.

### 4.2 Classification

Conveyor belts shall be classified as follows:

- **Class 1:** resistant to test temperatures of up to 100 °C.
- **Class 2:** resistant to test temperatures of up to 125 °C.
- **Class 3:** resistant to test temperatures of up to 150 °C.

These classes do not correspond to the temperature of the transported product as mentioned in the Note to 4.1. Depending on the use for which the belt is intended, the manufacturer should state the class to be used for assessing compliance with this International Standard.

### 4.3 Procedure

#### 4.3.1 Exposure to heat

Cut a sample of belt of full thickness measuring 400 mm × 400 mm from the centre of the belt at a distance of at least 100 mm from the edges. Place it in an air oven in accordance with ISO 188 for 7 days at a temperature of 100 °C for class 1 belts, 125 °C for class 2 belts or 150 °C for class 3 belts.

After exposure to heat, remove the belt sample from the oven and leave it to cool.

#### 4.3.2 Preparation of test pieces for evaluating properties

##### 4.3.2.1 Test pieces for measuring hardness of covers

The test pieces shall either be the belt sample itself or covers removed from the belt by cutting away the covers from the belt sample. Test pieces shall be lightly buffed on each surface but left at maximum thickness. Condition the test pieces for 24 h at a temperature of  $(23 \pm 2)$  °C and a relative humidity of  $(50 \pm 5)$  % (atmosphere B in accordance with ISO 18573).

##### 4.3.2.2 Test pieces for measuring elongation at break and tensile strength

Cut away the covers from the belt samples treated as described in 4.3.1 and bring them to a thickness of  $(2 \pm 0,2)$  mm by cutting on both faces and finishing off by a light buffing. Condition the test pieces for 24 h at a temperature of  $(23 \pm 2)$  °C and a relative humidity of  $(50 \pm 5)$  % (atmosphere B in accordance with ISO 18573).



For belts with a textile carcass, the test results of which can be affected by the humidity, a temperature of  $(20 \pm 2)$  °C and a relative humidity of  $(65 \pm 5)$  % (atmosphere A in accordance with ISO 18573) may be selected, by agreement between the parties concerned, provided that this is clearly indicated in the test report.

In the special case of tropical conditions, reference should be made to ISO 23529 [temperature  $(27 \pm 2)$  °C and relative humidity  $(65 \pm 5)$  %, atmosphere C in accordance with ISO 18573].

### **4.3.3 Determination of properties**

#### **4.3.3.1 Hardness**

Using the test pieces prepared as described in 4.3.2.1, measure the hardness of covers using one of the methods specified in ISO 48, according to the available thickness of the rubber material.


#### **4.3.3.2 Elongation at break and tensile strength**

Using the test pieces as described in 4.3.2.2, measure the elongation at break of covers and tensile strength in accordance with ISO 37.

#### **4.3.3.3 Initial values**

Determine the initial values of hardness, elongation at break and tensile strength by measuring these properties using test pieces cut from the same belt and prepared as described in 4.3.2, but without exposure to heat.

**NOTE** Users of this International Standard need to be aware of the limitations of the results obtained in that two measurements do not provide a complete picture of the rate of change of the measured properties with time. The two points obtained do not allow the path of the curve relating the measured properties to time to be determined. Figure 1 illustrates this in that the curve between the two points shown could follow any number of paths; although for the purposes of illustration, three possible paths, A, B and C, are shown.



**Key**  
X                    time  
Y                    measured property

**Figure 1 — Changes in measured properties with time**

#### **4.4 Expression of results**

Record the results for the hardness of covers, the elongation at break of covers and the tensile strength of covers for the samples not exposed to heat and those exposed to heat. Calculate the variation in hardness, elongation at break and breaking strength between the results obtained for the samples not exposed to heat and those obtained for the samples exposed to heat.

### **5 Test report**

The test report shall contain the following information:

- a) reference to this International Standard (i.e. ISO 4195);
- b) identification of the conveyor belt tested;
- c) the belt class as given in 4.2;
- d) the test piece used (see 4.3.2);
- e) the conditions of exposure to heat;
- f) details of the conditioning used;
- g) the results of the test as described in 4.4;
- h) date of the test.

## Bibliography

- [1] ISO 21183-1, *Light conveyor belts — Part 1: Principal characteristics and applications*





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™