BS ISO 4381:2011



BSI Standards Publication

Plain bearings — Tin casting alloys for multilayer plain bearings



BS ISO 4381:2011 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of ISO 4381:2011. It supersedes BS ISO 4381:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee MCE/12, Plain bearings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

ISBN 978 0 580 73558 5

ICS 21.100.10; 77.120.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2012.

Amendments issued since publication

Date Text affected

INTERNATIONAL STANDARD

BS ISO 4381:2011 ISO 4381

Fourth edition 2011-11-01

Plain bearings — Tin casting alloys for multilayer plain bearings

Paliers lisses — Alliages moulés à base d'étain pour paliers lisses multicouches



BS ISO 4381:2011 ISO 4381:2011(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Con	Contents		
Forew	word	iv	
1	Scope	1	
2			
3	Requirements Chemical composition Material properties Selection of material		
3.1	Chemical composition		
3.2	Material properties		
3.3	Selection of material	1	
4	Designation	3	
Anne	ex A (informative) Guidance on use of bearing metals and the hardness of the mating be (shaft)		
Biblio	ography	5	

BS ISO 4381:2011 **ISO 4381:2011(E)**

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4381 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants*, their properties, characteristics, test methods and testing conditions.

This fourth edition cancels and replaces the third edition (ISO 4381:2000), which has been technically revised.

Plain bearings — Tin casting alloys for multilayer plain bearings

1 Scope

This International Standard specifies requirements for bearing metals based on tin casting alloys for multilayer plain bearings. The chemical composition and material properties refer to the original unprocessed material and are measured on representative samples. Testing results on final bearings can differ due to the influence of bearing production. Therefore, it is not intended that these results be compared with data given in this International Standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1143, Metallic materials — Rotating bar bending fatigue testing

ISO 4384-2, Plain bearings — Hardness testing of bearing metals — Part 2: Solid materials

ISO 4386-2:—¹⁾, Plain bearings — Metallic multilayer plain bearings — Part 2: Destructive testing of bond for bearing metal layer thicknesses greater than or equal to 2 mm

3 Requirements

3.1 Chemical composition

The chemical composition of alloy elements shall be within the limits specified in Table 1. The chemical analysis is decisive for the acceptance of the bearing metals.

3.2 Material properties

Material properties shall be in accordance with the data given in Table 1.

All material property values are mean values or ranges and are regarded as typical values for the designer. In view of the range of possible alloy compositions and the marked influence exerted by the cooling conditions on the mechanical properties, relatively large deviations from the indicated values are to be expected in individual cases.

3.3 Selection of material

Guidance on uses of bearing metals and on the hardness of the mating bearing part (shaft) is given in Annex A.

-

¹⁾ Under preparation.

Table 1 — Tin casting alloy

		Chemical composition, mass fraction	
Chemical element		%	
Grieffical element	-	70 SnSb8Cu4	
Sn		Remainder	
Sb		7 to 8	
Cu		3 to 4	
Impurities			
Pb		<0,35	
As		<0,1	
Bi		<0,08	
Fe		<0,1	
Al		<0,01	
Zn		<0,01	
Cd		<0,05	
Total others		0,2	
	Material p	roperties	
Brinell hardness	20 °C	22	
in accordance with ISO 4384-2	10000		
HBW 10/250/180	100 °C	10	
0,2 % tensile yield stress			
R _{p 0,2}	20 °C	46	
N/mm ²			
Tensile strength $R_{ m m}$			
N/mm ²	20 °C	77	
0,2 % compressive yield stress	20 °C	47	
σ_{d} 0,2 % compressive yield stress	20 C	41	
N/mm ²	100 °C	27	
Bond strength			
R _{Ch}		In accordance with ISO 4386-2:—, 8.1 and 8.2.	
N/mm ²			
Rotating bar bending fatigue			
R_{rbf}		± 29	
in accordance with ISO 1143		- 20	
10 ⁷ cycles, N/mm ²			
Linear thermal expansion coefficient, α ₁		22.0	
10 ⁻⁶ /K		23,9	
Melting temperature			
°C		233 to 360	
Casting temperature			
°C		440 to 460	
Density, $ ho$			
kg/dm ³		7,3	
19/4111			

4 Designation

EXAMPLE A bearing metal having the chemical composition indicated by the symbol SnSb8Cu4 is designated as follows:

Bearing metal ISO 4381 — SnSb8Cu4

Annex A

(informative)

Guidance on use of bearing metals and the hardness of the mating bearing part (shaft)

Bearing alloy	Characteristics and principal uses	Minimum hardness of the shaft ^a
SnSb8Cu4	Good sliding properties, conformability and high toughness; good embeddability; suitable for high sliding velocities in the hydrodynamic range, mean load; impact stress at low frequency; insensitive to reversed bending stress. Used for high loaded rolling mill bearings; for the production of wrapped bushes, thin-walled bearing liners with a wall thickness of up to about 3 mm and thrust washers.	160 HB

In multilayer plain bearings, the difference between the hardness of the bearing material and the shaft material should be such that welding under working conditions is safely avoided. The working conditions, in particular the lubrication conditions, have considerable influence on the selection of the shaft material. For this reason, the recommended hardness value for the shaft material is a minimum value. In general, unquenched and untempered shaft materials are used in the case of bearing materials based on tin.

Bibliography

- [1] ISO 4386-1, Plain bearings Metallic multilayer plain bearings Part 1: Non-destructrive ultrasonic testing of bond
- [2] ISO 4386-3, Plain bearings Metallic multilayer plain bearings Part 3: Non-destructive penetrant testing



British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

