

BS ISO 4708:2015



BSI Standards Publication

Composition cork — Gasket material — Test methods

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 4708:2015. It supersedes BS ISO 4708:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/81, Cork.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 87315 7

ICS 21.140; 79.100

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
4708

Third edition
2015-09-15

**Composition cork — Gasket material
— Test methods**

*Aggloméré composé de liège — Joints pour industries mécaniques —
Méthodes d'essai*



Reference number
ISO 4708:2015(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	2
5 Reagents	2
6 Sampling and preparation of test specimens	2
6.1 Sampling.....	2
6.2 Preparation of the test specimens.....	2
6.3 Conditioning.....	3
7 Tests	3
7.1 Determination of thickness.....	3
7.2 Determination of apparent density.....	3
7.3 Determination of tensile strength.....	3
7.4 Determination of compressibility and recovery.....	3
7.5 Resistance to boiling water.....	3
7.6 Flexibility.....	4
7.6.1 Method A.....	4
7.6.2 Method B.....	4
7.7 Behaviour of composition cork and rubbercork in fluids.....	4
7.7.1 Behaviour in ASTM IRM 903 oil.....	4
7.7.2 Behaviour in ASTM IRM 901 oil.....	5
7.7.3 Behaviour in ASTM Fuel A (or equivalent).....	5
8 Test report	6
Annex A (normative) Reagents' characteristics	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 87, *Cork*.

This third edition cancels and replaces the second edition (ISO 4708:2000). The major amendments are technical changes introduced in [Clause 4](#), [Clause 5](#) and [Annex A](#).

Composition cork — Gasket material — Test methods

1 Scope

This International Standard specifies test methods to determine the characteristics of agglomerated composition cork and rubbercork to be used as gaskets in the mechanical industry. The following characteristics are considered:

- thickness,
- apparent density,
- tensile strength,
- compressibility and recovery,
- flexibility,
- resistance to boiling water,
- behaviour in fluids.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 7322:2014, *Composition cork — Test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 633 and the following apply.

3.1

composition cork

product obtained from the agglutination of cork granules with the addition of a binder generally not derived from cork wood cells

3.2

rubbercork

product manufactured as a compound of cork granules and rubber, which can be used either in the form of granules or as a binder

3.3

failure

appearance of any crack, break or surface separation

3.4

disaggregation

substantial loss of particles and/or splitting open of a test specimen during the test

4 Apparatus

Material specified in ISO 7322, and the following.

- 4.1 **Series of mandrels**, with diameters ranging from 8 mm to 25 mm, in steps of 1 mm.
- 4.2 **Air circulation oven**, capable of being maintained at (100 ± 2) °C.
- 4.3 **Open containers**.
- 4.4 **Oven or climatic room**, capable of being maintained at (23 ± 5) °C and (50 ± 5) % relative humidity.
- 4.5 **Absorbent paper**, of analysis type.¹⁾
- 4.6 **Aluminium foil**.
- 4.7 **Cutting system**, to cut the test specimens.

5 Reagents

See [Annex A](#).

- 5.1 **ASTM IRM 903 oil**.²⁾
- 5.2 **ASTM IRM 901 oil**.²⁾
- 5.3 **ASTM Fuel A**.²⁾

6 Sampling and preparation of test specimens

6.1 Sampling

The number of packages from each lot (at least three packages) and the quantity of material to be taken from the sample shall be in accordance with ISO 2859-1 for the inspection level agreed between the interested parties.

6.2 Preparation of the test specimens

6.2.1 From each sheet of material and using the cutting system (4.7), take test specimens at a distance of at least 100 mm from the edges. The number and dimensions of the test specimens shall be as specified in [Table 1](#). Each test specimen shall be squarely cut with the edges perpendicular to its surface, and shall not show any cracks or folds.

6.2.2 The minimum and the maximum thicknesses of the test specimens for testing flexibility are specified in [Table 2](#).

1) Paper Whatman No. 4 has demonstrated proper absorptive properties for oils. This is an example of a suitable product available commercially. This information is given for the convenience of users of this International Standard and should not be taken as an endorsement by ISO of this product.

2) These are examples of suitable reagents. Other reagents may be used provided that they comply with the requirements specified in [Annex A](#).

6.3 Conditioning

Prior to testing, the test specimens shall be conditioned for 48 h at 23 °C in the oven or climatic room (4.4). In case of dispute, the test specimens shall be conditioned for 48 h at a temperature of (23 ± 5) °C and (50 ± 5) % relative humidity. Unless otherwise specified, all tests shall be carried out under the same temperature and humidity conditions.

Table 1 — Number and dimensions of test specimens

Type of test	Dimensions of test specimens mm	Number of test specimens
Compressibility and recovery	50 × 50	3 (single ply or 3 groups of <i>n</i> test specimens)
Flexibility	150 × 15	3
Sealing behaviour	∅ = 28,7	3
Behaviour in oil or in fuel	50 × 50	3 for each reagent

Table 2 — Thicknesses used for testing flexibility

Type of material	Minimum thickness mm	Maximum thickness mm
Composition cork	3,2	4,8
Rubbercork	3,2	4,8

7 Tests

7.1 Determination of thickness

Determine the thickness in accordance with ISO 7322:2014, 6.1.

7.2 Determination of apparent density

Determine the apparent density in accordance with ISO 7322:2014, 6.2.

7.3 Determination of tensile strength

Determine the tensile strength in accordance with ISO 7322:2014 6.3.

7.4 Determination of compressibility and recovery

Determine the compressibility and recovery in accordance with ISO 7322:2014, 6.4.

The dimensions of the test specimens are specified in [Table 1](#). The test specimens shall consist of a single ply or a number of superimposed plies to give a minimum test thickness of 3,2 mm.

Results obtained for test specimens outside this test thickness shall be regarded as merely indicative. For specification purposes, agreement on compressibility and recovery values shall be reached between the interested parties for those materials whose thickness, in a single ply or multiple plies, does not fall within the nominal thickness specified.

7.5 Resistance to boiling water

Determine the resistance to boiling water in accordance with ISO 7322:2014, 6.5.

7.6 Flexibility

7.6.1 Method A

7.6.1.1 Procedure

Firmly hold the test specimen at one point on a circular mandrel (4.1) and slowly but firmly, under finger pressure, force the test specimen to contact 180° of the full mandrel diameter for approximately (5 ± 1) s. Repeat this flexure using decreasing mandrel diameters on new test specimens until failure (3.3) occurs.

7.6.1.2 Calculation and expression of results

The test result is the minimum diameter, expressed in millimetres, on which the test specimen could be flexed without any signs of failure (3.3).

A flexibility factor may be calculated by dividing this minimum diameter by the nominal thickness of the test specimen.

7.6.2 Method B

7.6.2.1 Procedure

Place the test specimens in the oven (4.2) set at (100 ± 2) °C, for 70 h. After this period, remove the test specimens, allow them cool for (24 ± 1) h under laboratory ambient conditions. Carry out the test as specified in 7.6.1.1.

7.6.2.2 Calculation and expression of results

The test result is the minimum diameter, expressed in millimetres, on which the test specimen could be flexed without any signs of failure (3.3).

7.7 Behaviour of composition cork and rubbercork in fluids

These test methods provide a standardized procedure to measure the effect of immersion in specified fluids under definite conditions of time and temperature. The test results are not intended to give any direct correlation with service conditions, taking into account the wide variations in temperature and special use that may be found in gasket applications. The specific test fluids and test conditions outlined were selected as typical for purposes of comparing different materials and may be used as a routine test when agreed between the interested parties.

7.7.1 Behaviour in ASTM IRM 903 oil

7.7.1.1 Procedure

The test specimens shall have the dimensions defined in Table 1 and the material thickness defined in Table 2. The test specimens shall be conditioned before the test as specified in 6.3.

Determine the thickness of the test specimens as specified in 7.1.

Place the test specimens in the containers (4.3) with ASTM IRM 903 oil (or equivalent), for 72 h, at ambient temperature (between 22 °C and 30 °C). At the end of this period, remove the test specimens, clean them with absorbent paper (4.5) and determine the new thickness of the test specimens.

7.7.1.2 Calculation and expression of results

The change in thickness of the test specimen is given by the formula:

$$\Delta d = \frac{d_2 - d_1}{d_1} \times 100 \%$$

where

d_1 is the thickness of the test specimen before immersion, expressed in millimetres, rounded to the nearest 0,1 mm;

d_2 is the thickness of the test specimen after immersion, expressed in millimetres, rounded to the nearest 0,1 mm.

The test result is expressed as a percentage, rounded to the nearest integer.

7.7.2 Behaviour in ASTM IRM 901 oil

7.7.2.1 Procedure

The test specimens shall have the dimensions specified in [Table 1](#) and the material thickness specified in [Table 2](#). The test specimens shall be conditioned before the test as specified in [6.3](#).

Determine the thickness of the test specimen as specified in [7.1](#).

Place the test specimens in the containers (4.3) with ASTM IRM 901 oil (or equivalent), ensuring that the test specimens are separated from each other and from the bottom of the container and remain immersed in the test fluid. Cover the containers with aluminium foil (4.6) and place the containers for (70 ± 2) h in the oven ([4.2](#)) set at 100 °C.

After this period, remove the test specimens from the containers and immediately immerse them in a cool fresh portion of the test fluid, for 30 min to 60 min at ambient temperature (between 22 °C and 30 °C). Remove the test specimens from the containers, clean them with absorbent paper ([4.5](#)) and determine the new thickness of the test specimens.

7.7.2.2 Calculation and expression of results

The change in thickness of the test specimen is given by the formula:

$$\Delta d = \frac{d_2 - d_1}{d_1} \times 100 \%$$

where

d_1 is the thickness of the test specimen before immersion, expressed in millimetres, rounded to the nearest 0,1 mm;

d_2 is the thickness of the test specimen after immersion, expressed in millimetres, rounded to the nearest 0,1 mm.

The test result is expressed as a percentage, rounded to the nearest integer.

7.7.3 Behaviour in ASTM Fuel A (or equivalent)

7.7.3.1 Procedure

The test specimens shall have the dimensions specified in [Table 1](#) and the material thickness specified in [Table 2](#). The test specimens shall be conditioned before the test as specified in [6.3](#).

Determine the volume of the test specimen if test results are to be expressed as the change of this property.

Place the test specimens in the containers (4.3) with the reagent, for 24 h, at ambient temperature (between 22 °C and 30 °C). At the end of this period, remove the test specimens, clean them with absorbent paper (4.5) and make a visual examination or determine the new volume of the test specimens.

7.7.3.2 Calculation and expression of results

The test result is expressed either by:

- the existence or absence of disaggregation (3.4), or
- the change in volume, as a percentage of the initial volume, rounded to the nearest 0,1 %, calculated according to the formula:

$$\Delta V = \frac{V_2 - V_1}{V_1} \times 100 \%$$

where

V_1 is the volume of the test specimen before immersion, expressed in cubic millimetres, rounded to the nearest tenth;

V_2 is the volume of the test specimen after immersion, expressed in cubic millimetres, rounded to the nearest tenth.

8 Test report

The test report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 4708;
- b) the complete identification of the product tested, including the type, source and the manufacturer references;
- c) the sampling report;
- d) the results obtained;
- e) any deviation from this International Standard that may have affected the results.

Annex A (normative)

Reagents' characteristics

The reagents used to evaluate the disaggregation which has occurred in the material after its immersion, shall have the characteristics shown in [Table A.1](#). This evaluation may be made by visual observation, or by determination of the relative change in mass, thickness or volume.

Table A.1 — Characteristics of reagents

Characteristic	ASTM IRM 901 oil	ASTM IRM 903 oil	Fuel A
Saybolt viscosity at 38 °C (cSt)	—	31,9 – 34,1	
Saybolt viscosity at 99 °C (cSt)	18,12 – 20,34	—	
Flash point (COC) °C	≥ 243	≥ 163	—
-----	-----	-----	Isooctane ^a
^a In accordance with specifications given in Manual for Rating Motor Fuels by Motor and Research Methods.			

Bibliography

- [1] ASTM F36:2009, *Standard test method for compressibility and recovery of gasket materials*
- [2] ASTM F146:2012, *Standard test methods for fluid resistance of gasket materials*
- [3] ASTM F147:2009, *Standard test method for flexibility of non-metallic gasket materials*
- [4] ASTM D 471-12a, *Standard test method for rubber property – Effect of liquids*
- [5] ASTM D 2699, *Test method for research octane number of spark-ignition engine fuel*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™