

BS ISO 5433:2013



BSI Standards Publication

Leather — Bovine wet blue — Specification

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 5433:2013. It supersedes BS ISO 5433:1999 which is withdrawn.

It is considered the view of the UK committee that the application of this standard to bovine wet blue can be limiting on three counts:

1. The requirement for a water extract pH value of greater than 3.5 is considered restrictive as tanners are producing high quality bovine wet blue with water extract values of less than 3.5, such as a pH value 3.2.
2. It states that a 3.5 % chrome content is required to achieve a 100 °C shrinkage temperature. However, this shrinkage temperature is being commercially achieved at a chrome content of 3 %.
3. At the request of their customers, tanners are not placing trade names or names and addresses of the manufacturer on their packaging. The labelling requirements of the standard do not reflect the commercial realities that tanners operate within and would require the tanner and customer to disclose this information without any perceived benefit.

It is acknowledged by the UK committee that this standard can be applied for UK commercial transactions and aspects can be used in case of dispute between parties but all parties should be aware of the limitations detailed above for bovine wet blue production.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.
Published by BSI Standards Limited 2013

ISBN 978 0 580 80571 4

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2013.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 5433:2013

ISO
5433

Second edition
2013-08-15

**Leather — Bovine wet blue —
Specification**

Cuir — Peaux de bovins à l'état "bleu humide" — Spécifications



Reference number
ISO 5433:2013(E)

© ISO 2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
4.1 Raw material.....	2
4.2 Form and trimming.....	2
4.3 Tanning.....	2
4.4 Fungicidal additives.....	2
4.5 Presentation.....	3
4.6 Shrinkage temperature.....	3
4.7 Chemical requirements.....	3
5 Sampling	3
5.1 Sampling for routine testing.....	3
5.2 Sampling in case of dispute.....	3
5.3 Preparation of samples.....	4
6 Method of test	4
6.1 Visual tests.....	4
6.2 Shrinkage temperature.....	4
6.3 Volatile matter.....	4
6.4 pH of the water extract.....	4
6.5 Effectiveness of the fungicide.....	4
7 Packaging and marking	4
7.1 Packaging.....	4
7.2 Marking.....	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 120, *Leather*, Subcommittee SC 2, *Tanned leather*.

This second edition cancels and replaces the first edition (ISO 5433:1999), which has been technically revised.

Leather — Bovine wet blue — Specification

1 Scope

This International Standard specifies requirements, methods of sampling and methods of test for wet blue leather produced from bovine hides and parts of bovine hides tanned without hair and with the use of basic chromium sulfate as the primary tanning agent.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3380, *Leather — Physical and mechanical tests — Determination of shrinkage temperature up to 100 °C*

ISO 4045, *Leather — Chemical tests — Determination of pH*

ISO 4684, *Leather — Chemical tests — Determination of volatile matter*

ISO 5398-1, *Leather — Chemical determination of chromic oxide content — Part 1: Quantification by titration*

ASTM D4576, *Standard test method for mold growth resistance of wet blue*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

cured

preserved temporarily from putrefaction until it can be tanned

Note 1 to entry: Any method of curing, including wet or dry salting or drying, is included.

3.2

pigmentation

colouration produced by fungi growing on wet blue chrome leather

Note 1 to entry: The colouration produced by fungi will normally be black, white, green or yellow but can also be pink or violet.

3.3

belly

the part of the hide covering the underside and part of the legs of the animal

3.4

dosset

double back part of the hide remaining after the belly has been removed

3.5

shoulder

fore part of the hide covering the shoulders and the neck of the animal, with or without the head

3.6

butt

the part of the hide remaining after the belly and the shoulder have been removed

3.7

side

half a whole hide with offal (head, shoulder and belly) attached, obtained by dividing it along the line of the backbone

3.8

culatta

rear part of the bovine hide, comprising the butt, the belly middles and the hind shanks

3.9

front

fore part of the bovine hide, consisting of the shoulders and fore shanks

4 Requirements

4.1 Raw material

Bovine wet blue hides shall be processed from cured or fresh hides or part hides.

4.2 Form and trimming

4.2.1 Bovine wet blue hide shall be in one or more of the following forms, as specified by the purchaser:

- a) whole hides;
- b) bellies;
- c) dossets (double backs);
- d) shoulders;
- e) butts;
- f) sides;
- g) culattas;
- h) fronts.

4.2.2 The trim shall be as agreed between the supplier and purchaser

4.3 Tanning

After pretanning operations, bovine hides or part hides shall be tanned with basic chromium sulfate as the primary tanning agent. The cut cross-section shall be such that the hide is completely penetrated by the bluish colour of the chromium sulfate when examined visually. Tanning shall be carried out at a pH of 3,0 or above.

4.4 Fungicidal additives

Fungicides shall be used to inhibit mould growths in bovine wet blue leather.

NOTE 1 Fungicides used to inhibit mould growth and pigmentation should be effective and should not cause a health hazard. The types of fungicide used and their dosage should preferably be agreed between the purchaser and the supplier

NOTE 2 Fungicides should preferably be applied in quantities appropriate to ensure storage for up to 4 months at the temperature and humidity prevailing during storage or transportation.

4.5 Presentation

Bovine wet blue leather shall be well fleshed, and the grain side shall be free from hair, including short hair and fine hair. The size and grading shall be as agreed between the interested parties.

NOTE The wet blue leather should preferably have a tight grain and be free from creases, drum folds and stains caused by iron salts. At least 95 % of the number of pieces in a lot should be free from stains caused by chromium salts, and the aggregate of the stained area in any one piece should not exceed 10 % of the total area of the piece.

4.6 Shrinkage temperature

The shrinkage temperature shall meet the requirement for either low chrome tannage or full chrome tannage given in [Table 1](#), when determined using the method given in ISO 3380.

Table 1 — Shrinkage temperature

Tannage	Shrinkage temperature
Low chrome tannage	Minimum 85 °C
Full chrome tannage	Minimum 100 °C

4.7 Chemical requirements

Bovine wet blue leather shall comply with the requirements given in [Table 2](#).

Table 2 — Chemical requirements

Characteristic	Requirement
Volatile matter, %	As agreed between the interested parties
pH of water extract (minimum)	3,5

NOTE A minimum shrinkage temperature of 85 °C would normally require minimum chromic oxide content of 1,0 % relative to the dry mass, as determined by the method given by ISO 5398-1. Similarly, a minimum shrinkage temperature of 100 °C would require minimum chromic oxide content 3,5 %.

5 Sampling

5.1 Sampling for routine testing

The number and location of laboratory samples taken for routine testing shall be as agreed between the interested parties.

5.2 Sampling in case of dispute

The number of samples shall be as given in [Table 3](#) and the location shall be as specified in ISO 2418.

Table 3 — Number of samples to be taken in cases of dispute

Number of skins	Number of samples
Up to 100	3
101 to 300	4
301 to 500	5
501 to 700	6
701 and over	7

5.3 Preparation of samples

Prepare samples by wiping off excess water and keeping wrapped in filter paper for 30 min without applying any extra pressure.

6 Method of test

6.1 Visual tests

Examine the bovine wet blue hide for uniformity of colour of the surface, penetration of chromium sulfate, absence of short hair and cleanness of the flesh side.

6.2 Shrinkage temperature

Determine the shrinkage temperature by the method specified in ISO 3380.

6.3 Volatile matter

Determine the volatile matter by the method specified in ISO 4684.

6.4 pH of the water extract

Determine the pH of the water extract by the method specified in ISO 4045.

6.5 Effectiveness of the fungicide

Determine the effectiveness of the fungicide by the method specified in ASTM D4576.

7 Packaging and marking

7.1 Packaging

Bovine wet blue leathers shall be packaged suitably as agreed between the interested parties so as to preserve their original wet condition.

7.2 Marking

The following particulars shall be marked on each package or on a label attached to the package:

- a) the type of material (i.e. wet blue bovine skin), and the trade name or brand name, if any;
- b) the name and address of the manufacturer;
- c) the month and year of the tanning;

- d) the number of skins;
- e) any other details desired by the purchaser.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™