

BS ISO 5950:2012



BSI Standards Publication

# Electrolytic tin-coated cold-reduced carbon steel sheet of commercial and drawing qualities

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 5950:2012. It supersedes BS ISO 5950:2008 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/109, Coated and Uncoated Flat Products to be Used for Cold Forming.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 77260 3

ICS 77.140.50

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2012.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

**ISO**  
**5950**

Fifth edition  
2012-11-01

---

---

**Electrolytic tin-coated cold-reduced  
carbon steel sheet of commercial and  
drawing qualities**

*Tôles en acier au carbone laminées à froid, revêtues en continu  
d'un dépôt électrolytique d'étain, de qualités commerciale et pour  
emboutissage*



Reference number  
ISO 5950:2012(E)

© ISO 2012



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Designation system</b> .....	<b>2</b>
<b>5 Dimensions</b> .....	<b>2</b>
<b>6 Conditions of manufacture</b> .....	<b>2</b>
6.1 Chemical composition.....	2
6.2 Coating mass.....	3
6.3 Weldability.....	4
6.4 Fabrication qualities.....	4
6.5 Mill passivation.....	4
6.6 Coating condition.....	4
6.7 Application.....	5
6.8 Mechanical properties.....	5
6.9 Surface finish.....	5
6.10 Oiling.....	5
<b>7 Dimensional tolerances</b> .....	<b>5</b>
<b>8 Sampling</b> .....	<b>6</b>
8.1 Tensile test.....	6
8.2 Tests for mass of coating.....	6
<b>9 Test methods</b> .....	<b>6</b>
9.1 Tensile test (base metal).....	6
9.2 Coating tests.....	6
<b>10 Retests</b> .....	<b>6</b>
10.1 Machining and flaws.....	6
10.2 Additional tests.....	6
<b>11 Resubmission</b> .....	<b>7</b>
<b>12 Workmanship</b> .....	<b>7</b>
<b>13 Inspection and acceptance</b> .....	<b>7</b>
<b>14 Coil size</b> .....	<b>7</b>
<b>15 Marking</b> .....	<b>7</b>
<b>16 Information to be supplied by the purchaser</b> .....	<b>8</b>
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5950 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 12, *Continuous mill flat rolled products*.

This fifth edition cancels and replaces the fourth edition (ISO 5950:2008), which has been technically revised.

# Electrolytic tin-coated cold-reduced carbon steel sheet of commercial and drawing qualities

## 1 Scope

**1.1** This International Standard applies to cold-reduced carbon steel sheet of commercial and drawing qualities coated in coil or cut length forms by electro-deposition of tin. The product is commonly known as electrolytic tin-coated sheet and is used where solderability is desired, appearance is important, or a degree of corrosion resistance under specific conditions is advantageous and coating mass can be specified. The coating is expressed as the total coating on both surfaces, in grams per square metre. The coating mass specified should be compatible with the desired service life, thickness of the base metal and the forming requirements involved. A designation system (Clause 4) includes the coating designation, coating condition and quality.

**1.2** This International Standard does not cover tinplate and blackplate.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 16162, *Cold-rolled steel sheet products — Dimensional and shape tolerances*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **electrolytic tin-coated sheet**

product obtained by electrolytic deposition of tin on cold-reduced steel sheet on a continuous electrolytic tinning line to produce either tin-coated coils or tin-coated cut lengths

### 3.2

#### **skin pass**

light cold-rolling of the cold-reduced and annealed sheet prior to electro-tinning

NOTE The purposes of skin passing are one or more of the following:

- a) to minimize the appearance of coil breaks, stretcher strains and fluting;
- b) to control the shape;
- c) to obtain the required surface finish.

An increase in hardness and some loss in ductility will result from skin passing.

### 3.3

#### **aluminum killed**

steel which has been deoxidized with aluminum sufficient to prevent the evolution of gas during solidification

## 4 Designation system

The as-produced electrolytic tin-coated sheet coatings are designated as SN as shown in Table 4. The coating mass designation follows the SN and three spaces are allocated for coating mass designation. If only two spaces are required, such as for designation 56, then the 56 is preceded by a "0" to fill computer space and is shown as "056". Since this product is always skin-passed, the section in this designation system usually reserved for S or N will be used to indicate where the tin has been reflowed, or whether it is "matt" or not reflowed (see 6.6 and 6.9). Therefore, the designations for this tin condition will be

- BR: Bright reflowed, fused, melted,
- MA: Matt, dull, not reflowed, unmelted.

The numbers 01, 02, 03 and 04 are common to other standards indicating the qualities of commercial, drawing, deep drawing, and deep drawing aluminium killed.

**EXAMPLE** SN056BR03 is a complete designation, including coating, coating mass, coating condition and quality signifying:

- SN: Tin coating,
- 056: Coating designation (Table 4),
- BR: Bright; tin has been reflowed,
- 03: Deep drawing quality.

## 5 Dimensions

Electrolytic tin-coated sheet is normally produced in thicknesses from 0,50 mm to 0,85 mm and widths of 600 mm to 1 050 mm, in coils and cut lengths.

**NOTE** Some world markets define "electrolytic tinplate" as having a maximum thickness of 0,38 mm, in which case, the thickness range for "electrolytic tin-coated sheet" will have a minimum of 0,38 mm.

## 6 Conditions of manufacture

### 6.1 Chemical composition

The chemical composition (heat analysis) shall not exceed the values given in Tables 1 and 2. On request, a report of the heat analysis shall be made to the purchaser.

Each of the elements listed in Table 2 shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium or molybdenum present is less than 0,02 %, the analysis result may be reported as "< 0,02 %".

A verification analysis may be made by the purchaser to verify the specified analysis of the product and shall take into consideration any normal heterogeneity. Non-killed steels (such as rimmed or capped steels) are not technologically suited to product analysis. For killed steels, the sampling method and deviation limits shall be agreed upon between the interested parties at the time of ordering. The product analysis tolerances are shown in Table 3.

The processes used in making the steel and in manufacturing tin-coated sheet are left to the discretion of the manufacturer. When requested, the purchaser shall be informed of the steel-making process used.



**Table 1 — Chemical composition (heat analysis)**

Mass fractions in percent

Quality		C max.	Mn max. <sup>a</sup>	P max. <sup>a</sup>	S max.
Designation	Name				
01	Commercial	0,15	0,60	0,03	0,035
02	Drawing <sup>b</sup>	0,10	0,50	0,03	0,035
03	Deep drawing <sup>b</sup>	0,08	0,45	0,02	0,03
04	Deep drawing aluminum killed <sup>b</sup> (non-ageing)	0,06	0,45	0,02	0,03

<sup>a</sup> Higher maximum required for certain applications subject to agreement.

<sup>b</sup> If interstitial free (IF Steel) is to be applied to 02, 03 and 04 orders, the values of 0,15 % maximum Ti and 0,10 % maximum Nb and V are acceptable to ensure that the carbon and nitrogen are fully stabilized.

**Table 2 — Limits on additional chemical elements**

Mass fractions in percent

Elements <sup>a</sup>	Heat analysis max.	Product analysis max.
Cu <sup>b</sup>	0,20	0,23
Ni <sup>b</sup>	0,20	0,23
Cr <sup>b,c</sup>	0,15	0,19
Mo <sup>b,c</sup>	0,06	0,07
Nb <sup>d</sup>	0,008	0,018
V <sup>d</sup>	0,008	0,018
Ti <sup>d</sup>	0,008	0,018

<sup>a</sup> Each of the elements listed in this table shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium or molybdenum present is less than 0,02 %, the analysis may be reported as "< 0,02 %".

<sup>b</sup> The sum of copper, nickel, chromium and molybdenum shall not exceed 0,50 % on heat analysis. When one or more of these elements is specified, the sum does not apply; in which case, only the individual limits on the remaining elements will apply.

<sup>c</sup> The sum of chromium and molybdenum shall not exceed 0,16 % on heat analysis. When one or more of these elements is specified, the sum does not apply; in which case, only the individual limits on the remaining elements will apply.

<sup>d</sup> For stabilized steels, the maximum for titanium is 0,15 %, and the maximum for each of niobium and vanadium is 0,10 %, to ensure that the carbon and nitrogen are fully stabilized.

**Table 3 — Product analysis tolerances**

Mass fractions in percent

Element	Maximum of specified element	Tolerance over maximum specified
Carbon	0,15	0,03
Manganese	0,60	0,03
Phosphorus	0,03	0,01
Sulfur	0,035	0,01

NOTE The maximum tolerance in this table is the allowable excess over the specified requirement and not the heat analysis.

## 6.2 Coating mass

The coating mass shall conform to the requirements presented in Table 4 for the specific coating designation. The coating mass is the total amount of the tin, including both sides of the sheet, expressed

in grams per square metre (g/m<sup>2</sup>) of sheet. Methods for checking that the material complies with this International Standard are given in 8.2 and 9.2.

**Table 4 — Mass of coating (total both sides)**

Coating designation	Nominal coating	Minimum coating mass limits	
		Triple spot test check limits	Single spot test check limits
	g/m <sup>2</sup>	g/m <sup>2</sup> (of sheet)	g/m <sup>2</sup> (of sheet)
SN056	5,6	3,7	2,8
SN112	11,2	7,3	5,6
SN168	16,8	11,0	8,2
SN224	22,4	14,6	11,0

Because of the many variables and changing conditions that are characteristic of continuous tin coating, the mass of coating is not always evenly divided between the two surfaces of a tin-coated sheet, neither is the tin coating evenly distributed from edge to edge. However, it can normally be expected that not less than 40 % of the single-spot check limit will be found on either surface.

### 6.3 Weldability

The product is suitable for welding if appropriate welding conditions are selected; however, because of its excellent solderability, welding is seldom performed.

### 6.4 Fabrication qualities

**6.4.1** Commercial-quality electrolytic tin-coated sheet (quality 01) is intended for general fabricating purposes where sheet is used in the flat state, or for bending or moderate forming.

**6.4.2** Drawing quality electrolytic tin-coated sheet (qualities 02, 03, 04) is intended for drawing or severe forming. It is furnished according to the requirements of this International Standard or, with agreement where ordered, to fabricate an identified part, in which case, the mechanical properties in Table 5 do not apply. Drawing qualities are identified as follows:

- 02 Drawing quality
- 03 Deep drawing quality
- 04 Deep drawing quality aluminium killed (non-ageing)

**6.4.3** Interstitial free steel (IF Steel) can be applied in orders of 02, 03 and 04, provided that the customer is informed of the substitution and that related shipping documents reflect the actual material shipped.

### 6.5 Mill passivation

A passivating chemical or electrochemical treatment is applied to the surface of electrolytic tin-coated sheet to stabilize the plate surface characteristics compatible with a specific application.

### 6.6 Coating condition

The as-produced tin-coated sheet has a dull (matt) appearance (Clause 4 and 6.9). If it is heated to the melting point of tin, the tin reflows and has a bright (fused, melted) appearance. Some iron-tin alloy will also form at the steel surface interface during this heating process.

Normally “matt” finish sheet is produced from cold-reduced sheet having a “shot-blasted” surface, and “bright” finish sheet is produced from cold-reduced sheet having “ground” roll surfaces (6.9). All tinning lines have strip thickness limits on bright finish sheet because of melting limitations.

## 6.7 Application

Tin-coated steel shall be identified for fabrication by the name of the part or by the intended application. Steel sheet of drawing qualities (02, 03 and 04) may be produced to make an identified part, which shall be previously agreed between the manufacturer and purchaser. In this case, the part name, the details of fabrication and special requirements (freedom from stretcher strains or fluting, coating performance requirements) shall be specified and the mechanical properties of Table 5 do not apply.

## 6.8 Mechanical properties

Except when ordering an identified part, as explained in 6.7, at the time that the steel is made available for shipment, the mechanical properties shall be as stated in Table 5 when they are determined on test pieces obtained according to the requirements of 8.1 (mechanical tests). Prolonged storing of the sheet can cause changes in mechanical properties (increase in hardness and decrease in elongation), leading to a decrease in drawability. To minimize this effect, quality 04 should be specified.

**Table 5 — Mechanical properties**

Quality		$R_m$ max. <sup>a</sup>	$A$ min. <sup>b</sup> %	
Designation	Name	MPa	$L_o = 50$ mm	$L_o = 80$ mm
01	Commercial <sup>c</sup>			
02	Drawing	370	31	30
03	Deep drawing	350	35	34
04	Deep drawing aluminum killed (non-ageing)	340	37	36

$R_m$  tensile strength  
 $A$  percentage elongation after fracture  
 $L_o$  gauge length of original test piece  
1 MPa = 1 N/mm<sup>2</sup>  
<sup>a</sup> The minimum tensile strength for qualities 02, 03 and 04 would normally be expected to be 270 MPa. All tensile strength values are determined to the nearest 10 MPa.  
<sup>b</sup> For material up to and including 0,6 mm in thickness, the elongation values in this table shall be reduced by 1.  
<sup>c</sup> The hardness of quality 01 steel sheet is expected not to exceed the equivalent of Rockwell HRB65 at the time it is made available for shipment.

## 6.9 Surface finish

Normally two surface finishes are produced for electrolytic tin-coated sheet. These surfaces are obtained by skin passing the strip on either shot-blasted or ground rolls. Shot-blasted rolls impart a rough (SBF) finish produced for matt (dull, unmelted, not reflowed) finish tin-coated sheet, while ground rolls impart a smooth (BR) finish produced for bright (reflowed, melted, fused) electrolytic tin-coated sheet. The required finish shall be specified at the time of ordering.

## 6.10 Oiling

Electrolytic tin-coated sheet always has a lubricant film applied to both surfaces of the sheet as the last operation in the tinning line prior to shearing or coiling, to minimize abrasion. The oil is not intended as a drawing or forming lubricant and shall be easily removable with degreasing chemicals.

## 7 Dimensional tolerances

Dimensional and shape tolerances applicable to cold-reduced steel sheet shall be as given in ISO 16162.

## 8 Sampling

One representative sample for the tensile test required in Table 4 shall be taken from each lot of sheet for shipment. A lot consists of 50 t or less of sheet of the same designation rolled to the same thickness and condition.

### 8.1 Tensile test

If the order specifies mechanical properties, one representative sample for the tensile property test required in Table 5 shall be taken from each lot of sheet for shipment.

### 8.2 Tests for mass of coating

The manufacturer shall make such tests and measurements as deemed necessary to ensure that the material produced complies with the values given in Table 4. The purchaser may verify the mass of coating by use of the following sampling method.

Three specimens shall be cut, one from the mid-width position and one from each side, not closer than 25 mm from the side edge. The minimum specimen area shall be 2 000 mm<sup>2</sup>.

## 9 Test methods

### 9.1 Tensile test (base metal)

The tensile test shall be carried out in accordance with ISO 6892-1. Transverse test pieces shall be taken mid-way between the centre and edge of the sheet as rolled. Because the tin coating is very thin, the ends of test pieces are not usually required to have the tin removed prior to testing.

### 9.2 Coating tests

#### 9.2.1 Triple spot test

The triple spot test result is the average coating mass found on the three specimens taken according to 8.2. The tin-coating mass may be determined by any of the recognized and accepted analytical methods.

#### 9.2.2 Single spot test

The single spot test result shall be the minimum coating mass found on any one of the three pieces used for the triple spot test. Material that has been slit from wide coil shall be subject to a single spot test only.

## 10 Retests

### 10.1 Machining and flaws

If any test piece shows defective machining or develops flaws, it shall be discarded and another test piece substituted.

### 10.2 Additional tests

If a test does not give the specified results, two additional tests shall be carried out at random on the same lot. Both retests shall conform to the requirements of this International Standard; otherwise, the lot may be rejected.

## 11 Resubmission

The manufacturer may resubmit, for acceptance, the products that have been rejected during earlier inspection because of unsatisfactory properties, after he has subjected them to a suitable treatment (selection, heat treatment), which, on request, will be indicated to the purchaser. In this case, tests shall be carried out as if they applied to a new batch.

The manufacturer has the right to present the rejected products to a new examination for compliance with the requirements for another grade.

## 12 Workmanship

The surface condition shall be that normally obtained in this product.

The electrolytic tin-coated sheet in cut lengths shall be free from laminations, surface flaws and other imperfections that are detrimental to subsequent appropriate processing. Processing for shipment in coils does not afford the manufacturer the opportunity to observe readily or to remove defective portions, as can be carried out on the cut-length product.

## 13 Inspection and acceptance

**13.1** While not usually required for products covered by this International Standard, when the purchaser specifies that inspection and tests for acceptance be observed prior to shipment from the manufacturer's works, the manufacturer shall provide the purchaser's inspector with all reasonable facilities to determine that the steel is being furnished in accordance with this International Standard.

**13.2** Steel that is reported to be defective after arrival at the user's works shall be set aside, properly and correctly identified and adequately protected. The supplier shall be notified in order that he may properly investigate.

## 14 Coil size

When electrolytic tin-coated steel sheet is ordered in coils, a minimum inside diameter (I.D.) or range of acceptable inside diameters shall be specified. In addition, the maximum outside diameter (O.D.) and maximum acceptable coil mass shall be specified.

## 15 Marking

Unless otherwise stated, the following minimum requirements for identifying the steel shall be legibly stencilled on the top of each lift, or shown on a tag attached to each coil or shipping unit:

- a) the manufacturer's name or identifying brand;
- b) the number of this International Standard, i.e. ISO 5950:2012;
- c) the designation (coating, coating mass, coating condition and quality of base metal);
- d) the order number;
- e) the product dimensions;
- f) the lot number;
- g) the mass.

## 16 Information to be supplied by the purchaser

To adequately specify requirements in accordance with this International Standard, enquiries and orders shall include the following information:

- a) the number of this International Standard, i.e. ISO 5950:2012;
- b) the name and designation of the material, for example electrolytic tin-coated sheet, 056 coating, bright commercial quality, SN056BR01 (see Clause 4 and 6.4);
- c) the dimensions of the product (the thickness includes the coating) and the quantity required;
- d) the finish, i.e. whether SBF or ground roll (see 6.9);
- e) the application (name of part), if possible (6.7);
- f) for drawing qualities (03 and 04), whether ordered according to mechanical properties (6.8) or to fabricate an identified part (see 6.7);
- g) the coil size requirements (Clause 14);
- h) whether a report of the heat analysis is required (6.1);
- i) details of fabrication or special requirements;
- j) inspection and tests for acceptance prior to shipment from the producer's works, if required (see 13.1).

EXAMPLE ISO 5950:2012, electrolytic tin-coated steel sheet 056BR, commercial quality, designation SN056BR01, 0,7 × 1 200 mm × coil 20 000 kg, to form cookie tins.

## Bibliography

- [1] ASTM A599M, *Standard Specification for Tin Mill Products, Electrolytic Tin-Coated, Cold-Rolled Sheet*<sup>1)</sup>

---

1) This document is recognized by ISO/TC17/SC12 to cover a subject similar to that of this International Standard. This information is given for the convenience of users of this International Standard and constitutes neither an endorsement of the document by TC17/SC12 or ISO, nor a statement regarding its degree of equivalence with this International Standard.







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™