

BS ISO 7322:2014



BSI Standards Publication

Composition cork — Test methods

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 7322:2014. It supersedes BS ISO 7322:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/81, Cork.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 82096 0

ICS 79.100

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2014.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 7322:2014

ISO
7322

Third edition
2014-10-15

Composition cork — Test methods

Aggloméré composé de liège — Méthodes d'essai



Reference number
ISO 7322:2014(E)

© ISO 2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	1
5 Sampling and preparation of test specimens	2
5.1 Sampling.....	2
5.2 Preparation of test specimen.....	2
5.3 Conditioning.....	2
6 Tests	3
6.1 Thickness.....	3
6.2 Apparent density.....	3
6.3 Tensile strength.....	4
6.4 Compressibility and recovery.....	4
6.5 Resistance to boiling water.....	6
7 Test report	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 87, *Cork*.

This third edition cancels and replaces the second edition (ISO 7322:2000). Minor editorial details have been introduced in this edition.

Composition cork — Test methods

1 Scope

This International Standard specifies test methods for the determination of the following characteristics of composition cork:

- thickness,
- apparent density,
- tensile strength,
- compressibility and recovery,
- resistance to boiling water.

This International Standard is applicable to the product in sheet or roll form.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

composition cork

product obtained from the agglutination of cork granules with the addition of a binder generally not derived from cork cells

3.2

rubbercork

product manufactured as a compound of cork granules and rubber, which can be used either in the form of granules or as a binder

4 Apparatus

4.1 Static load press, with flat parallel plates of dimensions greater than those of the test specimens to be tested, one fixed and the other mobile to enable the load application at a constant rate, and equipped with the following items.

4.1.1 Cylindrical indentors, made of stainless steel having the following diameters:

- 28,7 mm, for testing composition cork,
- 12,8 mm, for testing rubbercork.

4.1.2 Dial gauge, attached to the movable plate, capable of being read to the nearest 0,02 mm.

4.1.3 Weights, for adjusting the applied load, having masses accurate to $\pm 1\%$.

4.2 Tensile testing machine, with one fixed jaw and one mobile jaw 12 mm apart (to test composition cork) or 50,8 mm apart (to test rubbercork), with readings are accurate to $\pm 1\text{ N}$.

The mobile jaw shall move unloaded at a speed of 300 mm/min.

4.3 Balance, with a resolution of 0,01 g.

4.4 Oven or climatic room, with temperature and humidity controls.

4.5 Vernier gauge, with a constant contact force, and a resolution of 0,1 mm.

4.6 Metal ruler, with a resolution of 1 mm.

4.7 Chronometer with a resolution of 1 s.

4.8 Cutting system, to cut the test specimens.

4.9 Open container, for water.

5 Sampling and preparation of test specimens

5.1 Sampling

From each lot, the number of packages, at least three, and the quantity of material to be taken from the sample shall follow ISO 2859-1 for the inspection level agreed between parties.

5.2 Preparation of test specimen

From each sheet of the material, cut the test specimens as indicated in [Table 1](#), at least 100 mm away from the edges. Each test specimen shall be squarely cut with the edges perpendicular to its surface, showing no cracks or folds.

5.3 Conditioning

Test specimens shall be conditioned for 48 h at 23 °C. In case of dispute, the test specimens shall be conditioned at a temperature of $(23 \pm 2)^\circ\text{C}$ and $(50 \pm 5)\%$ of relative humidity, for 48 h. Unless otherwise specified, the tests shall be carried out at the same temperature and humidity conditions.

Table 1 — Dimensions and number of test specimens

Test	Dimensions of test specimens mm	Number of test specimens	Notes
Thickness	100 × 50	5	
Apparent density	100 × 50	5	The test specimens for the thickness test may be used.
Tensile strength	100 × 50	3	If the composition cork was produced in rolls, take 3 test specimens in the direction of the compression plus 3 test specimens in the perpendicular direction.
Compressibility and recovery	50 × 50 or circular with $\varnothing = 28,7$	3 test specimens (in the case of single sampling) or 3 groups of <i>n</i> test specimens	
Resistance to boiling water	50 × 50	3	

6 Tests

6.1 Thickness

6.1.1 Procedure

Place one test specimen on the fixed plate of the static press (4.1). Apply the indenter (4.1.1) without shock at the centre of the test specimen and apply the mass defined in Table 2, in accordance with the type of composition cork concerned. After 15 s, read the thickness in the dial gauge (4.1.2).

For test specimens with thicknesses greater than 10 mm, a Vernier gauge (4.5) shall be used.

6.1.2 Calculation and expression of results

The thickness of the sample is the average of the results obtained for each test specimen. Express the results in millimetres, rounded off to the nearest 0,1 mm.

Table 2 — Applied masses for the thickness measurement

Material	Diameter of the indenter mm	Mass g	Force N	Pressure kPa
composition cork	28,7	450	4,4	6,8
rubbercork	12,8	450	4,4	34,3

6.2 Apparent density

6.2.1 Procedure

Use the Vernier gauge (4.5) or a metal ruler (4.6) to determine the length and the width of each test specimen, in millimetres, to the nearest 0,1 mm and record the values obtained. Determine the mass of each test specimen to the nearest 0,1 g and record the values obtained.

6.2.2 Calculation and expression of results

The apparent density of each test specimen, expressed in kilograms per cubic metre, is given by the Formula (1):

$$\frac{m}{l \times b \times d} \times 10^6 \quad (1)$$

where

- m* is the mass of the test specimen, expressed in gram, rounded to the nearest 0,1 g;
- l* is the length of the test specimen, expressed in millimetres, rounded to the nearest integer;
- b* is the width of the test specimen, expressed in millimetres, rounded to the nearest integer;
- d* is the thickness of the test specimen, obtained from [6.1](#), expressed in millimetres, rounded to the nearest 0,1 mm.

The apparent density of the sample is the average of the results obtained for each test specimen rounded off to the nearest integer.

6.3 Tensile strength

6.3.1 Procedure

Clamp one test specimen in the machine jaws so that the force is exerted on the length of the test specimen. Set the machine in operation and record the force (*F*) at which rupture occurs.

Any test specimen for which rupture occurs at the jaw level shall be eliminated and replaced by a new test specimen.

6.3.2 Calculation and expression of results

The tensile strength of each test specimen, expressed in kilopascals, is given by Formula (2):

$$\frac{F}{b \times d} \times 10^3 \quad (2)$$

where

- F* is the force at which rupture occurs, expressed in newtons, rounded to the nearest integer;
- b* is the width of the test specimen, expressed in millimetres, rounded to the nearest integer;
- d* is the thickness of the test specimen, expressed in millimetres, rounded to the nearest 0,1 mm.

The tensile strength of the sample is the average of the results obtained for each test specimen rounded to the nearest integer.

6.4 Compressibility and recovery

6.4.1 Procedure

The dimensions of test specimens are specified in [Table 1](#).

Test specimens shall consist in a single ply or a number of superimposed plies to give a minimum test thickness of 3,2 mm.

Determine the deflection of the indenter for each load specified in [Table 3](#) without any test specimen. Subtract any measurable value occurring on the static press from the thickness under total load. This value shall be subtracted from the readings with the test specimen.

NOTE The deflection in the testing apparatus can also be compensated by setting the dial gauge on the negative side of zero at a reading equal to the deflection.

Table 3 — Applied loads and corresponding pressures

Type of material	Diameter of the indenter mm	Preload N	Major load N	Total load N	Total pressure kPa
composition cork	28,7	4,5	440	445	700
composition cork with cellular rubber	28,7	4,5	440	445	700
rubbercork	12,8	4,5	351	355	2750

Centre the test specimen on the base of the press ([4.1](#)) and apply the preload; maintain this load for 15 s. Record the reading (d_1) in the dial gauge under the action of the preload.

Immediately and without shock, apply the major load so that the total load is reached in 10 s; maintain the total load for 60 s and record the thickness of the test specimen (d_2) in the dial gauge. Immediately remove the major load. After 60 s read the new thickness (d_3) under the preload.

6.4.2 Calculation and expression of results

The compressibility of each test specimen, expressed in percentage, is given by Formula (3):

$$\frac{d_1 - d_2}{d_1} \times 100 \quad (3)$$

The recovery of each test specimen, expressed in percentage, is given by Formula (4):

$$\frac{d_3 - d_2}{d_1 - d_2} \times 100 \quad (4)$$

where

- d_1 is the reading in the dial gauge, for each test specimen under the preload, expressed in millimetres, rounded to the nearest 0,1 mm;
- d_2 is the reading in the dial gauge, for each test specimen under total load, expressed in millimetres, rounded to the nearest 0,1 mm;
- d_3 is the reading in the dial gauge, for each test specimen after the recovery and under the preload, expressed in millimetres, rounded to the nearest 0,1 mm.

The test result is the average of the results obtained for each test specimen, expressed in percentage rounded to the nearest integer.

6.5 Resistance to boiling water

6.5.1 Procedure

Boil the water in a container (4.9). Place the test specimens and keep the water boiling for 3 h. Remove the test specimens and make their visual examination.

6.5.2 Expression of result

Express the test results by stating the existence or absence of disaggregation¹⁾ of the sample.

7 Test report

The test report shall include the following information:

- a) reference to this International Standard, i.e. ISO 7322;
- b) the complete identification of the product tested, including the type, source and the manufacturer's references;
- c) sampling report;
- d) results obtained;
- e) any deviation from this International Standard that may have affected the results.

1) A test specimen is said to disaggregate if it splits open and/or if it shows substantial loss of particles during the test.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™