

# Carbonaceous materials used in the production of aluminium — Green and calcined coke — Determination of ash content

ICS 71.100.10

## National foreword

This British Standard reproduces verbatim ISO 8005:2005 and implements it as the UK national standard. It supersedes BS 6043-2-2:1985 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CII/24, Raw materials for aluminium, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, the ISO title page, pages ii to iv, pages 1 to 3 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

### Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 12 January 2006

© BSI 12 January 2006

INTERNATIONAL  
STANDARD

**ISO**  
**8005**

Second edition  
2005-10-01

---

---

**Carbonaceous materials used in the  
production of aluminium — Green and  
calcined coke — Determination of ash  
content**

*Produits carbonés utilisés pour la production de l'aluminium — Coke  
cru et coke calciné — Détermination du taux de cendres*



Reference number  
ISO 8005:2005(E)



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8005 was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

This second edition cancels and replaces the first edition (ISO 8005:1984), which has been technically revised.

## Introduction

The content of ash or inorganic materials in coke is an important property, as ash will accumulate in the electrolyte when the coke is used for anodes. Constant ash content may also be an indication that the same raw materials are used.

# Carbonaceous materials used in the production of aluminium — Green and calcined coke — Determination of ash content

## 1 Scope

This International Standard specifies a method for the determination of ash in green and calcined coke used in the production of aluminium.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6375, *Carbonaceous materials for the production of aluminium — Cokes for electrodes — Sampling*

ASTM Practice E691–99, *Standard Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method*

## 3 Principle

Heating of a test portion of a dry, finely ground sample in a tared dish in a furnace at 700 °C, to constant mass.

## 4 Apparatus

**4.1 Jaw crusher**, or another suitable crusher, faced with a very hard alloy that will not be abraded and therefore will not contaminate the sample.

**4.2 Pestle and mortar**, or a suitable mill, of hard material that will not be abraded and therefore will not contaminate the sample.

Suitable materials are agate, tungsten or silicon carbide. Porcelain should not be used.

**4.3 Sieve**, 750 µm.

**4.4 Laboratory balance**.

**4.5 Desiccator**, containing a drying agent (e.g. activated alumina or molecular sieves).

**4.6 Platinum dish**, of capacity 50 ml to 60 ml, diameter about 65 mm to 72 mm, height about 15 mm; or an appropriate porcelain dish.

**4.7 Oven**, capable of maintaining a temperature of  $(105 \pm 5)$  °C.

**4.8 Electric furnace**, capable of being controlled at  $(700 \pm 10)$  °C, with an adequate air circulation.

## 5 Sampling and sample

Sample in accordance with ISO 6375.

## 6 Procedure

### 6.1 Preparation of the test sample

Use any suitable means to crush a representative portion of the material (Clause 5) to approximately 25 mm or smaller size and dry until it is totally dry [e.g. at  $(105 \pm 5)$  °C for 3 h]. Further crush the dry material, by means of the crusher (4.1), to approximately 6 mm or smaller size.

Thoroughly mix the dried crushed material; reduce it by quartering to a test sample of at least 50 g.

Grind the entire 50 g test sample with the pestle and mortar or in a mill (4.2) to such a fineness that it all passes through the 750 µm sieve (4.3).

### 6.2 Test portion

**6.2.1** Heat the platinum or porcelain dish (4.6) for 1 h in the furnace (4.8), controlled at  $(700 \pm 10)$  °C, allow it to cool to ambient temperature in the desiccator containing the drying agent (4.5) and weigh to the nearest 0,000 2 g.

**6.2.2** Weigh, to the nearest 0,000 2 g, a test portion of about 20 g of the dry, sieved test sample (6.1), or a quantity sufficient to provide a minimum of 0,020 g of ash, in the previously tared dish (6.2.1).

### 6.3 Determination

**6.3.1** Place the dish containing the test portion (6.2.2) into the cold furnace (4.8) and raise the temperature of the furnace to  $(700 \pm 10)$  °C.

Gradually heat to redness at such a rate as to avoid mechanical loss (in the case of green coke, this prevents a too rapid expulsion of volatile matter).

Maintain at  $(700 \pm 10)$  °C overnight, or for an adequate time to completely burn off the carbonaceous matter in the test portion. Remove the dish containing the ash from the furnace and cool it to room temperature in the desiccator containing the drying agent (4.5).

**6.3.2** Weigh the dish and ash as rapidly as possible; replace them in the furnace and repeat heating, cooling and weighing until the mass of the dish and contents does not differ by more than 0,000 5 g for two consecutive weighings.

## 7 Expression of results

### 7.1 Method of calculation

The ash content, expressed as a percentage by mass,  $w_a$ , is given by the formula:

$$w_a = (m_2 - m_1) \times \frac{100}{m_0}$$

where

$m_0$  is the mass, in grams, of the test portion (6.2.2);

$m_1$  is the mass, in grams, of the empty dish (6.2.1);

$m_2$  is the mass, in grams, of the dish containing the ash (6.3.2).



Report the result in weight percent to the nearest 0,01 %.

## 7.2 Precision

### 7.2.1 Laboratories, materials and determinations

The number of laboratories, materials, and determinations met the minimum requirements for determining precision specified in ASTM Practice E691 (see Table 1):

**Table 1 — Laboratories, materials and determinations**

	This study	ASTM E691 Minimum
Laboratories	8	6
Materials	6	4
Determinations:	4	2

### 7.2.2 Precision statement for test method

Repeatability  $r = 0,03$  % (weight percent)

Reproducibility  $R = 0,06$  % (weight percent)

## 8 Test report

The test report shall include the following information:

- a) an identification of the sample;
- b) a reference to this International Standard;
- c) the results and the method of expression used;
- d) any unusual features noted during the determination;
- e) any operation not included in this International Standard or in the International Standards to which reference is made, or regarded as optional;
- f) date of the test.

---

---

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.  
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.  
Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.  
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.  
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.  
Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.  
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.  
Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).