

BS ISO 8036:2015



BSI Standards Publication

Microscopes — Immersion liquids for light microscopy

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 8036:2015. It supersedes BS ISO 8036:2006 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CPW/172, Optics and Photonics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 88295 1

ICS 37.020

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
8036

Second edition
2015-06-01

**Microscopes — Immersion liquids for
light microscopy**

Microscopes — Liquides d'immersion pour microscopie optique



Reference number
ISO 8036:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Classification	1
4 Characteristics of immersion liquids	1
4.1 Optical properties	1
4.2 Transmittance	2
4.3 Autofluorescence	2
4.4 Viscosity	2
4.5 Density	2
5 Minimum requirements	3
6 Ingredients	3
7 Designation of immersion liquids	3
8 Labelling of containers	3
9 Technical data sheet	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 172, *Optics and photonics*, SC 5, *Microscopes and endoscopes*.

This second edition cancels and replaces the first edition (ISO 8036:2006), where in [Clause 6](#), the outdated reference to the EU Directive 91/155/EEC and its Amendments 93/112/EC and 01/58/EC were removed.

Microscopes — Immersion liquids for light microscopy

1 Scope

This International Standard describes the characteristics of immersion liquids used in microscopy. It classifies immersion liquids according to their field of application and specifies requirements and test methods for each type.

This International Standard further specifies a system of designation for immersion liquids, the information to be included on container labels, and the information to be supplied in technical data sheets.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2592, *Determination of flash and fire points — Cleveland open cup method*

ISO 8255-1, *Microscopes — Cover glasses — Part 1: Dimensional tolerances, thickness and optical properties*

ISO 8255-2, *Microscopes — Cover glasses — Part 2: Quality of materials, standards of finish and mode of packaging*

3 Classification

Depending on their field of application, immersion liquids are classified as follows:

- type N: immersion oil for general use in light microscopy;
- type F: immersion oil which meets the requirements of fluorescence microscopy;
- type G: spectrally pure glycerol (commonly known as glycerine) for glycerol immersion.

4 Characteristics of immersion liquids

4.1 Optical properties

The optical properties of immersion liquids are defined by the refractive index at the wavelength $\lambda = 546,07$ nm, n_e , at a defined temperature (23 °C) and pressure (1 013,25 hPa), as well as by the Abbe number (reciprocal of the dispersive power), v_e .

The Abbe number, v_e , is calculated using Formula (1):

$$v_e = \frac{n_e - 1}{n_{F'} - n_{C'}} \quad (1)$$

where

$n_{F'}$ is the refractive index at $\lambda = 479,99$ nm;

$n_{C'}$ is the refractive index at $\lambda = 643,85$ nm.

The refractive indices are usually measured with an Abbe refractometer at constant temperature with a tolerance of $\pm 0,1$ °C. A mercury-cadmium spectral lamp is used as the light source.

4.2 Transmittance

Modern detection methods in light microscopy require an extension of the spectral range of immersion liquids.

The transmittance is measured using a suitable spectrophotometer in quartz cuvettes with an optical path length through the immersion liquid of $d = 10$ mm against an empty reference cuvette.

4.3 Autofluorescence

The autofluorescence of immersion liquids is measured with a fluorescence spectrometer. Quinine sulfate in 0,05 mol/l sulfuric acid is used as the fluorescence standard. For the fluorescence measurement, the following excitation and emission wavelengths are used:

- F(365 nm/450 nm) = fluorescence excitation at 365 nm, measurement of fluorescence emission at 450 nm;
- F(405 nm/485 nm) = fluorescence excitation at 405 nm, measurement of fluorescence emission at 485 nm.

As the fluorescence emission decreases during the measurement, the autofluorescence of immersion liquids is averaged over a measurement time of 60 s.

Immersion liquid samples and standard liquids are measured in a fluorescence cuvette made of quartz or special optical glass with an optical path length through the immersion liquid of $d = 10$ mm. The reagents used shall meet the quality standards for fluorescence spectroscopy.

Prepare a quinine sulfate stock solution of 500 mg/l with 0,05 mol/l sulfuric acid. Before use, prepare two standard solutions of 0,1 mg/l and 2,5 mg/l quinine sulfate in 0,05 mol/l sulfuric acid by diluting the stock solution 1:5000 and 1:200, respectively. Store the stock solution in a closed brown glass bottle at 6 °C to 12 °C for no more than two months. Always prepare the standard solutions fresh on the day of use.

As an alternative to quinine sulfate solution, solid-state fluorescence standards with the same shape as a 10 mm cuvette may be used. These shall be calibrated against a quinine sulfate standard solution at least once a year.

NOTE 1 Solid-state fluorescence standards are available as spectroscopy accessories.

The information regarding the autofluorescence of the immersion liquids is given in terms of the equivalent amount of quinine sulfate, in mg/l.

NOTE 2 Quinine sulfate is more suitable for use as a fluorescence standard than rhodamine B because immersion oils tend, like quinine sulfate, to emit in the blue region in the case of UVA excitation, while rhodamine B emits in the green region.

4.4 Viscosity

The viscosity of the immersion liquid shall be measured by means of a capillary viscometer, e.g. an Ubbelohde viscometer, at a temperature of 23 °C.

4.5 Density

The density of the immersion liquid shall be measured at a temperature of 23 °C by means of a hydrometer or a pycnometer.

5 Minimum requirements

See [Table 1](#).

6 Ingredients

Immersion liquids conforming to this International Standard shall not contain ingredients which are known to have any adverse effects on safety or health.

7 Designation of immersion liquids

Immersion liquids conforming to this International Standard shall be designated as in the following example:

EXAMPLE Immersion liquid ISO 8036 Type F.

8 Labelling of containers

Immersion liquids are commonly packed and marketed in brown glass bottles or in oilers made from polyethylene or polypropylene. The labelling of these containers shall include the following information:

- the product name;
- the designation in accordance with this International Standard;
- labelling required by regulations for hazardous freight;
- the refractive index, n_e , at 23 °C;
- the Abbe number, v_e ;
- the batch number;
- the expiration date when stored in the unopened original packaging in accordance with the manufacturer's instructions;
- information on how to obtain technical and safety data;
- the name and address of the manufacturer and the supplier, plus the country of origin if different from that given in the manufacturer's address.

Table 1 — Minimum requirements for immersion liquids^a

Parameter	Type N (standard)	Type F (for fluorescence)	Type G (glycerol) ^b
Reference temperature (°C)	23	23	23
Tolerance (°C)	±0,1	±0,1	±0,1
Spectral range (nm)	400 to 900	320 to 1 100	230 to 1 100
Refractive index, n_e	1,518 0 ± 0,000 5	1,518 0 ± 0,000 5	1,450 ± 0,005
Abbe number, v_e	43 ± 4	43 ± 4	58 ± 4
Transmittance ($d = 10$ mm)			
at 1 100 nm	—	80 %	70 %

^a Immersion liquids, with the exception of glycerol, may not contain volatile or hygroscopic ingredients. Specifications for these liquids assume the use of a cover glass as specified in ISO 8255-1 and ISO 8255-2.

^b Glycerol is hygroscopic and its physical properties depend on its water content.

^c Autofluorescence of type N oil has no specified values, but high values can be expected.

Table 1 (continued)

Parameter	Type N (standard)	Type F (for fluorescence)	Type G (glycerol) ^b
at 1 000 nm	—	80 %	70 %
at 900 nm	90 %	90 %	90 %
at 800 nm	95 %	95 %	98 %
at 760 nm	95 %	95 %	98 %
at 600 nm	95 %	95 %	98 %
at 500 nm	95 %	95 %	98 %
at 450 nm	85 %	95 %	98 %
at 420 nm	75 %	95 %	98 %
at 400 nm	60 %	95 %	98 %
at 380 nm	—	90 %	95 %
at 365 nm	—	80 %	95 %
at 350 nm	—	70 %	90 %
at 330 nm	—	40 %	80 %
at 320 nm	—	20 %	70 %
at 310 nm	—	—	50 %
at 230 nm to 300 nm	—	—	30 %
Autofluorescence (mg/l quinine sulfate)			
F(365 nm/450 nm)	c	0,06	0,02
F(405 nm/485 nm)	c	1,20	0,50
F(313 nm/450 nm)	—	—	0,05
Viscosity (mm ² /s)			
at 23 °C ± 0,1 °C	50 to 1 500	50 to 1 500	b
<p>^a Immersion liquids, with the exception of glycerol, may not contain volatile or hygroscopic ingredients. Specifications for these liquids assume the use of a cover glass as specified in ISO 8255-1 and ISO 8255-2.</p> <p>^b Glycerol is hygroscopic and its physical properties depend on its water content.</p> <p>^c Autofluorescence of type N oil has no specified values, but high values can be expected.</p>			

9 Technical data sheet

The manufacturer or the supplier of an immersion liquid shall make a technical data sheet available on request. This data sheet shall contain the following information:

- product name;
- manufacturer;
- designation in accordance with this International Standard;
- field of application;
- chemical basis;
- reference temperature for refractive index measurements;
- spectral range;

- refractive indices n_e , n_D (at sodium D-line), n_g (at mercury g-line), n_F' , n_C ;
- Abbe number, v_e ;
- temperature coefficient of refractive index in the range 15 °C to 40 °C;
- transmittance within the spectral range for an optical path length $d = 10$ mm;
- autofluorescence;
- behaviour with regard to microscopy stains;
- density at 23 °C;
- viscosity at 23 °C;
- flash point determined in accordance with ISO 2592 (Cleveland open cup method);
- storage conditions;
- recommended cleaning agents;
- information on disposal.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™