

BS ISO 8287:2011



BSI Standards Publication

Magnesium and magnesium alloys — Unalloyed magnesium — Chemical composition

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 8287:2011.

The UK participation in its preparation was entrusted to Technical Committee NFE/35, Light metals and their alloys.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 70478 9

ICS 77.120.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2011.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

BS ISO 8287:2011

ISO
8287

Third edition
2011-12-01

Magnesium and magnesium alloys — Unalloyed magnesium — Chemical composition

*Magnésium et alliages de magnésium — Magnésium non allié —
Composition chimique*



Reference number
ISO 8287:2011(E)

© ISO 2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8287 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 5, *Magnesium and alloys of cast or wrought magnesium*.

This third edition cancels and replaces the second edition (ISO 8287:2000), which has been technically revised.

Introduction

This International Standard classifies commercially available cast unalloyed magnesium into a number of grades suitable for the applications for which they might be used. The grades listed in this International Standard are identical to those in EN 12421:1998.

Magnesium and magnesium alloys — Unalloyed magnesium — Chemical composition

1 Scope

This International Standard specifies the chemical composition of cast unalloyed magnesium. It specifies classification, designation, testing rules, marking, packing, transportation, storage, and information contained in the contract.

This International Standard is for cast unalloyed magnesium produced by the silicon-thermo process or molten salt electrolysis process.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 80000-1:2009, *Quantities and units — Part 1: General*

EN 12421:1998, *Magnesium and magnesium alloys — Unalloyed magnesium*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

unalloyed magnesium

magnesium with a minimum purity of 99,0 % by mass

3.2

cast unalloyed magnesium

unalloyed magnesium cast in a variety of shapes

4 Information to be supplied by the purchaser

The enquiry and order shall define the product required and shall contain the following information:

- a) material designation;
- b) product shape;
- c) quantity (for example number, mass, etc.);
- d) any requirements for declarations of conformity;
- e) any additional requirements agreed between the manufacturer and the purchaser.

5 Designation

The material shall be designated by the appropriate symbols given in Table 1.

6 Manufacture

The manufacturing process shall be left to the discretion of the manufacturer unless otherwise agreed at the time of ordering.

NOTE The manufacturing process covers all operations up to the delivery of the product.

7 Chemical composition

The chemical composition of cast unalloyed magnesium shall conform to the requirements for the appropriate material given in Table 1.

Unless otherwise specified in the enquiry and order, the chemical composition of the cast unalloyed magnesium shall relate to that of samples taken from the melt at the time of pouring.

8 General condition of the product

The product shall have a clean surface in accordance with the agreement between the manufacturer and the purchaser, and shall be free from visible and internal defects to a level also agreed between the manufacturer and the purchaser.

9 Testing conditions

9.1 Inspection and acceptance

9.1.1 The product quality certificate should be filled in by the supplier.

9.1.2 The purchaser should retest the products received. If the results of the retest do not conform to this International Standard or the purchase order, the purchaser should inform the supplier within 3 months from the date the products were received, and a solution should be reached between the supplier and the purchaser.

9.2 Batches

Pure magnesium should be submitted to testing in batches; each consignment should be from the same issue of the melting furnace products. No limits exist on the weight of each single consignment.

10 Testing

Analysis to ensure conformity with the chemical composition requirements given in Table 1 shall be carried out on samples taken by the manufacturer and representative of the material delivered.

Table 1 — Chemical composition of cast unalloyed magnesium

Material designation		Chemical composition													
		% by mass													
In accordance with ISO system	In accordance with EN 12421	Min. or	Al	Mn	Si	Fe	Cu	Ni	Pb	Sn	Na	Ca	Zn	Others ^a (each)	Mg ^b
ISO Mg 99,5	EN-MB10010	Min.	— 0,1	— 0,1	— 0,1	— 0,1	— 0,1	— 0,1	— 0,1	— —	— 0,01	— 0,01	— —	— 0,05	99,5 —
ISO Mg 99,80A	EN-MB10020	Min.	— 0,05	— 0,05	— 0,05	— 0,05	— 0,02	— 0,001	— 0,02	— 0,01	— 0,003	— 0,003	— 0,05	— 0,05	99,80 —
ISO Mg 99,80B	EN-MB10021	Min.	— 0,05	— 0,05	— 0,05	— 0,05	— 0,02	— 0,002	— 0,02	— 0,01	— —	— —	— 0,05	— 0,05	99,80 —
ISO Mg 99,80C		Min.	— 0,05	— 0,1	— 0,02	— 0,004	— 0,005	— 0,001	— —	— —	— —	— —	— —	— 0,01	99,80 —
ISO Mg 99,90		Min.	— 0,02	— 0,03	— 0,03	— 0,04	— 0,004	— 0,001	— —	— —	— —	— —	— —	— 0,01	99,90 —
ISO Mg 99,95A	EN-MB10030	Min.	— 0,01	— 0,006	— 0,006	— 0,003	— 0,005	— 0,001	— 0,005	— 0,005	— 0,003	— 0,003	— 0,005	— 0,005	99,95 —
ISO Mg 99,95B	EN-MB10031	Min.	— 0,015	— 0,015	— 0,015	— 0,005	— 0,005	— 0,001	— 0,005	— 0,005	— —	— —	— 0,01	— 0,005	99,95 —
ISO Mg 99,98		Min.	— 0,004	— 0,002	— 0,003	— 0,002	— 0,0005	— 0,0005	— 0,001	— 0,004	— —	— —	— 0,004	— 0,005	99,98 —
ISO Mg 99,99		Min.	— 0,002	— 0,002	— 0,003	— 0,002	— 0,0003	— 0,0003	— 0,002	— 0,002	— —	— —	— 0,003	— 0,003	99,99 —

^a The sum of the mass percents of Cd, Hg, As and Cr should be less than 0,01 %. For products used in the food and medicine fields, these four elements must be inspected.

^b By difference.

11 Rounding of results

In recording the results of the chemical analysis, the result obtained for any property specified in this International Standard shall be expressed to the same number of decimal places as the corresponding value in this International Standard. Rounding shall be carried out as specified in ISO 80000-1:2009, Annex B, Clauses B.2 and B.3. In Clause B.3, it is left to the discretion of the manufacturer as to whether to use Rule A or B, unless the use of one of the rules has been agreed at the time of acceptance of the order.

12 Declaration of conformity and inspection documents

If agreed between the manufacturer and the purchaser or when specified on the order, the manufacturer shall provide a declaration of product conformity or an inspection document listing the results of the analysis of the chemical elements given in Table 1, and of any other element which may have been previously agreed upon.

13 Marking

Unless otherwise agreed, each product, or bundle of products, shall be clearly marked with the following:

- manufacturer's identification, molten furnace number, and mark of test on each ingot;
- each bundle should have a bright colour, waterproofing, a label that does not fall off easily and on which is clearly marked the smelting number, bunch of numbers, net weight, number of ingots, designation, manufacturing date, place of origin, and manufacturer's logo.

The method of marking is left to the discretion of the manufacturer. Markings shall be indelible and shall not be a source of contamination.

14 Packing

Unless otherwise agreed by the supplier and the purchaser, the pure magnesium ingot should

- a) be packed on a pure magnesium metal plate or a dry wooden plate,
- b) be covered and wrapped by a whole plastic film, then enlaced by PVC belts,
- c) contain pure magnesium ingots from a maximum of 2 smelting numbers in each bunch, and
- d) contain 1 000 kg \pm 50kg or 500 kg \pm 20 kg of pure magnesium ingots in each bunch.

15 Transportation

The pure magnesium ingots should use rainproof vehicles or vehicles equipped with rainproof applications or clean containers for the transportation. Special care should be taken when loading and unloading during rain and when the ingots are dripping wet.

16 Storage

The pure magnesium ingots should be stored in a dry, clean, ventilated warehouse which contains no corrosive medium.

17 Quality certificate

Each batch of products should have a quality certificate attached, indicating the following:

- a) supplier's name;
- b) designation;
- c) batch number;
- d) net weight and ingot number;
- e) the analysis and test results;
- f) the number of this International Standard.

18 Complaints

In the event of any product complaints, the manufacturer shall examine the validity of the complaint within a reasonable time.

Complaints may only be raised against defective products if the defect impairs their processing and use to a more than negligible extent. This shall apply unless otherwise agreed at the time of acceptance of the order.

The purchaser shall give the manufacturer the opportunity to judge whether the complaints are justified.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™