

BS ISO 8312:2015



BSI Standards Publication

Rubber compounding ingredients — Stearic acid — Definition and test methods

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 8312:2015. It supersedes BS ISO 8312:1999 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 89097 0

ICS 83.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 8312:2015

ISO
8312

Second edition
2015-09-15

**Rubber compounding ingredients —
Stearic acid — Definition and test
methods**

*Ingrédients de mélange du caoutchouc — Acide stéarique —
Définition et méthodes d'essai*



Reference number
ISO 8312:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Sampling.....	2
5 Physical and chemical properties.....	2
6 Test report.....	2
Annex A (normative) Determination of ash at 550 °C ± 25 °C.....	4
Annex B (normative) Determination of copper content — Atomic absorption spectrometric method.....	6
Annex C (normative) Determination of manganese content — Atomic absorption spectrometric method.....	8
Annex D (normative) Determination of iron content — Atomic absorption spectrometric method.....	10
Annex E (normative) Determination of nickel content — Atomic absorption spectrometric method.....	12
Annex F (normative) Determination of mineral acidity — Titrimetric method.....	14
Annex G (normative) Determination of copper content — Molecular absorption spectrometric method.....	16
Annex H (normative) Determination of manganese content — Molecular absorption spectrometric method.....	17
Annex J (normative) Determination of iron content — Molecular absorption spectrometric method.....	18
Annex K (normative) Determination of nickel content — Molecular absorption spectrometric method.....	19
Annex L (normative) Classification of stearic and stearic acid/palmitic acid blends and typical physical and chemical properties.....	20
Bibliography.....	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 8312:1999), of which it constitutes a minor revision with the following changes:

- atomic absorption spectrometric method is stated as the preferred method in the Scope;
- Normative references in [Clause 2](#) were updated and a Bibliography was added.

Rubber compounding ingredients — Stearic acid — Definition and test methods

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard defines stearic acid (including blends of stearic and palmitic acid) for use as a compounding ingredient in the rubber industry and specifies the test methods for describing its properties.

Classification of stearic acid and stearic acid/palmitic acid blends according to iodine value and typical chemical and physical properties for such materials for use in the rubber industry are given in [Annex L](#). [Annex L](#) is given for information only.

In this International Standard, the atomic absorption spectrometric method is the preferred method.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 660, *Animal and vegetable fats and oils — Determination of acid value and acidity*

ISO 662, *Animal and vegetable fats and oils — Determination of moisture and volatile matter content*

ISO 935, *Animal and vegetable fats and oils — Determination of titre*

ISO 1042:1998, *Laboratory glassware — One-mark volumetric flasks*

ISO 3596, *Animal and vegetable fats and oils — Determination of unsaponifiable matter — Method using diethyl ether extraction*

ISO 3657, *Animal and vegetable fats and oils — Determination of saponification value*

ISO 3961, *Animal and vegetable fats and oils — Determination of iodine value*

ISO 4058, *Magnesium and its alloys — Determination of nickel — Photometric method using dimethylglyoxime*

ISO 5508, *Animal and vegetable fats and oils — Analysis by gas chromatography of methyl esters of fatty acids*

ISO 6685, *Chemical products for industrial use — General method for determination of iron content — 1,10-Phenanthroline spectrophotometric method*

ISO 7780:1998, *Rubbers and rubber latices — Determination of manganese content — Sodium periodate photometric methods*

ISO 8053, *Rubber and latex — Determination of copper content — Photometric method*

ISO 12966-2, *Animal and vegetable fats and oils — Gas chromatography of fatty acid methyl esters — Part 2: Preparation of methyl esters of fatty acids*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 stearic acid (for use in the rubber industry)
 mixture of straight-chain saturated fatty acids composed substantially of stearic acid in the form $C_{17}H_{35}COOH$ and palmitic acid in the form $C_{15}H_{31}COOH$

4 Sampling

Sampling shall be carried out in accordance with ISO 15528, using a stainless-steel sampling device.

5 Physical and chemical properties

The physical and chemical properties shall be determined by the methods of test listed in [Table 1](#).

Table 1 — List of physical and chemical properties of stearic acid and the methods used for their determination

Property	Test method
Acid value, mg KOH/g	ISO 660
Saponification value, mg KOH/g	ISO 3657
Titre value, °C	ISO 935
Fatty acids, C_{16} to C_{18} , including unsaturates, percentage (mass fraction)	ISO 5508 and ISO 12966-2
Total matter volatile at $105\text{ °C} \pm 3\text{ °C}$, percentage (mass fraction)	ISO 662, oven method
Ash at $550\text{ °C} \pm 25\text{ °C}$, percentage (mass fraction)	Annex A
Iodine value, g/100 g	ISO 3961
Mineral acidity, $\text{cm}^3/100\text{ g}$	Annex F
Copper, mg/kg	Annex B ^a or G
Manganese, mg/kg	Annex C ^a or H
Iron, mg/kg	Annex D ^a or I
Unsaponifiable matter, percentage (mass fraction)	ISO 3596
Nickel, mg/kg	Annex E ^a or K
Note Where an atomic absorption spectrometer is not available, the molecular absorption spectrometric methods given in Annexes G, H, J and K may be used.	
^a For speed and simplicity, the methods given in Annexes B, C, D and E are recommended.	

6 Test report

The test report shall include the following information:

- a) all details necessary for complete identification of the product tested;
- b) a reference to this International Standard, i.e. ISO 8312;

- c) the results obtained:
- percentage ash w_A , from [A.4](#);
 - copper content w_{Cu} , from [B.6](#) or from [Annex G](#) (state the method used);
 - manganese content w_{Mn} , from [C.6](#) or from [Annex H](#) (state the method used);
 - iron content w_{Fe} , from [D.6](#) or from [Annex J](#) (state the method used);
 - nickel content, w_{Ni} , from [E.6](#) or from [Annex K](#) (state the method used);
 - mineral acidity, N_{ma} , from [E.5](#);
 - the results of other tests which may have been performed (see [Table 1](#));
- d) any unusual features noted during the determinations;
- e) any operations not included in this International Standard, or in other International Standards cited, which might have affected the results;
- f) the dates of the tests.

Annex A (normative)

Determination of ash at 550 °C ± 25 °C

A.1 Principle

A weighed test portion is carefully volatilized without ignition, and the residue is ashed in a furnace at 550 °C ± 25 °C. The mass of ash is determined as a percentage of the mass of the original test portion.

A.2 Apparatus

Ordinary laboratory apparatus, plus the following:

A.2.1 Silica crucible.

A.2.2 Heat-resistant non-conducting (insulating) material in plate form, approximately 150 mm × 150 mm.

A.2.3 Analytical balance, accurate to 0,1 mg.

A.2.4 Muffle furnace, capable of being maintained at a temperature of 550 °C ± 25 °C.

A.3 Procedure

A.3.1 Heat the clean silica crucible ([A.2.1](#)) to 600 °C, allow to cool in a desiccator and weigh empty to 0,1 mg.

A.3.2 Place about 10 g of sample in this crucible and re-weigh to 0,1 mg. Place in a hole in the sheet of heat-resistant material ([A.2.2](#)).

A.3.3 Heat the crucible and contents gently in order to volatilize the test portion, taking care to ensure that the vapour does not ignite and that hot gases from the burner do not enter the crucible.

A.3.4 When all volatile material has been removed, place the crucible in the muffle furnace ([A.2.4](#)), maintained at 550 °C ± 25 °C, and ignite the contents for 30 min.

A.3.5 Place the crucible in a desiccator and allow to cool.

A.3.6 Re-weigh the crucible to the nearest 0,1 mg.

A.3.7 Repeat the operations specified in [A.3.3](#), [A.3.4](#) and [A.3.5](#), until successive mass determinations differ by less than 2 mg.

A.3.8 Retain the ash obtained in [A.3.6](#) if subsequent use can be made in another test.

A.4 Expression of results

Calculate the percentage ash, w_A , in accordance with Formula (A.1):

$$w_A = \frac{m_2 - m_1}{m_0} \times 100 \quad (\text{A.1})$$

where

w_A is the percentage ash;

m_0 is the mass, in grams, of the test portion;

m_1 is the mass, in grams, of the empty crucible;

m_2 is the mass, in grams, of the crucible and ash.

Annex B (normative)

Determination of copper content — Atomic absorption spectrometric method

B.1 Principle

Ash made in accordance with [Annex A](#) is dissolved in hydrochloric acid and the solution made up to standard volume. The absorbance is measured at 324,7 nm in an atomic absorption spectrometer. The copper content is determined by reference to a calibration graph prepared by measuring the absorbance of standard copper solutions.

B.2 Reagents

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

B.2.1 Hydrochloric acid, a mass fraction of 10 % solution.

B.2.2 Copper, standard solution corresponding to 10 mg of Cu per dm³.

B.3 Apparatus

Ordinary laboratory apparatus, plus the following:

B.3.1 Atomic absorption spectrometer, fitted with a copper hollow-cathode lamp.

B.3.2 One-mark volumetric flasks, two of capacity 10 cm³ and six of capacity 50 cm³, complying with the requirements of ISO 1042:1998, class A.

B.4 Procedure

B.4.1 Obtain a sample of ash by conducting the determination specified in [Annex A](#).

B.4.2 Dissolve the ash so obtained in 5 cm³ of dilute hydrochloric acid ([B.2.1](#)). Transfer the solution quantitatively to a 10 cm³ one-mark volumetric flask (see [B.3.2](#)).

B.4.3 Dilute the digested ash to exactly 10 cm³ in the one-mark volumetric flask by adding water.

B.4.4 Set the wavelength of the spectrometer ([B.3.1](#)) to 324,7 nm and aspirate the test solution into the flame, followed immediately by water, and then blank solution made up from the same reagents and using the same procedure but omitting the test portion.

B.4.5 Repeat this procedure and record the mean values of absorbance of the test solution and the blank test solution.

B.5 Preparation of the calibration graph

B.5.1 Preparation of solutions

Into a series of six 50 cm³ one-mark volumetric flasks (see B.3.2), transfer the volumes of the standard copper solution (B.2.2) indicated in Table B.1, dilute to the mark with water and mix.

Table B.1 — Standard calibration solutions for determination of copper

Volume of standard copper solution (B.2.2) cm ³	Copper content µg/cm ³
0,5	0,1
2,5	0,5
5,0	1,0
10,0	2,0
15,0	3,0
25,0	5,0

B.5.2 Spectrometric measurements

Aspirate each of the standard calibration solutions in turn into the flame of the atomic absorption spectrometer (B.3.1) and record their absorbances at a wavelength of 324,7 nm, following the instructions of the instrument manufacturer.

Aspirate water into the flame after each measurement.

B.5.3 Plotting the calibration graph

Plot a graph having the masses, in micrograms, of copper per cm³ of the calibration solutions as abscissae and the corresponding values of absorbance as ordinates.

B.6 Expression of results

By reference to the calibration graph prepared as described in B.5.3, determine the copper content corresponding to the absorbances of the test solution and the blank test solution.

The concentration of copper to be determined shall fall within the linear part of the calibration curve.

The total copper content of the sample, w_{Cu} , expressed in milligrams per kilogram, is given in Formula (B.1):

$$w_{\text{Cu}} = \frac{10 (m_3 - m_4)}{m_0} \quad (\text{B.1})$$

where

m_0 is the mass, in grams, of the test portion;

m_3 is the copper content, in micrograms per cm³, of the test solution;

m_4 is the copper content, in micrograms per cm³, of the blank test solution.

Express the result to the nearest 0,1 mg/kg.

Annex C (normative)

Determination of manganese content — Atomic absorption spectrometric method

C.1 Principle

Ash made in accordance with [Annex A](#) is dissolved in hydrochloric acid and the solution made up to standard volume. The absorbance is measured at 279,5 nm in an atomic absorption spectrometer. The manganese content is determined by reference to a calibration graph prepared by measuring the absorbance of standard manganese solutions.

C.2 Reagents

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

C.2.1 Hydrochloric acid, a mass fraction of 10 % solution.

C.2.2 Manganese, standard solution corresponding to 10 mg of Mn per dm³.

C.3 Apparatus

Ordinary laboratory apparatus, plus the following:

C.3.1 Atomic absorption spectrometer, fitted with a manganese hollow-cathode lamp.

C.3.2 One-mark volumetric flasks, two of capacity 10 cm³ and six of capacity 50 cm³, complying with the requirements of ISO 1042:1998, class A.

C.4 Procedure

Carry out the procedure given in [B.4](#), but set the wavelength specified in [B.4.4](#) to 279,5 nm instead of 324,7 nm.

C.5 Preparation of the calibration graph

Prepare a calibration graph for manganese following the instructions given in [B.5](#), but using the standard manganese solution ([C.2.2](#)) and recording the absorbances at 279,5 nm instead of 324,7 nm.

C.6 Expression of results

Determine the manganese content corresponding to the absorbances of the test solution and the blank test solution by reference to the calibration graph prepared as described in [C.5](#).

The concentration of manganese to be determined shall fall within the linear part of the calibration curve.

The total manganese content of the sample, w_{Mn} , expressed in milligrams per kilogram, is given in Formula (C.1):

$$w_{\text{Mn}} = \frac{10 (m_5 - m_6)}{m_0} \quad (\text{C.1})$$

where

m_0 is the mass, in grams, of the test portion;

m_5 is the manganese content, in micrograms per cm^3 , of the test solution;

m_6 is the manganese content, in micrograms per cm^3 , of the blank test solution.

Express the result to the nearest 0,1 mg/kg.

Annex D (normative)

Determination of iron content — Atomic absorption spectrometric method

D.1 Principle

Ash made in accordance with [Annex A](#) is dissolved in hydrochloric acid and the solution made up to standard volume. The absorbance is measured at 248,3 nm in an atomic absorption spectrometer. The iron content is determined by reference to a calibration graph prepared by measuring the absorbance of standard iron solutions.

D.2 Reagents

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

D.2.1 Hydrochloric acid, a mass fraction of 10 % solution.

D.2.2 Iron, standard solution corresponding to 10 mg of Fe per dm³.

D.3 Apparatus

Ordinary laboratory apparatus, plus the following:

D.3.1 Atomic absorption spectrometer, fitted with an iron hollow-cathode lamp.

D.3.2 One-mark volumetric flasks, two of capacity 10 cm³ and six of capacity 50 cm³, complying with the requirements of ISO 1042:1998, class A.

D.4 Procedure

Carry out the procedure given in [B.4](#), but set the wavelength specified in [B.4.4](#) to 248,3 nm instead of 324,7 nm.

D.5 Preparation of the calibration graph

Prepare a calibration graph for iron following the instructions given in [B.5](#), but using the standard iron solution ([D.2.2](#)) and recording the absorbances at 248,3 nm instead of 324,7 nm.

D.6 Expression of results

Determine the iron content corresponding to the absorbances of the test solution and the blank test solution by reference to the calibration graph prepared as described in [D.5](#).

The concentration of iron to be determined shall fall within the linear part of the calibration curve.

The total iron content of the sample, w_{Fe} , expressed in milligrams per kilogram, is given in Formula (D.1):

$$w_{\text{Fe}} = \frac{10 (m_7 - m_8)}{m_0} \quad (\text{D.1})$$

where

m_0 is the mass, in grams, of the test portion;

m_7 is the iron content, in micrograms per cm^3 , of the test solution;

m_8 is the iron content, in micrograms per cm^3 , of the blank test solution.

Express the result to the nearest 0,1 mg/kg.

Annex E (normative)

Determination of nickel content — Atomic absorption spectrometric method

E.1 Principle

Ash made in accordance with [Annex A](#) is dissolved in hydrochloric acid and the solution made up to standard volume. The absorbance is measured at 232,0 nm in an atomic absorption spectrometer. The nickel content is determined by reference to a calibration graph prepared by measuring the absorbance of standard nickel solutions.

E.2 Reagents

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

E.2.1 Hydrochloric acid, a mass fraction of 10 % solution.

E.2.2 Nickel, standard solution corresponding to 10 mg of Ni per dm³.

E.3 Apparatus

Ordinary laboratory apparatus, plus the following:

E.3.1 Atomic absorption spectrometer, fitted with a nickel hollow-cathode lamp.

E.3.2 One-mark volumetric flasks, two of capacity 10 cm³ and six of capacity 50 cm³, complying with the requirements of ISO 1042:1998, class A.

E.4 Procedure

Carry out the procedure given in [B.4](#), but set the wavelength specified in [B.4.4](#) to 232,0 nm instead of 324,7 nm.

E.5 Preparation of the calibration graph

Prepare a calibration graph for nickel following the instructions given in [B.5](#), but using the standard nickel solution ([E.2.2](#)) and recording the absorbances at 232,0 nm instead of 324,7 nm.

E.6 Expression of results

Determine the nickel content corresponding to the absorbances of the test solution and the blank test solution by reference to the calibration graph prepared as described in [E.5](#).

The concentration of nickel to be determined shall fall within the linear part of the calibration curve.

The total nickel content of the sample, w_{Ni} , expressed in milligrams per kilogram, is given in Formula (E.1):

$$w_{\text{Ni}} = \frac{10 (m_9 - m_{10})}{m_0} \quad (\text{E.1})$$

where

m_0 is the mass, in grams, of the test portion;

m_9 is the nickel content, in micrograms per cm^3 , of the test solution;

m_{10} is the nickel content, in micrograms per cm^3 , of the blank test solution.

Express the result to the nearest 0,1 mg/kg.

Annex F (normative)

Determination of mineral acidity — Titrimetric method

F.1 Principle

A test portion is dissolved in light petroleum, extracted with water and the aqueous phase titrated with standard volumetric potassium hydroxide solution or standard volumetric sodium hydroxide solution.

F.2 Reagents and materials

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

F.2.1 Light petroleum distillate, boiling point 60 °C to 80 °C.

F.2.2 Potassium hydroxide, standard volumetric solution, $c(\text{KOH}) = 0,01 \text{ mol/dm}^3$.

F.2.3 Sodium hydroxide, standard volumetric solution, $c(\text{NaOH}) = 0,01 \text{ mol/dm}^3$.

F.2.4 Filtered methyl orange, indicator solution.

F.3 Apparatus

Ordinary laboratory apparatus, plus the following:

F.3.1 Conical flasks, of capacity 250 cm³ and 500 cm³.

F.3.2 Separating funnels, of capacity 500 cm³.

F.4 Procedure

F.4.1 Weigh about 50 g of sample into a 500 cm³ conical flask (see [F.3.1](#)). Add 100 cm³ of light petroleum distillate ([F.2.1](#)).

F.4.2 Warm the mixture in a fume cupboard, taking care to avoid flames.

F.4.3 Transfer the contents of the conical flask to a 500 cm³ separating funnel ([F.3.2](#)).

F.4.4 Rinse the 500 cm³ conical flask with 10 cm³ of warm water at 40 °C and add to the separating funnel.

F.4.5 Immediately add a further 40 cm³ of water to the separating funnel.

F.4.6 Swirl, but do not shake vigorously, to avoid the risk of forming an emulsion, and allow to settle.

F.4.7 Run off the lower, aqueous, layer from the separating funnel into a 250 cm³ conical flask ([F.3.1](#)).

F.4.8 Wash the light petroleum distillate layer remaining in the separating funnel twice with 50 cm³ of water, each time running off the lower layer into the 250 cm³ conical flask, the total contents of which should now measure 150 cm³.

F.4.9 Titrate the aqueous solution in the conical flask with either potassium hydroxide solution (F.2.2) or sodium hydroxide solution (F.2.3), using filtered methyl orange indicator solution (F.2.4).

F.5 Expression of results

Calculate the mineral acidity, N_{ma} , expressed as cm³ of hydrochloric acid solution, $c(\text{HCl}) = 0,01 \text{ mol/dm}^3$, per 100 g of sample, using Formula (F.1):

$$N_{\text{ma}} = \frac{100 V}{m} \quad (\text{F.1})$$

where

V is the volume, in cm³, of potassium hydroxide solution (F.2.2) or sodium hydroxide solution (F.2.3) used for the titration;

m is the mass, in grams, of the test portion.

Annex G (normative)

Determination of copper content — Molecular absorption spectrometric method

Treat the ash obtained from determinations made in accordance with [Annex A](#) by the procedure given in ISO 8053 and report the results in accordance with that International Standard.

Annex H (normative)

Determination of manganese content — Molecular absorption spectrometric method

Treat the ash obtained from determinations made in accordance with [Annex A](#) by the procedure given in ISO 7780:1998, Clause 4 (restricted method), and report the results in accordance with that International Standard.

Annex J (normative)

Determination of iron content — Molecular absorption spectrometric method

Treat the ash obtained from determinations made in accordance with [Annex A](#) with acid to form a test solution of less than 60 cm³ and determine the iron content by the procedure given in ISO 6685, reporting the results in accordance with that International Standard.

Annex K (normative)

Determination of nickel content — Molecular absorption spectrometric method

Treat the ash obtained from determinations made in accordance with [Annex A](#) with acid to form a test solution.

Determine the nickel content by following, as appropriate, the procedure described in ISO 4058 in which a colour is generated by the reagent dimethylglyoxime. Report the results in accordance with that International Standard.

Annex L (normative)

Classification of stearic and stearic acid/palmitic acid blends and typical physical and chemical properties

L.1 General

The purpose of standardizing on a limited number of grades is to avoid a proliferation of grades. Material meeting the requirements given herein is suitable for use in rubber compounds. It does not follow that material not meeting these requirements is unsuitable for such use.

L.2 Classification

Two classes, A and B, are described.

Class A includes four grades of stearic acid with a minimum of 80 % C₁₆ to C₁₈ fatty acids and having, respectively, very low, low, medium and high unsaturation as determined by their iodine value.

Class B includes two grades of stearic/palmitic acid with a minimum of 90 % C₁₆ to C₁₈ fatty acids and containing stearic and palmitic acids in the nominal ratios 65:30 and 40:50, respectively.

L.3 Typical physical and chemical properties

Typical physical and chemical properties as determined by the methods described in [Clause 5](#) are given in [Table L.1](#).

L.4 Quality control

The method of manufacture and degree of quality control should be such that a uniform material is produced complying throughout with the descriptions given in [Table L.1](#).

L.5 Physical form and appearance

L.5.1 Physical form

The material should be in a form suitable to facilitate weighing out and incorporation into rubber compounds.

L.5.2 Appearance

The material should be a white or pale-cream solid at local ambient temperatures. When heated to above the temperature indicated by its titre value, it should melt to a clear liquid having no visible impurities.

L.6 Density

The density of each class of stearic acid is typically 850 kg/m³.

Table L.1 — Typical values/ranges of grades

Property	Class A				Class B	
	Stearic Very low I.V.	Stearic Low I.V.	Stearic Medium I.V.	Stearic High I.V.	Stearic/ palmitic 65/30	Stearic/ palmitic 40/50
5.1 Iodine value, g/100 g	0 to 5	5 to 10	10 to 20	>20	<2	<2
5.2 Acid value, mg KOH/g	200 to 210					
5.3 Saponification value, mg KOH/g	200 to 210					
5.4 Titre value, °C	40 to 60	40 to 60	40 to 60	40 to 60	50 to 70	50 to 70
5.5 C16 to C18 fatty acids, including unsaturated, %, min.	80	80	80	80	90	90
5.6 Matter volatile at 105 °C, %, max.	0,15	0,5	0,5	0,5	0,5	0,5
5.7 Ash at 550 °C, %, max.	0,2	0,2	0,2	0,2	0,1	0,1
5.8 Mineral acidity, ml of 0,01 mol/dm ³ HCl/100 g, max.	20	20	20	20	20	20
5.9 Copper, mg/kg, max.	5	5	5	5	5	5
5.10 Manganese, mg/kg, max.	5	5	5	5	5	5
5.11 Iron, mg/kg, max.	50	50	50	50	50	50
5.12 Nickel, mg/kg, max.	50	50	50	50	50	50
5.13 Unsaponifiable matter, %, max.	1	3	3	3	0,2	0,5

Bibliography

- [1] ISO 5794-1, *Rubber compounding ingredients — Silica, precipitated, hydrated — Part 1: Non-rubber tests*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™